
**Plain bearings — Bearings containing
dispersed solid lubricants**

Paliers lisses — Paliers contenant des lubrifiants solides dispersés

STANDARDSISO.COM : Click to view the full PDF of ISO 20054:2016



STANDARDSISO.COM : Click to view the full PDF of ISO 20054:2016



COPYRIGHT PROTECTED DOCUMENT

© ISO 2016, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

	Page
Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Symbols and units	1
5 Characteristics	1
5.1 Structure	1
5.2 Bearing characteristics	2
5.3 Applicable field	3
6 Material	3
6.1 Metal matrix	3
6.2 Solid lubricant	4
6.3 Combination of metal matrix and solid lubricant	4
7 Dimension	5
7.1 General	5
7.2 General dimension	5
7.2.1 Seamless bush	5
7.2.2 Wrapped bush	7
7.3 Tolerance classes and limit deviations	7
7.3.1 General	7
7.3.2 Housing fit	7
7.3.3 Shaft clearance	7
8 Assembling	8
9 Surface finish	8
Annex A (informative) Guide for selection of a bearing metal matrix for bearings containing dispersed solid lubricants	9
Annex B (informative) Actual applications of a bearing containing dispersed solid lubricants	10
Bibliography	11

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

The committee responsible for this document is ISO/TC 123, *Plain bearings*, Subcommittee SC 7, *Special types of plain bearings*.

Plain bearings — Bearings containing dispersed solid lubricants

1 Scope

This document specifies a bearing containing dispersed solid lubricants which is used as a solid lubricant bearing.

NOTE In the solid lubricant bearing among self-lubricating bearings there is a solid type, a coated type, an embedded type and a dispersed type, which is specified by this document.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 3547-1, *Plain bearings — Wrapped bushes — Part 1: Dimensions*

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

4 Symbols and units

See Table 1.

Table 1 — Symbols and units

Symbol	Description	Unit
B	Width of the bush	mm
D_i	Inside diameter of the bush	mm
D_o	Outside diameter of the bush	mm

5 Characteristics

5.1 Structure

A bearing containing dispersed solid lubricants is made of sintered composite materials that contain solid lubricants dispersed uniformly in the metal matrix and is manufactured by powder metallurgy (see [Figure 1](#)).

This document includes multi-layered bearings with the sintered layer on a steel backing and both seamless and wrapped bushes (see [Figure 2](#)).

Figure 3 shows a typical microstructure of the bearings containing dispersed solid lubricants. The dispersed solid lubricants in the metal matrix vary in grain size and volume.



a) Seamless bush (fine solid lubricants type)



b) Seamless bush (coarse solid lubricants type)

Figure 1 — Overview of bearings containing dispersed solid lubricants (single-layered)



a) Seamless bush




b) Wrapped bush


Key

- 1 sintered layer
- 2 steel backing

Figure 2 — Overview of bearings containing dispersed solid lubricants (multi-layered)



a) Fine solid lubricants type



b) Coarse solid lubricants type

Key

- 1 metal matrix
- 2 dispersed solid lubricant

Figure 3 — Microstructure of a bearing containing dispersed solid lubricants


5.2 Bearing characteristics

A bearing containing dispersed solid lubricants obtains its sliding performance from the self-lubricating effects of solid lubricants and the mechanical strength of metal matrix.

The sliding performance and mechanical strength vary according to the volume of solid lubricants. Higher sliding performance requires more solid lubricants, while higher mechanical strength requires less solid lubricants.

Since solid lubricants are dispersed over the entire material, the bearings are particularly suitable for extra low speed or micro-motion applications, minimising static friction to achieve smooth sliding at the start of motion.

The solid lubricants are drawn out over both surfaces from the bearing material when it slides against the mating surface, forming a solid lubricant film. As the solid lubricant film is consumed, it is replenished from the bearing material to maintain a continuous film throughout the life of the product (see [Figure 4](#)).



Key

- 1 mating member
- 2 metal matrix
- 3 dispersed solid lubricant
- 4 solid lubricant film
- A sliding direction

Figure 4 — Lubricating mechanism of a bearing containing dispersed solid lubricants

5.3 Applicable field

The bearing can be used for rotational motion, reciprocating motion, oscillating motion and frequent start/stop cycles. The bearing is also used in such applications where no fluid lubrication can be expected because of high load and low speed operation. Bearings with appropriate materials are suited to applications with high or low temperature, liquids, gases and *in vacuo*.

The bearing has been developed to operate satisfactorily without oil or grease lubricants. However, if the application permits, oil or grease may be utilized to improve bearing durability, prevent dust from entering the bearing, flush out wear debris or prevent corrosion of the bearing components.

6 Material

6.1 Metal matrix

The constituent elements of the metal matrix in the bearing define the physical, chemical and mechanical properties of the bearing. The chemical composition and manufacturing methods (sintering and heat treatment) influence the bearing metal matrix properties.

Metal matrix base materials are principally copper, nickel or iron. [Table 2](#) shows the operating temperature for the alloy types.

Table 2 — Types of alloy and their operating temperature

Alloy type	Operating temperature ^a
	°C
Copper based alloys	-200 to 450
Nickel based alloys	-200 to 600
Iron based alloys	0 to 700
^a Operating temperature varies according to the composition.	

The most commonly-used, copper-based metal matrix group is Cu-Sn, but Cu-Ni-Sn and Cu-Ni-Fe alloys offer enhanced thermal resistance and strength.

The nickel-based metal matrix group includes Ni-Cu-Fe alloys, which offer high corrosion resistance.

The iron-based metal matrix group includes Fe-Cu alloys, which offer higher thermal resistance than copper-based alloys by the formation of iron oxide lubricant films. In addition, there are high-heat resistant Fe-Ni-Cu alloys and stainless alloys (Fe-Cr-Ni alloys, etc.).

Metal matrix may contain small additive additions to enhance performance. The surface of metal matrix may have an additional running-in coating.

A guide for the selection of a bearing metal matrix for bearings containing dispersed solid lubricants is shown in [Figure A.1](#) of [Annex A](#).

6.2 Solid lubricant

Many types of solid lubricants are available. They are selected to suit the operating conditions because their friction performances are influenced by the operating environment. The majority of bearings incorporate graphite and molybdenum disulphide as solid lubricants. Other solid lubricants with low friction, suited to demanding environments, include tungsten disulphide, boron nitride and polytetrafluoroethylene (PTFE). [Table 3](#) shows an outline for the operating temperatures and the atmosphere for the solid lubricants.

The size and type of solid lubricants are selected based on the operating conditions.

Table 3 — Types of solid lubricants and their properties

Type	Operating temperature °C	Atmosphere		
		In air	In water	In vacuum
Graphite	-120 to 600	good	applicable	poor
MoS ₂	-100 to 400	good	poor	good
WS ₂	-180 to 600	good	poor	good
BN	up to 900 ^a	good	-	-
PTFE	-260 to 260	good	good	good

^a BN shows good performance in an oxidising atmosphere at high temperature.

6.3 Combination of metal matrix and solid lubricant

According to a combination of the metal matrix with the solid lubricant types, their grain size, their volume and manufacturing methods permit satisfactory bearing selection for a wide range of applications. Determination of the composition of both metal matrix and solid lubricant is a critical task.

[Table 4](#) shows typical examples of metal matrix and solid lubricant combinations and suitable applications. Further, examples of actual applications of a bearing containing dispersed solid lubricants are shown in [Table B.1](#) of [Annex B](#).

Table 4 — Typical examples of metal matrix and solid lubricant combinations and suitable applications

Alloy type	Metal matrix ^a	Solid lubricants ^a	Applications
Copper based alloys	Cu-Sn base	Graphite	General use for average conditions. (up to 350 °C)
		MoS ₂	
		Graphite and MoS ₂	In vacuum and air. (up to 350 °C)
	Cu-Ni-Sn base	Graphite	For wear resistance. (up to 350 °C)
	Cu-Ni-Fe base	Graphite	For corrosion resistance. (up to 450 °C)
Nickel based alloys	Ni-Cu-Fe base	Graphite	For corrosion resistance. (up to 550 °C)
	Ni base	Graphite	For highest corrosion resistance. (up to 600 °C)
Iron based alloys	Fe-Cu base	Graphite and MoS ₂	High temperature in air. (up to 600 °C)
	Fe-Ni-Cu base	Graphite and/or BN	High temperature and corrosion resistance. (up to 700 °C)

^a It may be processed with oil impregnation. In case that the effect of oil impregnation is necessary, the ambient temperature should be less than 120 °C.

7 Dimension

7.1 General

The housing fit and shaft clearance are important factors to consider when determining the dimensions of a bearing. The many combinations of bearing materials, applications and range of operating conditions do not permit uniform application of tolerances to the bearing component parts (housing, bush and shaft).


Since the optimum fit varies depending upon the operating environments, discussion is necessary between the supplier and the user to achieve the optimum fit.

7.2 General dimension

7.2.1 Seamless bush

Bushes need to have adequate thickness for maintaining the strength.

[Figure 5](#) shows a seamless bush, and [Table 5](#) lists the preferred nominal inside and outside diameters and widths. Bearings of sizes outside those shown in [Table 5](#) shall be subject to agreement between the supplier and the user.



Key

X surface roughness, see [Table 7](#)

Figure 5 — Seamless bush

Table 5 — Preferred nominal dimensions for seamless bushes

Dimensions in millimetres

Inside diameter D_i	Outside diameter D_o	Width ^a B							
		8	10	12	15	20	25	30	35
8	12	8	10	12	–	–	–	–	–
10	14	8	10	12	15	–	–	–	–
12	18	8	10	12	15	–	–	–	–
13	19	10	12	15	20	–	–	–	–
14	20	10	12	15	20	–	–	–	–
15	21	10	12	15	20	–	–	–	–
16	22	10	12	15	20	25	–	–	–
18	24	10	12	15	20	25	–	–	–
20	28	10	12	15	20	25	30	–	–
20	30	10	12	15	20	25	30	–	–
22	32	12	15	20	25	30	–	–	–
25	33	12	15	20	25	30	35	–	–
25	35	12	15	20	25	30	35	–	–
28	38	15	20	25	30	35	40	–	–
30	38	15	20	25	30	35	40	–	–
30	40	15	20	25	30	35	40	–	–
32	42	15	20	25	30	35	40	–	–
35	45	20	25	30	35	40	50	–	–
40	50	20	25	30	35	40	50	60	–
40	55	20	25	30	35	40	50	60	–
45	55	25	30	35	40	50	60	70	–
45	60	25	30	35	40	50	60	70	–
50	60	30	35	40	50	60	70	80	–
50	65	30	35	40	50	60	70	80	–
55	70	30	35	40	50	60	70	80	–
60	75	30	35	40	50	60	70	80	–

^a The width B may be achieved with multiple connected bushes.

Table 5 (continued)

Inside diameter D_i	Outside diameter D_o	Width ^a							
		B							
65	80	35	40	50	60	70	80	-	-
70	85	35	40	50	60	70	80	100	-
70	90	35	40	50	60	70	80	100	-
75	90	40	50	60	70	80	100	-	-
75	95	40	50	60	70	80	100	-	-
80	100	40	50	60	70	80	100	120	-
90	110	50	60	70	80	90	100	120	-
100	120	50	60	70	80	90	100	120	140

^a The width B may be achieved with multiple connected bushes.

7.2.2 Wrapped bush

The preferred dimensions for wrapped bushes with a steel backing are based on ISO 3547-1.

The large-diameter wrapped bushes with the steel backing may use wall thickness 3 mm for inside diameter ≥ 75 mm, and may use wall thickness 3 mm or 5 mm for inside diameter ≥ 250 mm to get higher rigidity.

7.3 Tolerance classes and limit deviations

7.3.1 General

Table 6 shows the preferred tolerance classes and limit deviations for operations at ambient temperature.

7.3.2 Housing fit

In general, an interference fit is preferable. A wide range of operating temperatures can make it difficult to maintain the correct interference when bush and housing have dissimilar materials due to differential thermal expansion between the bush and housing. Furthermore, high temperature operation may cause stress relaxation, or high alternating load operation may reduce or eliminate interference. Under such operating conditions, mechanical retention using screws or dowel pins should be applied.

7.3.3 Shaft clearance

Notes on the clearance between a bush and a shaft are as follows.

- Interference between housing bore and bush outside diameter will cause the bush inside diameter to reduce during fitting.
- Thermal expansion or contraction should be considered if the bush is to be subjected to a wide temperature operating range. Higher bush-to-shaft clearances are recommended for high-temperature applications.

Table 6 — Preferred tolerance classes and limit deviations

Inside diameter of bush	Outside diameter of bush	Housing bore diameter	Shaft diameter
C7 ^a	r6	H7	h7 ^a
D6 to E6 ^b	r6	H7	g6 ^b
^a In general case. ^b For high accuracy (less clearance).			

8 Assembling

Since the bush of a bearing containing dispersed solid lubricants is often fitted by means of press-fitting, a mandrel or a press machine is used. In the case of a bearing where the interference fit is large, the operation of press-fitting can be facilitated by chamfering the outside of the bush and the inside of the housing.

Seamless bushes can be cooled using liquid nitrogen or dry ice (CO₂) to facilitate fitting. This method causes less distortion of the material and hence results in a more precise fitted bore size and shape.

Discussion is recommended between the supplier and the user as some metal matrix materials are unsuitable for freeze-fitting.

9 Surface finish

Surface roughness of the bush shall be in accordance with [Table 7](#).

Table 7 — Surface finish of a bush

Surface	Surface roughness ^a x in Figure 5
Inside surface	Ra 1,6
Outside surface	Ra 3,2
^a Surface roughness is measured across the metal matrix, excluding surface depressions at solid lubricant islands.	