
**Textile floor coverings — Water
impermeability test**

Revêtements de sol textiles — Essai d'imperméabilité à l'eau

STANDARDSISO.COM : Click to view the full PDF of ISO 20251:2016



STANDARDSISO.COM : Click to view the full PDF of ISO 20251:2016



COPYRIGHT PROTECTED DOCUMENT

© ISO 2016, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

	Page
Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	1
5 Materials	1
6 Sampling and selection of specimen	1
7 Conditioning and testing	2
8 Procedure	2
9 Assessment of the results	2
10 Expression of the results	2
11 Test report	2
Bibliography	3

STANDARDSISO.COM : Click to view the full PDF of ISO 20251:2016

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

The committee responsible for this document is ISO/TC 219, *Floor coverings*.

Textile floor coverings — Water impermeability test

1 Scope

This document specifies a laboratory test method for determining the water impermeability of textile floor coverings.

This method cannot be used to characterize a wall-to-wall installation of textile floor covering tiles.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 139, *Textiles — Standard atmospheres for conditioning and testing*

ISO 1957, *Machine made textile floor coverings — Selection and cutting of specimens for physical tests*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 2424 apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

4 Principle

A specified amount of coloured liquid is poured onto a textile floor covering, where it is contained in a concentrated area for 24 h. The floor covering is then evaluated for liquid penetration through the product.

5 Materials

5.1 Methylene blue solution (1 g/l) (CAS number 61-73-4).

5.2 Open-ended cylinder, 110 mm diameter and 110 mm high, non-water permeable, lightweight material, e.g. PVC.

5.3 White tissue paper.

6 Sampling and selection of specimen

Select three specimens from the sample in accordance with ISO 1957, each specimen measuring a minimum of 350 mm × 350 mm.

7 Conditioning and testing

The specimens shall be conditioned and the test conducted in the standard atmosphere for testing textiles of (65 ± 4) % relative humidity and (20 ± 2) °C, as specified in ISO 139.

8 Procedure

- a) Each specimen, use surface uppermost, is laid on top of a clean white tissue on a horizontal surface.
- b) Place the cylinder (5.2) in the middle of the textile floor covering specimen and pour 100 ml of the coloured liquid (5.1) into the centre of the cylinder. Remove the cylinder as soon as the liquid solution has soaked into the textile floor covering.
- c) The specimens are left to stand for 24 h in the standard atmosphere before evaluation.

9 Assessment of the results

Assess the white tissue beneath each specimen for evidence of water penetration through the backing.

10 Expression of the results

Record for each specimen whether or not the sample showed water penetration.

Record the conclusion of water impermeability if none of the specimens showed water penetration.

11 Test report

The test report shall contain the following information:

- a) a statement that the tests were performed in accordance with this document, i.e. ISO 20251;
- b) the date of the test;
- c) the complete identification of the product tested, including type, source, colour, and manufacturer's reference numbers;
- d) the previous history of the sample;
- e) the water permeability or impermeability of the examined textile floor covering;
- f) any deviation from this document, which may have affected the results.