

705

International Standard



2037

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

Metal pipes and fittings — Stainless steel tubes for the food industry

Tuyauteries et raccords métalliques — Tubes en acier inoxydable pour l'industrie alimentaire

First edition — 1980-12-01

STANDARDSISO.COM : Click to view the full PDF of ISO 2037:1980

UDC 621.643.23 : 664

Ref. No. ISO 2037-1980 (E)

Descriptors : pipes, pipe fittings, stainless steels, dimensions, dimensional tolerances, thickness, food industry.

Price based on 2 pages

ISO 2037-1980 (E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards institutes (ISO member bodies). The work of developing International Standards is carried out through ISO technical committees. Every member body interested in a subject for which a technical committee has been set up has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work.

Draft International Standards adopted by the technical committees are circulated to the member bodies for approval before their acceptance as International Standards by the ISO Council.

International Standard ISO 2037 was developed by Technical Committee ISO/TC 5, *Metal pipes and fittings*.

It was submitted directly to the ISO Council, in accordance with clause 5.10.1 of part 1 of the Directives for the technical work of ISO. It cancels and replaces ISO Recommendation R 2037-1971, which had been approved by the member bodies of the following countries :

Australia	Greece	Romania
Austria	Hungary	South Africa, Rep. of
Belgium	India	Sweden
Canada	Israel	Switzerland
Czechoslovakia	Italy	Thailand
Denmark	Korea, Rep. of	United Kingdom
Egypt, Arab Rep. of	Netherlands	USSR
France	Norway	
Germany, F. R.	Poland	

No member body had expressed disapproval of the document.

Metal pipes and fittings — Stainless steel tubes for the food industry

1 Scope and field of application

Dimensions in millimetres

This International Standard lays down the dimensions and tolerances and specifies surface roughness, materials and hygienic requirements for seamless or welded stainless steel tubes in straight lengths for the food industry.

2 References

ISO 468, *Surface roughness — Parameters, their values and general rules for specifying surfaces.*¹⁾

ISO 1127, *Stainless steel tubes — Dimensions, tolerances and masses per unit length.*

ISO 2604/2, *Steel products for pressure purposes — Quality requirements — Part 2 : Wrought seamless tubes.*

ISO 2604/5, *Steel products for pressure purposes — Quality requirements — Part 5 : Longitudinally welded austenitic stainless steel tubes.*

ISO 4200, *Plain end steel tubes, welded and seamless — General tables of dimensions and conventional masses per unit length.*

3 Dimensions

The dimensions given in the table opposite are chosen from ISO 1127, series 1 and 2 outside diameter. For further information concerning the series see also ISO 4200.

Outside tube diameter	Thickness
12	1
17,2	1
21,3	1
25	1,2
33,7	1,2
38	1,2
40	1,2
51	1,2
63,5	1,6
70	1,6
76,1	1,6
88,9	2
101,6	2
114,3	2
139,7	2
168,3	2,6
219,1	2,6
273	2,6
323,9	2,6
355,6	2,6
406,4	3,2

NOTE — The diameters 18, 22 and 28 mm stated in ISO/R 2037 should not be used in future.

1) At present at the stage of draft. (Revision of ISO/R 468-1966.)