

Second edition
2019-06

AMENDMENT 1
2022-04

**Cryogenic vessels — Large
transportable vacuum-insulated
vessels —**

Part 1:
**Design, fabrication, inspection and
testing**

AMENDMENT 1

*Réipients cryogéniques — Réipients transportables isolés sous vide
de grande contenance —*

Partie 1: Conception, fabrication, inspection et essais

AMENDEMENT 1



Reference number
ISO 20421-1:2019/Amd.1:2022(E)

© ISO 2022

STANDARDSISO.COM : Click to view the full PDF of ISO 20421-1:2019/Amd 1:2022



COPYRIGHT PROTECTED DOCUMENT

© ISO 2022

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 220, *Cryogenic vessels*.

A list of all parts in the ISO 20421 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

STANDARDSISO.COM : Click to view the full PDF of ISO 20421-1:2019/Amd 1:2022

Cryogenic vessels — Large transportable vacuum-insulated vessels —

Part 1: Design, fabrication, inspection and testing

AMENDMENT 1

10.3.2.1

Replace Table 3 with the following:

Table 3 — Inner-vessel minimum wall thickness

Dimensions in millimetres

Inner vessel diameter D_i	Minimum wall thickness for reference material ^a s_r
$D_i \leq 1\,800$	3
$D_i > 1\,800$	4

^a Reference material is material having a product R_m [N/mm²] $\times A_5$ [%] of approximately 10 000, which yields $(R_m \times A_5)^{1/3} = 21,4$.
For other materials, the required minimum thickness of the metal used shall be calculated from Annex J.
Minimal wall thickness can be found in applicable national regulations.

10.3.2.4 b)

Replace with the following:

b) External pressure (pressure on the convex surface):

— cylindrical shells: $S_p = 1,4$;

$S_k = 2,6$ for out of roundness $u \leq 1,5$ %;

$S_k = 2,0 + 0,4 \times u$ for out of roundness $u \leq 1,0$ % may be used if there is evidence of reduced safety factor for buckling analysis by better manufacturing quality (reduced out of roundness).

— spherical region: $S_p = 2,1$;

$S_k = 2,6 + 0,001\,8 R/s_e$;

— knuckle region: $S_p = 1,6$.

10.3.3.4 a)

Replace with the following:

- a) Internal pressure (pressure on the concave surface): $S \geq 1,33$, for steels having a clearly-defined yield point or guaranteed 0,2 % proof strength for steels with no clearly-defined yield point (1 % for austenitic steels).

In the outer vessel as part of the fastening under each of the forces, the safety factor to be observed shall be as follows:

$S \geq 1,33$ for fixed tanks;

$S = 1,5$ for tank containers.

J.1

Add the following sentence to the end of the subclause:

The minimum thickness shall however not be less than the minimum wall thickness.

Minimum wall thickness can be found in applicable national regulations for the transport of dangerous goods.

J.2

Replace the text with the following:

The required minimum equivalent thickness shall be calculated according to Formula J.1:

$$s_r = \frac{464 \times s_0}{\sqrt[3]{(R_m \times A_5)^2}} \quad \text{J.1}$$

$(R_m \times A_5)^{2/3} = 464$ for reference material having a product R_m [N/mm²] \times A_5 [%] of approximately 10 000.

where

A_5 is the minimum elongation at 20 °C of the metal to be used;

s_r is the required thickness, in mm, of a seamless shell based on the circumferential stress, or of a formed end, for the designated pressure using $\eta = 1$;

s_0 is the minimum shell thickness for the metal chosen;

R_m is the minimum required tensile strength at 20 °C of the metal to be used.

For A_5 the following also applies:

In the case of sheet metal, the axis of the tensile test-piece shall be at right angles to the direction of rolling. The permanent elongation at fracture shall be measured on test-pieces of circular cross-section