
**Fine ceramics (advanced ceramics,
advanced technical ceramics) —
Vocabulary**

Céramiques techniques — Vocabulaire

STANDARDSISO.COM : Click to view the full PDF of ISO 20507:2014



STANDARDSISO.COM : Click to view the full PDF of ISO 20507:2014



COPYRIGHT PROTECTED DOCUMENT

© ISO 2014

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

	Page
Foreword	iv
1 Scope	1
2 Terms and definitions	1
2.1 General terms.....	1
2.2 Terms for form and processing.....	10
2.3 Terms for properties and testing.....	18
2.4 Abbreviations for ceramic materials.....	22
2.5 Abbreviations for processes.....	29
Bibliography	31

STANDARDSISO.COM : Click to view the full PDF of ISO 20507:2014

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

The committee responsible for this document is ISO/TC 206, *Fine ceramics*.

This second edition cancels and replaces the first edition (ISO 20507:2003), which has been technically revised.

Fine ceramics (advanced ceramics, advanced technical ceramics) — Vocabulary

1 Scope

This International Standard is a vocabulary, which provides a list of terms and associated definitions typically used for fine ceramic (advanced ceramic, advanced technical ceramic) materials, products, applications, properties, and processes. This International Standard contains, in separate lists, those abbreviations which have found general acceptance in the scientific and technical literature; they are given together with the corresponding terms and definitions or descriptions.

In this International Standard, the terms are defined using the term “fine ceramic”. The definitions apply equally to “advanced ceramics” and “advanced technical ceramics”, which are considered to be equivalent.

This International Standard does not include terms which, though used in the field of fine ceramics, are of a more general nature and are also well known in other fields of technology.

NOTE Terms and definitions of a more general nature are available in ASTM C 1145,^[1] EN 14232,^[2] and JIS R 1600.^[3] A list of some International Standards and draft International Standards of ISO/TC 206 “Fine ceramics” containing terms defined in this International Standard is given in the Bibliography.

2 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

2.1 General terms

2.1.1

advanced ceramic

advanced technical ceramic

fine ceramic

highly engineered, high performance, predominately non-metallic, inorganic, ceramic material having specific functional attributes

Note 1 to entry: The use of fine ceramic, advanced ceramic, and advanced technical ceramic is interchangeably accepted in business, trade, scientific literature, and International Standards.

2.1.2

antibacterial ceramic

fine ceramic that reveals surface antibacterial activity, usually associated with an antibacterial agent or photocatalytic behaviour, and is widely used for sanitary ware, tiles, and various kinds of apparatus

2.1.3

bio-sourced ceramic

fine ceramic produced from bio-sourced material

2.1.4

bioceramic

fine ceramic employed in or used as a medical device which is intended to interact with biological systems

Note 1 to entry: Bioceramics typically comprise products to repair or replace bone, teeth, and hard tissue, or to support soft tissue and/or control its function.

Note 2 to entry: Implants require a degree of biocompatibility.

Note 3 to entry: Bioceramics that are intended to interact actively with biological systems are often based on crystalline hydroxy(l)apatite; also, partially crystallized glass or glass-bonded ceramic is used.

2.1.5

carbon-carbon composite

fine ceramic composed of a carbon matrix containing carbon fibre reinforcement

Note 1 to entry: A carbon-carbon composite is mainly used for airplane breaks, and can also be used as furnace parts or heat resistant tiles for aerospace applications.

Note 2 to entry: The reinforcement is generally continuous.

2.1.6

ceramic

pertaining to the essential characteristics of a ceramic and to the material, product, manufacturing process, or technology

2.1.7

ceramic

essentially inorganic and non-metallic material

Note 1 to entry: The concept "ceramic" comprises products based on clay as raw material and also materials which are typically based on oxides, nitrides, carbides, silicides, borides, carbon etc.

2.1.8

ceramic armor

armor uses by armor vehicle and personnel for its attenuative properties

2.1.9

ceramic capacitor

capacitor in which the dielectric material is a ceramic

EXAMPLE BL (boundary layer) capacitor, multilayer ceramic capacitor.

2.1.10

ceramic catalyst carrier

nonreactive ceramic substrate to support a catalyst

Note 1 to entry: A ceramic catalyst carrier is typically made with a thin wall, has a large surface area and is used in contact with fluid matter.

2.1.11

ceramic coating

layer of oxide ceramic and/or non-oxide ceramic adhering to a substrate

Note 1 to entry: Ceramic coatings are produced by a variety of processes, e.g. dipping, plasma spraying, sol-gel coating, physical vapour deposition or chemical vapour deposition coating.

Note 2 to entry: Ceramic coatings are usually subdivided into thin ceramic coatings (<10 µm) and thick coatings (>10 µm).

2.1.12

ceramic cutting tool

tool for machining operations, consisting of a fine ceramic having excellent wear, damage, and heat resistance

Note 1 to entry: Machining includes operations such as turning, drilling, and milling.

2.1.13

ceramic filter

2.1.13.1**electrical**

filter using a piezoelectric ceramic as a resonator

2.1.13.2**porous**

porous ceramic matter to be used in filtering a gas or a liquid

2.1.14**ceramic for electrical applications**

DEPRECATED: electrical ceramics

ceramic for electronic applications

DEPRECATED: electronic ceramic

DEPRECATED: electroceramic

fine ceramic used in electrical and electronic engineering because of intrinsic, electrically related properties

Note 1 to entry: These intrinsic properties include electrical insulation, mechanical strength, and corrosion resistance.

Note 2 to entry: This term includes ceramics for passive electrical applications, i.e. a ceramic with no active electrical behaviour, having a high electrical resistivity, used for electrical insulation functions.

Note 3 to entry: This term may apply to silicate ceramics such as steatite and electrical porcelain.

2.1.15**ceramic for nuclear applications**

DEPRECATED: nuclear ceramic

fine ceramic having specific material properties required for use in nuclear environment

Note 1 to entry: Ceramics for nuclear applications include materials for nuclear fuels, neutron absorbers, burnable neutron poisons, diffusion barrier coatings, and inert container elements; structural application like "fuel cladding" or "assembly duct".

2.1.16**ceramic for optical applications**

DEPRECATED: optical ceramic

fine ceramic used in optical applications because of its intrinsic properties

EXAMPLE Transparent alumina is used for high-pressure sodium lamp envelopes.

Note 1 to entry: Optical ceramics are tailored typically to exploit transmission, reflection, and absorption of visible and near-visible electromagnetic radiation.

2.1.17**ceramic heating resistor**

heater making use of an electric conductive or a semi-conductive property of ceramics

2.1.18**ceramic honeycomb**

fine ceramic body having multiple channels typically arranged in a honeycomb structure

Note 1 to entry: A ceramic honeycomb is typically used as a ceramic catalyst carrier, a filter or a heat exchanger regenerator, and is typically made of cordierite, mullite, or aluminium titanate.

2.1.19**ceramic ionic conductor**

electroceramic in which ions are transported by an electric potential or chemical gradient

2.1.20

ceramic matrix composite

CMC

fine ceramic composed of a ceramic matrix containing reinforcement

Note 1 to entry: The reinforcement is often continuous, i.e. ceramic filaments, distributed in one or more spatial directions, but this term is also used for discontinuous reinforcement, e.g. short ceramic fibres, ceramic whiskers, ceramic platelets, or ceramic particles.

Note 2 to entry: C/C composites are included in CMC composites.

2.1.21

ceramic optical waveguide

optical waveguide formed on the surface of a ceramic substrate

Note 1 to entry: Optical single crystal of LiNbO₃ is typically used as a substrate for a ceramic optical waveguide.

2.1.22

ceramic sensor

sensor making use of semi-conductive, piezoelectric, magnetic, or dielectric properties of a fine ceramic

2.1.23

ceramic substrate

ceramic body, sheet, or layer of material on which some other active or useful material or component may be deposited or laid

EXAMPLE An electronic circuit laid on an alumina ceramic sheet. In catalysis, the formed, porous, high-surface-area carrier on which the catalytic agent is widely and thinly distributed for reasons of performance and economy.

2.1.24

ceramic varistor

ceramic material having high electrical resistivity at low voltage but high electrical conductivity at high voltage

Note 1 to entry: A zinc oxide varistor can be used as a protector in an electronic circuit.

2.1.25

cermet

composite material consisting of at least one distinct metallic and one distinct ceramic phase, the latter normally being present at a volume fraction greater than 50 %

Note 1 to entry: The ceramic phase, typically, has high hardness, high thermal strength, good corrosion resistance, and the metallic phase has good toughness and elastoplastic behaviour.

Note 2 to entry: The term "cermet" is a contracted form of ceramic metal.

Note 3 to entry: Materials containing typically less than 50 % by volume of ceramic phase are commonly called "metal matrix composites".

2.1.26

continuous fibre ceramic composite

CFCC

ceramic matrix composite in which one or more reinforcing phases consists of continuous fibres

2.1.27

diamond-like carbon

DLC

form of carbon made by a CVD or PVD process, having hardness much higher than graphite but lower than diamond

Note 1 to entry: Diamond-like carbon is typically used as a hard coat material for engineering components or memory disks.

2.1.28**dielectric ceramic**
ceramic dielectric

electroceramic having controlled dielectric properties

2.1.29**discontinuous fibre-reinforced ceramic composite**

ceramic matrix composite material reinforced by chopped fibres

2.1.30**electro-optic ceramic**

fine ceramic with a refractive index which changes in response to an applied electric field

Note 1 to entry: An electro-optic ceramic is a type of non-linear optical ceramic, used for optical shutters, optical modulating devices, optical memory devices, etc. Transparent ferroelectrics are used as electro-optic ceramics, LiNbO_3 single crystals, or PLZT polycrystals with low light scattering. The term "electro-optic" is often erroneously used as a synonym for "optoelectronic".

2.1.31**environmental barrier coating**
EBC

ceramic coating possibly multilayered used to protect fine ceramics of environmental aggression

2.1.32**far-infrared radiative ceramic**

fine ceramic with specific property to radiate in the far-infrared

Note 1 to entry: Far-infrared radiative ceramics are typically used as heaters for industrial and domestic applications.

2.1.33**ferrite**

fine ceramic with ferrimagnetic behaviour, having ferric oxide as a major constituent

Note 1 to entry: Magnetic ceramic is used as a synonym of ferrite, but encompasses non-oxide containing materials as well.

2.1.34**ferroelectric ceramic**

non-linear polarizable electroceramic, generally with a high level of permittivity, exhibiting hysteresis in the variation of the dielectric polarization as a function of the electric field strength and in the temperature dependence of the permittivity

Note 1 to entry: Polarization results in electrostrictive, piezoelectric, pyroelectric, and/or electro-optic properties, which disappear above the transition or Curie temperature.

2.1.35**ferromagnetic ceramic**

fine ceramic that exhibits a spontaneous magnetization without an applied external magnetic field, in which unpaired electrons with a small magnetic field of their own, align with each other and show a large net magnetic moment

Note 1 to entry: Most ferrites that contain iron oxide as the main constituent show ferromagnetism.

2.1.36**functional ceramic**

fine ceramic, the intrinsic properties of which are employed to provide an active function

EXAMPLE Electronic or ionic conductor, component with magnetic, chemical, or mechanical sensing function.

2.1.37

functionally graded ceramic

fine ceramic, the properties of which are deliberately varied from one region to another through spatial control of composition and/or microstructure

2.1.38

geopolymer

inorganic polymeric ceramics formed from both aluminium and silicon sources

2.1.39

glass-ceramic

fine ceramic derived from bulk glass or glass powder by controlled devitrification

Note 1 to entry: The glass is thermally treated to induce a substantial amount of crystallinity on a fine scale.

2.1.40

hard ferrite

ferrite having strong magnetic anisotropy and high coercivity

EXAMPLE Barium hexaferrite, used as permanent magnets in loudspeakers; strontium hexaferrite, used as permanent magnet segments in electric motors.

2.1.41

high-temperature superconductor

HTS

HTSC

superconducting ceramic having superconducting properties at temperatures above 77 K, the boiling point of liquid nitrogen

Note 1 to entry: Superconducting ceramics typically comprise certain combinations of oxides of copper, rare earths, barium, strontium, calcium, thallium, and/or mercury.

2.1.42

hybrid photocatalyst

photocatalyst (material) combined with other functional materials in order to complement and enhance the photocatalytic function

EXAMPLE Photocatalytic air purifying materials combined with an adsorbent and antibacterial material, in turn combined with an antibacterial agent, to continue to function in the absence of light.

2.1.43

indoor-light-active photocatalyst

substance that carries out many functions based on oxidization and reduction reactions produced by an artificial light source for general lighting service, including decomposition and removal of air and water contaminants, deodorization, and antibacterial, antifungal, self-cleaning, and antifogging actions

2.1.44

in-plane reinforced (2D) ceramic matrix composite

ceramic matrix composite with continuous reinforcement, which is distributed principally in two directions

2.1.45

low emission ceramic

ceramic matrix composite with continuous reinforcement, which is distributed principally in two directions

2.1.46

machinable ceramic

ceramic that, after the last consolidation heat treatment, can be machined to tight tolerances using conventional hardmetal or abrasive tools

EXAMPLE Boron nitride, glass-ceramics, and porous aluminas.

Note 1 to entry: The natural mineral talc and pyrophyllite, machined, and heat-treated, are sometimes also referred to as machinable ceramics.

2.1.47

metallized ceramic

fine ceramic product with a coherent, predominantly metal layer applied to its surface

Note 1 to entry: Processes for metallization include painting, printing, electrolytic deposition, and physical vapour deposition.

Note 2 to entry: Metallization is carried out for specific modification of surface properties or to produce an interlayer for promoting the formation of a high integrity bond with another material (often metallic).

2.1.48

monolithic ceramic

fine ceramic which has undergone consolidation through sintering to obtain a microstructure consisting predominantly of ceramic grains of one or more phases which are homogeneously distributed on a scale which is small compared to the dimensions of the part

Note 1 to entry: Ceramic parts with low or moderate porosity are included, whereas ceramic matrix composites with ceramic filaments are excluded.

Note 2 to entry: A secondary phase can also be non-ceramic.

2.1.49

multiferroic ceramic

fine ceramic that exhibits more than one ferroic characteristic, i.e. ferromagnetism, ferroelectricity, and ferroelasticity, simultaneously

Note 1 to entry: Multiferroic ceramics consist of two categories, i.e. single-phase multiferroics, and composites or heterostructures exhibiting more than one ferroic characteristic. Typical single-phase multiferroics are TbMnO_3 , BiFeO_3 , etc.

2.1.50

multidirectional ceramic matrix composite

ceramic matrix composite with continuous reinforcement which is spatially distributed in at least three directions

2.1.51

multilayered ceramic matrix composite

ceramic matrix composite where the matrix is composed of layers of different chemical compositions

2.1.52

nanocomposite ceramic

composite with highly designed microstructure in which fine particles of nanometric size are dispersed in a ceramic matrix

Note 1 to entry: See particulate reinforced ceramic matrix composite ([2.1.57](#)).

2.1.53

nanostructured ceramic

ceramic material for which at least one of its structural or microstructural elements has one of its dimension is between 1 nm to 100 nm

2.1.54

non-oxide ceramic

fine ceramic produced primarily from substantially pure metallic carbides, nitrides, borides, or silicides or from mixtures and/or solid solutions thereof

2.1.55

optoelectronic ceramic

electroceramic, typically a ferroelectric ceramic in which the optical properties are controlled by electrical means

2.1.56

oxide ceramic

fine ceramic produced primarily from substantially pure metallic oxides or from mixtures and/or solid solutions thereof

Note 1 to entry: This term may also be applied to ceramics other than fine ceramics.

2.1.57

particulate reinforced ceramic matrix composite

ceramic matrix composite in which the reinforcing components are particles of equiaxed or platelet geometry (in contrast to whiskers or short fibres)

Note 1 to entry: See nanocomposite ceramic ([2.1.52](#)).

2.1.58

piezoelectric ceramic

piezoceramic

electroceramic, typically a ferroelectric ceramic in which the elastic and dielectric properties are coupled, with practically linear dependence, between the magnitude and direction of mechanical force applied and the electric charge created, or conversely, between the strength and direction of an electric driving field and the elastic deformation obtained

Note 1 to entry: Typical piezoelectrics are barium titanate and lead zirconium titanate.

Note 2 to entry: Elastic deformation under the influence of an electric driving field is termed the inverse piezoelectric effect.

Note 3 to entry: Piezoelectric ceramics are capable of transforming mechanical energy into electrical energy or signals and vice versa.

2.1.59

photocatalyst

substance that performs one or more catalytic functions based on oxidation or reduction reactions under photoirradiation

Note 1 to entry: The functions include decomposition and removal of air and water contaminants, deodorization, antibacterial, self-cleaning, and antifogging actions. A photocatalyst can also be used for light energy conversion.

2.1.60

photocatalytic material

material in which or on which the photocatalyst is added by coating, impregnation, mixing, etc

Note 1 to entry: Materials include ceramic, metal, plastic, paper, cloth, etc. for general purposes.

2.1.61

relaxor dielectric

class of perovskite ferroelectric that shows significant changes in permittivity, ϵ , and loss tangent, $\tan \delta$, with frequency

2.1.62

semiconducting photocatalyst

substance that displays photocatalytic action based on its electronic band structure

Note 1 to entry: This applies to metal oxides like titanium dioxide, and sulfides. Photocatalysts which are not semiconducting includes metal complexes.

2.1.63**silicate ceramic**

ceramic, made mainly from minerals and/or other siliceous raw materials, resulting in a microstructure with a substantial amount of silicate phases

Note 1 to entry: Electrical porcelain and steatite ceramics are typical silicate ceramics.

2.1.64**soft ferrite**

ferrite having a weak magnetic anisotropy, resulting in high magnetic permeability and low magnetic loss

EXAMPLE Manganese-zinc-ferro-ferrite with spinel type crystal structure, used for coils, transformers for energy conversion; ferrite with garnet-type crystal structure, such as yttrium iron garnet, used for microwave applications.

2.1.65**structural ceramic**

fine ceramic employed primarily in structural applications for its mechanical or thermomechanical performance

Note 1 to entry: The term "structural ceramic" is also applied to clay products for constructional purposes.

2.1.66**spintronic ceramic**

ceramic that utilizes charge (electronic conductivity) and the spin (magnetization) of electrons

Note 1 to entry: Typical applications include the magnetic head on a hard disk utilizing the GMR (giant magneto resistivity) effect, as well as non-volatile MRAM (magneto-resistive random access memory), etc.

2.1.67**superconducting ceramic**

electroceramic showing practically zero electrical resistance below a certain temperature

Note 1 to entry: Superconducting ceramics typically comprise certain combinations of oxides of copper, rare earths, barium, strontium, calcium, thallium and/or mercury and most of them are high-temperature superconductors.

2.1.68**surface-modified ceramic**

fine ceramic in which the surface has been subjected to a deliberate physical or compositional modification

Note 1 to entry: Surface modification is normally intended to enhance properties or performance.

Note 2 to entry: Modification processes include ion diffusion, ion implantation, ion exchange, and chemical reactions such as oxidation.

2.1.69**thick ceramic coating**

ceramic coating of a thickness typically equal to or greater than 10 μm

Note 1 to entry: Thick ceramic coatings are produced typically by thick film technology such as dipping (slurry), screen printing, or plasma spraying and so on.

2.1.70**thin ceramic coating**

ceramic coating of a thickness typically less than 10 μm

Note 1 to entry: Thin ceramic coatings are produced typically by thin film technology such as sol-gel coating process (dipping, spin coating), chemical and physical vapour deposition process.

2.1.71

unidirectional (1D) ceramic matrix composite

ceramic matrix composite with continuous reinforcement which is distributed in one single direction

Note 1 to entry: The reinforcement typically comprises ceramic filaments.

2.2 Terms for form and processing

2.2.1

as-fired surface

external surface of a ceramic product after sintering

Note 1 to entry: The as-fired surface may be relatively rough compared with surfaces machined after sintering and may have e.g. pits and adherent debris.

2.2.2

binder

one or more mainly organic compounds which are added to the ceramic body in order to enhance compaction and/or to provide enough strength to the green body to permit handling, green machining, or other operations prior to sintering

2.2.3

binder phase

tough matrix phase embedding a rigid, hard, main, ceramic phase in a composite material

EXAMPLE Binder phase: cobalt, nickel; hard phase: tungsten carbide, tantalum carbide.

Note 1 to entry: A tough matrix phase reduces the brittleness and crack sensitivity and improves the strength and toughness of the composite material.

2.2.4

**calcining
calcination**

process for changing the chemical composition and/or phases of a powder or powder compact by the action of heat and atmosphere, prior to consolidation and processing

Note 1 to entry: This process is typically used for the removal of organic material, combined water and/or volatile material from a powder or powder compact.

2.2.5

**casting
drain (hollow) casting**

forming ceramic ware by introducing a body slip into an open, porous mould, and then draining off the remaining slip when the cast piece has reached the desired thickness

2.2.6

ceramic agglomerate

accretion of ceramic particles forming a coherent, but weakly bonded mass

Note 1 to entry: Ceramic agglomerates are unintentionally generated during manufacture and preparation of ceramic powders for ceramic production and may be difficult to break down.

2.2.7

ceramic aggregate

accretion of ceramic particles forming a coherent mass with strong interfacial bonding

Note 1 to entry: Ceramic aggregates are intentionally generated during manufacture and preparation of ceramic powders and are difficult to break down.

2.2.8**ceramic body**

totality of all inorganic and organic raw material constituents after preparation of ceramic powder but before the shaping and heat treatment to produce a ceramic

2.2.9**ceramic fibre**

unit of ceramic matter characterized by a high length to diameter ratio

Note 1 to entry: Ceramic fibres are used as reinforcement in ceramic matrix composites in which case the diameter is usually smaller than 20 μm , the aspect ratio typically being greater than 100. This includes the short and long fibre.

2.2.10**ceramic filament**

unit of ceramic matter of small diameter and very long length, considered to be continuous

Note 1 to entry: Ceramic filaments are typically used as reinforcement in continuous fibre ceramic matrix composites, as tow and as woven or non-woven fabrics.

2.2.11**ceramic grain**

individual crystal within the polycrystalline microstructure of a ceramic

Note 1 to entry: This term is also used for individual, usually hard, particles of abrasive or refractory materials.

2.2.12**ceramic granulate**

mass of granules produced from a ceramic body, usually in a free flowing form, used as a feedstock for producing a green body

Note 1 to entry: There are many granulation processes; the size of the granules is typically 40 μm or greater.

2.2.13**ceramic particle**

small quantity of ceramic matter, monocrystalline, polycrystalline, or amorphous, in a discrete mass of size and shape controlled by its fabrication process

Note 1 to entry: Individual particles may accrete into unintentional ceramic agglomerates or intentional ceramic aggregates, or may be processed to form a ceramic granulate.

2.2.14**ceramic platelet**

unit of ceramic matter, consisting typically of a single crystal in a plate-like shape

Note 1 to entry: Ceramic platelets may consist of oxide or non-oxide material.

Note 2 to entry: Ceramic platelets are used as reinforcement in ceramic matrix composites in which case the width of the platelets is usually smaller than 50 μm .

2.2.15**ceramic (powder) preparation
preparation of ceramic powder**

process of converting powders and additives into a ceramic body, usually by comminution and/or mixing of the powder with binders and lubricants to provide the required chemical and physical characteristics

2.2.16**ceramic precursor**

chemical or mixture of chemicals employed for the manufacture of a ceramic powder, ceramic granulate, thin ceramic coating, monolithic ceramic or a ceramic matrix composite, or ceramic fibres, ceramic whiskers or ceramic platelets, differing in composition from the fabricated ceramic product

EXAMPLE Gaseous silicon tetrachloride used for the formation of silicon nitride and silicon carbide; metal alkoxides used for the formation of metal oxide powders.

Note 1 to entry: This term is usually applied to gas or liquid mixtures which are decomposed to form ceramic materials.

2.2.17

ceramic whisker

unit of ceramic matter, consisting typically of a single crystal having a needle-like shape

Note 1 to entry: Ceramic whiskers may consist of oxide or non-oxide material.

Note 2 to entry: Ceramic whiskers may be used as reinforcement in ceramic matrix composites, in which case, the diameter of the crystals is usually smaller than 3 μm , the aspect ratio being less than 100.

2.2.18

chemical vapour deposition

CVD

process for producing a fine ceramic by reacting gaseous species and condensing the reaction product or by heterogeneous reaction at the surface of a substrate

Note 1 to entry: This process may be used for the preparation of a solid ceramic or a ceramic powder or a ceramic coating or for infiltration of a heated substrate.

2.2.19

chemical vapour deposition coating process

CVD coating process

chemical vapour deposition used for the formation of a fine ceramic coating on a substrate

2.2.20

chemical vapour infiltration

CVI

chemical vapour deposition used for producing a fine ceramic by heterogeneous reaction at the pore surface of a heated porous ceramic preform

Note 1 to entry: CVI is typically used to produce ceramic filament reinforced ceramic matrix composites.

2.2.21

cold isostatic pressing

CIP

process of preparing a green body from a ceramic powder or a ceramic granulate by the use of (pseudo-) isostatic pressure at or near room temperature

Note 1 to entry: This process is sometimes called "CIPing".

2.2.22

consolidation

process of rigidizing a ceramic body

Note 1 to entry: Consolidation methods include mechanical densification, chemical bonding and sintering.

2.2.23

doctor blade process

process to form a ceramic sheet in which ceramic powder, binder, and solvent are mixed and spread by a knife edge (or a doctor blade) on to a carrier film

Note 1 to entry: The doctor blade process is used to form a ceramic sheet with good dimensional accuracy by adjusting the distance between a knife edge (or a doctor blade) and a carrier film.

Note 2 to entry: The doctor blade process is frequently called tape casting ([2.2.65](#)).

2.2.24

extrude

to shape a plastic body by forcing material through a die

2.2.25**filler**

organic or inorganic additive to a fine ceramic, polymer or metallic body to control processing or properties

Note 1 to entry: Examples of the use of this term include: (a) organic (or rarely, inorganic) additives to a fine ceramic body which decompose or burn out during consolidation to create intentional porosity, e.g. discrete polymer particles, (b) predominantly inert, usually particular, fine ceramic substances introduced into a fine ceramic body to control processing or properties, e.g. silicon carbide particles used in a silicon-based polymer precursor for dimensional control during subsequent consolidation, (c) predominantly inert, usually particular fine ceramic materials introduced into a different matrix in order to modify properties, e.g. aluminium oxide or hydroxide introduced into a polymer to modify stiffness or wear resistance.

2.2.26**gel casting**

process of shaping and forming a green body using the phenomenon of gelation of a suspension

2.2.27**gas pressure sintering****GPS**

sintering by the combined application of heat and gas pressure

EXAMPLE Gas pressure sintered silicon nitride, GPSSN.

Note 1 to entry: The gas pressure is typically not greater than 10 MPa.

2.2.28**green body****green part**

ceramic body that is compacted and/or shaped, but not yet heat-treated

2.2.29**green machining**

machining of a green body to a predetermined shape

2.2.30**hot isostatic pressing****HIP**

process of making a fine ceramic by application of an isostatic gas pressure at elevated temperatures

Note 1 to entry: The object may be an encapsulated powder or green body, or a pre-densified fine ceramic. Gas pressures are typically much greater than 10 MPa.

Note 2 to entry: This process is sometimes called "HIPing".

2.2.31**(uniaxial) hot pressing****HP**

process of making a fine ceramic, normally by application of a unidirectional (uniaxial) force at elevated temperature

Note 1 to entry: For uniaxial hot pressing, an inductively heated graphite die is usually employed.

2.2.32**hydrothermal synthesis**

process of preparing fine ceramics and other inorganic materials by chemical reaction in aqueous solution under high temperature and pressure in a pressure vessel such as an autoclave

Note 1 to entry: Fine ceramics in powder, film, or bulk forms may be prepared by hydrothermal synthesis.

2.2.33

injection moulding

IM

process of shaping a green body by injecting an appropriately formulated mass into a mould or die

2.2.34

liquid phase sintering

LPS

sintering achieved by the presence of a liquid phase

Note 1 to entry: The amount and properties of the liquid phase are determined by the composition of the green body, temperature and pressure. This process is enhanced by accelerated diffusion and dissolution-precipitation phenomena.

2.2.35

low-pressure chemical vapour deposition

LPCVD

chemical vapour deposition at low gas pressure

Note 1 to entry: The gas pressure is typically less than 0,01 MPa.

2.2.36

machined and refired

state of treatment of a fine ceramic component which has been machined and subsequently refired to modify the surface properties

2.2.37

manufacture of ceramic powders by flame pyrolysis

process of formation of ceramic particles by passing reactants through the combustion zone of a flame

2.2.38

manufacture of ceramic powders by gas-phase reaction

process of formation of ceramic particles from gaseous reactants using an external stimulus

EXAMPLE Silicon nitride powder produced by reaction between silicon tetrachloride gas and ammonia gas.

Note 1 to entry: External stimuli include heating, electrical discharge and laser irradiation.

2.2.39

manufacture of ceramic powders by sol-gel technique

process of formation of ceramic particles by using sol-gel processing in which the sol is dispersed into fine droplets before conversion into a gel, followed by further processing

Note 1 to entry: See sol-gel processing ([2.2.59](#)).

Note 2 to entry: The conversion of sol into gel can be by a reaction such as dehydration. The common route is a hydrolysis reaction followed by condensation to give direct precipitation of fine ceramic particles.

Note 3 to entry: Further processing includes drying and calcining of gel.

2.2.40

melt infiltration process

process used to fill CMC porosity by liquid infiltration of melt metal

2.2.41

metal-organic chemical vapour deposition

MOCVD

chemical vapour deposition using single or mixed metal-organic vapours

2.2.42**microwave sintering**

use of high power, high frequency electromagnetic waves (microwaves) to heat a green body by internal dielectric loss to a sufficient temperature for sintering

Note 1 to entry: The action of the microwaves may in some cases accelerate the sintering process.

2.2.43**plasma-enhanced chemical vapour deposition****PECVD**

chemical vapour deposition using a plasma assisted reaction

Note 1 to entry: The reaction in the gaseous phase can e.g. be stimulated by application of a plasma formed by coupled laser or other plasma generator.

Note 2 to entry: Also known as Plasma Activated Chemical Vapour Deposition (PACVD).

2.2.44**physical vapour deposition****PVD**

process for producing, e.g. a ceramic film by transport of the required chemical species, some or all of which are generated from a source or sources by physical means such as thermal, electron beam, arc or laser evaporation or sputtering, and deposition onto a prepared substrate with or without the assistance of a reactive atmosphere, ionic bombardment or a gas plasma

2.2.45**polycrystalline diamond****PCD**

polycrystalline form of carbon with cubic crystalline structure

Note 1 to entry: Polycrystalline diamond is normally prepared by high-pressure and high temperature processing to achieve direct bonding between diamond grains.

Note 2 to entry: Polycrystalline diamond film is normally prepared by low-pressure chemical vapour deposition.

2.2.46**plasma process**

process for producing fine ceramics by using a high-temperature plasma, based on the vaporization of raw materials by the plasma and a subsequent condensation/deposition process

Note 1 to entry: Fine ceramics in powder, film, or bulk forms may be formed by plasma processes.

2.2.47**polymer derived ceramic****PDC**

polymer used to obtain ceramics by pyrolysis

2.2.48**polymer impregnation pyrolysis****PIP**

process of matricing for CMC by several cycles of polymer impregnation and pyrolysis

2.2.49**post-sintering****PS**

sintering after a previous consolidation stage

EXAMPLE Post-sintered reaction-bonded silicon nitride, PSRBSN.

2.2.50

pressureless sintering

PLS

sintering in the absence of a raised mechanical or gas pressure

EXAMPLE Pressureless-sintered silicon nitride, PLSSN.

2.2.51

pyrolytic carbon

form of carbon produced through the thermal decomposition of carbon-containing precursors

Note 1 to entry: Precursors are, e.g. long-chain polymers or reacting gaseous mixtures.

Note 2 to entry: Pyrolytic carbon is used as interphase in ceramic matrix composite, which is the solid form of carbon deposited on a hot surface by cracking of gaseous or liquid hydrocarbons.

2.2.52

pyrolytic graphite

form of high-purity graphite produced from the vapour phase by thermal decomposition of carbon-containing gas and deposition on to a substrate

Note 1 to entry: Pyrolytic graphite usually has a highly oriented microstructure and strongly anisotropic properties.

2.2.53

reaction bonding

RB

process for producing a fine ceramic by consolidation of a green body by a chemical reaction between gaseous, liquid, or solid species at elevated temperature producing a bond between ceramic particles

EXAMPLE Silicon nitride objects can be produced by the reaction of silicon with nitrogen; reaction-bonded silicon nitride, RBSN.

Note 1 to entry: The use of this term for a process that falls under the definition of reaction sintering is deprecated.

2.2.54

reaction sintering

RS

process for producing a fine ceramic by consolidation of a green body by a solid state chemical reaction accompanied by solid state sintering at high temperatures to produce a bond between ceramic particles

EXAMPLE During the production of aluminium titanate ceramics, aluminium titanate can be formed by a solid state reaction between aluminium oxide and titanium oxide.

Note 1 to entry: The use of this term for liquid or gaseous reaction bonding process is deprecated.

2.2.55

reinforcement

ceramic particles, ceramic whiskers, ceramic platelets, ceramic fibres, or ceramic filaments incorporated in a fine ceramic, normally for the purpose of improving mechanical properties

Note 1 to entry: The reinforcement may alternatively be non-ceramic.

Note 2 to entry: The mechanical properties may be improved as regards their strength, toughness, wear resistance, hardness, creep resistance, or other characteristics.

Note 3 to entry: For ceramic matrix composites continuous reinforcement, i.e. ceramic filaments, is often used.

2.2.56

roll compaction

process of shaping a green body by feeding a granulated ceramic body between contra-rotating rollers which compact it into a strip or sheet

2.2.57**self-sustained high temperature synthesis
SHS**

process for producing a solid fine ceramic in which primarily the heat of the exothermic reaction from reactant(s) is utilized

Note 1 to entry: Also known as self-propagating high temperature synthesis.

2.2.58**sintering**

process of densification and consolidation of a green body by the application of heat with resulting joining of ceramic particles and increasing contact interfaces due to atom movement within and between the ceramic grains of the developing polycrystalline microstructure

Note 1 to entry: Sintering may take place either directly or through the agency of a secondary phase, e.g. in reaction sintering and liquid-phase sintering.

2.2.59**sol-gel processing**

chemical synthesis of ceramic materials typically based on hydrolysis of ceramic precursors (alkoxides, acids, hydroxides) and subsequent condensation or aggregation to form sols followed by conversion to a gel and further processing

Note 1 to entry: A sol is a liquid dispersion of colloidal solid particles of up to several hundred nanometers in size, while a gel is a rigid interconnected network filled with either gas or liquid.

Note 2 to entry: Further processing includes, e.g. drying, calcining, and sintering.

Note 3 to entry: Organically-modified inorganic networks (ormocers) can be formed by sol-gel processing.

2.2.60**sol-gel coating process**

process for producing a fine ceramic coating on a product by initially covering the surface with ceramic precursor followed by sol-gel processing

2.2.61**sol-gel consolidation technique**

processing technique to produce a fine ceramic by using sol-gel processing in combination with casting, extrusion or impregnation with subsequent drying and sintering

Note 1 to entry: The size of articles produced by this technique is often limited by the large shrinkage arising from such processes.

2.2.62**solid casting**

slip casting of a ceramic material without pour-off residue especially forming solid pieces or hollow ware if mold has a core

2.2.63**spark plasma sintering****SPS**

sintering process in which a compact of powder is pressed using a die and is rapidly heated by pulsing direct current through the powder and/or the die

2.2.64**supercritical field synthesis**

process for producing fine ceramics in a supercritical fluid of carbon dioxide or water

Note 1 to entry: Since a supercritical condition has the diffusivity characteristics of a gas phase and the solubility characteristics of a liquid phase, it is possible to prepare different chemical products compared with other liquid and gas phase processes.

Note 2 to entry: Supercritical field synthesis may be used to form fine ceramic powders, films, and bulk materials.

2.2.65

tape casting

process of shaping a green body in the form of a tape by casting a slurry of ceramic body (slip) as a film on a flat surface, followed by drying

Note 1 to entry: Organic additions to the slip give the tape flexibility and permit forms to be made from it by cutting, stamping, or punching, from which components such as substrates, packages, and capacitors can be manufactured.

Note 2 to entry: Most tape casting uses a doctor blade process ([2.2.23](#)).

2.2.66

vitreous carbon

form of carbon derived through solid phase carbonization from a preform comprising an appropriate highly cross-linked polymer

Note 1 to entry: Vitreous carbon is characterized by a pseudo-amorphous, isotropic structure with low density, and non-permeability for gases.

2.3 Terms for properties and testing

2.3.1

antibacterial

condition inhibiting the growth of bacteria on the surface of flat surface materials or cloths

2.3.2

antifungal activity

inhibition of germination or inactivation of fungal spores on the surface of materials

2.3.3

apatite-forming ability

capability to develop apatite on the surface

2.3.4

bulk density of ceramics

value obtained by dividing the mass of test specimen by the bulk volume of ceramic specimen

2.3.5

chip

piece of material broken off the edge or corner of a ceramic test-piece or component

Note 1 to entry: When pieces of material break off the edges or corners of a test-piece or component, they leave a "chipped area".

2.3.6

competing failure modes

distinguishably different types of fracture initiation processes in ceramic test-pieces or components that result from concurrent critical flaw distributions

2.3.7

compound critical flaw distribution

flaw distribution in ceramic test-pieces or components which contain more than one type of strength-controlling flaw not occurring in a purely concurrent manner

Note 1 to entry: All test-pieces contain flaw type A and some additionally contain a second independent type B.

2.3.8

compressive strength

maximum value of uniaxial compressive stress at the instant of collapse of a ceramic test-piece, either by shearing or fragmentation

2.3.9**concurrent critical flaw distribution**
competing critical flaw distribution

type of flaw distribution where every ceramic test-piece or component contains representative defects of each independent flaw type which compete with each other to cause failure

2.3.10**crack**

plane of fracture in a ceramic test-piece or component without complete separation

2.3.11**critical flaw**

flaw acting as the source of a failure in a ceramic test-piece or component

2.3.12**critical flaw distribution**

distribution of type, shape, and size of critical flaws in a population of ceramic test-pieces or components

2.3.13**exclusive critical flaw distribution**

type of flaw distribution where each test-piece or component contains defects from a single population, but more than one population is present in the batch

2.3.14**extraneous flaw**

type of flaw which is not created during manufacturing

EXAMPLE Test-pieces with flaws from machining, which do not occur in the manufactured components.

2.3.15**flaw**

inhomogeneity, discontinuity, or other structural irregularity in ceramic material

EXAMPLE Grain boundary, large grain, pore, impurity, crack.

Note 1 to entry: The term "flaw" should not be taken to mean that the material is functionally defective, but rather as an inevitable microstructural inhomogeneity.

Note 2 to entry: When the material is mechanically loaded, a flaw provides a stress concentration and enhances the risk of mechanical failure.

2.3.16**flaw distribution**

spread of type, shape, and size of flaws within a single ceramic test-piece or component

2.3.17**flexural strength**

maximum stress supported by a specified beam in bending at the instance of failure as determined at a given stress rate in a particular environment

2.3.18**four-point flexural strength****four-point bending strength**

strength determined by bending a beam-shaped ceramic test-piece whereby the test-piece is supported on bearings near its ends, and is loaded equally at two positions symmetrically disposed about the centre of the supported span

Note 1 to entry: The term "quarter-point flexural strength" is sometimes used for the strength as measured by the four-point flexure geometry wherein the load positions are each one-quarter of the support span from the support bearings.

2.3.19

indoor lighting environment

indoor lighting environment with an artificial light source for general lighting service that does not include sunlight

2.3.20

photocatalyst antibacterial activity value

numerical difference between the logarithmic values of the total number of viable bacteria on the material with and without photocatalytic treatment after photoirradiation

Note 1 to entry: This value includes the decrease of the number of bacteria without UV irradiation.

Note 2 to entry: In ISO 27447, the film adhesion method and glass adhesion method are used for flat surface materials and textiles, respectively.

2.3.21

photocatalyst antifungal activity value

numerical difference between the logarithmic values of the total number of surviving fungal spores (colonies) on the material with and without photocatalytic treatment after UV irradiation

Note 1 to entry: This value includes the decrease of the number of fungal without UV irradiation.

2.3.22

photonic efficiency

percentage of the incident photon flux that induces a photochemical reaction in a photocatalyst

Note 1 to entry: It is assumed that one photon can induce the decolourization of one dye molecule in the case of methylene blue.

2.3.23

pore

cavity in a ceramic

Note 1 to entry: Pores may be located in the interior or at the surface. Pores at the surface are usually called pits.

2.3.24

porous region

inhomogeneity comprising a concentration of pores in a ceramic

Note 1 to entry: If interconnected to the surface of a ceramic test-piece or component, such a region will retain dye when dye-tested.

2.3.25

precrack

crack that is intentionally induced into the test specimen prior to testing the specimen to fracture

2.3.26

proof testing

application of a predetermined stress to a ceramic test-piece or component over a defined period of time to ascertain whether it contains a serious strength-limiting defect

Note 1 to entry: Removal of the failed test-pieces or components from a batch modifies the failure statistics of the survivors, such that the two-parameter Weibull distribution is typically no longer valid.

2.3.27

ring-on-ring strength

maximum value of equibiaxial flexural stress, at fracture, generated in a symmetrical plate-shaped ceramic test-piece by applying forces to opposing sides through dissimilar sized concentric ring contacts

2.3.28**R-curve behaviour**

increase in apparent toughness with crack growth in ceramic test-pieces or components

Note 1 to entry: This effect may arise as a consequence of changes to microcrack distributions ahead of the crack or of local internal stressing, e.g. through phase transformations, or through uncracked or wedged ligaments behind the crack tip.

2.3.29**self-loaded deformation**

deformation that results when a ceramic test-piece or component distorts under its own weight at elevated temperatures

Note 1 to entry: Self-loaded flexural deformation is sometimes referred to as “sagging”.

2.3.30**self-cleaning effect**

maintenance of surface cleanliness of a material by employing a photocatalyst loaded onto the surface

EXAMPLE Glass, tiling and other facings for buildings, and plastics and coatings for general purposes.

Note 1 to entry: Self cleaning using photocatalysis is achieved through decomposition of surface contaminants by redox reactions, and/or hydrophilicity that allows stains or dirt to be easily removed by the flow of (rain) water over the surface.

2.3.31**specific photocatalytic activity**

measure of capacity of a material to promote a specific photochemical reaction under defined conditions

Note 1 to entry: Specific photocatalytic activity is expressed in mole per square metre and hour [mol/(m²h)].

2.3.32**static fatigue**

degradation of strength under a constant load smaller than the failure load

Note 1 to entry: Weakening typically occurs by subcritical crack growth (or slow crack growth).

2.3.33**subcritical crack growth****slow crack growth**

extension of existing cracks or flaws in the microstructure of a ceramic test-piece or component under a stress which does not produce instantaneous failure

Note 1 to entry: Subcritical crack growth can be caused by stress corrosion, creep crack growth, or active corrosion.

2.3.34**subcritical crack growth parameters****slow crack growth parameters**

parameters describing the relationship between crack growth velocity and stress intensity factor at the crack tip in a ceramic test-piece or component

2.3.35**strength by sphere indentation**

maximum force to the fracture of a test-piece when a compressive force is applied to the test-piece through the spherical indenter

2.3.36**thermal shock resistance**

ability of a ceramic test-piece or component to withstand stress induced by rapid changes of temperature

Note 1 to entry: Thermal shock resistance is determined by the material properties, the shape and size of the test-piece or component and the thermal environment.

Note 2 to entry: This term may be used in a more specific sense for a specified type of test, e.g. quenching into water from a high initial temperature.

2.3.37

three-point flexural strength

three-point bending strength

strength determined by bending a beam-shaped ceramic test-piece whereby the test-piece is supported on bearings near its ends and a central load is applied

2.4 Abbreviations for ceramic materials

2.4.1

ALN

aluminium nitride

fine ceramic based principally on aluminium nitride

Note 1 to entry: Aluminium nitride typically contains a small amount of oxygen.

2.4.2

ALON

aluminium oxynitride

fine ceramic, based principally on aluminium oxynitride

Note 1 to entry: Aluminium oxynitride is generally in a cubic crystalline phase form.

2.4.3

Ap

apatite

group of calcium-phosphates including bone mineral and the main inorganic constituent of bones and teeth similar to hydroxy(l)apatite, which has the composition $\text{Ca}_{10}(\text{PO}_4)_6(\text{OH})_2$

Note 1 to entry: Bone mineral may also contain ions such as CO_3^{2-} , F^- , Na^+ and Mg^{2+} .

Note 2 to entry: In the mineralogical field, the term "apatite" is used as a group name for apatite minerals including fluorapatite, chlorapatite, etc.

2.4.4

AT

aluminium titanate

fine ceramic, based principally on aluminium titanate

Note 1 to entry: Aluminium titanate as a crystalline phase is sometimes referred to as tialite.

2.4.5

ATZ

alumina toughened zirconia

zirconium oxide-based fine ceramic, normally of the TZP type, with aluminium oxide added

Note 1 to entry: The aluminium oxide addition increases hardness, stiffness and strength.

2.4.6

BN

boron nitride

fine ceramic, based principally on boron nitride

Note 1 to entry: The chemical formula of the compound boron nitride and the abbreviation are identical.

Note 2 to entry: The abbreviation "BN" is normally applied to material having the hexagonal crystalline structure.

2.4.7**BTO****barium titanium oxide**

fine ceramic, based principally on barium titanium oxide

Note 1 to entry: Barium titanium oxide typically comprises a crystalline perovskite structure phase.

Note 2 to entry: BT is also used instead of BTO.

2.4.8**CAS****calcium aluminosilicate**

fine ceramic, glass, or glass-ceramic material based principally on oxides of calcium, aluminium, and silicon

Note 1 to entry: Calcium aluminosilicate typically contains the crystalline phases anorthite, gehlenite, or other calcium silicate-based phases.

Note 2 to entry: Cement phase literature may incorporate numbers into this abbreviation.

2.4.9**CBN****cubic boron nitride**

fine ceramic, based principally on boron nitride having a cubic crystalline structure

Note 1 to entry: Boron nitride in the cubic crystalline form is analogous in structure to diamond.

2.4.10**CMC****ceramic matrix composite**

fine ceramic, composed of a ceramic matrix containing reinforcement

Note 1 to entry: The reinforcement is often continuous, i. e. ceramic filaments, distributed in one or more spatial directions, but this term is also used for discontinuous reinforcement, e.g. short ceramic fibres, ceramic whiskers, ceramic platelets, or ceramic particles.

Note 2 to entry: C/C composites are included in CMC composites.

2.4.11**CSZ****cubic stabilized zirconia**

fine ceramic, based principally on zirconium oxide, which contains sufficient additional oxide species to retain the cubic crystal modification on cooling from the processing temperature to room temperature

Note 1 to entry: Theoretically CSZ should contain only the cubic crystal modification, but depending on the composition and the thermal history small amount of other crystal modifications can be present.

Note 2 to entry: Typically stabilizers include magnesia, calcia, yttria, or other rare-earth species.

2.4.12**EBC****environmental barrier coating**

ceramic coating possibly multilayered used to protect fine ceramics of environmental aggression

2.4.13**FSZ****fully stabilized zirconia**

fine ceramic, based principally on zirconium oxide, which contains sufficient stabilizing oxide species to retain only the high-temperature cubic crystal modification on cooling from the processing temperature to room temperature

Note 1 to entry: The stabilizer is typically one or more of magnesia, calcia, yttria, and other rare earth species.

2.4.14

GPSSN

gas pressure sintered silicon nitride

fine ceramic, based principally on silicon nitride, densified by gas pressure sintering

Note 1 to entry: When sintering silicon nitride, the gas atmosphere elected should normally contain nitrogen in order to inhibit the dissociation of the nitride at elevated temperatures.

2.4.15

HA

hydroxy(l)apatite

fine ceramic, based principally on oxides of calcium and phosphorus with hydroxyl ions typically forming the crystalline phase hydroxy(l)apatite

Note 1 to entry: In the bio-medical field including the biomaterial field, HAp is also acceptable as an abbreviation of hydroxyapatite to avoid confusion with abbreviation of hyaluronan (hyaluronic acid), HA.

2.4.16

HPSC

hot-pressed silicon carbide

fine ceramic, based principally on silicon carbide, densified by the action of an applied force (normally unidirectional) at elevated temperature

2.4.17

HPSN

hot-pressed silicon nitride

fine ceramic, based principally on silicon nitride, densified by the action of an applied force (normally unidirectional) at elevated temperature

2.4.18

HTS

HTSC

high-temperature superconductor

superconducting ceramic having superconducting properties at temperatures above 77 K, the boiling point of liquid nitrogen

2.4.19

ITO

indium tin oxide

fine ceramic, based principally on oxides of indium and tin

Note 1 to entry: Indium tin oxide typically comprises a crystalline bixbyite structure phase.

2.4.20

LAS

lithium aluminosilicate

fine ceramic, typically a glass or glass-ceramic, based principally on oxides of lithium, aluminium, and silicon

Note 1 to entry: Lithium aluminium silicate typically contains crystalline phases such as petalite, beta-eucryptite, or their solid solutions.

2.4.21

LPSSC

liquid-phase sintered silicon carbide

fine ceramic, based principally on silicon carbide, densified by liquid-phase sintering at high temperatures

2.4.22**MAS****magnesium aluminosilicate**

fine ceramic, typically a glass or glass-ceramic, based principally on oxides of magnesium, aluminium and silicon

Note 1 to entry: Magnesium aluminium silicate typically contains the crystalline phase cordierite.

2.4.23**MAT****magnesium aluminium titanate**

fine ceramic, based principally on oxides of magnesium, aluminium and titanium

Note 1 to entry: Magnesium aluminium titanate typically contains the crystalline phase pseudo-brookite.

2.4.24**PCD****polycrystalline diamond**

polycrystalline form of carbon with cubic crystalline structure

Note 1 to entry: Polycrystalline diamond is normally prepared by high-pressure and high-temperature processing to achieve direct bonding between diamond grains.

Note 2 to entry: Polycrystalline diamond film is normally prepared by low-pressure chemical vapour deposition.

2.4.25**PLZT****lead lanthanum zirconium titanate**

fine ceramic, based principally on oxides of lead, lanthanum, zirconium and titanium

Note 1 to entry: Lead lanthanum zirconium titanate typically comprises crystalline perovskite structure phase.

2.4.26**PMN****lead magnesium niobate**

fine ceramic, based principally on oxides of lead, magnesium, and niobium

Note 1 to entry: Lead magnesium niobate typically comprises crystalline perovskite structure phase.

2.4.27**PMNT****lead magnesium niobium titanate****PMN-PT****lead magnesium niobate-lead titanate**

fine ceramic, based principally on oxides of lead, magnesium, niobium, and titanium

2.4.28**PSRBSN****post-sintered reaction-bonded silicon nitride**

fine ceramic, based principally on silicon nitride, which as a green body, comprising elemental silicon and liquid-phase forming sintering aids, is first reaction-bonded in a nitrogen atmosphere, followed by sintering at higher temperatures

Note 1 to entry: When sintering silicon nitride, the gas atmosphere selected should normally contain nitrogen in order to inhibit the dissociation of the nitride at elevated temperatures.

2.4.29

PSZ

partially stabilized zirconia

fine ceramic, based principally on zirconium oxide, which contains insufficient stabilizing oxide species to retain only the high-temperature cubic crystal modification on cooling from the processing temperature to room temperature

Note 1 to entry: The stabilizer is typically magnesia, calcia, yttria, or ceria. Normally the material partially destabilizes on cooling to comprise two or more different modifications.

2.4.30

PZT

lead zirconium titanate

fine ceramic, based principally on oxides of lead, zirconium, and titanium

Note 1 to entry: Lead zirconium titanate typically comprises crystalline perovskite structure phases.

2.4.31

RBAO

reaction-bonded aluminium oxide

fine ceramic, based principally on aluminium oxide, typically densified by the in-situ reaction between oxygen and elemental aluminium inside a green body containing aluminium oxide and aluminium powders

2.4.32

RBSC

reaction-bonded silicon carbide

fine ceramic, based principally on silicon carbide, typically densified by the in-situ reaction between carbon and elemental silicon inside a green body containing silicon carbide, silicon, and carbon powders

Note 1 to entry: The object may be porous if the reaction is with particulate silicon, or dense if the reaction is with liquid silicon by infiltration. In the latter case an elemental silicon phase is normally present.

Note 2 to entry: The term "reaction-sintered silicon carbide" and the abbreviation "RSSC" are sometimes used, but both are deprecated, because reaction sintering is not involved.

2.4.33

RBSN

reaction-bonded silicon nitride

fine ceramic, based principally on silicon nitride, produced principally by the in-situ reaction of nitrogen with a green body comprising primarily elemental silicon

Note 1 to entry: Reaction-bonded silicon nitride usually exhibits an open porosity.

Note 2 to entry: The term "reaction-sintered silicon nitride" and the abbreviation "RSSN" are sometimes used, but both are deprecated, because reaction sintering is not involved.

2.4.34

RSC

recrystallized silicon carbide

fine ceramic, based principally on silicon carbide, prepared in coarse-grained porous form by sintering at very high temperature

2.4.35

SBF

simulated body fluid

in the evaluation of fine ceramics for biomedical use, an inorganic solution having a similar composition to human blood plasma without organic components

Note 1 to entry: In the bio-medical field, a substitute for body fluid and cell culture medium, e.g. Ringer's solution, Hank's solution and Eagle's minimum essential medium, are sometimes called "simulated body fluid" or "pseudo-body fluid".