
**Textiles — Determination of twist in
yarns — Direct counting method**

*Textiles — Détermination de la torsion des fils — Méthode par
comptage direct*

STANDARDSISO.COM : Click to view the full PDF of ISO 2061:2010



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

STANDARDSISO.COM : Click to view the full PDF of ISO 2061:2010



COPYRIGHT PROTECTED DOCUMENT

© ISO 2010

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	2
3 Terms and definitions	2
4 Principle.....	3
5 Apparatus	3
6 Standard atmosphere.....	3
7 Sampling.....	3
8 Test specimens.....	4
8.1 Length.....	4
8.1.1 Single spun yarns.....	4
8.1.2 Single multifilament, plied and cabled yarns	4
8.2 Selection.....	4
8.3 Number of test specimens.....	4
9 Procedure 1 — Determination of the direction of twist	5
10 Procedure 2 — Determination of the amount of twist	6
10.1 Preliminary procedure	6
10.2 Single, spun yarn.....	6
10.3 Single, multifilament yarns.....	6
10.4 Plied yarns	7
10.5 Cabled yarns	7
11 Calculation of results	7
11.1 Average twist per specimen	7
11.2 Average twist per sample	8
11.3 Variation of observations	8
11.4 Change in length on untwisting.....	8
11.5 Twist factor (α).....	8
12 Expression of results	9
13 Test report.....	9
13.1 Single yarns	9
13.2 Plied yarns	10
13.3 Cabled yarns	10
Annex A (informative) Suggested procedure for sampling	11
Bibliography.....	12

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 2061 was prepared by Technical Committee ISO/TC 38, *Textiles*, Subcommittee SC 23, *Fibres and yarns*.

This third edition cancels and replaces the second edition (ISO 2061:1995), of which it constitutes a minor revision by replacing the use of the outdated term *folded* with *plied*.

The principal additional modifications consist of the following:

- editing Clause 3, *Terms and definitions*, in accordance with the ISO/IEC Directives, Part 2:2004;
- deleting publication dates from normative references;
- a Bibliography has been added.

Textiles — Determination of twist in yarns — Direct counting method

1 Scope

1.1 This International Standard specifies a method for the determination of the direction of twist in yarns, the amount of twist, in terms of turns per unit length, and the change in length on untwisting, by the direct counting method.

1.2 This International Standard is applicable to

- a) single yarns (spun and filament),
- b) plied yarns, and
- c) cabled yarns.

Separate procedures are given for each type of yarn. The method is designed primarily for yarns in packages, but, with special precautions, the procedures can be used for yarns taken from fabrics. It is not suitable for the determination of twist in a monofilament.

NOTE See also ISO 1890^[1], which was prepared especially for the needs of glass textile technology, and ISO 7211-4^[2].

1.3 This International Standard covers the determination of twist in plied and cabled yarns as follows:

- a) in plied yarns: the final twist of the plied yarns and the original twist of the single yarn before plying;
- b) in cabled yarns:
 - the final cabling twist of the yarn;
 - the original twist of the plied yarn after plying, but prior to the last stage of processing;
 - the twist of the single yarn before plying.

1.4 If desired, the twist of single and plied yarn components as they lie in the final structure can be determined by the special procedure given in 10.5.7.

1.5 This International Standard is not applicable, except by agreement, to yarns which stretch more than 0,5 % when the tension increases from 0,5 cN to 1,0 cN per unit linear density of the yarn expressed in tex. Such yarns can be tested under special conditions of tension which are accepted by all parties interested in the test results.

1.6 This International Standard is not suitable for products of open-end spinning and intermingled (interlaced) multifilament yarns.

1.7 This International Standard is not applicable to yarns which are too large to permit their being placed in the clamps of the testing apparatus without crushing or distortion severe enough to affect the test results.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 2, *Textiles — Designation of the direction of twist in yarns and related products*

ISO 139, *Textiles — Standard atmospheres for conditioning and testing*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

twist

number of turns about the axis of a yarn based on its nominal gauge length before untwisting

NOTE Twist should preferably be expressed as turns per metre (turns/m), but it may be expressed as turns per centimetre (turns/cm).

3.2

gauge length

distance between two effective clamping points of the test specimen mounted in the testing equipment

3.3

initial length

length of a test specimen under a specified pretension at the beginning of a test

3.4

change in length on untwisting

increase or decrease in initial length observed when the specimen is untwisted, expressed as the percentage extension, or contraction, based on the specimen initial length

3.5

moisture equilibrium for testing

that state reached when the rate of increase in mass of a sample or specimen in a specified (test) atmosphere does not exceed that prescribed for the material being tested

NOTE 1 See ISO 139.

NOTE 2 A textile material is in moisture equilibrium with the ambient atmosphere when it does not exchange water with this atmosphere; its mass then remains constant as long as the experiment is carried out in an unchanged atmosphere. For test purposes, moisture equilibrium is reached by absorption, starting from a relatively low moisture content.

3.6

yarn package

length or lengths of yarn in a form suitable for use, handling, storing or shipping

NOTE Packages may be comprised of unsupported yarn, such as balls, or supported yarn, such as skeins, cakes, bobbins, cops, cones, pirns, spools, tubes or beams.

3.7

twist factor

measure of the spiralling orientation of the fibres in a spun yarn or of the filaments in a filament yarn

NOTE The twist factor is related to the angle which fibres on the surface of the yarn make with the axis of the yarn, and is a measure of the hardness of the resulting yarn due to twist.

4 Principle

The twist in a known length of yarn is removed by rotating one end of the specimen with respect to the other until the components of the yarn being tested are parallel. The exact number of turns required to remove the twist is reported in terms of turns per unit length of yarn.

5 Apparatus

5.1 Twist counter, consisting of a pair of clamps, one of which is rotatable in either direction and positively connected to a revolution counter. The position of one or both clamps shall be adjustable to permit testing yarn lengths from 10 mm to 500 mm. There shall be no play in the clamp which might affect the gauge length.

5.1.1 Means shall be provided for applying tension to the specimen and for rapidly determining the specimen length with an accuracy of $\pm 0,5$ mm or ± 2 %, whichever is smaller.

NOTE The limit of 2 % is consistent with the highest accuracy required in counting the number of turns in the specimen.

5.1.2 The counting device shall be capable of recording the number of revolutions of the rotatable clamp.

5.1.3 If the contraction or extension of the untwisted specimen is to be measured, the movable but nonrotatable clamp shall be capable of travelling with essentially no friction.

5.2 Dissecting needle.

5.3 Means for magnifying the specimen being tested.

5.4 Equipment for reeling laboratory sample skeins (optional).

6 Standard atmosphere

6.1 The standard atmospheres for preconditioning, conditioning and testing shall be as specified in ISO 139.

The amount of twist is not affected directly by changes in relative humidity, but since wide changes in humidity cause changes in the length of some materials, all determinations should be made on samples in equilibrium with the appropriate standard atmosphere.

6.2 Generally, it is not necessary to precondition samples before conditioning for twist tests.

7 Sampling

7.1 Samples shall be taken in one of the following ways:

- a) according to the directions, if any, given in the material specification;
- b) according to procedures approved by ISO for textile products, if directions on sampling are not included in the material specification;
- c) according to the method given in Annex A, if neither a) nor b) is applicable.
 - 1) Bulk samples shall be taken as directed in A.1.
 - 2) Laboratory-sample packages shall be taken from the bulk sample as directed in A.2.

8 Test specimens

8.1 Length

8.1.1 Single spun yarns

The initial length of the specimen shall be as great as possible, but shall be somewhat less than the average length of the staple fibre used to spin the yarn. The initial lengths of specimens listed in Table 1 are commonly used.

Table 1 — Specimen lengths

Type of yarn material	Specimen initial length mm
Cotton	10 and 25
Worsted	25 and 50
Woolen	25 and 50
Bast fibre	100 and 250

8.1.2 Single multifilament, plied and cabled yarns

8.1.2.1 Take an initial length of 250 mm ± 0,5 mm if the nominal twist is > 1 250 turns/m.

8.1.2.2 Take an initial length of 500 mm ± 0,5 mm if the nominal twist is < 1 250 turns/m.

8.2 Selection

8.2.1 Test specimens shall be taken, at the lowest tension practicable, from the end of the package if this is the normal method of use; otherwise, take the yarn from the side of the package. Discard the few metres of yarn at the beginning and end of the package in order to avoid damaged sections.

8.2.1.1 If it is desired to reel laboratory sample skeins, the yarn specimens shall be taken as specified in 8.2.1 and shall be representative of the original package.

8.2.2 If two or more test specimens are taken from an individual yarn package, they shall be taken at random intervals of at least 1 m in order to minimize the effects of cyclic variation introduced during the manufacture. If more than two specimens are taken from an individual package, take groups of specimens, not more than five to a group, at intervals of several metres.

8.3 Number of test specimens

8.3.1 Take the number of specimens required in the material specification, when applicable.

8.3.2 In the absence of material specification, take a number of specimens designed to give the precision specified below, following the directions given in 8.3.3 or 8.3.4, depending on the information available on the variation of twist results in the material being tested.

8.3.3 If information on variation is available, take a number of specimens, *n*, calculated by the formula given in Table 2, to secure the precision specified at a probability of 95 %.

Table 2 — Formula for number of specimens, n , using information on variation

Type of yarn	Range of twist	Precision	Formula for n^a
Single multifilament	Less than 40 turns/m	$\pm 4,0$ turns/m	$0,240\sigma^b$
Single multifilament	40 turns/m to 100 turns/m	$\pm 5,0$ turns/m	$0,154\sigma^b$
All other yarns	—	$\pm 5,0$ %	$0,154\nu^c$

^a Where n is the number of tests.

^b Where σ is the standard deviation of individual results, determined from extensive past records on similar material.

^c Where ν is the coefficient of variation of individual test results, determined from extensive past records on similar material.

8.3.4 If no information on variation is available or in the case of a dispute, determine the number of specimens as follows.

- Take the number of specimens, n , specified in Table 3, which also indicates the variation assumed to calculate n .
- Calculate the coefficient of variation, ν , or the twist results by normal statistical methods. If the variation is such that the precision with 95 % confidence is greater than 5 %, increase the number of tests. The number of tests required can be calculated as follows:

$$n = \left(\frac{1,96\nu}{5} \right)^2$$

where

n is the number of tests;

ν is the coefficient of variation of individual test results, determined from extensive past records on similar materials.

Table 3 — Number of specimens, n , in the absence of information on variation

Type of yarn	Range of twist	n	Assumed variation ^a
Single, spun	All	50	$\nu = 18$ %
Single, multifilament	Less than 40 turns/m	20	$\sigma = 8,0$ turns/m
Single, multifilament	40 turns/m to 100 turns/m	20	$\sigma = 10,0$ turns/m
Single, multifilament	More than 100 turns/m	20	$\nu = 10$ %
Plied and cabled yarns	All	20	$\nu = 10$ %

^a Where ν and σ are as defined in Table 2, footnotes^b and ^c.

9 Procedure 1 — Determination of the direction of twist

9.1 Hold one end of the yarn in such a position that a short length (at least 100 mm) is suspended in a vertical position. Examine the vertical section of the yarn and determine if the slope of the yarn elements (fibres, filaments or component yarns) conforms to the slope of the central portion of the letters “S” or “Z”.

9.2 Designate the direction of twist as “S” or “Z” as observed, in accordance with ISO 2.

10 Procedure 2 — Determination of the amount of twist

10.1 Preliminary procedure

10.1.1 Bring the laboratory sample packages, or the laboratory sample skeins reeled from the packages (see 5.4), to equilibrium in the standard atmosphere for testing as specified in ISO 139.

10.1.2 Unwind the yarn over the end or from the side of the package, as in normal use of the package and at the lowest practicable tension, taking care, when unwinding and handling the samples, to avoid any change in the original twist. Unwind and discard approximately 5 m of yarn before taking the first specimen.

10.1.3 Mount the specimen in the clamps of the twist counter (5.1) before cutting it free from the package. If additional specimens are to be taken from the package, hold the free end in a stationary clip or clamp, or under a weight, to prevent loss of twist.

10.2 Single, spun yarn

10.2.1 Set the movable clamp of the twist counter (5.1) at the distance specified for the nominal staple length of the fibres in the spun yarn being tested, $\pm 0,5$ mm (see 8.1.1). Remove any lateral play in the clamps which might significantly affect the gauge length of the specimen. Verify the gauge length by measuring the clamp separation with an accurate gauge or caliper. Set the revolution counter to zero.

10.2.2 Taking care not to disturb the twist, mount the specimen in the clamps under a pretension equivalent to $(0,5 \pm 0,1)$ cN/tex.

10.2.2.1 If yarns which extend 0,5 % or more under the specified pretension are to be tested, they shall be subjected to a pretension which produces an extension not greater than 0,1 %. The pretension used in these exceptional cases shall be reported and shall be agreed to by all persons interested in the test results.

10.2.3 Remove the twist by turning the rotatable clamp until it is possible to pass a needle (5.2) from the face of the nonrotatable clamp to the face of the rotatable clamp between the untwisted fibres. Use a means of magnification (5.3), if necessary, to make sure that all the twist has been removed.

10.2.4 Note the direction of twist as indicated on the revolution counter. Be sure it agrees with the direction determined by inspection of the specimen. (See Clause 9.)

10.2.5 Record the initial length, the direction of twist and the number of turns (to the accuracy specified in 5.1) in the specimen.

10.2.6 Repeat the operation until the required number of specimens, n , has been tested (see 8.3).

10.3 Single, multifilament yarns

10.3.1 Set the clamps of the twist counter at a distance of 250 mm (or, by agreement, 500 mm) $\pm 0,5$ mm. Remove any lateral play in the clamps that might significantly affect the gauge length of the specimen. Verify the gauge length of the specimen by measuring the clamp separation with an accurate gauge or caliper. Set the revolution counter to zero.

10.3.2 Proceed as directed for single, spun yarns in 10.2.2 to 10.2.5.

10.3.3 When information on change in length on untwisting is desired, release the mechanism fixing the movable clamp and determine the length of the original specimen after untwisting and under the original tension. Note the change in length and specify increase or decrease in length.

10.3.4 Repeat the operation until the required number of specimens, n , has been tested (see 8.3).

10.4 Plied yarns

10.4.1 Determine the plied twist by the procedures given for single, multifilament yarns in 10.3.1 to 10.3.3.

10.4.2 After removing the twist from the plied yarn, cut loose and remove all but one of the component yarns to obtain an individual end of the single yarn. It is assumed that all components of the original yarn have the same direction and amount of twist. If this is not known to be so, it shall be verified. If any difference in kind exists, each component yarn shall be tested and reported separately.

If the component yarns are spun yarns, additional specimens will be required, and it is desirable to save the cut-away strands without loss of twist to provide the specimens.

10.4.3 If the single yarn component has been spun from staple fibres, determine the twist in the single yarn in accordance with 10.2, but if the single yarn component is multifilament, determine the twist in accordance with 10.3.

10.4.4 When information on change in length on untwisting is desired, release the mechanism fixing the movable clamp and determine the length of the original components after untwisting and under the original tension. Note the change in length and specify increase or decrease in length.

10.4.5 Repeat the operation until the required number of specimens, n , has been tested (see 8.3).

10.5 Cabled yarns

10.5.1 Determine the cable twist as directed for single multifilament yarns in 10.3.1 to 10.3.3 to obtain the total number of turns of hawser or cable twist in the test specimens.

10.5.2 After removing the cable twist, cut loose and discard all but one of the component yarns to obtain an individual strand of plied yarn. Note the length under the original tension and determine the plied twist as directed for multifilament yarns in 10.3.1 to 10.3.3 to obtain the total number of turns of the plied yarn component (see 10.4.2).

10.5.3 Cut loose and remove all but one of the component yarns to obtain an individual single yarn (see 10.4.2).

10.5.4 If the single yarn has been spun from staple fibres, determine the single yarn twist in accordance with 10.2, but if the single yarn is multifilament, determine the single yarn twist in accordance with 10.3.

10.5.5 When information on change in length on untwisting is desired, release the mechanism fixing the movable clamp and determine the length of the original specimen after untwisting and under the original tension. Note the change in length and specify increase or decrease in length.

10.5.6 Repeat the operation until the required number of specimens, n , has been tested (see 8.3).

10.5.7 If it is desired to determine the final twist in the plied and single yarn components, all strands shall be cut free from the original specimen, except for the component to be tested. The strands remaining in the clamps may be tested as directed for spun or single filament yarns in 10.2 or 10.3.

11 Calculation of results

11.1 Average twist per specimen

Calculate the average twist per test specimen, in turns per metre, using the formula:

$$t_x = \frac{1000x}{l}$$

where

- t_x is the average twist, in turns per meter;
- l is the length of the test specimen before untwisting;
- x is the total number of turns observed in the test specimen.

11.2 Average twist per sample

Calculate the average twist per sample, in turns per metre, using the formula:

$$\bar{t}_x = \frac{\sum t_x}{n}$$

where

- \bar{t}_x is the average twist per sample;
- $\sum t_x$ is the sum of the average twist in all test specimens;
- n is the number of test specimens.

11.3 Variation of observations

If the coefficient of variation and 95 % confidence interval of the twist are desired, they shall be calculated by standard statistical methods.

11.4 Change in length on untwisting

11.4.1 If the change in initial length is desired, it shall be calculated according to the following formula and reported as extension or contraction, as appropriate.

$$\Delta l = \frac{l_u - l_t}{l_t} \times 100$$

where

- $|\Delta l|$ is the percentage extension if Δl is a positive value;
- $|\Delta l|$ is the percentage contraction if Δl is a negative value;
- l_t is the length of the twisted specimen;
- l_u is the length of the untwisted specimen.

11.4.2 Values calculated for yarn spun from short fibres are considered too unreliable to be reported.

11.5 Twist factor (α)

11.5.1 If desired, the twist factor can be calculated, as follows:

$$\alpha = t \left(\frac{\rho_t}{1000} \right)^{1/2}$$

where

α is the twist factor;

t is the twist, in turns per metre;

ρ_t is the linear density, expressed in tex.

11.5.2 The twist factor can also be calculated from the metric count, as follows:

$$\alpha = t \left(\frac{1}{\rho_t} \right)^{1/2}$$

where

α is the twist factor;

t is the twist, in turns per metre;

ρ_t is the linear density, expressed in the metric system.

12 Expression of results

12.1 Report the amount of twist in all yarns, as follows:

- a) turns per metre, preferably, or
- b) turns per centimetre.

12.2 Compute and report the amount of twist separately for all components of plied or cabled yarns.

12.3 If desired, report the increase or decrease in length during untwisting, expressed as a percentage of the initial length for multifilament, plied or cabled yarns.

13 Test report

The test report shall state that the tests were performed in accordance with this International Standard and should indicate which of any alternative or optional requirements have been met. In addition, it shall give the following information, depending on the type of yarn.

13.1 Single yarns

- a) For each package, the average twist (arithmetic mean) in the yarn, in turns per metre or turns per centimetre;
- b) for all packages, the average twist (arithmetic mean) in the yarn, in turns per metre or turns per centimetre;
- c) 95 % confidence interval (with appropriate dimension);
- d) direction of twist, "S" or "Z", in the yarn;
- e) average change in length, if required, after removal of the twist, in percent (multifilament yarns only);

- f) form of the material sample (yarn package, warps, fabrics);
- g) sampling scheme used;
- h) number of specimens examined;
- i) average length of the test specimens, in millimetres;
- j) pretension used;
- k) coefficient of variation of twist, if required, in each yarn, in percent;
- l) twist factor, if required.

13.2 Plied yarns

- a) For each package, the average plied twist, in turns per metre or turns per centimetre;
- b) for all packages, the average plied twist, in turns per metre or turns per centimetre;
- c) for each package, the average single yarn twist, in turns per metre or turns per centimetre (specify, if after processing);
- d) for all packages, the average single yarn twist, in turns per metre or turns per centimetre (specify, if after processing);
- e) direction of each twist, "S" or "Z";
- f) average change in length, if required, after removal of each twist, in percent, and items 13.1 f) to 13.1 k);
- g) twist factor, if required.

13.3 Cabled yarns

- a) For each package, the average cable twist, in turns per metre or turns per centimetre;
- b) for all packages, the average cable twist, in turns per metre or turns per centimetre;
- c) for each package, the average plied twist, in turns per metre or turns per centimetre (specify, if after final processing);
- d) for all packages, the average plied twist, in turns per metre or turns per centimetre (specify, if after final processing);
- e) for each package, the average single yarn twist, in turns per metre or turns per centimetre (specify, if after final processing);
- f) for all packages, the average single yarn twist, in turns per metre or turns per centimetre (specify, if after final processing);
- g) direction of each twist, "S" or "Z";
- h) average change in length, if required, after removal of each twist, in percent, and items 13.1 f) to 13.1 k);
- i) twist factor, if required.