
International Standard



2064

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

Metallic and other non-organic coatings — Definitions and conventions concerning the measurement of thickness

Revêtements métalliques et autres revêtements non organiques — Définitions et principes concernant le mesurage de l'épaisseur

Second edition — 1980-07-15

STANDARDSISO.COM : Click to view the full PDF of ISO 2064:1980

UDC 669.058 : 531.717 : 001.4

Ref. No. ISO 2064-1980 (E)

Descriptors : coatings, metal coatings, measurement, thickness, definitions.

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards institutes (ISO member bodies). The work of developing International Standards is carried out through ISO technical committees. Every member body interested in a subject for which a technical committee has been set up has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work.

Draft International Standards adopted by the technical committees are circulated to the member bodies for approval before their acceptance as International Standards by the ISO Council.

International Standard ISO 2064 was developed by Technical Committee ISO/TC 107, *Metallic and other non-organic coatings*, and was circulated to the member bodies in March 1979.

It has been approved by the member bodies of the following countries :

Australia	Germany, F.R.	South Africa, Rep. of
Austria	Hungary	Spain
Brazil	India	Sweden
Bulgaria	Israel	Switzerland
Canada	Italy	United Kingdom
Chile	Japan	USA
Czechoslovakia	Netherlands	USSR
Denmark	Poland	
France	Romania	

No member body expressed disapproval of the document.

This second edition cancels and replaces the first edition (i.e. ISO 2064-1973).

Metallic and other non-organic coatings — Definitions and conventions concerning the measurement of thickness

0 Introduction

An important requirement of most coating specifications is that the coating shall have a thickness not less than a given value (and in a few cases not greater than a certain value). The method to be used for measuring the thickness of a particular coating is laid down in the coating specification.

The main purpose of this International Standard is to define exactly what is meant by the term "minimum thickness" when used in specifications for metallic and related coatings. In this context, the minimum thickness is defined as a local thickness over a small area.

With some methods, for example the microscopical method, it is possible to detect appreciable variations in thickness across extremely small areas (for example pits or cracks) which might be considered as places where the specified minimum thickness has not been achieved. However, with other test methods (for example the coulometric method or various non-destructive methods), such minute local variations in thickness cannot be detected. Therefore, the only practicable definition of minimum thickness is one that allows comparable results to be obtained by any of the approved test methods. Hence the minimum thickness should be a local thickness over an area that is as small as practicable, but not too small to accommodate any of the specified test methods. These areas are termed "reference areas" and are often large enough to accommodate a number of separate measurements by the chosen method. In order to obtain consistent results, especially with non-destructive tests, the mean of the measurements of such tests on the reference area should be taken as the local thickness.

In practice, it is usually permissible to test the coating at any place on the significant surface in order to find the minimum thickness on an article. Articles are usually tested at areas where the coating may be expected to be thinnest and so the definition of minimum thickness is the lowest value of local thickness (as defined in clause 2) found by the chosen method.

NOTE — In the case of some coatings, such as hot-dipped and sprayed metal coatings, the coating specifications may call for compliance with a minimum local or an average thickness, or both. These may differ from the parameters defined in this International Standard and the relevant product specifications should be consulted.

1 Scope and field of application

This International Standard defines terms concerning the measurement of the thickness of metallic and other non-

organic coatings on any substrate. In addition, it specifies some general rules to be followed in the measurement of minimum thicknesses of coatings.

2 Definitions

For the purpose of this International Standard, the following definitions apply:

2.1 significant surface : The part of the article covered or to be covered by the coating and for which the coating is essential for serviceability and/or appearance.

2.2 measuring area : The area of the significant surface over which a single measurement is made.

"Measuring area" for the following methods is defined as:

- a) for analytical methods, the area over which the coating is removed;
- b) for the anodic dissolution method, the area enclosed by the sealing ring of the cell;
- c) for the microscopical method, the place at which a single measurement is made;
- d) for non-destructive methods, the probe area or the area influencing the reading (see also the Introduction).

2.3 reference area : The area within which a specified number of single measurements is required to be made.

2.4 local thickness : The mean of the thickness measurements, of which a specified number is made within a reference area (see also the Introduction).

2.5 minimum local thickness : The lowest value of the local thicknesses found on the significant surface of a single article (see also the Introduction).

2.6 maximum local thickness : The highest value of the local thicknesses found on the significant surface of a single article.

2.7 average thickness : Either the value obtained by analytical methods (see 4.1) or the mean value of a specified