

INTERNATIONAL STANDARD

ISO 2066

Third edition
2004-04-01

Resilient floor coverings — Determination of moisture content of agglomerated composition cork

*Revêtements de sol résilients — Détermination de la teneur en eau de
l'aggloméré de liège*

STANDARDSISO.COM : Click to view the full PDF of ISO 2066:2004



Reference number
ISO 2066:2004(E)

© ISO 2004

PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

STANDARDSISO.COM : Click to view the full PDF of ISO 2066:2004

© ISO 2004

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 2066 was prepared by the European Committee for Standardization as EN 12105 and was adopted, under a special "fast-track procedure", by Technical Committee ISO/TC 87, *Cork*, in parallel with its approval by the ISO member bodies.

This third edition cancels and replaces the second edition (ISO 2066:1986), of which it constitutes a technical revision.

STANDARDSISO.COM : Click to view the full PDF of ISO 2066:2004

Foreword

This European Standard has been prepared by Technical Committee CEN/TC 134 "Resilient and textile floor coverings", the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by January 1999, and conflicting national standards shall be withdrawn at the latest by January 1999.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

STANDARDSISO.COM : Click to view the full PDF of ISO 2066:2004

1 Scope

This European Standard specifies a method for determining the moisture content of agglomerated cork.

2 Definitions

For the purposes of this standard the following definitions apply:

2.1 agglomerated composition cork: Product obtained from the agglutination of cork granules with the addition of a binder, generally not derived from cork cells [EN 12466]

2.2 moisture content: The loss in mass of a test specimen after being dried under specified conditions.

3 Principle

A test specimen is weighed, dried under specified conditions then re-weighed. From this, the loss in mass is calculated.

4 Apparatus

4.1 Balance, with readability to 0,05 g.

4.2 Oven, ventilated and controlled at $(103 \pm 5)^\circ\text{C}$.

4.3 Desiccator, containing an efficient dessicant (e.g. silica gel).

4.4 Open, dry containers.

4.5 Cutting system , to take the test specimens.

5 Sampling and preparation of test pieces

From a representative sample of the available material, take three square test specimens of approximate dimensions of 100 mm x 100 mm and the thickness of the material. Test specimens shall be cut at a distance at least 100 mm from the edges of the sample.

6 Procedure

Carry out all weighings to the nearest 0,5 g. Weigh each dried container (m_0). Place each test specimen in a container and weigh each set (m_1).

Place the containers with the test specimens in the oven and dry for at least 3 h. After this period, remove the containers with the test specimens and let them cool in the dessicator for about 30 min; re-weigh each set with the same precision (m_2).

Repeat this procedure until constant mass is obtained (i.e. until two consecutive weighings do not differ by more than 0,5 g).

7 Calculation and expression of results

Calculate the moisture content, H , of each test specimen as a percentage using the following expression:

$$H = \frac{m_1 - m_2}{m_2 - m_0} \times 100$$

where:

m_0 is the mass of the container expressed in grams, rounded up to the nearest 0,5 g,

m_1 is the mass of the test specimen and the container before drying, expressed in grams, rounded up to the nearest 0,5 g,

m_2 is the mass of the test specimen and the container after drying, expressed in grams, rounded up to the nearest 0,5 g.

Calculate the test result as the mean value of the moisture content for the three tests specimens, expressed in percentage, rounded up to the nearest integer.

8 Test report

The test report shall contain the following information:

- a) reference to this European Standard, i.e. EN 12105:1998;
- b) a complete identification of the product tested, including type, source and manufacturer's reference numbers;
- c) the previous history of the sample;
- d) the test result in percent;
- e) any deviation from this standard that may have affected the results