
**Granulated cork, broken cork and
crushed cork — Sampling for the
determination of moisture content**

*Granulés de liège, liège concassé et liège trituré — Échantillonnage
pour la détermination de la teneur en humidité*

STANDARDSISO.COM : Click to view the full PDF of ISO 2067:2019



STANDARDSISO.COM : Click to view the full PDF of ISO 2067:2019



COPYRIGHT PROTECTED DOCUMENT

© ISO 2019

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

| | Page |
|-------------------------------------|----------|
| Foreword..... | iv |
| 1 Scope..... | 1 |
| 2 Normative references..... | 1 |
| 3 Terms and definitions..... | 1 |
| 4 General..... | 1 |
| 5 Sampling method..... | 1 |
| 5.1 Products in bulk..... | 1 |
| 5.2 Products in packages..... | 1 |
| 6 Sampling report..... | 2 |

STANDARDSISO.COM : Click to view the full PDF of ISO 2067:2019

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 87, *Cork*.

This fourth edition cancels and replaces the third edition (ISO 2067:1998), which has been technically revised.

The main change compared to the previous edition is the title and the scope have been modified.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Granulated cork, broken cork and crushed cork — Sampling for the determination of moisture content

1 Scope

This document specifies a sampling method for the determination of moisture content of granulated cork, broken cork and crushed cork.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 633, *Cork — Vocabulary*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 633 apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

4 General

The whole package shall be handled in batches and, in the case of products in packages, all the packages of a same batch shall be identical and include, in a similar proportion, a single type of cork (granulated cork, broken cork or crushed cork) from those mentioned in the title of this document.

No more than 24 h shall elapse between the time of determination of the initial total mass of the batch and the time at which the laboratory samples are made.

5 Sampling method

5.1 Products in bulk

Determine the total initial mass of the batch by direct weighing.

From the whole batch, take randomly at least 25 l of granulated cork, broken cork or crushed cork, at points distant from each other and well distributed in the batch.

Divide the approximately 25 l of granulated cork, broken cork or crushed cork into two similar laboratory samples and place them in properly identified and hermetically sealed containers. One laboratory sample shall be directly used for the moisture test and the other one shall be given to the entity responsible for the sampling, for a possible control.

5.2 Products in packages

Count the total number of packages in the batch.

Determine the total initial mass of the batch (mass of packages included) by direct weighing.

From the whole batch, take randomly some packages containing granulated cork, broken cork or crushed cork: 5 packages minimum which will correspond to at least 50 l.

Open each package and determine the corresponding mass of each one. Extrapolate the value obtained for the total number of packages, thus obtaining the total mass of the packages.

From the different opened packages, take randomly an equal volume of granulated cork, broken cork or crushed cork, in order to obtain a total mass of about 25 l.

Divide the approximately 25 l of granulated cork, broken cork or crushed cork into two similar laboratory samples and place them in properly identified and hermetically sealed containers. One laboratory sample shall be directly used for the moisture test and the other one shall be given to the entity responsible for the sampling, for a possible control.

6 Sampling report

The sampling report shall include the following information:

- a) designation of the product;
- b) product identification mark or the batch number;
- c) a reference to this document, i.e. ISO 2067:2019;
- d) supplier's name and customer's name;
- e) total number of packages that make up the batch, if applicable;
- f) number of packages containing granulated cork, broken cork or crushed cork that have been taken from the batch and their whole mass, if applicable;
- g) date of determination of the total initial mass of the batch;
- h) date of end of sampling;
- i) location of the batch to be sampled;
- j) name of the entity responsible to carry out the sampling;
- k) total initial mass of the batch (packages included, if applicable);
- l) total initial mass of the batch (packages excluded, if applicable);
- m) details of any incidents which may have influenced the sampling results.