
**Textiles — Man-made fibres —
Determination of dye uptake of cationic
dyeable modified polyester fibres**

*Textiles — Fibres fabriquées — Détermination de l'absorption des
colorants par les fibres de polyester à pression normale*

STANDARDSISO.COM : Click to view the full PDF of ISO 20920:2018



STANDARDSISO.COM : Click to view the full PDF of ISO 20920:2018



COPYRIGHT PROTECTED DOCUMENT

© ISO 2018

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword.....	iv
Introduction.....	v
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	1
4 Principle.....	2
5 Reagents and materials.....	2
6 Apparatus.....	2
7 Test preparation.....	2
7.1 Pre-treatment of samples.....	2
7.2 Conditioning of samples.....	3
7.3 Preparation of dye stock solutions.....	3
8 Procedure.....	3
9 Calculation and expression of the results.....	3
10 Precision of the method.....	4
11 Test report.....	4
Annex A (informative) Precision experiment.....	5
Bibliography.....	6

STANDARDSISO.COM : Click to view the full PDF of ISO 20920:2018

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 38, *Textiles*, Subcommittee SC 23, *Fibres and yarns*.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

Typical polyester fibres as sold on the market can be dyed at temperatures above 100 °C and high pressures by using disperse dye. As part of the highly modified polyester products, cationic dyeable polyester (CDP) can be dyed at lower temperatures by using cationic dye. For some modified species in particular, easy cationic dyeable polyester (ECDP) can be dyed under 100 °C at normal pressure. Due to this key improvement, cationic dyeable modified polyester fibres are becoming more and more popular on the market. This test method is used to evaluate the dye uptake rate of cationic dyeable modified polyester fibres by using cationic dye.

STANDARDSISO.COM : Click to view the full PDF of ISO 20920:2018

STANDARDSISO.COM : Click to view the full PDF of ISO 20920:2018

Textiles — Man-made fibres — Determination of dye uptake of cationic dyeable modified polyester fibres

WARNING — The use of this document can involve hazardous materials, operations, and equipment. It does not purport to address all of the safety risks associated with its use.

1 Scope

This document specifies a method for determining the dye uptake of cationic dyeable modified polyester fibres by using cationic dye.

It is applicable to cationic dyeable modified polyester fibres, including staple fibres and filament yarns.

It is not applicable to polyester partially oriented yarns.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 105-C10, *Textiles — Tests for colour fastness — Part C10: Colour fastness to washing with soap or soap and soda*

ISO 139, *Textiles — Standard atmospheres for conditioning and testing*

ISO 3696, *Water for analytical laboratory use — Specification and test methods*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.1

cationic dyeable modified polyester fibre

polyester fibre modified with third monomer or fourth monomer copolymerization which can be dyed by using cationic dyestuffs

EXAMPLE Cationic dyeable polyester (CDP) and easy cationic dyeable polyester (ECDP).

Note 1 to entry: The third monomer, such as a sulfonic acid group, is applied as a modifying agent to polymerize CDP.

Note 2 to entry: The third monomer, such as a sulfonic acid group, and the fourth monomer, such as carboxylic acid groups or other flexible groups, are applied as modifying agents to polymerize ECDP.

3.2

dye uptake

ratio of dye absorption into the specimen in both chemical and physical ways

4 Principle

Samples are dyed with a specified cationic dye and then the absorbance of the dye solution is measured by the spectrophotometer at the specified wavelength. The dye uptake of the samples is calculated by comparison with a dye solution used as a blank sample.

5 Reagents and materials

Unless otherwise specified, use only reagents of recognized analytical grade.

5.1 Grade 3 water, meeting the requirements of ISO 3696.

5.2 Cationic red X-GRL, CAS No. 12221-69-1.

5.3 Acetic acid and sodium acetate buffer solution, pH = 5.

Transfer 10 g of sodium acetate and 20 ml of acetic acid into a 100 ml volumetric flask, dilute with water (5.1) to volume and mix.

5.4 Soap, meeting the requirements of ISO 105-C10.

6 Apparatus

The usual laboratory apparatus and, in particular, the following.

6.1 Spectrophotometer, with 1 cm cuvette.

6.2 Dyeing machine, with a dyeing temperature of (100 ± 3) °C and a heating rate of $(1,5 \pm 0,5)$ °C/min.

6.3 Laundering device, meeting the requirements of ISO 105-C10.

6.4 Balance, accurate to 0,1 mg.

6.5 Volumetric flasks, 100 ml, 250 ml and 1 000 ml.

6.6 Graduated Pipettes, 5 ml, 10 ml and 50 ml.

6.7 Dyeing cups, 300 ml.

6.8 Beakers, 25 ml and 250 ml.

6.9 Glass rods.

7 Test preparation

7.1 Pre-treatment of samples

Remove the oil of samples with the laundering device (6.3). Dissolve 5 g of soap (5.4) in 1 l of water (5.1). Use a liquor ratio of 50:1. Wash the samples for 30 min at 70 °C and then rinse them with water (5.1). Dry the samples in air at a temperature not exceeding 60 °C.

This pre-treatment may be omitted when evidence shows that the oil content does not affect test results, especially for staple fibres.

7.2 Conditioning of samples

Condition the samples at the standard atmosphere specified in ISO 139 after pre-treatment.

7.3 Preparation of dye stock solutions

Weigh 1 g of cationic red dye (5.2) to an accuracy of 0,1 mg and dissolve with water (5.1) in a beaker (6.8). Transfer to a 100 ml volumetric flask (6.5), dilute with water (5.1) to volume and mix. The solution contains 10 g/l of cationic dye.

The dye stock solution should be stored in shade and its validity period is 14 days.

8 Procedure

8.1 Weigh two specimens (see 7.2) of 1,5 g each, accurate to 0,01 g.

8.2 Transfer 8 ml of cationic dye stock solution (see 7.3) and 1 ml of buffer solution (5.3) into one 1 000 ml volumetric flask. Dilute with water (5.1) to volume and mix. The 80 mg/l cationic dye solution is prepared.

If another concentration of dyeing liquid is used, indicate it in the report.

8.3 Transfer 150 ml of the solution (see 8.2) into three dyeing cups (6.7), one for blank test (without samples) and the other two for specimen test. The liquor ratio is 100:1.

8.4 Start dyeing at 50 °C. Then raise the temperature to 100 °C with a heating rate of 1,5 °C/min. Dye specimens for 60 min at 100 °C. Then cool the dye solution to room temperature.

8.5 Take out the specimens. Dilute the blank-sample dye solution (without samples) and the residual dye solutions (with samples) to suitable concentration with water (5.1) in order to ensure that the absorbance of solutions is between 0,1 and 0,5.

8.6 After adjusting the spectrophotometer (6.1) to zero absorbance against water (5.1), measure the absorbance of solutions at the highest wave peak (532 nm).

9 Calculation and expression of the results

Calculate the dye uptake of each specimen according to Formula (1).

$$\omega = \left(1 - \frac{A_i \times n_i}{A_0 \times n_0} \right) \times 100 \quad (1)$$

where

ω is the dye uptake of the specimen, expressed in %;

A_i is the absorbance of the diluted residual solutions (with samples);

n_i is the dilution ratio of the residual solutions (with samples);

A_0 is the absorbance of the diluted blank-sample dye solution (without samples);

n_0 is the dilution ratio of the blank-sample dye solution (without samples).

The result is expressed as the arithmetic mean value of the two specimens, rounded to the nearest 0,1.

10 Precision of the method

See [Annex A](#).

11 Test report

The test report shall include the following information:

- a) a reference to this document, i.e. ISO 20920:2018;
- b) all details necessary for the identification of the sample tested;
- c) the mass of the test specimens;
- d) the concentration of dye solution used;
- e) the test results;
- f) any unusual features observed;
- g) the date of the test;
- h) any other information as needed.

STANDARDSISO.COM : Click to view the full PDF of ISO 20920:2018

Annex A (informative)

Precision experiment

A.1 Description

Five laboratories participated in a precision experiment, providing test results for four materials, each tested twice. Results have been analysed according to ISO 5725-2.

A.2 Repeatability

Using the method specified in this document, an operator tested identical specimens twice, using the same apparatus, in a short period of time and calculated the difference between the respective two mean values.

Determine 10 cases with only one instance above the repeatability listed in [Table A.1](#).

A.3 Reproducibility

Using the method specified in this document, operators in two laboratories, using different apparatus, tested identical specimens twice and calculated the difference between the respective two mean values.

Determine 10 cases with only one instance above the reproducibility listed in [Table A.1](#).

Table A.1 — Precision of this test method

Material	Repeatability <i>r</i>	Reproducibility <i>R</i>
Cationic dyeable polyester staple fibre (CDP)	3,62	4,94
Easy cationic dyeable polyester staple fibre (ECDP)	2,42	2,49
Cationic dyeable polyester drawn yarn (CDP)	2,60	4,36
Cationic dyeable polyester drawn textured yarn (CDP)	2,57	2,98

A.4 Mean value

Test two specimens and calculate the two mean values. If the difference equals or exceeds the repeatability and reproducibility listed in [Table A.1](#), the two mean values should be considered significantly different at the 95 % probability level.