

---

---

**Cryogenic vessels — Gas/materials  
compatibility**

*Réipients cryogéniques — Compatibilité gaz/matériaux*

STANDARDSISO.COM : Click to view the full PDF of ISO 21010:2004



**PDF disclaimer**

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

STANDARDSISO.COM : Click to view the full PDF of ISO 21010:2004

© ISO 2004

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

**Contents**

Page

<b>Foreword</b> .....	iv
<b>1 Scope</b> .....	1
<b>2 Normative references</b> .....	1
<b>3 Compatibility of materials with gases other than oxygen</b> .....	1
<b>4 General requirements for oxygen service</b> .....	1
<b>4.1 Evaluation of materials for oxygen service</b> .....	1
<b>4.2 Evaluation of metallic materials</b> .....	2
<b>4.3 Evaluation of non-metallic materials</b> .....	3
<b>4.4 Test methods and acceptance criteria</b> .....	3
<b>4.5 Alternative method of acceptance</b> .....	5
<b>Annex A (informative) Metallic materials commonly used for liquid oxygen service</b> .....	6
<b>Annex B (normative) Spontaneous ignition test (Bomb test)</b> .....	7
<b>Annex C (normative) Pressure surge test</b> .....	12
<b>Bibliography</b> .....	15

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 21010 was prepared by Technical Committee ISO/TC 220, *Cryogenic vessels*.

STANDARDSISO.COM : Click to view the full PDF of ISO 21010:2004

# Cryogenic vessels — Gas/materials compatibility

## 1 Scope

This International Standard specifies gas/materials compatibility requirements (such as chemical resistance) for cryogenic vessels but it does not cover mechanical properties (e.g. for low temperature applications).

It gives general guidance for compatibility with gases and detailed compatibility requirements for oxygen and oxygen-enriched atmospheres. This International Standard also defines the testing methods for establishing oxygen compatibility of materials (metallic and non-metallic) to be used for cryogenic vessels and associated equipment.

This International Standard focuses on materials that are normally with or could be in contact with cryogenic fluids.

## 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 10297:1999, *Gas cylinders — Refillable gas cylinder valves — Specification and type testing*

ISO 23208, *Cryogenic vessels — Cleanliness for cryogenic service*

## 3 Compatibility of materials with gases other than oxygen

Cryogenic vessels are used in a range of temperatures from very low temperature to ambient temperature. On excluding oxygen, compatibility problems such as corrosion and hydrogen embrittlement normally occur at ambient temperature and become negligible at cryogenic temperatures.

In the case of gases other than oxygen, ISO 11114-1 and ISO 11114-2 may be used as a guide for cryogenic vessels.

## 4 General requirements for oxygen service

### 4.1 Evaluation of materials for oxygen service

#### 4.1.1 General

The selection of a material for use with oxygen and/or in an oxygen-enriched atmosphere is primarily a matter of understanding the circumstances that cause oxygen to react with the material. Most materials in contact with oxygen will not ignite without a source of ignition energy. When an energy input rate, as converted to heat, is greater than the rate of heat dissipation, and the resulting heat increase is continued for sufficient time, ignition and combustion will occur. Thus, two things shall be considered:

- the material's minimum ignition temperature;
- the energy sources that will produce a sufficient increase in the temperature of the material.

These should be viewed in the context of the entire system design so that the specific factors listed below will assume proper relative significance.

The specific factors are:

- the properties of the materials, including the factors affecting ease of ignition and the conditions affecting potential resultant damage (heat of reaction);
- the operating conditions: pressure, temperature, gas velocity, oxygen concentrations and oxygen state (gaseous or liquid) and surface contamination in accordance with ISO 23208;
- the potential sources of ignition: friction, heat of compression, heat from mass impact, heat from particle impact, static electricity, electric arc, resonance and internal flexing etc.;
- the reaction effect (consequences on the surroundings, etc.);
- additional factors: performance requirements, prior experience, availability and cost.

**CAUTION — This International Standard specifies the minimum acceptance requirements for materials in oxygen and enriched air service. In the cases of severe conditions and when the operating pressure is above 40 bar, additional tests to those specified should be considered.**

#### 4.1.2 Evaluation of the insulation system

Insulation systems for cryogenic vessels that can come into contact with oxygen or condensed enriched air, shall be tested in accordance with 4.4.4. Any representative sample that passed the tests in 4.4.3 need not be tested in accordance with 4.4.4.

#### 4.2 Evaluation of metallic materials

Metallic materials commonly used for the construction of cryogenic vessels do not normally present any incompatibility when in contact with oxygen. Annex A lists the metallic materials commonly used for liquid oxygen.

The cases in which ignition or violent reactions can occur are when very thin materials are used with high surface to volume ratio, and when high ignition energy is available (e.g. pump failure). Materials thinner than 0,1 mm shall be tested in accordance with 4.4.3 in conditions as close as possible to the actual operational conditions. Materials to be used in applications where the ignition energy is potentially high should be subjected to special consideration.

For cryogenic vessels intended for oxygen service, the test described in 4.4.3 shall be performed with oxygen. When materials are located in an area where contact with condensed enriched air and the presence of potential sources of ignition is a risk, the test described in 4.4.3 shall be performed with cryogenic O<sub>2</sub>/N<sub>2</sub> mixtures containing at least 50 % oxygen.

NOTE Condensed enriched air can be produced on surfaces with temperatures colder than  $-191,3\text{ }^{\circ}\text{C}$  at 1 atm<sup>1)</sup> (= 101,325 Pa).

---

1) According to Annex C of ISO 31-3:1992, the use of this unit is deprecated.

### 4.3 Evaluation of non-metallic materials

Example of non-metallic materials include, e.g., plastics, elastomers, lubricants, ceramics, glasses and glues. Some of these materials present a high risk of ignition when in contact with oxygen and should be avoided or carefully selected and used in limited quantities.

Some fully oxidized materials, such as ceramics and glass, present no risk of ignition provided they are not contaminated.

Any combustible non-metallic materials, used in steady or incidental contact with liquid oxygen, where the presence of a potential source of ignition is a risk, shall be tested in accordance with 4.4.2 and 4.4.3. Consideration shall be given to testing materials used in those parts of the system where liquid oxygen accumulation may incidentally occur.

For cryogenic vessels intended for oxygen service the test described in 4.4.3 shall be performed with oxygen. When materials are located in an area where contact with condensed enriched air and the presence of potential sources of ignition is a risk, the test described in 4.4.3 shall be performed with cryogenic O<sub>2</sub>/N<sub>2</sub> mixtures containing at least 50 % oxygen.

NOTE Condensed enriched air can be produced on surfaces with temperature colder than – 191,3 °C at 1 atm (101,325 Pa).

Any combustible non-metallic materials, used in steady or incidental contact with gaseous oxygen where the presence of potential sources of ignition is a risk, shall be tested in accordance with 4.4.2. Consideration shall be given to testing materials used in those parts of the system where gaseous oxygen accumulation may incidentally occur.

### 4.4 Test methods and acceptance criteria

#### 4.4.1 General

Each material to be tested shall be clearly identified, usually by the commercial name and the manufacturer's name.

#### 4.4.2 Ignition tests

##### 4.4.2.1 Pass criteria

Two alternative test methods are described in 4.4.2.2 and 4.4.2.3. Materials not satisfying the requirements of 4.4.2.1 or 4.4.2.2 can still be used providing they successfully pass, in their actual operating configuration, the "Oxygen pressure surge test" described in 5.3.8 of ISO 10297:1999 (e.g. for a valve sealing material, the entire valve or a representative assembly shall be tested).

##### 4.4.2.2 Spontaneous ignition test ("Bomb test")

###### 4.4.2.2.1 Test procedure

The test procedure is given in Annex A.

###### 4.4.2.2.2 Acceptance criteria

The spontaneous ignition temperature determined in accordance with 4.4.2.2.1 shall be no less than the values given in Table 1.

**Table 1 — Minimum spontaneous ignition temperature**

Maximum permissible pressure bar	Minimum spontaneous ignition temperature (SIT) °C	Remark
3	200	
10	230	
20	250	
40	300	
100	350	
150	375	Complementary test may be advisable (see 4.1)
207	400	
207 < pressure ≤ 345	400	
NOTE Intermediate values can be determined by linear interpolation.		

**4.4.2.3 Pressure surge test**

**4.4.2.3.1 Test procedure**

The test procedure is given in Annex B.

**4.4.2.3.2 Acceptance criteria**

No reaction shall be observed during 5 consecutive pressure surge impacts at the intended maximum working pressure.

**4.4.3 Mechanical impact test in liquid oxygen (LOX)**

**4.4.3.1 Test procedure**

The mechanical impact test shall be performed at atmospheric pressure in liquid oxygen generally as described in [4] to [8]. This is an example of preferred test equipment but the details are not mandatory. The test shall be conducted :

- on material with the surface condition that is intended for use;
- on material in a physical form delivered for use (i.e. solid, powder etc.);
- at an impact energy per unit contact area of at least 79 J/cm<sup>2</sup>.

**4.4.3.2 Acceptance criteria**

No reaction shall be detected within a series of 10 tests.

**4.4.4 Insulation test**

Representative samples of the insulation system, when touched with a glowing platinum wire in a 100 % oxygen atmosphere at 1 bar pressure, shall not sustain combustion.

NOTE Representative samples of the insulation system should be as installed in the vessel; the full thickness of the insulation should be tested.

#### 4.5 Alternative method of acceptance

The use of materials in cryogenic vessels based on documented evidence of previous long-term satisfactory service, or favourable risk assessment is acceptable.

STANDARDSISO.COM : Click to view the full PDF of ISO 21010:2004

## Annex A (informative)

### Metallic materials commonly used for liquid oxygen service

Cryogenic vessels and associated equipment		Metallic materials commonly used				
		Low alloy steels	Nickel steels	Austenitic stainless steels	Copper and copper alloys	Aluminium and aluminium alloys
Large transportable vessels	Inner vessel		×	×		
	Outer jacket	×		×		
Small transportable vessels	Inner vessel		×	×		
	Outer jacket	×		×		
Static vessels	Inner vessel		×	×		
	Outer jacket	×				
Valves and protective devices				×	×	
Flexible hoses				×		
Vaporizers				×		×
Insulation systems						×

Compatibility of all materials should be evaluated before use.

## Annex B (normative)

### Spontaneous ignition test (Bomb test)

#### B.1 General

This annex defines a test method to determine the spontaneous ignition temperature of non-metallic materials in pressurized gaseous oxygen.

Spontaneous ignition temperature is a criterion for the comparison and the classification of materials, and can be used as an aid in the choice of materials used in the presence of pressurized gaseous oxygen.

#### B.2 Principle

A small quantity of the test material is slowly heated in oxygen under pressure. The continuous recording of pressure and temperature is used to determine spontaneous ignition, which is seen as a sudden increase in temperature and pressure.

#### B.3 Preparation of test pieces

Test pieces shall be prepared by procedures that prevent contamination.

Test pieces can be in liquid or solid form. In the case of solids, the materials shall be cut into a minimum of 6 pieces. The total mass of the pieces used in each test shall be at least 60 mg.

#### B.4 Test equipment

Figure B.1 shows the basic principle of the test equipment. When other methods of heating are used, the heating rate of the specimen is up to 20 °C/min. If an inductively heated furnace is used, the temperature rate can be up to 110 °C/min.

A thermocouple inside a finger of a glove (positioned as close as possible to the test piece) is used to monitor, on a recorder, temperature variation to an accuracy of  $\pm 2$  °C.

The internal pressure shall be monitored and recorded to an accuracy of  $\pm 2$  bar.

The equipment, in particular the autoclave, shall be designed to resist violent internal reactions (e.g. explosions).

#### B.5 Oxygen purity

The gas used shall contain not less than 99,5 % oxygen. The hydrocarbon content shall be less than 10 ml/m<sup>3</sup>.

## B.6 Test procedure

The test piece contained in the sample holder is put into the bomb. The bomb is then sealed and purged to remove any air and any possible residual combustion products from a previous test. Oxygen is then introduced at a minimum pressure that will produce at least 120 bar at ignition.

Whilst continuously recording the temperature and pressure, raise the temperature at a rate of 20 °C/min by adjustment of the heating power, until the spontaneous ignition temperature or 400 °C or higher is reached.

The spontaneous ignition temperature is indicated on the temperature and pressure recorder by the sudden increase in both temperature and pressure caused by the internal reaction.

## B.7 Results

The record of the test is used as shown in Figure B.2, to determine the three parameters,  $T_i$ ,  $\Delta T$  and  $\Delta P$

where

$T_i$  is the spontaneous ignition temperature;


$\Delta T$  is the increase in temperature at moment of ignition;

$\Delta P$  is the increase in pressure at moment of ignition.

Materials are classified in accordance with their spontaneous ignition temperature.


Temperature and pressure increases,  $\Delta T$  and  $\Delta P$ , characterize the violence of the reaction.

STANDARDSISO.COM : Click to view the full PDF of ISO 21010:2004

**Key**

- 1 test sample
- 2 oxygen inlet: 120 bar at minimum ignition conditions
- 3 pressure transducer
- 4 temperature monitor
- 5 heating element: 20 °C/min to a maximum of 500 °C

**Figure B.1 — Bomb for spontaneous ignition test**



**Key**

- X time (minutes)
- Y temperature  $T$  (°C)
- Z pressure  $P$  (bar)
- 1 temperature and pressure variations against time
- 2 pressure at SIT
- 3 peak pressure
- 4 peak temperature
- 5 spontaneous ignition temperature

**Figure B.2 — Spontaneous ignition test — Temperature and pressure versus time**

### B.8 Test report

Test results are recorded on a report sheet, an example of which is given below.

<b>SPONTANEOUS IGNITION</b>	<b>Test No</b>
	<b>Date</b>
1 - <u>TEST PERFORMED FOR</u>	_____
2 - <u>TESTED MATERIAL</u>	_____
Function	_____
Conditions of use	Temperature in °C _____ Pressure in bar _____
Assumed composition	_____
Condition, shape, appearance	_____
Manufacturer	_____
Supplier	_____
Trade name	_____
<b>3 - RESULTS</b>	
Mass of test piece in grams:	

Pressure in bar			Temperature in °C		
At SIT	Peak	$\Delta P$	At SIT	Peak	$\Delta T$

<b>Remarks:</b>
4 - <u>SPONTANEOUS IGNITION TEMPERATURE</u> (°C)
5 - <u>COMMENTS</u>
Authorized signature

## Annex C (normative)

### Pressure surge test

NOTE This Annex needs detailed review at a later date.

#### C.1 General

This annex defines a test method for establishing the maximum working pressure by examining the reactivity of non-metallic materials (solids, pastes or liquids) when exposed to a pressure surge of oxygen, air or of a gas mixture containing oxygen.

This test simulates processes that may occur in service on non-metallic materials (e.g. in shut-off installations when operated too quickly, or on rupture of equipment or pipes, etc.).

This method may be applied to intended working pressures equal to or greater than 10 bar.

#### C.2 Principle

A small quantity of the test material is exposed to a gaseous oxygen pressure surge generated by operating a quick opening valve between a tube containing the test material and a vessel containing oxygen under high pressure.

The pressure in the tube is raised from initial pressure,  $P_i$ , to final pressure,  $P_f$ , as near adiabatically as possible, given by the adjustable pressure of an oxygen accumulator.

A possible reaction of the test material with oxygen is indicated by a steep temperature rise, superimposed on the temperature rise obtained by adiabatic compression.

In this method the maximum working pressure is defined as the maximum final pressure,  $P_f$ , at which no reaction of a sample with oxygen can be observed.

#### C.3 Preparation of test samples

Solid materials are finely divided into a minimum of 6 pieces, liquids are coated on fibrous ceramic materials.

A total mass of 0,2 g to 0,5 g shall be used for each test.

#### C.4 Test equipment

Figure C.1 shows the basic components of the test equipment.

The test sample is placed into a steel tube (see Figure C.1, 10) 15 cm<sup>3</sup> in volume. This reaction vessel is connected to an oxygen accumulator (see Figure C.1, 7) via a 750 mm long pipe (see Figure C.1, 9, internal diameter 14 mm) and a pneumatically operated quick-opening valve (see Figure C.1, 6) guaranteeing a pressure-rise time of 20<sub>-5</sub><sup>0</sup> ms.

Two heaters (see Figure C.1, 4) are used for heating the oxygen accumulator and the reaction vessel up to (60 ± 3) °C.