
**Non-active surgical implants — Joint
replacement implants — Particular
requirements**

*Implants chirurgicaux non actifs — Implants de remplacement
d'articulation — Exigences particulières*

STANDARDSISO.COM : Click to view the full PDF of ISO 21534:2007



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

STANDARDSISO.COM : Click to view the full PDF of ISO 21534:2007



COPYRIGHT PROTECTED DOCUMENT

© ISO 2007

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword.....	v
Introduction	vi
1 Scope	1
2 Normative references	1
3 Terms and definitions.....	2
4 Intended performance	2
5 Design attributes.....	3
5.1 General.....	3
5.2 Surface finish of metallic or ceramic implants articulating on ultra-high-molecular-weight polyethylene (UHMWPE)	3
5.3 Surface finish of metallic or ceramic partial implants	3
5.4 Surfaces of convex, spherically-conforming metallic or ceramic implants articulating on UHMWPE.....	3
5.5 Surfaces of spherically-conforming metallic or ceramic partial implants.....	3
5.6 Surfaces of concave, spherically-conforming UHMWPE components.....	3
6 Materials	4
6.1 General.....	4
6.2 Dissimilar metals or alloys	4
7 Design evaluation	4
7.1 General.....	4
7.2 Preclinical evaluation	4
7.3 Clinical investigation.....	5
7.4 Post market surveillance	5
8 Manufacture and inspection	5
8.1 General.....	5
8.2 Metal surfaces	5
8.3 Plastic surfaces.....	5
8.4 Ceramic surfaces.....	5
9 Sterilization.....	6
9.1 General.....	6
9.2 Expiry	6
10 Packaging	6
11 Information supplied by the manufacturer	6
11.1 General.....	6
11.2 Labelling of implants for use on one side of the body only.....	6
11.3 Instructions for orientation of implants.....	6
11.4 Markings for orientation of the implants.....	6
11.5 Placing of markings on implants	6
11.6 Restrictions on use.....	7
11.7 Re-sterilization of zirconia ceramics	7
11.8 Labelling of implants for use with or without bone cement.....	7
Annex A (informative) List of International Standards for materials found acceptable for the manufacture of implants	8
Annex B (informative) List of International Standards for materials found acceptable or not acceptable for articulating surfaces of implants.....	9

Annex C (informative) List of materials found acceptable or non-acceptable for metallic combinations for non-articulating contacting surfaces of implants 11

Bibliography 12

STANDARDSISO.COM : Click to view the full PDF of ISO 21534:2007

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 21534 was prepared by Technical Committee ISO/TC 150, *Implants for surgery*, Subcommittee SC 4, *Bone and joint replacements*.

This second edition cancels and replaces the first edition (ISO 21534:2002), which has been technically revised.

Introduction

There are three levels of International Standard dealing with non-active surgical implants. These are as follows, with level 1 being the highest:

- level 1: general requirements for non-active surgical implants and instrumentation used in association with implants;
- level 2: particular requirements for families of non-active surgical implants;
- level 3: specific requirements for types of non-active surgical implant.

This International Standard is a level 2 standard and contains requirements that apply to all non-active surgical implants in the family of joint replacement implants.

The level 1 standard contains requirements that apply to all non-active surgical implants. It also indicates that there are additional requirements in the level 2 and level 3 standards. The level 1 standard has been published as ISO 14630.

Level 3 standards apply to specific types of implants within a family, such as knee and hip joints. To address all requirements, it is recommended that a standard of the lowest available level be consulted first.

STANDARDSISO.COM : Click to view the full PDF of ISO 21534:2007

Non-active surgical implants — Joint replacement implants — Particular requirements

1 Scope

This International Standard specifies particular requirements for total and partial joint replacement implants, artificial ligaments and bone cement, hereafter referred to as implants. For the purposes of this International Standard, artificial ligaments and their associated fixing devices are included in the term "implant".

It specifies requirements for intended performance, design attributes, materials, design evaluation, manufacturing, sterilization, packaging and information to be supplied by the manufacturer.

Some tests required to demonstrate conformance to this International Standard are contained in or referenced in level 3 standards.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 4287, *Geometrical Product Specifications (GPS) — Surface texture: Profile method — Terms, definitions and surface texture parameters*

ISO 7206-4, *Implants for surgery — Partial and total hip joint prostheses — Part 4: Determination of endurance properties of stemmed femoral components*

ISO 7206-8, *Implants for surgery — Partial and total hip joint prostheses — Part 8: Methods of determining endurance performance of stemmed femoral components*

ISO 14155-1, *Clinical investigation of medical devices for human subjects — Part 1: General requirements*

ISO 14242-1, *Implants for surgery — Wear of total hip-joint prostheses — Part 1: Loading and displacement parameters for wear-testing machines and corresponding environmental conditions for tests*

ISO 14242-2, *Implants for surgery — Wear of total hip joint prostheses — Part 2: Methods of measurement*

ISO 14243-2, *Implants for surgery — Wear of total knee-joint prostheses — Part 2: Methods of measurement*

ISO 14630:—¹⁾, *Non-active surgical implants — General requirements*

ISO 14879-1, *Implants for surgery — Total knee-joint prostheses — Part 1: Determination of endurance properties of knee tibial trays*

1) To be published. (Revision of ISO 14630:2005)

3 Terms and definitions

For the purposes of this document, the terms and definitions in ISO 14630 together with the following apply.

3.1

artificial ligament

device, including its necessary fixing devices, intended to augment or replace the natural ligament

3.2

joint replacement implant

implantable device, including ancillary implanted components and materials, intended to provide function similar to a natural joint and which is connected to the corresponding bones

3.3

mean centre

position within the spherical head for which the average of the distances to a set of points uniformly distributed over the surface of the sphere is minimum

3.4

radial separation value

difference between the mean radius of the spherical surface and the radius to the point on the spherical surface furthest from the mean centre

NOTE The units of the radial separation value are in micrometres.

4 Intended performance

For the purpose of this International Standard, the intended performance of implants shall conform to Clause 4 of ISO 14630:—, and the design input shall additionally address the following matters:

- a) intended minimum and maximum relative angular movement between the skeletal parts to which the joint replacement implant is attached;
- b) expected maximum load actions (forces and moments) to be transmitted to the bony parts to which the joint replacement implant is attached;
- c) dynamic response of the body to the shape/stiffness of the implants;
- d) expected wear of articulating surfaces;
- e) suitability of the dimensions and shape of the implant for the population for which it is intended;
- f) strength of the adhesion and durability of surface coatings or surface treatments.

NOTE 1 The clinical indications and contra-indications for the use of a particular implant are complex and should be reviewed by the surgeons when they are selecting implants to be used for particular patients, relying upon their own personal judgment and experience.

NOTE 2 The lifetime of an implant depends on the interaction of various factors; some are the responsibility of the manufacturer, some, such as the implantation technique, are the responsibility of the surgeon in conducting the operation, and some relate to the patient, for example, the biological and physiological response to the implant, the medical condition of the patient, the conduct of the patient in respect of increasing body weight, carriage of heavy loads and adopting a high level of physical activity.

5 Design attributes

5.1 General

The development of the design attributes to meet the performance intended by the manufacturer shall conform to the requirements of Clause 5 of ISO 14630:—, and in addition, account shall be taken of the following points:

- a) the strength of adhesion and durability of surface coatings and surface treatments;
- b) the wear of the articulating and other surfaces;
- c) stability of the implant while allowing prescribed minimum and maximum relative movements between the skeletal parts;
- d) avoidance of cutting or abrading tissue during function other than insertion or removal;
- e) the creep resistance and rupture characteristics, particularly as they relate to ligaments.

NOTE 1 Methods of assessment of the wear of articulating and other surfaces are prescribed in, e.g. ISO 14242-2 and ISO 14243-1, -2 and -3.

NOTE 2 More specific requirements, such as that for hip joint replacements, might appear in other standards.

5.2 Surface finish of metallic or ceramic implants articulating on ultra-high-molecular-weight polyethylene (UHMWPE)

The articulating surfaces of metallic or ceramic components of total joint replacements intended to articulate on UHMWPE shall have a surface roughness value R_a no greater than 0,1 μm (when measured in accordance with 7.2.2).

5.3 Surface finish of metallic or ceramic partial implants

The articulating surface of metallic or ceramic components of partial joint replacements shall have a surface roughness value R_a no greater than 0,5 μm (when measured in accordance with 7.2.2).

5.4 Surfaces of convex, spherically-conforming metallic or ceramic implants articulating on UHMWPE

The articulating surface of convex spherically conforming metallic or ceramic components of total joint replacements intended to articulate on UHMWPE shall have a surface roughness R_a no greater than 0,05 μm and a radial separation value for sphericity no greater than 10 μm (when measured in accordance with 7.2.2 and 7.2.3).

5.5 Surfaces of spherically-conforming metallic or ceramic partial implants

The articulating surface of spherically conforming metallic or ceramic components of partial joint replacements shall have a surface roughness value R_a no greater than 0,5 μm and a radial separation value for sphericity no greater than 100 μm (when measured in accordance with 7.2.2 and 7.2.3).

5.6 Surfaces of concave, spherically-conforming UHMWPE components

The articulating surface of concave, spherically-conforming UHMWPE components of total joint replacements shall have a surface roughness R_a no greater than 2 μm and a radial separation value for sphericity no greater than 200 μm (when measured in accordance with 7.2.2 and 7.2.3).

6 Materials

6.1 General

The requirements of Clause 6 of ISO 14630:— apply together with the particular requirement of 6.2 of the present document.

NOTE 1 Annex A gives a list of International Standards for materials found acceptable through proven use for the manufacture of implants or for use in association with implants.

NOTE 2 Annex B gives lists of International Standards for pairs of materials found acceptable or not acceptable through proven use for articulating surfaces of implants.

NOTE 3 Where 6.1 of ISO 14630:— states that the acceptability of materials may be demonstrated by selection from the materials found suitable by proven clinical use in similar applications, for the purposes of this International Standard, proven use should be demonstrated by records of implantation of at least 500 of the implants and recorded satisfactory clinical use over a period of not less than five years.

6.2 Dissimilar metals or alloys

For applications in which two dissimilar metals or alloys or the same metals or alloys in different metallurgical states are in contact where articulation is not intended, combinations used shall not produce unacceptable galvanic effects.

NOTE Annex C gives lists of International Standards for acceptable and unacceptable metallic combinations for use in non-articulating bearing surfaces of implants.

7 Design evaluation

7.1 General

Joint replacement implants shall be evaluated in order to demonstrate that the intended performance is achieved. This evaluation shall be in accordance with Clause 7 of ISO 14630:— together with the particular requirements of 7.2 to 7.4. This evaluation shall be undertaken using components fully representative of the final condition ready for implantation.

7.2 Preclinical evaluation

7.2.1 General

Preclinical evaluation shall consider:

- a) biocompatibility of any materials not previously used;
- b) mechanical loads and the related movements to which the implants can be subjected when functioning as prescribed by ISO 14630;
- c) fatigue testing of highly stressed parts in accordance with ISO 7206-4, ISO 7206-8 and ISO 14879-1;
- d) wear testing of articulating bearing surfaces in accordance with e.g. ISO 14242-1, ISO 14242-2 and ISO 14243-1;
- e) the suitability of the dimensions and shape of the implant for the intended population;

NOTE The suitability of the dimensions and shape of the implant for the intended population can be demonstrated by cadaver implantation, the use of imaging systems such as X-ray, CAT scan or magnetic resonance imaging, or by reference to corresponding implants of proven clinical use (see Note 3 of 6.1).

- f) adhesion and durability of coatings if present.

7.2.2 Surface roughness measurement

Surface roughness shall be measured according to one of the methods given in ISO 4287.

7.2.3 Sphericity measurement

Radial separation values for sphericity shall be measured according to a method demonstrated to be accurate and repeatable.

NOTE A suitable method is described in the National Physical Laboratory (NPL) [30].

7.3 Clinical investigation

The clinical investigation shall be conducted according to the general requirements of ISO 14155-1.

7.4 Post market surveillance

The post-market performance of joint replacement implants shall be determined.

NOTE Suitable methodologies include survival analysis (with revision as the endpoint) and clinical assessment. Where it is available, relevant information from joint replacement registries are taken into account.

8 Manufacture and inspection

8.1 General

The requirements of Clause 8 of ISO 14630:— apply together with the particular requirements of 8.2 to 8.4.

8.2 Metal surfaces

All polishing operations on metallic components shall be performed using an iron-free material. Clean, degrease, rinse and dry all components and examine the articulating surfaces using normal or corrected vision. The surfaces shall be free of any imperfections that would impair their function and also be free from deposited finishing materials or other contaminants.

NOTE Examples of imperfections which might impair function include scale, tool marks, nicks, scratches, cracks, cavities, burrs and other defects.

8.3 Plastic surfaces

Articulating surfaces of plastic components shall not be prepared using non-removable abrasive or polishing compounds. Clean, degrease (if necessary), rinse and dry the components and examine them using normal or corrected vision. The surfaces shall be free from particulate contamination.

8.4 Ceramic surfaces

Ceramic components shall be cleaned, degreased, rinsed, dried and examined using normal or corrected vision. The articulating surfaces shall be free of any imperfections that would impair their function.

NOTE Examples of imperfections which might impair function include particulate contamination, chemical discolouration (spots or larger areas), tool marks, nicks, chips, cavities and cracks.

9 Sterilization

9.1 General

The requirements of Clause 9 of ISO 14630:— apply together with the following.

The effects of the sterilization process shall not impair the intended performance of the implant [see Clause 4 and 7.2.1 c), d) and f)].

Implants containing UHMWPE and sterilized by ionizing radiation, shall not be supplied for clinical use if an accumulated dose of radiation higher than 40 kGy has been received. This requirement does not apply if radiation intended to improve the mechanical characteristics of the material is combined with the radiation for sterilization purposes.

9.2 Expiry

The manufacturer shall conduct an investigation, and record the results, to ascertain the expiry date to be marked on the labelling for the implant.

10 Packaging

The requirements of Clause 10 of ISO 14630:— shall apply. The expiry date (see 9.2) shall be marked on the label.

11 Information supplied by the manufacturer

11.1 General

The requirements of Clause 11 of ISO 14630:— shall apply together with the requirements in 11.2 to 11.8.

11.2 Labelling of implants for use on one side of the body only

Labelling for implants designed for use on one side of the body only shall bear the symbol "LEFT" or "L" for implants to be used on the left side or "RIGHT" or "R" for implants to be used on the right side.

11.3 Instructions for orientation of implants

The instruction leaflet and/or manual shall, where necessary, indicate the required orientation of the implant relative to the body part. It shall also refer to the relevant marking(s) on the implant or the label (see 11.2 and 11.4).

11.4 Markings for orientation of the implants

The implant shall bear the symbol "ANT" on the front and/or "POST" on the back where this is necessary for interpretation of the instructions relating to the required orientation of the implant relative to the body given in the instruction leaflet and/or manual (see 11.3).

11.5 Placing of markings on implants

Markings shall be placed on the implant where they will not impair its intended function [see 7.2.1 c), d) and f)].

11.6 Restrictions on use

If an implant is intended for a restricted population this shall be stated in the instructions for use or in the manual.

11.7 Re-sterilization of zirconia ceramics

Components manufactured from zirconia ceramics shall include an instruction advising users "Do not sterilize using moist heat".

11.8 Labelling of implants for use with or without bone cement

Labelling for implants shall bear an appropriate legend as shown in Table 1.

Table 1 — Labelling

Usage	Legend	Alternative legend
Implants intended to be used with bone cement	FOR USE WITH CEMENT	CEMENTED
Implants intended to be used without bone cement	UNCEMENTED	CEMENTLESS
Implants intended to be used optionally	USE WITH CEMENT OR UNCEMENTED	NO LEGEND

Annex A (informative)

List of International Standards for materials found acceptable for the manufacture of implants

The following International Standards deal with materials that have been found acceptable through proven use for the manufacture of implants. The inclusion of materials in this annex does not imply their satisfactory use in any particular application; neither does it relieve the manufacturer of the obligation to undertake a design evaluation such as prescribed in Clause 7.

ISO 5832-1, *Implants for surgery — Metallic materials — Part 1: Wrought stainless steel*

ISO 5832-2, *Implants for surgery — Metallic materials — Part 2: Unalloyed titanium*

ISO 5832-3, *Implants for surgery — Metallic materials — Part 3: Wrought titanium 6-aluminium 4-vanadium alloy*

ISO 5832-4, *Implants for surgery — Metallic materials — Part 4: Cobalt-chromium-molybdenum casting alloy*

ISO 5832-5, *Implants for surgery — Metallic materials — Part 5: Wrought cobalt-chromium-tungsten-nickel alloy*

ISO 5832-6, *Implants for surgery — Metallic materials — Part 6: Wrought cobalt-nickel-chromium-molybdenum alloy*

ISO 5832-7, *Implants for surgery — Metallic materials — Part 7: Forgeable and cold-formed cobalt-chromium-nickel-molybdenum-iron alloy*

ISO 5832-8, *Implants for surgery — Metallic materials — Part 8: Wrought cobalt-nickel-chromium-molybdenum-tungsten-iron alloy*

ISO 5832-9, *Implants for surgery — Metallic materials — Part 9: Wrought high nitrogen stainless steel*

ISO 5832-11, *Implants for surgery — Metallic materials — Part 11: Wrought titanium 6-aluminium 7-niobium alloy*

ISO 5832-12, *Implants for surgery — Metallic materials — Part 12: Wrought cobalt-chromium-molybdenum alloy*

ISO 5833, *Implants for surgery — Acrylic resin cements*

ISO 5834-1, *Implants for surgery — Ultra-high-molecular-weight polyethylene — Part 1: Powder form*

ISO 5834-2, *Implants for surgery — Ultra-high-molecular-weight polyethylene — Part 2: Moulded forms*

ISO 6474, *Implants for surgery — Ceramic materials based on high purity alumina*

ISO 13356, *Implants for surgery — Ceramic materials based on yttria-stabilized tetragonal zirconia (Y-TZP)*

ISO 13779-1, *Implants for surgery — Hydroxyapatite — Part 1: Ceramic hydroxyapatite*

ISO 13779-2, *Implants for surgery — Hydroxyapatite — Part 2: Coatings of hydroxyapatite*

ISO 13779-4, *Implants for surgery — Hydroxyapatite — Part 4: Determination of coating adhesion strength*

Annex B (informative)

List of International Standards for materials found acceptable or not acceptable for articulating surfaces of implants

B.1 Suitable material combinations

For the articulating surfaces of joint replacement implants the following combinations of the materials listed in Annex A have been found to be acceptable in particular applications provided adequate attention is given to design, surface finish and surface treatment. The inclusion of materials in this annex does not imply their satisfactory use in any particular application; neither does it relieve the manufacturer of the obligation to undertake a design evaluation such as prescribed in Clause 7.

- a) wrought stainless steel (ISO 5832-1)/UHMWPE (ISO 5834-1, ISO 5834-2);
- b) wrought high nitrogen stainless steel (ISO 5832-9)/UHMWPE (ISO 5834-1, ISO 5834-2);
- c) cobalt-chromium-molybdenum casting alloy (ISO 5832-4)/UHMWPE (ISO 5834-1, ISO 5834-2);
- d) wrought cobalt-chromium tungsten-nickel alloy (ISO 5832-5)/UHMWPE (ISO 5834-1, ISO 5834-2);
- e) forgeable and cold-formed cobalt-chromium-nickel-molybdenum-iron alloy (ISO 5832-7)/UHMWPE (ISO 5834-1, ISO 5834-2);
- f) wrought cobalt-nickel-chromium-molybdenum-tungsten-iron alloy (ISO 5832-8)/UHMWPE (ISO 5834-1, ISO 5834-2);
- g) wrought titanium 6-aluminium 4-vanadium alloy²⁾ (ISO 5832-3)/UHMWPE (ISO 5834-1, ISO 5834-2);
- h) wrought titanium 6-aluminium 7-niobium alloy²⁾ (ISO 5832-11)/UHMWPE (ISO 5834-1, ISO 5834-2);
- i) ceramic materials based on alumina²⁾ (ISO 6474)/UHMWPE (ISO 5834-1, ISO 5834-2);
- j) ceramic materials based on zirconia (ISO 13356)/UHMWPE (ISO 5834-1, ISO 5834-2);
- k) ceramic materials based on alumina (ISO 6474)/ceramic materials based on alumina (ISO 6474);
- l) forgeable and cold-formed cobalt-chromium-nickel-molybdenum-iron alloy (ISO 5832-7)/forgeable and cold-formed cobalt-chromium-nickel-molybdenum-iron alloy (ISO 5832-7);
- m) wrought cobalt-chromium-molybdenum alloy (ISO 5832-12)/cobalt-chromium-molybdenum casting alloy (ISO 5832-4);
- n) wrought cobalt-nickel-chromium-molybdenum alloy (ISO 5832-6)/UHMWPE (ISO 5834-1, ISO 5834-2);
- o) wrought cobalt-chromium-molybdenum alloy (ISO 5832-12)/UHMWPE (ISO 5834-1, ISO 5834-2).

2) Particular attention to surface treatment of the articulating surface might be necessary.

B.2 Unsuitable combinations of materials for articulating surfaces

The following combinations have been found to be unacceptable for the articulating surfaces of joint replacement implants:

- a) stainless steel (ISO 5832-1, ISO 5832-9)/titanium based alloy (ISO 5832-3, ISO 5832-11);
- b) stainless steel (ISO 5832-1, ISO 5832-9)/stainless steel (ISO 5832-1, ISO 5832-9);
- c) stainless steel (ISO 5832-1, ISO 5832-9)/unalloyed titanium (ISO 5832-2);
- d) stainless steel (ISO 5832-1)/cobalt based alloys (ISO 5832-4, ISO 5832-5, ISO 5832-6, ISO 5832-7, ISO 5832-8, ISO 5832-12);
- e) unalloyed titanium (ISO 5832-2)/unalloyed titanium (ISO 5832-2);
- f) unalloyed titanium (ISO 5832-2)/titanium based alloys (ISO 5832-3, ISO 5832-11);
- g) unalloyed titanium (ISO 5832-2)/cobalt based alloys (ISO 5832-4, ISO 5832-5, ISO 5832-6, ISO 5832-7, ISO 5832-8, ISO 5832-12);
- h) unalloyed titanium (ISO 5832-2)/UHMWPE (ISO 5834-1, ISO 5834-2);
- i) titanium based alloys (ISO 5832-3, ISO 5832-11)/cobalt based alloys (ISO 5832-4, ISO 5832-5, ISO 5832-6, ISO 5832-7, ISO 5832-8, ISO 5832-12).

STANDARDSISO.COM : Click to view the full PDF of ISO 21534:2007