

---

---

**Petroleum and natural gas industries —  
External coatings for buried or  
submerged pipelines used in pipeline  
transportation systems —**

**Part 5:  
External concrete coatings**

*Industries du pétrole et du gaz naturel — Revêtements externes des  
conduites enterrées ou immergées utilisées dans les systèmes de  
transport par conduites —*

*Partie 5: Revêtements extérieurs en béton*



**PDF disclaimer**

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

STANDARDSISO.COM : Click to view the full PDF of ISO 21809-5:2010



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2010

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

Page

Foreword .....	v
Introduction.....	vi
1 Scope .....	1
2 Normative references .....	1
3 Terms and definitions .....	4
4 Symbols and abbreviated terms .....	7
4.1 Symbols.....	7
4.2 Abbreviated terms .....	7
5 General requirements .....	7
5.1 Rounding .....	7
5.2 Compliance with this part of ISO 21809 .....	7
6 Information supplied by the purchaser.....	7
6.1 General information .....	7
6.2 Additional information .....	8
7 Materials .....	8
7.1 Pipe .....	8
7.2 Cement.....	9
7.3 Supplementary cementitious materials .....	9
7.4 Aggregate — Fine and coarse.....	10
7.5 Heavyweight aggregate .....	10
7.6 Lightweight aggregate .....	11
7.7 Recycled concrete as aggregate .....	11
7.8 Water.....	11
7.9 Steel reinforcement .....	12
7.10 Concrete admixtures .....	12
7.11 Reclaimed concrete .....	12
8 Concrete mix .....	12
9 Coating application .....	13
9.1 Qualification .....	13
9.2 Application of concrete coating.....	15
9.3 Environmental conditions .....	15
9.4 Pipe .....	15
9.5 Steel reinforcement .....	15
9.6 Concrete cutback .....	17
9.7 Anode installation .....	17
10 Curing methods .....	17
11 Inspection and testing .....	17
11.1 General .....	17
11.2 Test procedures.....	19
11.3 Retesting .....	21
11.4 Test results .....	22
12 Repair of concrete coated pipe.....	22
12.1 General .....	22
12.2 Damaged areas .....	23
12.3 Cracks.....	23
12.4 Gaps.....	23

12.5	Stripping .....	23
13	Markings .....	23
14	Handling and storage .....	23
15	Test reports and certificate of compliance .....	24
Annex A (normative)	Water absorption test .....	25
Annex B (normative)	Shear resistance test .....	28
	Bibliography .....	29

STANDARDSISO.COM : Click to view the full PDF of ISO 21809-5:2010

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 21809-5 was prepared by Technical Committee ISO/TC 67, *Materials, equipment and offshore structures for petroleum, petrochemical and natural gas industries*, Subcommittee SC 2, *Pipeline transportation systems*.

ISO 21809 consists of the following parts, under the general title *Petroleum and natural gas industries — External coatings for buried or submerged pipelines used in pipeline transportation systems*:

- *Part 1: Polyolefin coatings (3-layer PE and 3-layer PP)*
- *Part 2: Fusion-bonded epoxy coatings*
- *Part 3: Field joint coatings*
- *Part 4: Polyethylene coatings (2-layer PE)*
- *Part 5: External concrete coatings*

## Introduction

It is necessary that users of this part of ISO 21809 be aware that further or differing requirements might be needed for individual applications. This part of ISO 21809 is not intended to inhibit a vendor from offering, or the purchaser from accepting, alternative equipment or engineering solutions for the individual application. This can be particularly applicable if there is innovative or developing technology. If an alternative is offered, it is the responsibility of the vendor to identify any variations from this part of ISO 21809 and provide details.

STANDARDSISO.COM : Click to view the full PDF of ISO 21809-5:2010

# Petroleum and natural gas industries — External coatings for buried or submerged pipelines used in pipeline transportation systems —

## Part 5: External concrete coatings

### 1 Scope

This part of ISO 21809 specifies the requirements for qualification, application, testing and handling of materials required for the application of reinforced concrete coating externally to either bare pipe or pre-coated pipe for use in pipeline transportation systems for the petroleum and natural gas industries as defined in ISO 13623.

The external application of concrete is primarily used for the negative buoyancy of pipes used in buried or submerged pipeline systems and/or for the mechanical protection of the pipe and its pre-coating.

This part of ISO 21809 is applicable to concrete thicknesses of 25 mm or greater.

### 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 31-0:1992, *Quantities and units — Part 0: General principles*

ISO 1920-5: 2004, *Testing of concrete — Part 5: Properties of hardened concrete other than strength*

ISO 10474, *Steel and steel products — Inspection documents*

EN<sup>1)</sup> 197-1, *Cement — Part 1: Composition, specifications and conformity criteria for common cements*

EN 206-1, *Concrete — Part 1: Specification, performance, production and conformity*

EN 450-1, *Fly ash for concrete — Part 1: Definition, specifications and conformity criteria*

EN 450-2, *Fly ash for concrete — Part 2: Conformity evaluation*

EN 934-2, *Admixtures for concrete, mortar and grout — Part 2: Concrete admixtures — Definitions, requirements conformity, marking and labelling*

EN 1008, *Mixing water for concrete — Specification for sampling, testing and assessing the suitability of water, including water recovered from processes in the concrete industry, as mixing water for concrete*

---

1) CEN, European Committee for Standardization, Central Secretariat, Rue de Stassart 36, B-1050, Brussels, Belgium.

## ISO 21809-5:2010(E)

EN 10080, *Steel for the reinforcement of concrete — Weldable reinforcing steel — General*

EN 10016-2, *Non-alloy steel rods for drawing and/or cold rolling — Part 2: Specific requirements for general purpose rod*

EN 10204, *Metallic products — Types of inspection documents*

EN 10244-2, *Steel wire and wire products — Non-ferrous metallic coatings on steel wire — Part 2: Zinc or zinc alloy coatings*

EN 12390-2, *Testing hardened concrete — Part 2: Making and curing specimens for strength tests*

EN 12390-3, *Testing hardened concrete — Part 3: Compressive strength of test specimens*

EN 12390-7, *Testing hardened concrete — Part 7: Density of hardened concrete*

EN 12504-1, *Testing concrete in structures — Cored specimens — Taking, examining and testing in compression*

EN 12620, *Aggregates for concrete*

EN 13055-1, *Lightweight aggregates — Part 1: Lightweight aggregates for concrete, mortar and grout*

EN 13263-1, *Silica fume for concrete — Part 1: Definitions, requirements and conformity criteria*

ACI<sup>2)</sup> 308.1-98, *Standard Specification for Curing Concrete*

ASTM<sup>3)</sup> A82/A82M, *Standard Specification for Steel Wire, Plain, for Concrete Reinforcement*

ASTM A185, *Standard Specification for Steel Welded Wire Reinforcement, Plain, for Concrete*

ASTM A641, *Standard Specification for Zinc-Coated (Galvanized) Carbon Steel Wire*

ASTM A810, *Standard Specification for Zinc-Coated (Galvanized) Steel Pipe Winding Mesh*

ASTM C31/C31M, *Standard Practice for Making and Curing Concrete Test Specimens in the Field*

ASTM C33, *Standard Specification for Concrete Aggregates*

ASTM C39, *Standard Test Method for Compressive Strength of Cylindrical Concrete Specimens*

ASTM C40, *Standard Test Method for Organic Impurities in Fine Aggregates for Concrete*

ASTM C42/C42M, *Standard Test Method for Obtaining and Testing Drilled Cores and Sawed Beams of Concrete*

ASTM C128, *Standard Test Method for Density, Relative Density (Specific Gravity) and Absorption of Fine Aggregate*

ASTM C150, *Standard Specification for Portland Cement*

ASTM C171, *Standard Specification for Sheet Materials for Curing Concrete*

ASTM C172, *Standard Practice for Sampling Freshly Mixed Concrete*

---

2) American Concrete Institute, 38800 Country Club Drive, Farmington Hills, MI 48331, USA.

3) American Society for Testing and Materials, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959, USA.

- ASTM C309, *Standard Specification for Liquid Membrane-Forming Compounds for Curing Concrete*
- ASTM C330, *Standard Specification for Lightweight Aggregates for Structural Concrete*
- ASTM C331, *Standard Specification for Lightweight Aggregates for Concrete Masonry Units*
- ASTM C332, *Standard Specification for Lightweight Aggregates for Insulating Concrete*
- ASTM C494, *Standard Specification for Chemical Admixtures for Concrete*
- ASTM C595, *Standard Specification for Blended Hydraulic Cements*
- ASTM C617, *Standard Practice for Capping Cylindrical Concrete Specimens*
- ASTM C618, *Standard Specification for Coal Fly Ash and Raw or Calcined Natural Pozzolan for Use in Concrete*
- ASTM C637, *Standard Specification for Aggregates for Radiation-Shielding Concrete*
- ASTM C642, *Standard Test Method for Density, Absorption, and Voids in Hardened Concrete*
- ASTM C989, *Standard Specification for Slag Cement for Use in Concrete and Mortars*
- ASTM C1157, *Standard Performance Specification for Hydraulic Cement*
- ASTM C1176, *Standard Practice for Making Roller-Compacted Concrete in Cylinder Molds using a Vibrating Table*
- ASTM C1240, *Standard Specification for Silica Fume Used in Cementitious Mixtures*
- ASTM C1435, *Standard Practice for Molding Roller-Compacted Concrete in Cylinder Molds Using a Vibrating Hammer*
- ASTM C1602, *Standard Specification for Mixing Water Used in the Production of Hydraulic Cement Concrete*
- ASTM C1604/C1604M, *Standard Test Method for Obtaining and Testing Drilled Cores of Shotcrete*
- ASTM D2216, *Standard Test Methods for Laboratory Determination of Water (Moisture) Content of Soil and Rock by Mass*
- ASTM D4643, *Standard Test Method for Determination of Water (Moisture) Content of Soil by Microwave Oven Heating*
- ASTM D4959, *Standard Test Method for Determination of Water (Moisture) Content of Soil by Direct Heating*
- ASTM D6176, *Standard Practice for Measuring Surface Atmospheric Temperature with Electrical Resistance Temperature Sensors*

### 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

- 3.1 aggregate**  
(fine and coarse) granular material such as sand, crushed stone, iron blast furnace slag, magnetite, ilmenite, or hematite used with a cement medium to form concrete or mortar
- 3.2 anode**  
sacrificial metallic attachment that is electrically connected to the steel pipe
- 3.3 applicator**  
company which undertakes the coating application in compliance with the provisions of this part of ISO 21809
- 3.4 cementitious material**  
inorganic material or a mixture of inorganic materials that sets and develops strength by chemical reaction with water by formation of hydrates and is capable of doing so under water
- 3.5 certificate of compliance**  
document issued in accordance with ISO 10474 or EN 10204, stating compliance with the purchase order for concrete coated pipes, but without mention of any test results, issued in accordance with the purchasing requirements
- 3.6 compression wrap process**  
process by which the concrete mix is discharged into a coating head and applied in a continuous helical strip with pressure onto rotating pipe
- 3.7 compressive strength**  
maximum compressive stress at the point of failure
- 3.8 concrete admixture**  
material, other than aggregate, water, cement or supplementary cementitious material, or fibre reinforcement, that is added as an ingredient to the concrete mix or one of its components, to enhance or modify the properties of the concrete or application process
- 3.9 concrete coated pipe weight**  
weight of the concrete coated pipe in air after the concrete cutback has been completed
- 3.10 core**  
cylindrical specimen of a specific or designated diameter drilled from hardened concrete coating to be tested in compression or examined petrographically
- 3.11 cover**  
distance between the surface of the reinforcement and the outer surface of the concrete
- 3.12 cube**  
specimen of specific dimensions prepared from fresh concrete to be tested in compression

**3.13****curing**

action taken to maintain moisture and temperature conditions in a freshly placed cementitious mixture to allow hydraulic cement hydration and (if applicable) pozzolanic reactions to occur so that the required properties of the mix can develop

**3.14****cutback**

length of pipe left without concrete coating at each end

**3.15****cylinder**

cylindrical specimen prepared from fresh concrete to be tested in compression

**3.16****electrical isolation**

absence of electrical continuity between the steel pipe and reinforcement

**3.17****field specimen**

cores, cubes, cylinders, prisms or *in situ* specimens taken from the hardened concrete coating

**3.18****form process****pour process**

process by which the concrete mix is poured into a mould on a stationary pipe

**3.19****gap**

annular separation between the concrete coating and the underlying substrate

**3.20****holiday**

pre-coating discontinuity that exhibits electrical conductivity when exposed to a specific voltage

**3.21****impact resistance**

resistance of concrete coating against interference and accidental loads

**3.22****impingement process**

process by which the concrete is discharged at high velocity onto a rotating pipe

**3.23****mix design**

unique blend of aggregates, cement, water, and supplementary cementitious materials and/or admixtures that will result in a concrete mix

**3.24****negative buoyancy**

weight of the concrete coated pipe less the positive buoyancy of the concrete coated pipe when considered as a closed cylinder immersed in the service environment

**3.25****NPS**

nominal pipe size in USC units (inches)

**3.26**

**phi tape  
pi tape**

tape used to measure the diameter of the concrete coated pipe

**3.27**

**pre-coating**

any coating or coating system applied to the external surface of the steel pipe prior to the application of the concrete coating

**3.28**

**purchaser**

company responsible for providing the product order requirements

**3.29**

**reclaimed concrete**

concrete that is reintroduced into the mix and does not require processing before reuse

**3.30**

**recycled concrete as aggregate**

concrete that has been reprocessed for use as aggregate

**3.31**

**shear resistance**

resistance against relative displacement (movement) along the interface between the concrete coating and the underlying pre-coating

**3.32**

**slip form process**

process whereby the concrete is applied to a vertical pipe by means of a slip form mould

**3.33**

**specific gravity**

ratio of mass of a volume of material to the mass of an equal volume of distilled water at a stated temperature

**3.34**

**steel reinforcement**

bars, wires, fibres, or strands, which are embedded in the concrete coating in such a manner that the reinforcement and the concrete act together in resisting forces

**3.35**

**supplementary cementitious material**

**SCM**

natural or man-made siliceous or siliceous and aluminous materials that can be used to either partially substitute Portland cement or increase the total content of cementitious material in concrete mixes to improve the strength and durability of concrete

**EXAMPLE**

Fly ash, ground granulated blast furnace slag, silica fume, calcined shale or metakaolin.

**3.36**

**supplier**

provider or manufacturer of supplies or materials used in the application of concrete coating

**3.37**

**test report**

document that provides the quantitative test results for tests conducted in accordance with the requirements of this part of ISO 21809

## 4 Symbols and abbreviated terms

### 4.1 Symbols

$D_b$	bare pipe diameter (mm)
$D_c$	average concrete coated pipe diameter (mm)
$t_c$	concrete thickness (mm)
$t_p$	pre-coating minimum thickness (mm)

### 4.2 Abbreviated terms

AWG	American wire gauge
h.	hour(s)
min	minute(s)

## 5 General requirements

### 5.1 Rounding

Unless otherwise stated in this part of ISO 21809, to determine conformance with the specified requirements, observed or calculated values shall be rounded to the nearest unit in the last right-hand place of figures used in expressing the limiting value, in compliance with ISO 31-0:1992, Annex B, Rule A.

NOTE For the purposes of this provision, the rounding method of ASTM E29 is equivalent to ISO 31-0:1992, Annex B, Rule A.

### 5.2 Compliance with this part of ISO 21809

A quality system and an environmental management system should be applied to assist compliance with the requirements of this part of ISO 21809.

NOTE ISO/TS 29001 gives sector-specific guidance on quality management systems and ISO 14001 gives guidance on the selection and use of an environmental management system.

The applicator shall be responsible for complying with all of the applicable requirements of this part of ISO 21809. It shall be permissible for the purchaser to make any investigation necessary in order to be assured of compliance by the applicator and to reject any material and/or concrete coating that does not comply.

## 6 Information supplied by the purchaser

### 6.1 General information

The purchase order shall include the following information:

- number of this part of ISO 21809 and year of publication (ISO 21809-5:2010);
- pipe quantity, outside diameter, wall thickness, minimum and maximum individual pipe lengths, type and thickness of pre-coating;
- bare pipe standard or specification designation, e.g. ISO 3183, or pre-coated pipe standard or specification designation, e.g. ISO 21809-2;

- d) concrete coating thickness, density or specific gravity or negative buoyancy, and compressive strength;
- e) applicable project specifications;
- f) reinforcement type, standard and cross-sectional area percentages;
- g) concrete coating cutback length and tolerances for each pipe end;
- h) pre-coating inspection and repair requirements;
- i) markings to be applied to the concrete coated pipe;
- j) frequency of concrete coating density test during coating production (see Table 2).

## 6.2 Additional information

The purchase order shall indicate which of the following provisions apply for the specific order item:

- a) plant inspection by the purchaser;
- b) additional tests, types and frequency;
- c) handling procedures;
- d) storage procedures;
- e) requirement for applicator to submit details of the facilities and the methods to be used for yard storage;
- f) waiver of test reports;
- g) other special requirements, e.g. impact resistance, shear resistance for tension transfer on the pipe lay vessel;
- h) anode location area.

## 7 Materials

### 7.1 Pipe

The supply of bare or pre-coated pipe to be concrete coated shall conform to the pipe and pre-coating standards or specifications that are specified in the purchase order.

**IMPORTANT — Pre-coated steel pipe might not necessarily have a surface condition that is appropriate for the application of concrete coating. Remediation of the bare steel pipe or pre-coating may therefore be required.**

## 7.2 Cement

The applicator shall use cement that is:

- a) certified by the supplier to be in compliance with the requirements of ASTM C150, ASTM C595, ASTM C1157 or EN 197-1;
- b) identified with the following information on the certification and/or delivery documents for each shipment of cement:
  - cement producer's name and location,
  - product description including type and classification of cement,
  - year and month of production;
- c) handled, transported and stored prior to use, in compliance with the cement manufacturer's recommendations and in compliance with the applicable standards;
- d) no more than six months from the date of manufacture, unless it is retested and proven to be in compliance with the original standard.

NOTE Cement stored in a warm, humid environment for an extended period of time could possibly lose significant properties.

For submarine service conditions using concrete mixes containing Portland cement as the only cementitious material, the tricalcium aluminate ( $C_3A$ ) content of the cement shall be less than or equal to 10,0 %. For all other service conditions the tricalcium aluminate content limit is not applicable.

For submarine service conditions using concrete mixes containing Portland cement as the only cementitious material, the alkali content shall not exceed 0,6 %, if potentially reactive aggregates are used.

## 7.3 Supplementary cementitious materials

If approved by the purchaser, the applicator shall use SCMs that are:

- a) certified by the supplier to be in compliance with the requirements of ASTM C618, ASTM C989, ASTM C1240, EN 450-1 or EN 13263-1;
- b) identified with the following information on the certification and/or delivery documents for each shipment of SCMs:
  - 1) SCM producer's name and location;
  - 2) product description including type and classification of SCM;
  - 3) year and month of production;
- c) handled, transported and stored prior to use, in compliance with the SCM supplier's recommendations and in compliance with the applicable standard;
- d) within time limits stated in the applicable standard, unless it is retested and proven to be in compliance with the original standard.

NOTE SCMs stored in a warm, humid environment for an extended period of time could possibly lose significant properties.

#### 7.4 Aggregate — Fine and coarse

The applicator shall use fine or a combination of fine and coarse aggregates that are:

- a) certified by the supplier to be in compliance with the requirements of ASTM C33 or EN 12620;
- b) identified with the following on the certification and/or delivery documents for each source of aggregate:
  - 1) aggregate supplier's name and location;
  - 2) product description including gradation;
  - 3) qualification standard or specification;
- c) stored in such a condition as to prevent contamination and shall remain in compliance with the applicable standard.

The applicator shall verify that the aggregate received meets the above requirements.

#### 7.5 Heavyweight aggregate

If required, the applicator shall use heavyweight aggregate with an oven-dried density higher than 3 000 kg/m<sup>3</sup>, such as iron ore or other dense material, that is:

- a) certified by the supplier to be in compliance with the requirements of ASTM C637 or EN 12620;
- b) identified with the following on the certification and/or delivery documents for each shipment of heavyweight aggregate:
  - 1) heavyweight aggregate supplier's name and location;
  - 2) product description including gradation;
  - 3) chemical composition;
  - 4) density;
- c) suitable in size for the application process, and achieves the required concrete coating properties;
- d) stored in such a condition as to prevent contamination and shall remain in compliance with the applicable standard.

The applicator shall verify that the aggregate received meets the above requirements.

## 7.6 Lightweight aggregate

If required, the applicator shall use lightweight aggregate with an oven-dried density lower than 2 000 kg/m<sup>3</sup>, such as expanded or sintered clay, shale, slate, perlite, slag, sintered fly ash, natural pumice, volcanic cinders or industrial cinders, that is:

- a) certified by the supplier to be in compliance with the requirements of ASTM C330, ASTM C331, ASTM C332 or EN 13055-1;
- b) identified with the following on the certification and/or delivery documents for each shipment of lightweight aggregate:
  - 1) lightweight aggregate supplier's name and location;
  - 2) product description including gradation;
  - 3) chemical composition;
  - 4) density;
- c) suitable in size for the application process, and achieves the required coating properties;
- d) stored in such a condition as to prevent contamination and shall remain in compliance with the applicable standard.

The applicator shall verify that the aggregate received meets the above requirements.

## 7.7 Recycled concrete as aggregate

The use of recycled concrete is acceptable if processed from current or previous concrete coating projects to achieve an aggregate suitable in size for the application process. The use of this aggregate in combination with new aggregates shall achieve the required concrete coating properties stated in Tables 1 and 2.

Every 100 m<sup>3</sup> of processed recycled concrete shall be tested for:

- a) moisture in compliance with ASTM D4643;
- b) cleanliness in compliance with ASTM C40;
- c) particle size in compliance with ASTM C33 or EN 12620;
- d) density in compliance with ASTM C128.

The percentage of recycled concrete used as aggregate shall not exceed 10 % by weight unless agreed on with the purchaser.

NOTE Percent mass fraction is commonly called "weight percent" in USC units.

## 7.8 Water

Water used in the production of concrete shall comply with ASTM C1602 or EN 1008. Water that is potable does not require testing for compliance.

## 7.9 Steel reinforcement

The concrete coating shall be reinforced by steel bars tied or welded to form cages or by wire mesh steel. Steel bars shall comply with ASTM A82 or EN 10080. Wire mesh reinforcement shall comply with ASTM A185 or EN 10016-2. Zinc coated wire mesh shall comply with ASTM A810 or EN 10244-2.

The applicator shall request and retain certificates for each shipment. The certificates shall contain the information required in the aforementioned standards.

## 7.10 Concrete admixtures

The use and types of concrete admixtures shall be agreed on with the purchaser and shall comply with ASTM C494 or EN 934-2. Concrete admixtures containing added chlorides shall not be used.

## 7.11 Reclaimed concrete

The use of reclaimed concrete is acceptable only when the material is reintroduced via a conveyance system into the process within 30 min of initial mixing with water.

## 8 Concrete mix

The concrete ingredients shall be homogeneously mixed according to the applicator's mix design to predetermined proportions based on the concrete density and compressive strength necessary to achieve the requirements of the purchase order.

Each time the source of aggregate, water or cement changes, and that change necessitates a modification of the mix design, the applicator shall verify by testing that the new mix design results in a concrete coating that meets the purchase order requirements.

The applicator shall have a documented process control system to assure continuity of the produced mix.

For submarine service conditions using concrete mixes containing Portland cement as the only cementitious material, the water to cement ratio in the concrete mix shall be equal to or less than 0,40 and the minimum cement content shall be 400 kg/m<sup>3</sup> of the concrete mix.

For all other service conditions using concrete mixes containing Portland cement as the only cementitious material, the water to cement ratio in the concrete mix shall be equal to or less than 0,45 and the minimum cement content shall be 350 kg/m<sup>3</sup> of the concrete mix.

For all service conditions using concrete mixes containing SCMs, the water to cement ratio in the concrete mix may be equal to or lower than concrete mixes containing only Portland cement to achieve equivalent or higher compressive strengths.

## 9 Coating application

### 9.1 Qualification

A qualification test in accordance with Table 1 shall be performed prior to the start of concrete coating production. Three test pipes representative of the requirements of the purchase order and agreed on with the purchaser shall be concrete coated and test results shall be in compliance with Table 1.

If a result for density, compressive strength or water absorption does not meet the requirements of Table 1, retesting shall be carried out in accordance with 11.3.

If a result for other test parameters does not meet the requirements of Table 1, retesting may be done in agreement with the purchaser.

NOTE This qualification test represents one pipe diameter coated with one thickness and one density of concrete.

If existing documentation from previous projects using the same application process, application equipment and materials demonstrates compliance with the requirements of Table 1, the purchaser may accept this documentation and waive the qualification test requirement.

Documents for qualification shall include:

- a) concrete coating materials;
- b) pipe outside diameter;
- c) type of pre-coating applied;
- d) concrete coating thickness;
- e) steel reinforcement;
- f) mix design;
- g) concrete coating application and curing procedures;
- h) inspection and test plan;
- i) measurement, testing procedures and results;
- j) procedure for testing shear resistant material, if applicable, which shall be provided by the applicator;
- k) procedure for testing impact resistance, if applicable, which shall be provided by the applicator;
- l) repair materials and procedures;
- m) handling and storage procedures;
- n) anode installation procedure, if applicable.

Table 1 — Qualification test requirements

Property	Subclause	Test method	Requirements	Tolerance	Frequency qualification
Pre-concrete coated pipe length	9.1	N/A	N/A (for informational purposes)	N/A (for informational purposes)	Each pipe
Concrete coating thickness <sup>a</sup>	11.2.1	11.2.1	As stated in purchase order	±6 mm	Ten measurements on each pipe
Pre-concrete coated pipe weight in air	11.2.3	Measurement	As stated in purchase order	N/A (for informational purposes)	Each pipe
Concrete coated pipe weight in air	11.2.4	Measurement	As stated in purchase order	+7,5 % -5	Each pipe
Concrete coating density <sup>a</sup>	11.2.5	ASTM C642 EN 12390-7	As stated in purchase order	±5 %	Each pipe
Concrete coating cutback length	9.6	Measurement	As stated in purchase order	±25 mm	Each end of each pipe
Reinforcement placement	9.5.5	9.5.5	As stated in 9.5.5	As stated in 9.5.5	Each pipe
Reinforcement electrical isolation	9.5.5.1	9.5.5.1	9.5.5.1	As stated in 9.5.5.1	Each pipe
Reinforcement overlap	9.5.5.2 9.5.5.3	11.2.2	9.5.5.2 9.5.5.3	9.5.5.2 or 9.5.5.3, as applicable	Each pipe
Preparation of compressive strength specimens from fresh concrete	11.2.6.1	ASTM C31 ASTM C172, ASTM C1176, ASTM C1435, or EN 12390-2	N/A	N/A	One set of three specimens
Preparation of compressive strength specimens from hardened concrete	11.2.6.2	ASTM C42, ASTM C617, ASTM C1604, or EN 12504-1	N/A	N/A	One set of three visually acceptable specimens per pipe
Compressive strength <sup>b</sup>	11.2.6	ASTM C39, ASTM C42, ASTM C1604, EN 12390-3	As stated in purchase order	As stated in purchase order	All specimens
Water absorption <sup>c</sup>	11.2.7	Annex A	Not to exceed 5 %	None	One test on one pipe
Shear resistance <sup>d</sup>	N/A	Annex B	As stated in purchase order	As stated in purchase order	Three tests on one pipe
Impact resistance <sup>d</sup>	11.2.8	Purchase order	As stated in purchase order	As stated in purchase order	One set on one pipe, when specified
Environmental conditions	9.3	ASTM D6176	9.3	For informational purposes only	Once on the day of qualification

<sup>a</sup> If the applicator has calculated the thickness and density of the concrete coating from the specific gravity or negative buoyancy stated in the purchase order, then the results shall be approved by the purchaser prior to the qualification test.

<sup>b</sup> For qualification, the method of testing compressive strength shall be agreed on between the purchaser and the applicator. Cores shall not be taken if the concrete thickness is less than 40 mm.

<sup>c</sup> Hardened concrete coating field specimens that have achieved a minimum compressive strength of 15 MPa shall be tested in compliance with Annex A for water absorption.

<sup>d</sup> Shear resistance and/or impact resistance qualification testing shall be conducted if specified in the purchase order.

## 9.2 Application of concrete coating

Concrete coating shall be applied by any one of the following processes:

- a) compression (wrap);
- b) impingement;
- c) form and/or pour;
- d) slip form.

## 9.3 Environmental conditions

Coating application shall take place only under the following conditions:

- a) pipe, pre-coating, reinforcement and concrete mix temperature shall be within the range of +3 °C to +35 °C;
- b) air temperature in the immediate vicinity of the concrete coating shall be within the range of +1 °C to +43 °C.

If the conditions for coating fall outside the above-mentioned, then the applicator shall present a procedure for the protection of the concrete coating to the purchaser for approval.

## 9.4 Pipe

### 9.4.1 Pre-coated pipe

If the pre-coated pipe has been handled or placed in stockpile, then all pipes shall be tested for holidays in compliance with the original pre-coating standard. Holidays shall be repaired as agreed with the purchaser.

The surface of the pre-coated pipe shall be free from dirt, mud, oils or any deleterious material which would prevent the application of the concrete coating in compliance with this part of ISO 21809.

If the pre-coating plant is connected directly to the concrete coating plant by a conveyor system, then additional testing for holidays of the pre-coated pipe is not required prior to the application of the concrete coating.

If concrete coating has been removed for any reason, then the pre-coated pipe shall be tested for holidays in compliance with the original pre-coating standard. Holidays shall be repaired as agreed with the purchaser.

### 9.4.2 Bare pipe

The surface of the bare pipe shall be free from dirt, mud, oils, loose scale or any deleterious material which would prevent the application of the concrete coating in compliance with this part of ISO 21809.

## 9.5 Steel reinforcement

### 9.5.1 General

Steel reinforcement shall be provided to limit spalling and control cracking of the concrete coating.

The reinforcement provided shall be a cage, welded wire mesh, woven wire mesh or a combination thereof. The type of reinforcement to be used shall be stated in the purchase order.

The reinforcement shall be free from oil, grease, dirt or other deleterious material.

The minimum amount of the steel reinforcement shall be 0,4 % circumferentially and 0,06 % longitudinally of the cross-sectional area of the concrete coating.

### 9.5.2 Cage reinforcement

Cage reinforcement shall be in the form of spirally wound cages, having a continuous hoop bar with a number of straight longitudinal bars evenly spaced around the spiral and tied or welded at each bar intersection. Alternatively, the continuous hoop bar may be replaced by single circumferential hoops.

The material used shall be in compliance with EN 10080 or ASTM A82. The welding of the materials shall result in a steel cage in compliance with EN 10080 or ASTM A185.

The diameter of the circumferential and longitudinal bars shall be calculated from the requirements of the purchase order or the requirements of 9.5.1. The minimum diameter of the reinforcement used for cages shall be 5 mm.

### 9.5.3 Welded wire mesh reinforcement

The reinforcement shall be applied by a method that provides continuity of the reinforcement.

The welded wire mesh used shall be galvanized and shall conform to ASTM A185, ASTM A641 and ASTM A810 or EN 10016-2.

The diameter of the circumferential and longitudinal wires shall be calculated from the requirements of the purchase order or the requirements of 9.5.1. The minimum diameter of the reinforcing wire shall be 1,5 mm.

### 9.5.4 Woven wire mesh reinforcement

The reinforcement shall be applied by a method that provides continuity of the reinforcement.

Woven wire mesh reinforcement shall conform to ASTM A810.

The minimum diameter of the woven wire mesh shall be 1,15 mm (AWG 17).

### 9.5.5 Reinforcement placement

#### 9.5.5.1 General

The reinforcement shall be a minimum of 10 mm from the surface of the pre-coating or bare pipe and shall have a minimum of 10 mm concrete cover. The reinforcement shall not protrude beyond the end of the concrete coating cutback unless otherwise agreed between applicator and the purchaser.

The reinforcement shall be electrically isolated from the pipe and the pre-coating. This isolation shall be tested twice per production shift with a calibrated instrument. The resistance shall be greater than 10 000  $\Omega$ .

If more than one layer of reinforcement is used, there shall be a minimum spacing of 5 mm between layers (excluding the overlap area).

#### 9.5.5.2 Cage reinforcement

The reinforcement shall be positioned within the middle third of the concrete coating.

Cages shall be rigidly held concentric to the pipe at the correct location by electrically insulating plastic, synthetic resin or concrete spacers.

Spacers shall have flush bases to prevent indentation into the pre-coating.

If multiple sections are required to achieve continuous reinforcement, the overlap between the longitudinal bars shall be a minimum of 200 mm with a minimum distance between circumferential reinforcement of 25 mm. Overlapping bars shall be mechanically connected as necessary to maintain continuity.

### 9.5.5.3 Woven or welded wire mesh reinforcement

A minimum of one layer of reinforcement shall be used. Additional layers of reinforcement may be necessary to meet the purchase order requirements or the percentage requirements of 9.5.1.

The longitudinal overlap shall be a minimum of 12 mm as measured from wire to wire.

## 9.6 Concrete cutback

The ends of the concrete coating shall be shaped 60° to 90° to the axis of the pipe.

The ends and inside of the pipe shall be free of concrete debris.

The concrete cutback length shall be measured from each end of each pipe to the start of the concrete coating and shall meet the requirements of Table 2.

## 9.7 Anode installation

If anodes are to be installed after the application of the concrete coating, pipes assigned for anode installation shall have a section of concrete removed of such a length as to accommodate an anode +100 mm minimum and at the location as agreed in the purchase order.

If anodes are installed prior to the application of the concrete coating, the reinforcement shall be a minimum distance of 15 mm from each end of the anode.

The anode shall not come into contact with the concrete coating reinforcement.

## 10 Curing methods

The concrete coating shall be cured by one or a combination of the following methods:

- a) water fogging or misting (in compliance with ACI 308.1);
- b) liquid membrane or sheet materials (in compliance with ASTM C309 or ASTM C171);
- c) steam.

It shall be demonstrated that the steam curing process has no deleterious effects on the concrete coating.

Whichever method is used, the concrete coating shall remain moist until a minimum compressive strength of 15 MPa is achieved as tested by field specimens.

## 11 Inspection and testing

### 11.1 General

During concrete coating production, quality control tests shall be carried out in accordance with Table 2 to demonstrate compliance with the purchase order and/or this part of ISO 21809. If a test result does not meet the requirements of Table 2, retesting shall be carried out in accordance with 11.3.

Acceptance of non-conforming coatings shall be at the purchaser's option.

Inspection, measurement and test equipment shall be calibrated to a standard at a frequency that assures the integrity of the inspections, measurements and tests. The calibration records shall include all information required to trace the calibration to the applicable standard, including reference to the unique identification of the standard.

Records of all calibrations shall be maintained by the applicator and shall be available for review.

Table 2 — Production quality control

Property	Clause/ Subclause	Test method	Requirements	Tolerance	Frequency
Aggregates	7.4, 7.5, 7.6	ASTM C33 EN 12620	Applicator's purchase order to supplier	Applicator's purchase order to supplier	Twice per week
Recycled aggregates	7.7	As in 7.7	Applicator's values	Applicator's values	Each 100 m <sup>3</sup> of processed material
Water content	8	ASTM D4643 or ASTM D4959 or ASTM D2216 or suitable alternative	Applicator's mix design	Applicator's mix design	Minimum of one every 2 h of production
Cement content and water/cement ratio	8	EN 206-1	Applicator's mix design	Applicator's mix design	Minimum of one every 2 h of production
Concrete coating thickness	11.2.1	11.2.1	Purchase order	±6 mm	Three measurements on each pipe
Concrete coating density	11.2.5	11.2.5	Purchase order	±5 %	As stated in the purchase order
Concrete coating cutback length	9.6	Measurement	Purchase order	±25 mm	Each end of each pipe
Concrete coated pipe weight in air	11.2.4	11.2.4	Purchase order	+7,5 % -5 % for each individual pipe; +5 % -2,5 % for rolling 25 consecutive pipe average	Each pipe
Reinforcement electrical isolation	9.5.5.1	9.5.5.1	9.5.5.1	As stated in 9.5.5.1	Twice per production shift
Reinforcement location	9.5.5	11.2.2	9.5.5.2 9.5.5.3	As stated in 9.5.5.1	Once per production day per pipe size or concrete thickness
Reinforcement overlap	9.5.5.2 9.5.5.3	11.2.2	9.5.5.2 9.5.5.3	As stated in 9.5.5.1	Once per production shift per pipe size or concrete thickness
Preparation of compressive strength test specimens from fresh concrete	11.2.6.1	ASTM C31, ASTM C172, ASTM C1176, ASTM C1435, or EN 12390-2	N/A	N/A	A set of three test specimens from the first 50 m <sup>3</sup> , then each 150 m <sup>3</sup> thereafter, or three test specimens at least twice per production shift, whichever is more frequent <sup>a</sup>
Preparation of compressive strength test specimens from hardened concrete	11.2.6.2	ASTM C42, ASTM C617, ASTM C1604, or EN 12504-1	Not applicable on concrete thicknesses less than 40 mm	N/A	A set of three visually acceptable test specimens from one pipe every 25 pipes coated
Compressive strength	11.2.6	ASTM C39, ASTM C42, ASTM C1604 or EN 12390-3	Purchase order	Purchase order	All test specimens

Table 2 (continued)

Property	Clause/ Subclause	Test method	Requirements	Tolerance	Frequency
Water absorption	11.2.7	Annex A	Not to exceed 5 %	None	Minimum of once per production shift, test specimens as in Annex A
Environmental conditions	9.3	9.3	9.3	As stated in 9.3	Each day at the start of production
<sup>a</sup> Test frequency may be relaxed, if agreed to by the purchaser.					

## 11.2 Test procedures

### 11.2.1 Concrete coating thickness — Diameter measurement

The outside diameter of the concrete coated pipe shall be measured using a pi tape or other appropriate diameter measurement methods. Each coated pipe shall have a minimum of three equally spaced measurements along the length of the pipe.

The concrete coating thickness,  $t_c$ , shall be calculated using Equation (1):

$$t_c = [(D_c) - (D_b + t_p + t_p)]/2 \quad (1)$$

where

$t_c$  is the concrete thickness (mm);

$D_c$  is the average concrete coated pipe diameter (mm);

$D_b$  is the bare pipe diameter (mm);

$t_p$  is the pre-coating minimum thickness (mm).

The minimum pre-coat thickness may be determined by reviewing the project records of the pre-coating process or by measuring a pre-coated pipe representative of the pipe to be concrete coated. Agreement shall be reached with the purchaser on the method of pre-coating measurement.

If the calculated concrete thickness does not meet the requirements of Table 1 or Table 2, as applicable, the pipe shall be stripped and recoated.

### 11.2.2 Placement of reinforcement

A section of freshly applied concrete approximately 75 mm × 200 mm shall be removed from the first pipe of each day's production down to the pre-coating. During the removal process, the applicator shall ensure the integrity of the original placement of the reinforcement.

Inspection of the exposed area shall confirm that the reinforcement is positioned and the overlap is as required in the purchase order. The exposed area shall be repaired by trowelling or otherwise packing a mix of like material.

If the wire is not positioned correctly, the pipe shall be rejected, stripped of the concrete coating and recoated. Each pipe following the rejected pipe shall be inspected in this manner until the position of the reinforcement is accepted. All rejected pipes shall be stripped and recoated.

Alternative test methods shall be subject to agreement with the purchaser prior to production.

### 11.2.3 Pre-concrete coated pipe weight in air

If required by the purchase order, the pre-coated steel pipe shall be weighed prior to the application of concrete coating using a weighing device that is calibrated to an accuracy of  $\pm 0,5$  % of the calibration weight. The calibration weight shall be representative of the anticipated production weights.

### 11.2.4 Concrete coated pipe weight in air

Each concrete coated pipe shall be weighed as it is removed from the coating machine, but after concrete cutback completion, using a weighing device that is calibrated to an accuracy of  $\pm 0,5$  % of the calibration weight. The calibration weight shall be representative of the anticipated production weights. The method of weighing the pipe shall be specified by the applicator in the manufacturing procedure.

Weight adjustment by recoating shall be performed within the first 30 min of cement coming into contact with water, provided the increased girth measurement meets the requirements of Table 1 or Table 2.

Weight adjustment by scraping and/or scabbling shall be performed, provided there is no damage to the concrete coating and the decreased girth measurement meets the requirements of Table 1 or Table 2.

The weight of each pipe joint shall be permanently recorded on the inside or outside of the pipe as specified in the purchase order by any method agreed on with the purchaser. The weight of each concrete coated pipe shall also be recorded on the applicator's records.

If the measured weight and girth measurement do not meet the requirements of Table 1 or Table 2, as applicable, the pipe shall be rejected, stripped and recoated.

### 11.2.5 Concrete coating density

The density of the hardened concrete shall be determined in accordance with ASTM C642 or EN 12390-7.

If the result does not meet the requirements of Table 1 or Table 2, as applicable, retesting shall be performed in accordance with 11.3.

### 11.2.6 Compressive strength

#### 11.2.6.1 Preparation of specimens from fresh concrete

Specimens shall be prepared from the fresh mix in compliance with ASTM C31, ASTM C172, ASTM C1176, ASTM C1435 or EN 12390-2. Preparation of specimens shall commence within 15 min after the concrete has been discharged from the mixing unit.

NOTE The standard methods of concrete consolidation by rodding or internal vibration, as described in ASTM C31 or EN 12390-2, might not be practical for low-moisture-content concrete mixes. Consolidation using vibrating table or vibrating hammer, as specified in ASTM C1176 and ASTM C1435, could possibly be more suitable.

#### 11.2.6.2 Preparation of specimens from hardened concrete

Specimens shall be prepared from hardened concrete in compliance with ASTM C42, ASTM C1604 or EN 12504-1. Specimens from hardened concrete shall not be taken from concrete thicknesses less than 40 mm. The core shall have a minimum diameter of 29 mm.

The cores shall be drilled at three locations along the pipe body: between 1 m and 2 m from each end, and within the middle 2 m. The specimens shall be visually inspected for obvious defects, such as voids, wire overlap, bars, cracks, dimensional irregularities or any other deleterious defects. Specimens with obvious defects shall be discarded.

A core having a maximum length of less than 95 % of its diameter before capping or a length less than its diameter after capping or end preparation shall not be tested. The maximum acceptable length of the core after capping or end preparation is 120 % of its diameter. The maximum thickness of the capping material, if used, shall be 3 mm.

Unbonded caps shall not be used.

### 11.2.6.3 Testing of specimens from hardened concrete

Specimens shall be tested in compliance with ASTM C39 or EN 12390-3. The test method used, including the conditioning of the specimens, shall be recorded.

NOTE Specimens tested dry or as-received could possibly have a higher compressive strength than specimens that are fully saturated for the same concrete coating.

If the result does not meet the requirements of the purchase order, as applicable, retesting shall be performed in accordance with 11.3.

### 11.2.7 Water absorption

Hardened concrete coating specimens that have achieved a minimum compressive strength of 15 MPa shall be tested in accordance with Annex A.

If the results do not meet the requirements of Table 1 or Table 2, as applicable, retesting shall be performed in accordance with 11.3.

### 11.2.8 Impact resistance

If an impact resistance test is required by the purchase order for coating qualification, an impact test procedure that is applicable to the service conditions shall be specified.

NOTE DNV-RP-F111 contains a methodology that can be used for impact testing for both offshore and onshore pipelines.

If the result does not meet the requirements of Table 1, the purchaser shall have the right to require additional tests.

### 11.2.9 Shear resistance

If a shear resistance test is required by the purchase order, the test procedure in Annex B shall be used. If the result does not meet the requirements of Table 1, the purchaser shall have the right to require additional tests.

### 11.2.10 Visual inspection

The finished concrete coating shall be visually inspected and any damaged areas and cracks shall be repaired in accordance with Clause 12.

## 11.3 Retesting

### 11.3.1 General

Retesting following a failed test shall only be permitted for density, compressive strength or water absorption tests.

### 11.3.2 Density

If a single concrete test specimen fails to meet the density requirements, spare specimens, if available, shall be tested.

If the spare test specimens meet the density requirements, the previously suspect concrete coated pipes shall be accepted.

If the spare test specimens fail to meet the density requirements or are not available, the purchaser shall have the right to order additional testing or to reject the concrete coated pipes represented by the failed concrete test specimens.

### 11.3.3 Compressive strength

If a single concrete test specimen fails to meet the specified strength requirements, spare specimens, if available, shall be tested.

If the spare test specimens meet the specified strength requirements, the previously suspect concrete coated pipes shall be accepted.

If the spares fail to meet the specified strength requirements, or are not available, the purchaser shall have the right to order additional testing or to reject the concrete coated pipes represented by the failed concrete test specimens.

### 11.3.4 Water absorption

If a single concrete test specimen fails to meet the specified water absorption requirements, spare specimens, if available, shall be tested.

If the spare test specimens meet the water absorption requirements, the previously suspect concrete coated pipes shall be accepted.

If the spares fail to meet the water absorption requirements, or are not available, the purchaser shall have the right to order additional testing or to reject the concrete coated pipes represented by the failed concrete test specimens.

## 11.4 Test results

Regardless of any waiver of test reporting specified in the purchase order, the results of all tests required in 11.2 and 11.3 shall be retained and available to the purchaser on request.

## 12 Repair of concrete coated pipe

### 12.1 General

Damaged areas and cracks in the finished concrete coating shall be repaired as stated in 12.2 and 12.3. The repair procedure and the repair materials shall be compatible with the applied coating. Repair work shall be performed with qualified materials and in compliance with procedures approved by the purchaser.