

INTERNATIONAL
STANDARD

ISO
22526-1

First edition
2020-01

**Plastics — Carbon and environmental
footprint of biobased plastics —**

Part 1:
General principles

STANDARDSISO.COM : Click to view the full PDF of ISO 22526-1:2020



Reference number
ISO 22526-1:2020(E)

© ISO 2020

STANDARDSISO.COM : Click to view the full PDF of ISO 22526-1:2020



COPYRIGHT PROTECTED DOCUMENT

© ISO 2020

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword.....	iv
Introduction.....	v
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	1
4 General principles.....	2
5 Carbon and environmental footprint of biobased plastics.....	2
5.1 Principle.....	2
5.2 Material carbon footprint.....	2
5.3 Process carbon footprint.....	5
5.4 Environmental (total) footprint (life cycle assessment).....	5
5.5 System boundaries of the ISO 22526 series.....	5
Bibliography.....	7

STANDARDSISO.COM : Click to view the full PDF of ISO 22526-1:2020

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 14, *Environmental aspects*.

A list of all parts in the ISO 22526 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

Increased use of biomass resources for manufacturing plastic products can be effective in reducing global warming and the depletion of fossil resources.

Current plastic products are composed of biobased synthetic polymers, fossil-based synthetic polymers, natural polymers and additives that can include biobased materials.

Biobased plastics refer to plastics that contain materials wholly or partly of biogenic origin.

STANDARDSISO.COM : Click to view the full PDF of ISO 22526-1:2020

[STANDARDSISO.COM](https://standardsiso.com) : Click to view the full PDF of ISO 22526-1:2020

Plastics — Carbon and environmental footprint of biobased plastics —

Part 1: General principles

1 Scope

This document specifies the general principles and the system boundaries for the carbon and environmental footprint of biobased plastic products. It is an introduction and a guidance document to the other parts of the ISO 22526 series.

This document is applicable to plastic products and plastic materials, polymer resins, which are based from biobased or fossil-based constituents.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 472, *Plastics — Vocabulary*

ISO 14020, *Environmental labels and declarations — General principles*

ISO 14040, *Environmental management — Life cycle assessment — Principles and framework*

ISO 14044, *Environmental management — Life cycle assessment — Requirements and guidelines*

ISO 14067, *Greenhouse gases — Carbon footprint of products — Requirements and guidelines for quantification*

ISO 16620-1, *Plastics — Biobased content — Part 1: General principles*

ISO 16620-2, *Plastics — Biobased content — Part 2: Determination of biobased carbon content*

ISO 16620-3, *Plastics — Biobased content — Part 3: Determination of biobased synthetic polymer content*

ISO 16620-4, *Plastics — Biobased content — Part 4: Determination of biobased mass content*

ISO 16620-5, *Plastics — Biobased content — Part 5: Declaration of biobased carbon content, biobased synthetic polymer content and biobased mass content*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 472, ISO 14067, ISO 16620-1, ISO 16620-2, ISO 16620-3, ISO 16620-4, ISO 16620-5 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

**3.1
carbon and environmental footprint**

life cycle assessment of biobased plastics products with considerations on the specific situations for biobased materials and products on the removal of CO₂ from the air in comparison with fossil-based plastics products

Note 1 to entry: The definition of the term “environmental footprint” used here is different from that of the one used in European Union, which is composed of “Product environmental footprint” and “Organization environmental footprint”.

**3.2
material carbon footprint**

amount (mass) of CO₂ removed from the air and incorporated into 1 kg of polymer molecule

**3.3
process carbon footprint**

carbon footprint for the process of converting the starting feedstock/resource to product at factory gate

4 General principles

4.1 The general principles for the development and use of environmental labels and declarations established in ISO 14020 shall be followed for modifications that will fit the special assessment linked to the origin of the material.

4.2 The general principles for guidance for decisions relating to both the planning and the conducting of an LCA in ISO 14040 shall also be followed.

5 Carbon and environmental footprint of biobased plastics

5.1 Principle

Carbon is the major basic element that is the building block of all plastics, fuels, and even life itself. Therefore, discussions on sustainability and environmental responsibility centre on the carbon footprint of bioplastics using biocarbon content analysis and life-cycle assessment of biobased plastics, in which the fossil carbon is replaced by bio-based carbon, offer the intrinsic value of a reduced carbon footprint and are in complete harmony with the rates and time scale of the biological carbon cycle. Identification and quantification of bio-based content is based on the radioactive C-14 signature associated with (new) biocarbon. Using experimentally determined biocarbon content values, one can calculate the intrinsic CO₂ emissions reduction achieved by substituting petrocarbon with biocarbon — the material carbon footprint. The process carbon footprint arising from the conversion of feedstock to final product is computed using life-cycle assessment methodology. The issue is of managing carbon (carbon-based materials) in a sustainable and environmentally responsible manner. Indeed, the burning issue of today is concern over increasing human-made CO₂ emissions with no offsetting sequestration and removal of the released CO₂. Reducing our carbon footprint is a major challenge. Reduced CO₂ emissions translate to minimizing global warming-climate change problems.

5.2 Material carbon footprint

Switching the manufacturing base (the origins of the carbon) from fossil carbon feedstock to bio-based carbon feedstock offers an intrinsic zero material (i.e. referred to the feedstock of the product) carbon footprint potentiality. This can be seen by reviewing biological carbon cycle. Nature cycles carbon through various environmental compartments with specific rates and time scales, as shown in [Figure 1](#). Carbon is present in the atmosphere as inorganic carbon in the form of CO₂. The current level of CO₂ in the atmosphere is around 380 ppm (parts per million) and is increasing. CO₂ and other greenhouse gases in the atmosphere trap the sun’s heat from radiating back to space, thereby providing a life-sustaining average planet temperature of 7,2 °C (45 °F).





Figure 1 — Biological carbon cycle-value proposition for using biorenewable carbon instead of fossil-based carbon feedstock

Increasing levels of CO_2 and other greenhouse gas emissions to the atmosphere traps more of the sun's heat, thereby raising the average temperature of the planet. While one might debate the severity of the effects associated with this or any other target level of CO_2 , there can be no disagreement that an uncontrolled, continued increase in levels of CO_2 in the atmosphere will result in a slow perceptible rise of the earth's temperature, global warming, and with it an associated severity of effects that will affect life on this planet as well known.

It is therefore prudent and necessary to try and maintain current CO_2 levels — the "zero carbon" approach. This can best be done by using renewable biomass crops to manufacture carbon-based products so that the CO_2 released at the end-of-life of the product was that originally captured by the crops, so that no extra CO_2 is added to the atmosphere. Specifically, the rate of CO_2 release to the environment at end-of-life equals the rate of photosynthetic CO_2 fixation by the original crops planted — a zero material carbon footprint, in case of total oxidation into CO_2 of the feedstock. In the case of fossil feedstock, the rate of carbon fixation is measured in millions of years, while the end-of-life release rate into the air is in 1 to 10 years. The math is simple, and this is not sustainable. It causes more CO_2 release than fixation, resulting in an increased carbon footprint and, with it, attendant global warming and climate change problems.


Based on the previous carbon cycle discussion and using basic stoichiometry, it was calculated that for every 100 kg of polyolefin (polyethylene, PE; polypropylene, PP) manufactured, a net 314 kg CO_2 is released into the air at its end-of-life (100 kg of PE contains 85,7 % kg carbon and upon combustion will yield 314 kg of CO_2 $(44/12) \times 85,7$). Similarly, PET (polyethylene terephthalate) contains 62,5 % carbon and would result in 229 kg of CO_2 released into the air at end-of life. However, if the carbon in the polyester or polyolefin comes from a biological feedstock, the net release of CO_2 into the air is zero, because the CO_2 released is fixed in a short time period by the next crop or biomass plantation (see [Figures 2, 3 and 4](#)). This is the intrinsic zero material carbon footprint for using a bio/renewable feedstock.



Key

- Y kg CO₂/kg disposed resin
- PLA Polylactic Acid
- bio-PET bio-PolyEthylene Terephthalate
- PET PolyEthylene Terephthalate


Figure 2 — Amount (mass) of CO₂ removed from the air per 1 kg production of resin (A) — Material carbon footprint



Key

- Y kg CO₂/kg disposed resin
- PLA Polylactic Acid
- bio-PET bio-PolyEthylene Terephthalate
- PET PolyEthylene Terephthalate

Figure 3 — Amount (mass) of CO₂ released to the air per 1 kg disposal of resin (B)

**Key**

Y	kg CO ₂ /kg disposed resin
PLA	Poly(lactic Acid)
bio-PET	bio-PolyEthylene Terephthalate
PET	PolyEthylene Terephthalate

Figure 4 — Amount (mass) of CO₂ released to the air per 1 kg production and disposal of resin (B-A)

5.3 Process carbon footprint

Carbon footprint from the conversion of feedstock to product – cradle to factory gate scenario and total environmental footprint should be calculated using life cycle assessment methodology of ISO 14040.

B2B value chain analysis or cradle to factory gate analysis should be clarified. Practitioners and users of life cycle assessment need to be careful in comparative analysis of products because of the boundary conditions selected and quality of data used. Life cycle assessment should primarily be used for improvements in environmental impact from base line and not as a marketing tool to show comparative analysis using partial skewed system boundaries.

The descriptions in the process carbon footprint of the biobased plastics are in line with ISO 14067.

5.4 Environmental (total) footprint (life cycle assessment)

Material carbon footprint and process carbon footprint do not solely provide information on its environmental impact, which should be also assessed through life cycle analysis, including not only carbon footprint but also other relevant impact categories. In addition, transparent and unambiguous communication within biobased value chains is facilitated by a harmonized framework for certification and declaration.

This document aims to provide specific life cycle assessment requirements and guidance for biobased products, excluding food, feed and energy, in accordance with ISO 14040 and ISO 14044.

This document informs and guides life cycle assessment and applications, including for example product category rules (PCR) development for biobased products.

The life cycle assessment of a bio-based product shall cover the whole product, not only the biobased parts. However, the focus of document is on how to handle the specificities of the biobased parts.

5.5 System boundaries of the ISO 22526 series

System boundaries of total scheme of the carbon and environmental footprint of biobased plastics are depicted in [Figure 5](#).