



INTERNATIONAL STANDARD ISO 22958:2005
TECHNICAL CORRIGENDUM 1

Published 2009-10-15

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

Textiles — Water resistance — Rain tests: exposure to a horizontal water spray

TECHNICAL CORRIGENDUM 1

Textiles — Résistance à l'eau — Essai d'arrosage: exposition à une pulvérisation horizontale

RECTIFICATIF TECHNIQUE 1

Technical Corrigendum 1 to ISO 22958:2005 was prepared by Technical Committee ISO/TC 38, *Textiles*, Subcommittee SC 2, *Cleansing, finishing and water resistance tests*.

Page 2, 6.2

Delete the existing text, and insert

“**White textile blotting paper**, of thickness approximately $(0,71 \pm 0,1)$ mm, a surface density (often known in the industry as “weight”) of $(370 \pm 18,5)$ g/m² and with an absorbent capacity of (220 ± 30) %.”²⁾”

Page 2, 8.1, line 1

Delete “ (150×150) mm”, insert “ (150 ± 3) mm \times (150 ± 3) mm”.