

Revised

---

**INTERNATIONAL STANDARD**



**2325**

---

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

---

**Size analysis of small coke (nominal top size 20 mm or less)**

First edition — 1972-12-01

STANDARDSISO.COM : Click to view the full PDF of ISO 2325:1972

---

UDC 662.749.2 : 620.168

Ref. No. ISO 2325-1972 (E)

**Descriptors** : coke, sieve analysis, size determination.

## FOREWORD

ISO (the International Organization for Standardization) is a worldwide federation of national standards institutes (ISO Member Bodies). The work of developing International Standards is carried out through ISO Technical Committees. Every Member Body interested in a subject for which a Technical Committee has been set up has the right to be represented on that Committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work.

Draft International Standards adopted by the Technical Committees are circulated to the Member Bodies for approval before their acceptance as International Standards by the ISO Council.

International Standard ISO 2325 was drawn up by Technical Committee ISO/TC 27, *Solid mineral fuels*.

It was approved in October 1971 by the Member Bodies of the following countries :

|                     |                       |                |
|---------------------|-----------------------|----------------|
| Australia           | Iran                  | Switzerland    |
| Austria             | Ireland               | Turkey         |
| Belgium             | New Zealand           | United Kingdom |
| Canada              | Poland                | U.S.A.         |
| Czechoslovakia      | Portugal              | U.S.S.R.       |
| Denmark             | Romania               | Yugoslavia     |
| Egypt, Arab Rep. of | South Africa, Rep. of |                |
| India               | Sweden                |                |

The Member Body of the following country expressed disapproval of the document on technical grounds :

France

# Size analysis of small coke (nominal top size 20 mm or less)

## 1 SCOPE AND FIELD OF APPLICATION

This International Standard specifies the method of determining the particle size distribution of a sample of coke having a nominal top size of 20 mm or less. Two methods of operation are described :

- a) where a restricted size analysis is required, using two sieves only;
- b) where a complete size analysis is required.

## 2 PRINCIPLE

The sample of coke is subjected to a process of size analysis by a specified procedure and the results are expressed in terms of the cumulative percentages by mass of the coke remaining on sieves of different sized apertures.

## 3 APPARATUS

**3.1 Perforated plate sieves**, of round aperture size respectively 20 mm and 10 mm, or **wire mesh test sieves** of the nearest equivalent square aperture (16 mm and 8 mm side respectively).

**3.2 Wire cloth test sieves** of the following aperture sizes : 16, 8, 4, 2 and 1 mm; 500, 250, 125 and 63  $\mu\text{m}$ . These sieves are conveniently shaken by means of an appropriate mechanical shaking machine.

**3.3 Lightweight containers**, of metal or plastics material, for the sample and the fractions sieved from it. The largest container shall be capable of holding 20 kg of sample.

**3.4 Weighing machines** suitable for weighing a mass of up to 30 kg, such that the weighing error does not exceed 0,1 % of the maximum mass of sample or 10 g, whichever is the smaller.

NOTE – The sieves shall comply, when selected and during use, with ISO/R 565, *Woven wire cloth and perforated plates in test sieves – Nominal apertures* and ISO .... (at present at the stage of draft proposal).

## 4 SAMPLE

The sample shall be representative of the coke. For coke containing appreciable quantities (over 20 %) above 10 mm, the mass of sample shall be 20 kg. For samples where the maximum size is 2 mm or less, the mass of sample shall be not less than 0,3 kg and preferably not more than 0,5 kg. Intermediate masses may be taken according to the top size of the sample.

## 5 PROCEDURE

### 5.1 Restricted size analysis on two sieves

Before commencing the test, dry the coke sample at a temperature of 200 °C (see Note 1).

Weigh the sample to the nearest 0,01 kg. Place the two sieves (3.1) or two of the sieves (3.2) one above the other in a suitable frame, with the sieve of larger aperture size uppermost. Place the receiving tray below the sieve of smaller aperture.

Transfer a quantity of the dry coke to the upper sieve, such that it is not choked by the coke. In general, this will mean that not more than 75 % of the sieve is covered by the coke. Shake the sieve by hand (see Note 2) until no more coke passes through the apertures. Remove the top sieve, transfer the oversize to a container of known mass and carry out the same procedure with the coke remaining on the lower sieve. Replace the empty sieves in the frame. Repeat the process until the whole sample has been treated in this manner, transferring the coke to the appropriate containers after each operation.

Weigh each container with its contents to the nearest 0,01 kg and calculate the total mass of coke which remains on each sieve after the sieving operations.

Transfer the coke which has passed through the lower sieve into the tray to a container of known mass and weigh.

**5.2 Complete size analysis** (using a mechanical sieving machine -- see Note 3)

Before commencing the test, dry the coke sample at a temperature of 200 °C (see Note 1).

Weigh the sample to an accuracy of 0,1 %. It will probably be advisable to carry out the size analysis in two stages if a complete range of apertures is to be covered, namely :

- using sieves with 16, 8, 4 and 2 mm apertures;
- using sieves with 1 000, 500, 250, 125 and 63 µm apertures.

The diameter of the sieves having apertures of 2 mm or over will generally be larger than that of sieves with smaller apertures.

When transferring from larger to smaller diameter sieves, it may be necessary to reduce the mass of material to a known proportion and to sieve this known reduced mass on the smaller diameter sieves, repeating the same sieving procedure (see Note 4).

Assemble the appropriate sieves in a nest in descending order of size and fit the receiver. Transfer the sample to the top sieve, fit the lid and shake the nest of sieves for 5 min.

At the end of this period, clean each sieve in turn, starting with the coarsest mesh sieve by inverting it over a paper or tray, tapping the side and carefully brushing the uppermost surface of the sieve. Add any loose particles dislodged during brushing to the oversize on the tray or on the paper. Replace the sieve in the nest and transfer the material in the tray or on the paper back to the sieve.

Repeat the process of sieving for 5 min, transfer the oversize from each sieve to a container of known mass, adding any material dislodged by brushing, and determine the mass of each fraction.

**NOTES**

- 1 See ISO/R 579, *Determination of total moisture in coke.*
- 2 Mechanical shaking may be used provided that its action does not break the coke and that the results are known to be not biased with respect to the results obtained by hand shaking.
- 3 Where a mechanical sieving machine is not available, the procedure specified in ISO/R 1953, *Size analysis of coal*, shall be adopted.
- 4 The loading of sieves will be dealt with in ISO ....., *Test sieving* (at present at the stage of draft proposal).

**6 CALCULATION AND REPORTING OF RESULTS**

Record the mass of each size fraction. Calculate the cumulative mass on each sieve, starting with the sieve of largest aperture.

The apparent loss, i.e. the difference between the total mass of the sample before and after the size analysis, shall be recorded. Loss in mass means loss of sample, and should not occur. If the loss is not more than 1 % of the original sample mass, it shall be added to the mass of the fraction of smallest size. If the loss is greater than 1 % of the original mass, the results of the size analysis shall be rejected.

Convert each cumulative mass to a percentage of the total mass (see Note).

The results shall be reported to the nearest 0,01 kg and 0,1 %.

NOTE — Where the sample of coke has been sub-divided during the size analysis, the results obtained on the sub-samples must be multiplied by the ratio of the respective masses in order to relate these results to the original sample of coke.

**7 PRECISION**

|                       | Maximum acceptable differences between results obtained |      |                           |
|-----------------------|---|------|---------------------------|
|                       | in the same laboratory                                  |      | in different laboratories |
| Nominal top size (mm) | 20  | 10   | 5                         |
| Mean size (mm)        | 0,60  | 0,12 | 0,06                      |

(see 7.2)

**7.1 In the same laboratory**

The results of duplicate determinations of mean size (see Note after 7.2) carried out at different times in the same laboratory, by the same operator, with the same apparatus on samples obtained by taking alternate increments from the same consignment of coke, shall not differ by more than the above value.

## 7.2 In different laboratories

No tolerance is quoted for determinations carried out in different laboratories because the transport of a coke sample involves the risk of breakage and thus alteration of the size distribution.

NOTE -- For all methods of sieving, the mean size is calculated using the results of the size analysis of the coke. The mean size may be calculated in the following way :

|                        |          |          |          |              |          |          |          |
|------------------------|----------|----------|----------|--------------|----------|----------|----------|
| Sieve apertures        | <i>a</i> | <i>b</i> | <i>c</i> | <i>d</i> ... | <i>h</i> | <i>j</i> | <i>k</i> |
| Cumulative percentages | <i>A</i> | <i>B</i> | <i>C</i> | <i>D</i> ... | <i>H</i> | <i>J</i> | <i>K</i> |

the symbols being allocated so that  $A = 0\%$  and  $K = 100\%$  (i.e.  $k = 0$  mm)

$$\text{then mean size} = \frac{B(a - c) + C(b - d) + \dots + J(h - k) + 100j}{200}$$

This formula is greatly simplified when a sieve series of constant interval is used. It is, of course, essential that the sieve apertures all be either round or square; otherwise, the equivalent apertures must be used in the calculation.

Alternative methods of calculation or graphical methods may lead to slightly different results; therefore, when comparing test results from different samples it is important to adhere to the same method of calculation.

STANDARDSISO.COM : Click to view the full PDF of ISO 2325:1972

[STANDARDSISO.COM](https://standardsiso.com) : Click to view the full PDF of ISO 2325:1972