
**Thermoplastic hoses and hose
assemblies — Wire or synthetic yarn
reinforced single-pressure types for
hydraulic applications — Specification**

*Tuyaux et flexibles en matière thermoplastique — Types hydrauliques
à pression unique, avec armature de fils métalliques ou synthétiques
— Spécifications*

STANDARDSISO.COM : Click to view the full PDF of ISO 23297:2017



STANDARDSISO.COM : Click to view the full PDF of ISO 23297:2017



COPYRIGHT PROTECTED DOCUMENT

© ISO 2017, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

	Page
Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 Classification	2
4.1 Classes.....	2
4.2 Types.....	2
4.3 Grades.....	2
5 Materials and construction	3
5.1 Hoses.....	3
5.2 Hose assemblies.....	3
6 Dimensions and tolerances	3
6.1 Diameters.....	3
6.2 Lengths of supplied hoses and hose assemblies.....	4
6.3 Outer cover thickness.....	4
6.4 Concentricity.....	4
7 Physical properties	5
7.1 Fluid and UV resistance of thermoplastic compounds.....	5
7.1.1 Fluid resistance.....	5
7.1.2 UV resistance.....	5
7.2 Performance requirements.....	5
7.2.1 Hydrostatic requirements.....	5
7.2.2 Change in length.....	6
7.2.3 Minimum bend radius.....	6
7.2.4 Resistance to impulse.....	6
7.2.5 Leakage of hose assemblies.....	7
7.2.6 Cold flexibility.....	7
7.2.7 Adhesion between components (applicable to type 1 hoses only).....	7
7.2.8 Vacuum resistance.....	7
7.2.9 Ozone resistance.....	8
8 Frequency of testing	8
9 Marking	8
9.1 Hoses.....	8
9.2 Hose assemblies.....	8
10 Packaging and storage	9
11 Test report	9
Annex A (normative) Type tests and routine tests	10
Annex B (informative) Production acceptance tests	11
Annex C (informative) Recommendations for lengths of supplied hoses and hose assemblies	12
Bibliography	13

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 1, *Rubber and plastics hoses and hose assemblies*.

This second edition cancels and replaces the first edition (ISO 23297:2008), of which it constitutes a minor revision. The changes compared to previous edition are as follows:

- the title of the document has been changed to refer to thermoplastic hoses and hose assemblies instead of thermoplastics hoses and hose assemblies, in keeping with the text of the document;
- the introduction has been amended to explain the current status of a new ISO standard for abrasion tests on rubber and plastic hose covers;
- Clause 2 has been updated: ISO 1746 and ISO 4672 have been cancelled and replaced by ISO 10619-1 and 10619-2, respectively; ISO 7326:2006 has been replaced by ISO 7326:2016;
- 7.2.3 and 7.2.6 have been amended to refer to the bend test standards ISO 10619-1 and ISO 10619-2;
- 7.2.9 has been amended to refer to ISO 7326:2016;
- 9.1 has been revised to stipulate that the hose manufacturer shall use the latest edition of this document, otherwise the year of publication shall be included in the marking;
- the bibliography has been amended by the deletion of ISO 6945 (standard withdrawn).

Introduction

The abrasion resistance tests for compound and plastic hose covers are not included in this document. ISO 20444¹⁾ is intended to specify abrasion tests on rubber and plastic hose covers.

STANDARDSISO.COM : Click to view the full PDF of ISO 23297:2017

1) Under preparation, to replace ISO 6945 (withdrawn).

[STANDARDSISO.COM](https://standardsiso.com) : Click to view the full PDF of ISO 23297:2017

Thermoplastic hoses and hose assemblies — Wire or synthetic yarn reinforced single-pressure types for hydraulic applications — Specification

1 Scope

This document specifies requirements for eight classes and two types (construction with adhesive bond between layers and construction without adhesive bond between layers) of wire or synthetic yarn reinforced hydraulic hoses and hose assemblies of nominal size from 3,2 to 31,5. Each class has a single maximum working pressure for all sizes. Such hoses are suitable for use with hydraulic fluids HH, HL, HM, HR, and HV as defined in ISO 6743-4 at temperatures ranging from $-40\text{ }^{\circ}\text{C}$ to $+100\text{ }^{\circ}\text{C}$ for grades A and B and $-40\text{ }^{\circ}\text{C}$ to $+120\text{ }^{\circ}\text{C}$ for grades C and D.

This document does not include requirements for end fittings. It is limited to the performance of hoses and hose assemblies. The hose assembly maximum working pressure is governed by the lowest maximum working pressure of the components.

NOTE It is the responsibility of the user, in consultation with the hose manufacturer, to establish compatibility of the hose with the fluid to be used.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1402, *Rubber and plastics hoses and hose assemblies — Hydrostatic testing*

ISO 1817, *Rubber, vulcanized or thermoplastic — Determination of the effect of liquids*

ISO 4671, *Rubber and plastics hoses and hose assemblies — Methods of measurement of the dimensions of hoses and the lengths of hose assemblies*

ISO 4892 (all parts), *Plastics — Methods of exposure to laboratory light sources*

ISO 6803, *Rubber or plastics hoses and hose assemblies — Hydraulic-pressure impulse test without flexing*

ISO 7233, *Rubber and plastics hoses and hose assemblies — Determination of resistance to vacuum*

ISO 7326:2016, *Rubber and plastics hoses — Assessment of ozone resistance under static conditions*

ISO 8033, *Rubber and plastics hoses — Determination of adhesion between components*

ISO 8330, *Rubber and plastics hoses and hose assemblies — Vocabulary*

ISO 8331, *Rubber and plastics hoses and hose assemblies — Guidelines for selection, storage, use and maintenance*

ISO 10619-1, *Rubber and plastics hoses and tubing — Measurement of flexibility and stiffness — Part 1: Bending tests at ambient temperature*

ISO 10619-2:2017, *Rubber and plastic hoses and tubing — Measurement of flexibility and stiffness — Part 2: Bending tests at sub-ambient temperatures*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 8330 apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <https://www.iso.org/obp>

4 Classification

4.1 Classes

Eight classes of hose are specified, distinguished by their maximum working pressure, as shown in Table 1. Each class may be manufactured in up to 10 nominal sizes.

Table 1 — Classes, nominal size and maximum working pressure

Class	35	70	140	210	280	350	420	560
MWPa (bar)	35	70	140	210	280	350	420	560
MWPa (MPa)	3,5	7	14	21	28	35	42	56
Nominal size								
3,2	X	X	X	X	X	X	X	X
5	X	X	X	X	X	X	X	X
6,3	X	X	X	X	X	X	X	X
8	X	X	X	X	X	X	X	X
10	X	X	X	X	X	X	X	X
12,5	X	X	X	X	X	X	X	X
16	X	X	X	X	X	X	X	X
19	X	X	X	X	X	X	X	X
25	X	X	X	X	X	X	X	X
31,5	X	X	X	X	X	X	X	X
X = applicable.								
^a Maximum working pressure.								

4.2 Types

Two types are specified according to their construction: type 1 with adhesion between the layers; and type 2 without adhesion between the layers. In type 1 hoses, the lining and cover are adhesively bonded (i.e. only separable by force) to the reinforcement; in type 2 hoses, these layers are not attached to the reinforcement.

4.3 Grades

Hoses are classified according to their resistance to impulse into four grades: A, B, C and D, as shown in Table 2.

Table 2 — Grades

Grade	Resistance to impulse		
	Temperature °C	Impulse pressure (% of MWP ^a)	Minimum number of cycles
A	100	133 %	200 000
B	100	133 %	500 000
C	120	133 % (classes 35, 70, 140, 210)	500 000
		120 % (classes 280, 350, 420, 560)	
D	120	133 % (classes 35, 70, 140, 210)	1 000 000
		120 % (classes 280, 350, 420, 560)	

^a Maximum working pressure.

The maximum working pressure by class is shown in Table 3.

Table 3 — Maximum working pressure

Class	35	70	140	210	280	350	420	560
MWP ^a (bar)	35	70	140	210	280	350	420	560
MWP ^a (MPa)	3,5	7	14	21	28	35	42	56
Grade								
A	X	X	X	X	X	X	X	X
B	X	X	X	X	X	X	X	X
C	X	X	X	X	X	X	X	X
D	X	X	X	X	X	X	X	X

X = applicable.

^a Maximum working pressure.

5 Materials and construction

5.1 Hoses

Hoses shall consist of a hydraulic-fluid-resistant thermoplastic lining, one or multiple layers of steel wire or synthetic yarn and an oil- and weather-resistant thermoplastic cover. Other protective materials over the thermoplastic cover are allowed for improved abrasion or other resistance.

5.2 Hose assemblies

Hose assemblies shall only be manufactured with those hose fittings which conform to the requirements of 7.2.1, 7.2.4 and 7.2.5 of this document.

Follow the manufacturer's instructions for proper preparation and fabrication of hose assemblies.

6 Dimensions and tolerances

6.1 Diameters

When measured in accordance with ISO 4671, the diameters of the hoses shall conform to the values given in Table 4.

Table 4 — Diameters of hoses

Nominal size	Inside diameter (all classes) mm		Maximum outside diameter of hose mm							
	min.	max.	Class 35	Class 70	Class 140	Class 210	Class 280	Class 350	Class 420	Class 560
3,2	3,1	4,0	8	8	9	9,5	9,5	9,5	10,5	10,5
5	4,6	5,4	10	10	11	12	12	12	14	15
6,3	6,1	7,0	12	12	14	14	14	14	16	16
8	7,7	8,5	13	13	15,5	15,5 (16,6 ^a)	16	16	17	17
10	9,3	10,3	16	16	17,5	18,5	19	19	20	21
12,5	12,3	13,5	20	20	21	23	23	23	24	25
16	15,5	16,8	23	23	25	27 (28 a)	28	28	28	29
19	18,6	19,8	27	28	29	32	32	33	33	34
25	25,0	26,4	34	36	36	39 (40,4 a)	39	40,5	40,5	43,5
31,5	31,4	33,0	45	45	46	48	49	50	50	51,5

^a These dimensions are allowable for textile yarn braided reinforcement only; for metal wire braided reinforcement of other classes and sizes, the standard dimensions apply.

6.2 Lengths of supplied hoses and hose assemblies

Recommendations for lengths of supplied hoses and hose assemblies are given in Annex C.

6.3 Outer cover thickness

When measured in accordance with ISO 4671, the outer cover thickness of the hoses shall conform to the values given in Table 5.

Table 5 — Outer cover thickness

Nominal size	Outer cover thickness mm	
	min.	max.
3,2	0,1	1,4
5	0,1	1,4
6,3	0,1	1,4
8	0,1	1,4
10	0,1	1,4
12,5	0,2	1,5
16	0,2	1,5
19	0,2	1,5
25	0,2	1,5
31,5	0,4	1,7

6.4 Concentricity

When measured in accordance with ISO 4671, the concentricity of the hoses shall conform to the values given in Table 6.

Table 6 — Concentricity of hoses

Nominal size	Maximum variation in wall thickness		
	Between internal diameter and outside diameter	Between internal diameter and outside diameter of the tubing	
	mm		
	Wire	Textile	
3,2, 5 and 6,3	0,5	0,8	0,2
over 6,3 and up to and including 19	0,8	1,0	0,5
25	1,1	1,3	0,6
31,5	1,2	1,3	0,7

7 Physical properties

7.1 Fluid and UV resistance of thermoplastic compounds

7.1.1 Fluid resistance

7.1.1.1 Test pieces

The fluid resistance tests shall be carried out on extruded sheets of lining and cover compound having minimum thickness 2 mm and an extruded state equivalent to that of the hose.

7.1.1.2 Oil resistance

For grades A and B, when tested in accordance with ISO 1817 by immersion in oil No. 3 for 168 h at a temperature of 100 °C, the percentage change in volume of the lining, ΔV_{100} , shall be between -10 % and +35 %.

For grades C and D, when tested in accordance with ISO 1817 by immersion in oil No. 3 for 168 h at a temperature of 120 °C, the percentage change in volume of the lining, ΔV_{100} , shall be between -10 % and +35 %.

For all grades, when tested in accordance with ISO 1817 by immersion in oil No. 3 for 168 h at a temperature of 70 °C, the percentage change in volume of the cover, ΔV_{100} , shall be between -10 % and +35 %.

7.1.2 UV resistance

When tested in accordance with ISO 4892 (e.g. accelerated in a Xenotester capable of generating wavelengths 300 nm to 800 nm and 45 W/m², exposure time 400 h), the samples shall show no crack or other defects at visual examination (without magnification) when bent over 180° at the smallest possible radius.

7.2 Performance requirements

7.2.1 Hydrostatic requirements

When tested in accordance with ISO 1402, the maximum working pressure, the proof pressure and the minimum burst pressure of the hoses and hose assemblies shall conform to the values given in Table 7.

Table 7 — Maximum working pressure, proof pressure and minimum burst pressure

Class	Maximum working pressure		Proof pressure		Minimum burst pressure	
	bar	MPa	bar	MPa	bar	MPa
35	35	3,5	70	7,0	140	14,0
70	70	7,0	140	14,0	280	28,0
140	140	14,0	280	28,0	560	56,0
210	210	21,0	420	42,0	840	84,0
280	280	28,0	560	56,0	1 120	112,0
350	350	35,0	700	70,0	1 400	140,0
420	420	42,0	840	84,0	1 680	168,0
560	560	56,0	1 120	112,0	2 240	224,0

7.2.2 Change in length

When tested in accordance with ISO 1402, the change in length of hose at the maximum working pressure shall not exceed ± 3 %.

7.2.3 Minimum bend radius

When determined in accordance with ISO 10619-1, the minimum bend radius shall conform to the values given in Table 8.

Use test pieces having a length at least four times the minimum bend radius. Measure the hose outside diameter with a calliper in the straight lay position before bending the hose. Bend the hose through 180° to the minimum bend radius and measure the flatness with the calliper.

When bent to the minimum bend radius given in Table 8, measured on the inside of the bend, the flatness shall not exceed 10 % of the original outside diameter.

7.2.4 Resistance to impulse

7.2.4.1 The resistance to impulse shall be determined in accordance with ISO 6803. The test fluid temperature shall be 100°C for grades A and B and 120°C for grades C and D.

7.2.4.2 For grade A, when tested at impulse pressure equal to 133 % of the maximum working pressure, the hose shall withstand a minimum of 200 000 impulse cycles.

For grade B, when tested at impulse pressure equal to 133 % of the maximum working pressure, the hose shall withstand a minimum of 500 000 impulse cycles.

For grade C, when tested at impulse pressure equal to 133 % of the maximum working pressure (classes 35, 70, 140 and 210) or 120 % of the maximum working pressure (classes 280, 350, 420 and 560), the hose shall withstand a minimum of 500 000 impulse cycles.

For grade D, when tested at impulse pressure equal to 133 % of the maximum working pressure (classes 35, 70, 140 and 210) or 120 % of the maximum working pressure (classes 280, 350, 420 and 560), the hose shall withstand a minimum of 1 000 000 impulse cycles.

After the impulse test, carry out a leakage test at maximum working pressure for 5 min. There shall be no leakage or other malfunction.

7.2.4.3 There shall be no leakage or other malfunction before reaching the specified number of cycles.

7.2.4.4 This test shall be considered a destructive test and the test piece shall be destroyed.

7.2.5 Leakage of hose assemblies

When tested in accordance with ISO 1402, there shall be no leakage or evidence of failure. This test shall be considered a destructive test and the test piece shall be destroyed after the test.

Table 8 — Minimum bend radius

Nominal size	Minimum bend radius							
	mm							
	Class 35	Class 70	Class 140	Class 210	Class 280	Class 350	Class 420	Class 560
3,2	25	25	25	25	30	45	45	50
5	35	35	35	35	35	60	60	70
6,3	45	45	45	45	50	70	70	80
8	50	50	50	50	50	80	80	110
10	60	60	75	75	75	110	110	150
12,5	75	75	90	90	90	150	150	175
16	110	110	125	125	125	175	175	225
19	170	170	185	185	185	200	225	250
25	230	230	250	250	250	260	275	310
31,5	280	300	320	320	320	340	375	440

7.2.6 Cold flexibility

When tested in accordance with method B of ISO 10619-2:2017 at a temperature of $-40\text{ }^{\circ}\text{C}$, there shall be no cracking of the lining or cover. The test piece shall not leak or crack when subjected to a proof pressure test in accordance with ISO 1402 after regaining ambient temperature.

7.2.7 Adhesion between components (applicable to type 1 hoses only)

The requirement for adhesion between components depends on the hose construction (material of reinforcement) and the application of the hose (there are applications where adhesion between components is not necessary and reinforcement materials where achieving adhesion between lining and reinforcement is not possible). The service conditions determine which type of construction — type 1 (bonded) or type 2 (non-bonded) — is chosen for the application of the hose assembly.

When tested in accordance with ISO 8033, the adhesion between lining and reinforcement shall not be less than $0,8\text{ N/mm}$ (for hoses of type 1 construction, e.g. when vacuum in the bore may occur during service) and the adhesion between cover and reinforcement shall also be not less than $0,8\text{ N/mm}$.

7.2.8 Vacuum resistance

When tested in accordance with ISO 7233, hoses and hose assemblies shall conform to the values given in Table 9. This requirement is applied to all classes and bore diameters of type 1 hoses only.

Table 9 — Degree of vacuum

Nominal size	Negative gauge pressure (classes 35 to 520 inclusive) bar ^a
3,2 to 31,5 inclusive	-0,8
^a 0,1 bar = 10 kPa.	

7.2.9 Ozone resistance

When tested in accordance with method 1 or 2 of ISO 7326:2016, no cracking or deterioration of the cover shall be visible under $\times 2$ magnification.

8 Frequency of testing

Type testing and routine testing shall be as specified in Annex A.

Type tests are those tests required to confirm that a particular hose meets all the requirements of this document. Type testing shall be repeated at a minimum every five years or whenever a change in the method of manufacture or materials occurs. Type testing shall be performed on all sizes, classes, types and grades of each design in the manufacturer's range.

Routine tests are those tests required to be carried out on each length of finished hose prior to dispatch.

Production acceptance tests are those tests, specified in Annex B, which should preferably be carried out to control the quality of manufacture. The frequencies specified in Annex B are given for guidance only.

9 Marking

9.1 Hoses

Hoses shall be marked with at least the following information, and the marking shall be repeated every 760 mm or less:

- manufacturer's name or identification, e.g. XXX;
- the number of this document, i.e. ISO 23297;
- the type and grade, e.g. 1A;
- the nominal bore size, e.g. 16;
- maximum working pressure in bar, e.g. 280 bar;
- the quarter and last two digits of year of manufacture, e.g. 3Q17

EXAMPLE XXX/ISO 23297/1A/16/280bar/3Q17

For 9.1 b), the hose manufacturer shall use the latest edition of this document, otherwise the year of publication shall be included in the marking.

9.2 Hose assemblies

The hose assemblies shall be permanently marked, preferably on the hose fittings or on a metal ring adjacent to the fitting, with at least the following information:

- the manufacturer's name or identification, e.g. XXX;
- the part number or identification number (if applicable), e.g. YYY;

- c) the maximum working pressure²⁾ of the assemblies, in bar, e.g. 16;
- d) last two digits of month and year of assembly, e.g. 09/17.

EXAMPLE XXX/YYYY/16/09/17

10 Packaging and storage

Packaging and storage shall be undertaken in accordance with ISO 8331. Recommendations on lengths of supplied hoses and hose assemblies are given in Annex C.

11 Test report

When requested by the purchaser, the manufacturer or supplier shall provide a test report with each length or batch (specify size of batch) of hoses or hose assemblies supplied to the purchaser, identifying each hose length or assembly positively, including identification as marked on the hose, the lot number and the client's order number (serial numbers when applicable).

STANDARDSISO.COM : Click to view the full PDF of ISO 23297:2017

2) The maximum working pressure (MWP) of the assembly is the lowest maximum working pressure of any of its components. The MWP of a hose assembly comprising ISO hose and ISO hose fittings shall not exceed the lower of the respective ISO maximum working pressure values.

Annex A (normative)

Type tests and routine tests

Table A.1 gives the tests to be carried out for type testing and routine testing as defined in Clause 8.

Table A.1 — Frequency of testing

Property	Type testing	Routine testing
Compound tests		
Oil resistance test for cover compound material	X	N/A
Oil resistance test for lining compound/material	X	N/A
UV resistance test for cover compound/material	X	N/A
Hose tests		
Visual examination (inside and outside)	X	X
Measurement of inside diameter	X	X
Measurement of outside diameter	X	X
Measurement of outer cover thickness	X	X ^b
Measurement of concentricity	X	X ^b
Minimum bend radius test	X	X ^b
Proof test	X	X
Burst test ^a	X	X ^b
Change in length test	X	X ^b
Impulse test	X	N/A
Leakage test ^a	X	X ^b
Cold bend test	X	N/A
Adhesion	X	X ^b
Vacuum test (type 1 only)	X	N/A
Ozone resistance test of cover	X	N/A
UV resistance test for cover	X	N/A
UV resistance test of hose sample	X	N/A
X = test required.		
N/A = test not applicable.		
^a Burst test and leakage test can be performed on a suitable length of sample fixed in a test rig.		
^b Routine tests to be carried out on a sample of every 3 000 m produced or less (in case of shorter production runs).		