
**Woven polypropylene sacks for bulk
packaging of foodstuffs**

*Sacs tissés en polypropylène pour l'emballage en vrac de denrées
alimentaires*

STANDARDSISO.COM : Click to view the full PDF of ISO 23560:2015



STANDARDSISO.COM : Click to view the full PDF of ISO 23560:2015



COPYRIGHT PROTECTED DOCUMENT

© ISO 2015

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

	Page
Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Manufacture	1
4.1 Raw materials.....	1
4.2 Fabric.....	2
5 Sack	2
6 Liner	3
7 Requirements	3
7.1 Conditioning and test conditions.....	3
7.2 Construction parameters.....	3
7.3 UV resistance.....	3
7.4 Mass of the bale.....	3
7.5 Drop testing.....	3
8 Food compatibility	3
9 Marking and packaging	3
9.1 Marking on sacks.....	3
9.2 Packaging.....	4
9.3 Marking on bales.....	4
10 Sampling and criteria for conformity	4
10.1 Sampling.....	4
10.2 Criteria for conformity.....	4
Annex A (normative) Method of calculation of the mass of a sack	6
Annex B (normative) Breaking strength of fabric and bottom seam	7
Annex C (normative) Drop testing	8
Bibliography	9

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

The committee responsible for this document is ISO/TC 61, *Plastics*, Subcommittee SC 11, *Products*.

This second edition cancels and replaces the first edition (ISO 23560:2008), which has been technically revised.

Introduction

With the removal of trade barriers between nations, there is a need for an International Standard for the packaging, transportation, and storage of foodstuffs such as cereals. Polypropylene (PP) sacks made from woven fabric are an ideal choice for the packaging of foodstuffs. Such sacks are produced from food-grade polypropylene and ensure the mechanical strength needed for storage and transportation.

This International Standard describes the construction of the sacks, their dimensions, and test methods suitable for ensuring the long-term storage and transportation of foodstuffs in the sacks.

STANDARDSISO.COM : Click to view the full PDF of ISO 23560:2015

STANDARDSISO.COM : Click to view the full PDF of ISO 23560:2015

Woven polypropylene sacks for bulk packaging of foodstuffs

1 Scope

This International Standard specifies the general characteristics, requirements, and methods of test for woven polypropylene (PP) sacks. It is applicable to woven PP sacks, having a capacity of 50 kg or 25 kg, intended for the transport and storage of foodstuffs, such as cereals, sugar, and pulses.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 291, *Plastics — Standard atmospheres for conditioning and testing*

ISO 3451-1:2008, *Plastics — Determination of ash — Part 1: General methods*

ISO 4892-3:2013, *Plastics — Methods of exposure to laboratory light sources — Part 3: Fluorescent UV lamps*

ISO 4915, *Textiles — Stitch types — Classification and terminology*

ISO 6591-2, *Packaging — Sacks — Description and method of measurement — Part 2: Empty sacks made from thermoplastic flexible film*

ISO 13934-1, *Textiles — Tensile properties of fabrics — Part 1: Determination of maximum force and elongation at maximum force using the strip method*

ISO 13935-1, *Textiles — Seam tensile properties of fabrics and made-up textile articles — Part 1: Determination of maximum force to seam rupture using the strip method*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

woven PP sack

container made of woven polypropylene (PP) fabric, closed at one end, in certain cases combined with other flexible materials used, for instance, for the liner to provide the properties required for filling, storage, and distribution of the packaged commodity

4 Manufacture

4.1 Raw materials

A suitable grade of PP conforming to food contact requirements shall be utilized in the manufacture of the PP tape/fabric used in the sacks.

4.2 Fabric

The fabric used in the manufacture of woven PP sacks shall be woven as a tube on a circular loom from PP tapes having a width of $(2,5 \pm 1)$ mm. The tapes shall be woven sufficiently tight so that the packaged foodstuff does not leak out of the sack. The construction of the weave shall be sufficiently rough to ensure that filled sacks do not slip from a stack of sacks.

The required construction parameters of sacks are given in [Table 1](#).

Table 1 — Required construction parameters of fabric and sacks

Parameter		Requirement		Test method
		Type 1	Type 2	
Capacity (kg)		50	25	—
Dimensions (cm)	Inside length	100^{+2}_0	65^{+2}_0	ISO 6591-2
	Inside width	57^0_{-1}	48^0_{-1}	
Mass of sack (g)		135^{+9}_{-4}	67^{+4}_{-3}	See Annex A
Average breaking strength of fabric (N)	Lengthwise	≥ 918	≥ 816	See Annex B
	Widthwise	≥ 918	≥ 816	
Elongation at break of fabric (%)	Lengthwise	(20 ± 5)	(20 ± 5)	See Annex B
	Widthwise	(20 ± 5)	(20 ± 5)	
Average breaking strength of bottom seam (N)		≥ 377	≥ 337	See Annex B
Ash content (for UV stabilized fabric)		3 % max	3 % max	ISO 3451-1:2008, Method A, at $600 \text{ }^\circ\text{C} \pm 25 \text{ }^\circ\text{C}$
NOTE 1 The dimensions specified provide the optimum free space of at least 20 % of the length above the surface of the contents.				
NOTE 2 The masses given for the sacks are based on typical ones for fabric weighing 106 g/m^2 for type 1 sacks and 96 g/m^2 for type 2 sacks.				
NOTE 3 The average breaking strength of the fabric and the average breaking strength of the bottom seam are calculated with respect to a specimen width of 50 mm.				

Woven PP sacks of the dimensions specified in [Table 1](#) are suitable for the packaging of foodstuffs such as wheat, rice, pulses, millet, and other similar grains. Other sack dimensions are allowed by agreement between the purchaser and seller. The mass of such sacks shall be calculated by the method given in [Annex A](#).

5 Sack

5.1 The sack can be flat or gusseted.

5.2 The bottom seam shall be stitched with two rows of chain stitches in accordance with ISO 4915. The two rows of stitches shall be separated from each other by at least 4 mm and the outer stitch shall be at least 7 mm from the outer edge of the sack. The stitching shall be done through a single or double fold so that the stitches pass through a minimum of four layers of the fabric, made in such a way that the seam width is at least 25 mm. The number of stitches per unit length shall be (14 ± 2) stitches/dm. These requirements shall be verified by visual inspection.

5.3 The material used for stitching shall be polypropylene tape or any other thread suitable for the purpose. The stitching shall be uniform with no loose thread or knots. These requirements shall be verified by visual inspection.

5.4 The closure of the filled sack shall be designed to prevent leakage of the contents during transport and handling.

6 Liner

If required by the buyer, the unlaminated sacks shall be provided with a loose liner made of a suitable polyolefin film conforming to the requirements for food contact. The width of the liner shall be 10 % more than the width of the sack. The bottom seam of the liner shall be at least 25 mm from its bottom edge. The liner shall be free from pinholes, patches, tears, blisters, and other visible defects.

7 Requirements

7.1 Conditioning and test conditions

The atmospheres for conditioning and testing shall be as specified in ISO 291.

7.2 Construction parameters

The sacks shall conform to the requirements specified in [Table 1](#), within the limits specified in [10.2](#).

7.3 UV resistance

Sacks made of UV-stabilized fabric shall retain at least 50 % of their original breaking strength when tested (see [Annex B](#)) after exposure to UV radiation and weathering for 144 h in accordance with the procedure given in ISO 4892-3:2013, Table 4, method A, cycle No. 1.

7.4 Mass of the bale

The mass of a bale of sacks (excluding packing material) shall be within ± 3 % of the mass calculated by multiplying the number of sacks by the mass specified in [Table 1](#) for one sack.

7.5 Drop testing

When tested in accordance with [Annex C](#), sacks shall meet the requirements specified in that annex.

8 Food compatibility

When used for foodstuffs, as will normally be the case, the sacks shall meet the legal requirements for food contact of the country where they are to be used.

9 Marking and packaging

9.1 Marking on sacks

The identification mark of the manufacturer, along with any information required by the buyer, shall be printed on the sacks, using ink or another suitable method that will ensure legibility during use.

9.2 Packaging

The sacks shall be packed to form a circular bale, using a layer of woven PP fabric for wrapping, and suitably secured. Each bale shall contain 500 sacks or a multiple thereof.

9.3 Marking on bales

The bales shall be marked with the following information:

- a) the name of the manufacturer;
- b) the type of sack and the sack size;
- c) the gross mass of the bale;
- d) the net mass of the bale;
- e) the month and year of manufacture;
- f) any other information required by the buyer.

10 Sampling and criteria for conformity

10.1 Sampling

10.1.1 All the sacks of the same construction in a consignment shall be grouped together to constitute a lot.

10.1.2 The conformity of the lot to the requirements of this International Standard shall be determined on the basis of tests carried out on samples randomly selected from the lot.

10.1.3 The requirements for sampling for the various tests are specified in [Table 2](#).

Table 2 — Sample size and criteria for conformity

Number of sacks in lot	Number of bales to be sampled	Sample size for visual inspection and measurement of dimensions and mass	Sample size for measurement of breaking strength and elongation at break of fabric, breaking strength after exposure to UV radiation, breaking strength of seam, and ash content
Up to 12 500	3	13	8
12 501 to 25 000	5	20	8
25 001 to 50 000	8	32	13
50 001 and above	12	50	20

10.2 Criteria for conformity

The lot shall be considered as conforming to the requirements of this International Standard if the following conditions are satisfied:

- a) the number of sacks found defective in the case of visual inspection and measurement of dimensions shall be no more than 10 % of the sample size specified in [Table 2](#);
- b) none of the sacks shall have a mass which is more than 3 % below the lower limit specified in [Table 1](#);
- c) none of the bales of 500 sacks shall have a mass which is more than 3 % below the calculated mass of the bale;

- d) the average breaking strength of the fabric in both the lengthwise and width wise directions shall not be less than the values specified in [Table 1](#), and none of the individual values shall be more than 10 % below the value specified in [Table 1](#);
- e) 10 % of the sacks tested can have a bottom seam strength down to 323 N (33 kgf) in the case of 50 kg sacks and 294 N (30 kgf) in the case of 25 kg sacks, provided the average seam strength of all the sacks tested is ≥ 377 N (38 kgf) in the case of 50 kg sacks and ≥ 337 N (34 kgf) in the case of 25 kg sacks;
- f) no sack shall exhibit an elongation outside the range specified in [Table 1](#);
- g) none of the sacks tested after exposure to UV radiation and weathering shall have a breaking strength less than 50 % of the original breaking strength;
- h) none of the UV stabilized sack sample shall have ash content more than 3 % as given in [Table 1](#).

STANDARDSISO.COM : Click to view the full PDF of ISO 23560:2015

Annex A (normative)

Method of calculation of the mass of a sack

A.1 The total mass of a sack is made up of a) the mass of the fabric and b) the mass of the seam stitching tape or thread.

A.2 Calculate the mass of the sack using the relevant formulae given below.

a) Mass of tubular fabric (single-fold stitching):

$$m_f = (L + 40) \times 2W \times \rho_A \times 10^{-6} \quad (\text{A.1})$$

Mass of tubular fabric (double-fold stitching):

$$m_f = (L + 65) \times 2W \times \rho_A \times 10^{-6} \quad (\text{A.2})$$

b) Mass of stitching tape or thread:

$$m_{st} = L_1 \times T \times 10^{-6} \quad (\text{A.3})$$

where

m_f is the mass of the fabric, in g;

L is the length of the sack, in mm;

W is the width of the sack, in mm;

ρ_A is the mass per unit area of the fabric, in g/m²;

m_{st} is the mass of the stitching tape or thread, in g;

L_1 is the approximate length of the stitching tape or thread, in mm;

T is the linear density of the stitching tape or thread, in tex.