
**Plastics — Polyethylene (PE) and
polypropylene (PP) thermoplastics
— Determination of metal content by
ICP-OES**

*Plastiques — Polyéthylène (PE) et polypropylène (PP) —
Détermination de la teneur en métal par ICP-OES*

STANDARDSISO.COM : Click to view the full PDF of ISO 24047:2021



STANDARDSISO.COM : Click to view the full PDF of ISO 24047:2021



COPYRIGHT PROTECTED DOCUMENT

© ISO 2021

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	1
5 Reagents	2
6 Apparatus	2
7 Sample preparation	2
7.1 Cleaning glassware	2
7.2 Preparation of working standard solutions	3
7.3 Preparation of test solution	3
8 Procedure	3
8.1 Instrument set up	3
8.2 Preparation of calibration curve	3
8.3 Sample analysis	4
9 Expression of results	5
10 Precision	5
11 Test report	5
Annex A (informative) Summary of precision data	6
Bibliography	9

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electro technical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 9, *Thermoplastic materials*.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

Metal elements in polyethylene (PE) and polypropylene (PP) can lead to increased ash content and can impact material mechanical properties. In addition, some elements are also environmentally hazardous. This document provides a method to determine the metal content in PE and PP and it can serve as a measure for additive monitoring, quality control and post-reactor studies.

In this document, inductively coupled plasma optical emission spectrometry (ICP-OES) is used to determine the concentrations of certain elements in PE and PP. The main advantages of ICP-OES over atomic absorption spectroscopy (AAS) include multi-element measurement capability, longer linear dynamic range and less condensed phase interferences.

STANDARDSISO.COM : Click to view the full PDF of ISO 24047:2021

STANDARDSISO.COM : Click to view the full PDF of ISO 24047:2021

Plastics — Polyethylene (PE) and polypropylene (PP) thermoplastics — Determination of metal content by ICP-OES

WARNING — Persons using this document should be familiar with normal laboratory practice, if applicable. This document does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices.

1 Scope

This document specifies a method for the determination of metal content in polyethylene (PE) and polypropylene (PP) by inductively coupled plasma optical emission spectrometry (ICP-OES).

This document is applicable to the determination of the content of magnesium (Mg), aluminium (Al), calcium (Ca), zinc (Zn), chromium (Cr), titanium (Ti), iron (Fe), antimony (Sb), copper (Cu), lead (Pb), cadmium (Cd), etc. This document is not applicable to the determination of mercury (Hg) due to its volatility.

This method is suitable for base polymers of PE, PP, PE/PP copolymer and their blends.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 648, *Laboratory glassware — Single-volume pipettes*

ISO 1042, *Laboratory glassware — One-mark volumetric flasks*

ISO 3451-1, *Plastics — Determination of ash — Part 1: General methods*

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

4 Principle

PE and PP samples are incinerated and digested. Metal elements within are dissolved in aqueous solution. The solution is converted into aerosol via a nebulizer, and then injected into argon supported ICP-OES. At high temperature, the plasma atomizes metal elements in the solution and gives characteristic optical emission. The intensity of emission is proportional to the concentration of element. The content of metal elements in the sample is then calculated by comparing the emission intensities of the sample with the calibration curve.

5 Reagents

Use only reagents of recognized analytical grade and only distilled water or water of equivalent purity.

5.1 Concentrated nitric acid, density 1,42 g/ml.

WARNING — Highly corrosive. Handle with suitable skin and eye protection in a fume hood.

5.2 Metal element standard solutions, 1 000 mg/l of Mg, Al, Ca, Zn, Cr, Ti, Fe, Sb, Cu, Pb and Cd for each individual standard solution, or multi-element standard solution containing 100 mg/l Mg, Al, Ca, Zn, Cr, Ti, Fe, Sb, Cu, Pb and Cd.

5.3 Cleaning agent, for example a volume fraction of 10 % of nitric acid solution.

6 Apparatus

Usual laboratory apparatus and glassware and, in particular, the following.

6.1 Inductively coupled plasma optical emission spectrometer, atomic emission wavelength measurement range: 160 nm to 760 nm.

6.2 Analytical balance, accurate to 0,1 mg.

6.3 Beaker, quartz, 250 ml.

6.4 Watch glass, quartz.

6.5 Hot plate, or other appropriate heat source, Working temperature up to (500 ± 25) °C.

6.6 Muffle furnace, capable of being maintained at (750 ± 50) °C.

6.7 Pipette, glass, of suitable capacity ISO 648 class A.

6.8 Measuring cylinder, glass, 5 ml and 10 ml.

6.9 Volumetric flask, glass, 25 ml and 100 ml, ISO 1042 class A.

6.10 Fume hood, or other suitable means of ventilation.

6.11 Desiccator.

7 Sample preparation

WARNING — It is necessary that sample preparation procedure shall be carried out in a well-ventilated fume hood.

7.1 Cleaning glassware

Clean all glassware using cleaning agent (5.3).

7.2 Preparation of working standard solutions

7.2.1 Prepare a volume fraction of 3 % to 5 % of nitric acid solution from concentrated nitric acid (5.1) used as blank solution.

7.2.2 Prepare a series of five (5) working standard solutions from metal element standard solutions (5.2). The final concentrations of each element of Mg, Al, Ca, Zn, Cr, Ti, Fe, Sb, Cu, Pb and Cd in the working standard solutions are 0,50 mg/l, 1,00 mg/l, 5,00 mg/l, 10,00 mg/l and 20,00 mg/l. Concentrated nitric acid (5.1) shall be added during preparation, so that the volume fraction of nitric acid in the working standard solutions are 3 % to 5 %.

NOTE Commercially available standard solution can be used as well.

7.3 Preparation of test solution

7.3.1 Weigh 25 g (accurate to 0,1 mg) of the test sample into a beaker (6.3). The amount of test sample shall not reach the half volume of the beaker.

NOTE Adjustment of sample mass can be applied according to the metal content.

7.3.2 Heat the beaker with sample on a hot plate (6.5) or other suitable heating devices. Adjust the heating power so that the sample is burnt slowly until the sample is well charred.

7.3.3 Remove the beaker from its heating device and cover with a watch glass (6.4). Introduce the beaker (6.3) into a muffle furnace (6.6) pre-heated to (750 ± 50) °C, which is chosen from ISO 3451-1. Calcine the sample for 3 h.

NOTE Depending on the content of metal elements in the sample, alternative methods of sample digestion such as pressure, microwave or wet acid digestion can be taken into account, too.

7.3.4 Remove the beaker (6.3) with the watch glass (6.4) from the muffle furnace (6.6) and allow it to cool in the desiccator (6.11).

7.3.5 Gently add 5 ml of concentrated nitric acid (5.1) and 5 ml of water to the beaker (6.3) and heat it on the hot plate (6.5) to dissolve the inorganics. When the solution is condensed to about 1,00 ml, take the beaker off the plate and cool it to room temperature.

7.3.6 Transfer the solution to a 25 ml volumetric flask (6.9), wash the residue twice by water and top up to final volume with water.

NOTE Turbid solution can be left to settle overnight, or centrifuged to get clear supernatant.

8 Procedure

8.1 Instrument set up

Turn on the ICP-OES (6.1) and warm up to readiness. Set up the ICP-OES parameters and detection wavelength for each element. For recommended wavelengths, see Table 1. For other recommended instrumental parameters of the ICP-OES, see Table 2.

8.2 Preparation of calibration curve

Introduce the working standard solutions (7.2) into the ICP-OES, record the emission line intensity of the blank solution and for a series of 0,50 mg/l, 1,00 mg/l, 5,00 mg/l, 10,00 mg/l and 20,00 mg/l working standard solutions in the ICP-OES. Plot the emission line intensity against the concentration

of working standard solutions. Liner correlation coefficient of calibration curve should be not less than 0,995 for each element. Any deviation from the requirement needs re-calibration of the equipment with freshly prepared working standard solutions.

8.3 Sample analysis

Introduce the test solution and determine the concentration of each element. If the concentration of one or more elements is beyond the range of the working standard solutions, dilute the test solution with blank solution (7.2.1) accordingly.

Table 1 — Recommended wavelength for element determination

Element	Wavelength nm
Mg	279,553
Al	396,153
Ca	317,933
Zn	206,200
Cr	267,716
Ti	334,941
Fe	238.204
Sb	206.836
Cu	324.752
Pb	220.353
Cd	228.802

NOTE Users can choose other suitable wavelength for determination according to the instrument manufactures recommendations.

Table 2 — Recommended instrumental parameters

Power kW	Plasma gas flow rates l/min	Auxiliary gas flow rate l/min	Atomizer gas flow rate l/min	Pump rates ml/min
1,50 ± 0,01	16,0 ± 0,5	0,5 ± 0,1	0,80 ± 0,05	1,5

NOTE Users can choose other suitable parameters for determination according to the instrument manufactures recommendations.

9 Expression of results

The metal content of each element in sample is calculated by [Formula \(1\)](#):

$$w_X = \frac{C_X \times V}{m} \quad (1)$$

where

- w_X is the content of metal element X in sample, expressed in milligrams per kilogram (mg/kg);
- C_X is the concentration of metal element X in testing solution, calculated by the calibration curve, expressed in milligrams per liter (mg/l);
- X is the symbol of the element being tested;
- V is the test solution volume, expressed in millilitre (ml);
- m is the sample mass, expressed in grams (g).

The result shall be reported in 2 decimals.

10 Precision

Precision data have been determined by testing involving ten laboratories and thirteen different PE and PP samples. The results are summarized in [Annex A](#).

11 Test report

The test report shall include the following information:

- a) all information necessary for identification of the sample tested;
- b) a reference to this document, i.e. ISO 24047:2021;
- c) the results of the test, including the results of the individual determinations and their mean;
- d) any deviations from the procedure specified;
- e) any unusual features (anomalies) observed during the test;
- f) the date of the test.

Annex A (informative)

Summary of precision data

All the precision data have been calculated according to ISO 5725-2. The results of Mg, Al, Ca, Zn, Cr and Ti are given in [Table A.1](#) to [Table A.6](#), respectively. The precision of this test method on Fe, Sb, Cu, Pb, Cd are not listed because interlaboratory data are not available. In [Table A.1](#) to [Table A.6](#), No. is the serial number, sample is the sample name, p is the number of laboratories, m (mg/kg) is the general mean, S_r is the repeatability standard deviation, S_R is the reproducibility standard deviation, r (mg/kg) is the repeatability limit and R (mg/kg) is the reproducibility limit.

Table A.1 — Precision data for Mg

No.	Sample	p	m mg/kg	S_r	S_R	r mg/kg	R mg/kg
1	PE-1	8	4,23	0,131	0,178	0,37	0,50
2	PE-4	9	4,86	0,133	0,663	0,37	1,86
3	PE-2	9	4,92	0,112	0,391	0,31	1,09
4	PE-8	8	4,92	0,206	0,235	0,58	0,66
5	PE-3	8	5,42	0,149	0,645	0,42	1,81
6	PE-6	9	16,72	0,366	1,447	1,02	4,05
7	PP-2	7	4,78	0,105	0,275	0,29	0,77
8	PP-3	9	35,98	0,672	3,192	1,88	8,94
9	Ethylene-propylene copolymer	8	3,31	0,168	0,191	0,47	0,53

NOTE Mg content in other samples is lower than 0,50 mg/kg.

Table A.2 — Precision data for Al

No.	Sample	p	m mg/kg	S_r	S_R	r mg/kg	R mg/kg
1	PE-3	7	6,63	0,127	0,984	0,36	2,76
2	PE-1	10	11,43	0,667	1,031	1,87	2,89
3	PE-6	9	18,71	0,325	1,301	0,91	3,64
4	PE-4	8	22,35	1,056	2,124	2,96	5,95
5	PE-2	9	23,84	0,546	3,281	1,53	9,19
6	PP-1	10	32,35	1,359	2,629	3,81	7,36
7	PP-3	10	35,83	1,270	4,287	3,56	12,00
8	PP-2	9	49,19	1,006	3,711	2,82	10,39
9	PP-4	10	98,94	4,498	8,565	12,59	23,98
10	Ethylene-propylene copolymer	9	56,29	1,227	4,047	3,44	11,33

NOTE Al content in other samples is lower than 0,50 mg/kg.