

---

---

**Rubber, vulcanized or thermoplastic —  
Determination of density**

*Caoutchouc vulcanisé ou thermoplastique — Détermination de la  
masse volumique*

STANDARDSISO.COM : Click to view the full PDF of ISO 2781:2008



**PDF disclaimer**

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

STANDARDSISO.COM : Click to view the full PDF of ISO 2781:2008



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2008

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

**Contents**

Page

Foreword.....	iv
1 Scope .....	1
2 Normative references .....	1
3 Terms and definitions.....	1
4 Principle.....	2
5 Apparatus .....	2
6 Test piece .....	2
7 Time-interval between forming and testing .....	2
8 Conditioning of test pieces.....	2
9 Temperature of test .....	3
10 Procedure .....	3
10.1 Preparation of sample .....	3
10.2 Method A.....	3
10.3 Method B.....	4
11 Expression of results .....	4
11.1 Method A.....	4
11.2 Method B.....	5
12 Test report .....	5

STANDARDSISO.COM : Click to view the full PDF of ISO 2781:2008

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 2781 was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 2, *Testing and analysis*.

This fourth edition cancels and replaces the third edition (ISO 2781:1988), which has been technically revised. It also incorporates the Technical Corrigendum ISO 2781:1988/Cor.1:1996.

STANDARDSISO.COM : Click to view the full PDF of ISO 2781:2008

# Rubber, vulcanized or thermoplastic — Determination of density

**WARNING** — Persons using this International Standard should be familiar with normal laboratory practice. This standard does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices and to ensure compliance with any national regulatory conditions.

**CAUTION** — Certain procedures specified in this International Standard may involve the use or generation of substances, or the generation of waste, that could constitute a local environmental hazard. Reference should be made to appropriate documentation on safe handling and disposal after use.

## 1 Scope

This International Standard specifies two methods of test for the determination of the density of solid vulcanized and thermoplastic rubbers.

Such determinations are of importance in the control of the quality of a rubber compound and in the calculation of the mass of rubber required to produce a given volume of material.

This International Standard does not cover the determination of the relative density of rubber, which is the ratio of the mass of a given volume of rubber to the mass of an equal volume of pure water at a given temperature.

## 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 23529, *Rubber — General procedures for preparing and conditioning test pieces for physical test methods*

## 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

### 3.1

#### **density**

mass of unit volume of the rubber at a stated temperature

**NOTE** It is expressed in megagrams per cubic metre ( $\text{Mg/m}^3$ ).

## 4 Principle

Two methods, A and B, are given.

In method A, the mass of the test piece and the mass of water equal in volume to the volume of the test piece are determined using a balance equipped with a pan straddle. The apparent mass of the test piece when immersed in water is less than that in air by the mass of water displaced, the volume of water displaced being equal to that of the test piece.

Method B is intended to be used only when it is necessary to cut up the test piece into small pieces to eliminate air spaces, as in the case of narrow-bore tubing and electric-cable insulation. Measurements are made using a balance and a density bottle.

## 5 Apparatus

Ordinary laboratory apparatus and the following:

- 5.1 **Analytical balance**, accurate to  $\pm 1$  mg.
- 5.2 **Balance pan straddle**, of convenient size to support the beaker and permit determination of the mass of the test piece in water (for method A).
- 5.3 **Beaker**, 250 cm<sup>3</sup> capacity (or smaller if necessitated by the design of the balance) (for method A).
- 5.4 **Density bottle** (for method B).

## 6 Test piece

- 6.1 The test piece shall consist of a piece of the rubber with smooth surfaces, free from cracks and dust, and having a mass of at least 2,5 g. For method B, the shape of the test piece shall be such as to permit cutting into suitable pieces (see 10.3).
- 6.2 A minimum of two test pieces shall be made.

## 7 Time-interval between forming and testing

- 7.1 Unless otherwise specified for technical reasons, the following requirements for time-intervals shall be observed.
- 7.2 For all test purposes, the minimum time between forming and testing shall be 16 h.
- 7.3 For non-product tests, the maximum time between forming and testing shall be 4 weeks and, for evaluations intended to be comparable, the tests, as far as possible, shall be carried out after the same time-interval.
- 7.4 For product tests, whenever possible, the time between forming and testing shall not exceed 3 months. In other cases, tests shall be made within 2 months of the date of receipt by the customer of the product.

## 8 Conditioning of test pieces

- 8.1 Samples and test pieces shall be protected from direct sunlight during the interval between vulcanization and testing.

**8.2** Samples, after such preparation as is necessary, shall be conditioned at a standard laboratory temperature (that is,  $23\text{ }^{\circ}\text{C} \pm 2\text{ }^{\circ}\text{C}$  or  $27\text{ }^{\circ}\text{C} \pm 2\text{ }^{\circ}\text{C}$ ) for at least 3 h before the test pieces are cut from them.

These test pieces may be tested immediately but, if not, they shall be kept at the standard laboratory temperature until tested. If the preparation involves buffing, the interval between buffing and testing shall not exceed 72 h.

## 9 Temperature of test

The test shall normally be carried out at a standard laboratory temperature ( $23\text{ }^{\circ}\text{C} \pm 2\text{ }^{\circ}\text{C}$  or  $27\text{ }^{\circ}\text{C} \pm 2\text{ }^{\circ}\text{C}$ ), the same temperature being used throughout one test or series of tests intended to be comparable.

## 10 Procedure

### 10.1 Preparation of sample

If fabric is attached to, or embedded in, the sample, it shall be removed before cutting out the test pieces. The method of removal shall preferably avoid the use of a swelling liquid, but, if necessary, a suitable non-toxic liquid of low boiling point may be used to wet the contacting surfaces. Care shall be taken to avoid stretching the rubber during the separation from the fabric, and the liquid, if used, shall be allowed to evaporate completely from the rubber surfaces after separation. Cloth-marked surfaces shall be made smooth by buffing (see ISO 23529).

### 10.2 Method A

**10.2.1** Suspend the test piece (see Clause 6) from the hook on the balance (5.1) using a suitable length of filament so that the bottom of the test piece is about 25 mm above the straddle (5.2). The filament shall be made from a material which is insoluble in water and which does not absorb a significant amount of water. It shall either be counterbalanced or be weighed and, if weighed, its mass shall be deducted from subsequent weighings of the test piece (see 10.2.3).

**10.2.2** Weigh the test piece to the nearest milligram in air. Repeat the weighing with the test piece (and sinker, if required, see 10.2.4) immersed in freshly boiled and cooled distilled water or deionized water at a standard laboratory temperature ( $23\text{ }^{\circ}\text{C} \pm 2\text{ }^{\circ}\text{C}$  or  $27\text{ }^{\circ}\text{C} \pm 2\text{ }^{\circ}\text{C}$ ) contained in the beaker (5.3), placed on the straddle. Remove air bubbles adhering to the test piece (see 10.2.5 and 10.2.6) and weigh to the nearest milligram, watching for a few seconds to make sure that the reading does not drift gradually as a result of convection currents.

**10.2.3** Where the filament used has a mass less than 0,010 g, such as is the case with thin nylon filament, the correction to account for its mass is not necessary to ensure the stated accuracy of the final result. However, when the test piece is smaller than the one specified (e.g. when the density of small O-rings is to be measured), this can lead to inaccuracies and the mass of the filament needs to be taken into account in the final calculation. If a means of suspension other than a filament is used, the volume and mass of the suspension shall be taken into account in making the final calculation.

**10.2.4** When this procedure is used for rubber having a density less than  $1\text{ Mg/m}^3$ , a sinker is necessary; a further weighing of the sinker alone in water is required. Alternatively, a liquid of different density to water, which does not have any interaction with the rubber, may be used in place of the water, in which case the formulae given in 11.1 shall be modified to replace the density of water with the density of the liquid used.

**10.2.5** The main sources of error are

- a) air bubbles adhering to the surfaces of the test piece during weighing in water;
- b) surface tension effects on the filament;

- c) convection currents in the water in which the test piece is suspended, to minimize which the temperature of the water and of the air in the balance case shall be the same.

**10.2.6** In order to minimize the adherence of air bubbles to the test piece, it is permissible either to add a trace (say 1 part in 10 000) of surface-active material such as a detergent to the distilled water or to dip the test piece momentarily into a suitable liquid, such as methyl alcohol or denatured spirit, miscible with water and having a negligible swelling or leaching action on rubber. If the latter method is adopted, precautions shall be taken to minimize the carry-over of alcohol.

### 10.3 Method B

**10.3.1** Weigh the clean, dry density bottle and its stopper (5.4) before and after the insertion of the test piece (see Clause 6) cut into suitable pieces. The exact size and shape of the pieces will depend on the thickness of the original test piece. They should be such that no two dimensions are greater than 4 mm and the third not greater than 6 mm. Within these limitations, the pieces should be as large as possible. All cut edges shall be smooth. Fill the bottle, containing the rubber, completely with freshly boiled and cooled distilled water or deionized water at a standard laboratory temperature ( $23\text{ }^{\circ}\text{C} \pm 2\text{ }^{\circ}\text{C}$  or  $27\text{ }^{\circ}\text{C} \pm 2\text{ }^{\circ}\text{C}$ ). Remove air bubbles adhering to the rubber or to the walls of the bottle (see 10.2.6 above and 10.3.2 below). Insert the stopper, taking care that there is no air in the bottle or the capillary. Dry the outside of the bottle carefully. Weigh the bottle and contents. Empty the bottle completely and refill with freshly boiled and cooled distilled water or deionized water. After removing the air bubbles, inserting the stopper and drying, weigh the bottle and water. All the above weighings shall be made to the nearest milligram.

**10.3.2** The main source of error is air bubbles inside the bottle. It may be necessary to heat the bottle and contents to approximately  $50\text{ }^{\circ}\text{C}$  to dislodge bubbles, but in this case the bottle and contents shall be cooled before weighing. Alternatively, the bottle may be placed in a vacuum desiccator and the vacuum applied and released several times until no more air is extracted.

## 11 Expression of results

### 11.1 Method A

The density  $\rho$ , expressed in megagrams per cubic metre, is given by the formula:

$$\rho = \rho_w \frac{m_1}{m_1 - m_2}$$

where

$\rho_w$  is the density of water;

$m_1$  is the mass of the rubber, determined by weighing in air;

$m_2$  is the mass of the rubber less the mass of an equal volume of water, determined by weighing in water, both at standard laboratory temperature.

This method is accurate to the nearest  $0,01\text{ Mg/m}^3$ .

For most purposes, the density of water at standard laboratory temperature may be taken as  $1,00\text{ Mg/m}^3$ . However, for precise work, a factor to take account of the density of water at the test temperature shall be used.

When a sinker has been used, the calculation shall be modified as follows:

$$\rho = \rho_w \frac{m_1}{m_1 + m_2 - m_3}$$

where

- $\rho_w$  is the density of water;
- $m_1$  is the mass of the rubber, determined by weighing in air;
- $m_2$  is the mass of the sinker less the mass of an equal volume of water, determined by weighing in water, both at standard laboratory temperature;
- $m_3$  is the mass of the sinker and rubber less the mass of a volume of water equal to their combined volumes, determined by weighing in water, both at standard laboratory temperature.

Report the mean value.

## 11.2 Method B

The density  $\rho$ , expressed in megagrams per cubic metre, is given by the formula:

$$\rho = \rho_w \frac{m_2 - m_1}{m_4 - m_3 + m_2 - m_1}$$

where

- $\rho_w$  is the density of water;
- $m_1$  is the mass of the density bottle;
- $m_2$  is the mass of the density bottle plus test piece;
- $m_3$  is the mass of the bottle plus test piece plus water;
- $m_4$  is the mass of the density bottle filled with water.

For most purposes, the density of water at standard laboratory temperature may be taken as 1,00 Mg/m<sup>3</sup>. However, for precise work, a factor to take account of the density of water at the test temperature shall be used.

Report the mean value.

## 12 Test report

The test report shall include the following particulars:

- a) sample details:
  - 1) a full description of the sample and its origin,
  - 2) compound details and cure details, where appropriate,
  - 3) the method of preparation of the test pieces from the sample, for example moulded or cut;