



**INTERNATIONAL STANDARD ISO 2865 : 1973**  
**TECHNICAL CORRIGENDUM 1**

Published 1991-07-15

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION - МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ - ORGANISATION INTERNATIONALE DE NORMALISATION

**Aluminium oxide primarily used for the production of aluminium — Determination of boron content — Curcumin spectrophotometric method**

**TECHNICAL CORRIGENDUM 1**

*Oxyde d'aluminium principalement utilisé pour la production de l'aluminium — Dosage du bore — Méthode spectrophotométrique à la curcumine*

*RECTIFICATIF TECHNIQUE 1*

Technical corrigendum 1 to International Standard ISO 2865: 1973 was prepared by Technical Committee ISO/TC 47, *Chemistry, Sub-Committee SC 7, Aluminium oxide, cryolite, aluminium fluoride, sodium fluoride, carbonaceous products for the aluminium industry.*

*Page 1*

**Clause 2**

Replace the reference to ISO/R 802 by a reference to ISO 802: 1976.

Add the following reference:

*"ISO 2927: 1973, Aluminium oxide used primarily for the production of aluminium — Sampling."*

*Page 2*

**Subclause 6.1**

Replace the text of subclause 6.1 by the following text:

*"Weigh, to the nearest 0,001 g, 1 g of the laboratory sample, dried at 300 °C, prepared as described in ISO 2927 and ISO 802 : 1976, subclause 3.3."*

**UDC 661.862.22 : 546.27 : 543.42**

**Ref. No. ISO 2865 : 1973/Cor.1 : 1991 (E)**

**Descriptors :** aluminium, aluminium oxide, chemical analysis, determination of content, boron, spectrometric method.

© ISO 1991

Printed in Switzerland