

---

**INTERNATIONAL STANDARD**



**2928**

---

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

---

**Rubber hose for liquefied petroleum gases (LPG)**

*Tuyaux en caoutchouc pour gaz de pétrole liquéfiés*

First edition — 1975-04-01

STANDARDSISO.COM : Click to view the full PDF of ISO 2928:1975

---

UDC 621.643.33

Ref. No. ISO 2928-1975 (E)

**Descriptors :** rubber products, hoses, liquefied petroleum gases, mechanical properties, dimensions, marking, specifications.

Price based on 2 pages

## FOREWORD

ISO (the International Organization for Standardization) is a worldwide federation of national standards institutes (ISO Member Bodies). The work of developing International Standards is carried out through ISO Technical Committees. Every Member Body interested in a subject for which a Technical Committee has been set up has the right to be represented on that Committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work.

Draft International Standards adopted by the Technical Committees are circulated to the Member Bodies for approval before their acceptance as International Standards by the ISO Council.

International Standard ISO 2928 was drawn up by Technical Committee ISO/TC 45, *Rubber and rubber products*, and circulated to the Member Bodies in November 1974.

It has been approved by the Member Bodies of the following countries :

Australia	Ireland	South Africa, Rep. of
Brazil	Italy	Spain
Canada	Mexico	Sweden
Egypt, Arab Rep. of	New Zealand	Switzerland
Germany	Poland	Thailand
Hungary	Portugal	U.S.A.
India	Romania	U.S.S.R.

The Member Bodies of the following countries expressed disapproval of the document on technical grounds :

Belgium  
France  
United Kingdom

# Rubber hose for liquefied petroleum gases (LPG)

## 1 SCOPE AND FIELD OF APPLICATION

This International Standard specifies the requirements for flexible rubber hose for use with tank trucks or vehicles for the transport of liquefied petroleum gases (LPG).

The hose specified in this International Standard is intended for use "wet", i.e. permanently filled with liquid, and in the temperature range from  $-20^{\circ}\text{C}$  to  $+40^{\circ}\text{C}$ .

Although this International Standard states the requirements for hose and hose assemblies for use at a maximum working pressure of 2 MPa (20 bar), it is not intended to preclude the construction of hose for special applications capable of operating at higher working pressures.

### NOTES

1 The requirements for larger hose will be a matter for future study. In addition, a study will be made of the requirements for electrical resistance and recommended minimum bend radii.

2 Wire-reinforced hose is also used with liquefied petroleum gases, and attention is drawn to ISO 1436.

## 2 REFERENCES

ISO/R 36, *Determination of the adhesion strength of vulcanized rubbers to textile fabrics.*

ISO/R 37, *Determination of tensile stress-strain properties of vulcanized rubbers.*

ISO/R 188, *Vulcanized rubbers — Accelerated ageing or heat resistance tests.*

ISO/R 471, *Standard atmosphere for the conditioning and testing of rubber test pieces.*

ISO 1307, *Rubber hose — Bore sizes, tolerances on length and test pressures.*

ISO 1402, *Rubber hose — Hydrostatic testing.*

ISO 1436, *Wire reinforced, rubber covered hydraulic hose.*

ISO/R 1817, *Vulcanized rubbers — Methods of test for resistance to liquids.*

## 3 DIMENSIONS AND TOLERANCES

### 3.1 Bore

The bore of the hose shall be in accordance with the nominal dimensions and tolerances given in table 1, which is in accordance with ISO 1307.

NOTE — If special cases call for extra sizes :

For smaller or larger dimensions, further numbers shall be chosen from the R 10 series of preferred numbers, the tolerances being as given in ISO 1307.

For intermediate dimensions, numbers shall be chosen from the R 20 series of preferred numbers, the tolerances being as for the next larger bore size from the R 10 series.

TABLE 1 — Nominal bore

Values in millimetres

Nominal bore	Tolerance
8	$\pm 0,75$
10	$\pm 0,75$
12,5	$\pm 0,75$
16	$\pm 0,75$
20	$\pm 0,75$
25	$\pm 1,25$
31,5	$\pm 1,25$
40	$\pm 1,50$
50	$\pm 1,50$
63	$\pm 1,50$
80	$\pm 2,00$

### 3.2 Length

The tolerances on cut lengths of hose shall be as specified in ISO 1307.

## 4 PHYSICAL REQUIREMENTS ON FINISHED HOSE

### 4.1 Tensile strength and elongation at break of rubber lining and cover

The rubber used for the lining and cover of the hose shall, when tested in the manner described in ISO/R 37, have a