

INTERNATIONAL STANDARD



3057

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

Non-destructive testing — Metallographic replica techniques of surface examination

Essais non destructifs — Techniques de réplique métallographique pour l'examen des surfaces

First edition — 1974-04-01

STANDARDSISO.COM : Click to view the full PDF of ISO 3057:1974

UDC 620.18

Ref. No. ISO 3057-1974 (E)

Descriptors : surfaces, surface properties, tests, non-destructive tests, microscopy, replicas:

Price based on 2 pages

FOREWORD

ISO (the International Organization for Standardization) is a worldwide federation of national standards institutes (ISO Member Bodies). The work of developing International Standards is carried out through ISO Technical Committees. Every Member Body interested in a subject for which a Technical Committee has been set up has the right to be represented on that Committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work.

Draft International Standards adopted by the Technical Committees are circulated to the Member Bodies for approval before their acceptance as International Standards by the ISO Council.

International Standard ISO 3057 was drawn up by Technical Committee ISO/TC 135, *Non-destructive testing*, and circulated to the Member Bodies in February 1973.

It has been approved by the Member Bodies of the following countries :

Austria	France	South Africa, Rep. of
Belgium	Germany	Spain
Bulgaria	India	Sweden
Canada	Israel	Thailand
Chile	Mexico	Turkey
Czechoslovakia	Portugal	United Kingdom
Egypt, Arab Rep. of	Romania	U.S.S.R.

No Member Body expressed disapproval of the document.

Non-destructive testing – Metallographic replica techniques of surface examination

1 SCOPE

This International Standard specifies techniques of surface examination in which a transparent nitrocellulose varnish, or plastics material, with or without supports, is used to record inhomogeneities, both mechanical and metallurgical, in the condition of a metal surface.

2 FIELD OF APPLICATION

The techniques specified in this International Standard have the advantage of being suitable for locations where access is restricted. In addition, the replicas can be inspected on site with low-power optical aids or they may be transferred to a laboratory and examined under a powerful metallurgical microscope.

3 SURFACE PREPARATION

3.1 Degreasing

The surface shall be thoroughly cleaned, degreased and dried. This is conveniently achieved by the application of a suitable, approved solvent followed by acetone and drying in heated air.

3.2 Macrographic preparation

This preparation is applicable to all surfaces, including those resulting from service conditions, and to fracture faces. It calls for nothing more than the cleaning, degreasing and drying referred to in 3.1 above.

3.3 Micrographic preparation

3.3.1 This is intended for examination aimed at revealing the metallurgical state of the surface. After degreasing, the surface shall be subjected to a series of very fine mechanical polishing operations, each one progressively finer than the preceding one. In general, the dressing of the surface need not extend to a depth of more than 0,2 mm. In many cases, it will be considerably less. During these operations, care

should be taken to avoid over-heating and work-hardening the metal by ensuring that excessive pressure is not applied to the polishing tool. It is advisable to criss-cross successive polishing runs and to clean the surface after each run with acetone.

3.3.2 The mechanical polishing described above shall be followed by a final polishing. This may be done in any of the following ways :

- 1) by electrolytic means using a stainless steel electrode surrounded by spongy material impregnated with a suitable electrolyte;
- 2) by electrolytic means in a small bath;
- 3) by mechanical polishing with diamond paste.

After this polishing has been completed, the surface shall be washed first with water and then with acetone and dried in heated air. The final stage of the surface preparation is etching by an appropriate reagent. After etching, the surface shall once again be washed in water and acetone and dried.

4 APPLICATION OF THE REPLICATE

All possible precautions shall be taken to ensure that the replicate is applied under the driest possible conditions with all dust excluded.

4.1 Varnish replicate

The varnish shall be transparent and of a nitrocellulose or plastics base. Great care shall be taken not to agitate it prior to application, as such agitation can give rise to the formation of air bubbles which have a detrimental effect on results. The varnish shall be spread over the surface by means of a spatula (see note) made of rubber or plastics material, so as to form a thin layer of uniform thickness. The varnish shall then be allowed to dry for between 60 and 90 min.

NOTE — A brush should not be used for applying the varnish as it gives rise to air bubbles which remain trapped in the replica.