

# INTERNATIONAL STANDARD

**ISO  
3087**

Third edition  
1998-12-15

---

---

## Iron ores — Determination of the moisture content of a lot

*Minerais de fer — Détermination de l'humidité d'un lot*

STANDARDSISO.COM : Click to view the full PDF of ISO 3087:1998



Reference number  
ISO 3087:1998(E)

<b>Contents</b>	<b>Page</b>
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Definitions</b> .....	<b>1</b>
<b>4 Principle</b> .....	<b>1</b>
<b>5 Apparatus</b> .....	<b>1</b>
<b>6 Samples</b> .....	<b>2</b>
<b>7 Procedure</b> .....	<b>2</b>
<b>8 Verification</b> .....	<b>3</b>
<b>9 Calculation and expression of results</b> .....	<b>3</b>
<b>10 Test report</b> .....	<b>5</b>
<b>Annex A (normative) Determination of moisture content of adhesive or wet iron ores</b> .....	<b>6</b>
<b>Annex B (normative) Corrections for sprinkled water and/or rain-water</b> .....	<b>7</b>
<b>Annex C (informative) Precision of moisture measurement</b> .....	<b>12</b>
<b>Annex D (informative) Examples of test reports</b> .....	<b>13</b>

STANDARDSISO.COM : Click to view the full PDF of ISO 3087:1998

© ISO 1998

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization  
Case postale 56 • CH-1211 Genève 20 • Switzerland  
Internet iso@iso.ch

Printed in Switzerland

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 3087 was prepared by Technical Committee ISO/TC 102, *Iron ores*, Subcommittee 1, *Sampling*

This third edition cancels and replaces the second edition (ISO 3087:1987) which has been technically revised.

Annexes A and B form an integral part of this of this International Standard, annexes C and D are for information only.

STANDARDSISO.COM : Click to view the full PDF of ISO 3087:1998

## Introduction

Currently, large tonnages of iron ore are traded internationally and a small error in the measured moisture content (percentage by mass) of a lot has a considerable effect on the commercial transaction. The correct determination of moisture content of a lot is, therefore, a matter of importance for both the purchaser and the vendor.

This International Standard does not address the determination of the hygroscopic moisture content of a test sample for chemical analysis. If the hygroscopic moisture content is required to be determined, reference should be made to ISO 2596:1994, *Iron ores – Determination of hygroscopic moisture in analytical samples – Gravimetric and Karl Fischer methods*.

STANDARDSISO.COM : Click to view the full PDF of ISO 3087:1998

# Iron ores — Determination of the moisture content of a lot

## 1 Scope

This International Standard specifies a method for the determination of the moisture content of a lot of iron ore. This method is applicable to all iron ores, whether natural or processed.

## 2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this International Standard. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 3082:—<sup>1)</sup>, *Iron ores – Sampling and sample preparation procedures*.

ISO 11323:1996, *Iron ores – Vocabulary*.

## 3 Definitions

For the purposes of this International Standard, the definitions given in ISO 11323 apply.

## 4 Principle

Drying of the test portion in air at 105 °C to constant mass and measurement of the loss in mass. Calculation of the moisture content.

## 5 Apparatus

**5.1 Drying pan**, having a smooth surface, free from contamination and capable of accommodating the specified quantity of a test portion in a layer of nominal thickness not greater than 31,5 mm.

**5.2 Drying oven**, equipped with a temperature indicator and control apparatus capable of regulating the temperature at any point in the oven at 105 °C ± 5° C and so designed as to maintain this temperature with a current of air to ensure efficient drying but without any loss of sample, and fitted with a fan that allows for both the circulation and change of air.

**5.3 Weighing device**, accurate to at least 0,05 % of the initial mass of a test portion.

The capacity of the weighing device shall be enough for the initial mass of the test portion.

---

<sup>1)</sup> To be published. (Revision of ISO 3081:1986, ISO 3082:1987 and ISO 3083:1986)

## 6 Samples

Test samples which have been taken and prepared in accordance with ISO 3082 shall be used. The mass of a test portion, in relation to its nominal top size, is specified in table 1, in accordance with ISO 3082.

**Table 1 — Minimum mass of test portion**

Nominal top size of test portion (mm)	Minimum mass of test portion (kg)
31,5	10
22,4	5
10,0	1

## 7 Procedure

### 7.1 Number of moisture measurements

Carry out one moisture measurement per test portion on the number of test portions specified in table 2, according to the conditions of preparation of the test sample.

**Table 2 — Number of test portions**

Preparation of test sample	Number of partial samples per lot	Number of test portions to be tested
From gross sample	1	4
From partial sample	2	4
	3 to 7	2 minimum
	$\geq 8$	1 minimum
From increment	-	1 minimum

In order to minimize losses of moisture to the atmosphere, it is necessary to perform all the initial weighings of the test portions as quickly as possible after obtaining those test portions.

### 7.2 Measurement

Spread the test portion in a layer of nominal thickness not greater than 31,5 mm in the tared drying pan (5.1) and determine the total mass immediately. Record the total mass, the mass of the drying pan, the initial mass of the test portion ( $m_1$ ) and the numerical value of 0,05 % of the initial mass of the test portion.

Place the drying pan with the test portion in the drying oven (5.2) set at 105 °C, and maintain this temperature for not less than 4 h. Remove the drying pan with the test portion from the drying oven and weigh it immediately while still hot in order to minimize any reabsorption of moisture. Alternatively, weigh the test portion after cooling in air in a container having a close-fitting airtight lid. In each case, report the method of weighing.

Place once more, the drying pan with the test portion in the drying oven, heat for a further 1 h, and then repeat the weighing.

Repeat the procedure in the previous paragraph until the difference in mass between subsequent measurements becomes 0,05 % or less of the initial mass of the test portion.

NOTE 1 The weighing device should be protected from the influence of heat.

NOTE 2 Drying times will be dependent on the type of ore under test. For a series of measurements carried out on a particular type of ore, the drying time of the test portion may be specified by check experiments carried out beforehand.

NOTE 3 For convenience, the test portion of mass 10 kg for ore of particle size less than 31,5 mm may be divided into two portions, each of which is subjected to moisture measurement. In calculating the results, the mean of the two values of initial mass and the mean of the two values of the drying loss in mass should be used.

## 8 Verification

Regular checking of apparatus and procedures is essential to verify the test results. Checks shall be carried out prior to the commencement of a routine test in accordance with this International Standard and at regular intervals thereafter. The frequency of checking is a matter for each laboratory to determine. A detailed record of all verification activities shall be maintained for the following items:

- a) Sprinkled water measurement
  - volumenometer;
- b) Rainfall measurement
  - rain gauge;
- c) Moisture test
  - oven temperature/temperature regulation;
  - circulation and change of air in oven;
  - weighing device.

## 9 Calculation and expression of results

### 9.1 Test portion

The result of the determination of the moisture content,  $w_i$ , expressed as a percentage by mass, for each test portion, is given by equation (1) and reported to the second decimal place.

$$w_i = \frac{m_1 - m_2}{m_1} \times 100 \quad (1)$$

where

$m_1$  is the initial mass, in grams, of the test portion;

$m_2$  is the mass, in grams, of the test portion after drying.

### 9.2 Lot

The moisture content of a lot is given by one of equations (2) to (5) as the occasion may demand, and reported to the first decimal place.

**9.2.1** When moisture determination is conducted on the gross sample from the lot, the moisture of the lot is determined as follows.

When the range of the four test results does not exceed  $1,3r$  as shown in table 3, the arithmetic mean,  $\bar{w}$ , of the four results shall be the moisture content, expressed as a percentage by mass, of the lot as given by equation (2).

$$\bar{w} = \frac{w_1 + w_2 + w_3 + w_4}{4} \tag{2}$$

where  $w_1, w_2, w_3$  and  $w_4$  are the results of the determinations of the moisture contents, expressed as percentages by mass, on each of the four test portions.

When the range of the four test results exceeds  $1,3r$  given in table 3, the median shall be taken as the moisture content of the lot. The median of four test results is defined as the mean of the two non-extreme test results.

**Table 3 — Repeatability limit of moisture determination on the gross sample**

Average of moisture content $\bar{w}$ [% (m/m)]	Repeatability limit $r$ (%)	$1,3r$ (%)
$\bar{w} \leq 3$	0,20	0,26
$3 < \bar{w} \leq 6$	0,25	0,33
$6 < \bar{w}$	0,31	0,40

**9.2.2** When mass basis sampling has been performed and moisture determination is conducted on each partial sample, the weighted mean,  $\bar{w}$ , of the results from all the partial samples, considering the number of increments for each partial sample, shall be the moisture content, expressed as a percentage by mass, of the lot, as given by equation (3),

$$\bar{w} = \frac{\sum_{i=1}^k N_i w_i}{\sum_{i=1}^k N_i} \tag{3}$$

where

- $k$  is the number of partial samples;
- $N_i$  is the number of increments in the  $i$ th partial sample;
- $w_i$  is the result of the determination of the moisture content, expressed as a percentage by mass, of the  $i$ th partial sample, according to table 2 using as the number of test portions either 4 or 2.

If it is impracticable to sample the lot as a whole or desirable to sample a lot in separate parts of unequal mass as in the case of time basis sampling, the moisture content of each part shall be determined independently and the weighted mean,  $\bar{w}$ , of the results, expressed as a percentage by mass, of the lot calculated from the individual results using equation (4).

$$\bar{w} = \frac{\sum_{i=1}^k m_i w_i}{\sum_{i=1}^k m_i} \quad (4)$$

where

$k$  is the number of partial samples;

$m_i$  is the mass of the  $i$ th part;

$w_i$  is the result of the determination of the moisture content, expressed as a percentage by mass, of the  $i$ th part.

**9.2.3** When moisture determination is conducted on each increment, the arithmetic mean,  $\bar{w}$ , of the results for all increments obtained according to 9.1 shall be the moisture content, expressed as a percentage by mass, of the lot as given by equation (5)

$$\bar{w} = \frac{\sum_{i=1}^n w_i}{n} \quad (5)$$

where

$n$  is the number of increments;

$w_i$  is the result of the determination of the moisture content, expressed as a percentage by mass, of the  $i$ th increment.

## 10 Test report

The test report shall contain the following information.

- a) reference to this International Standard, i.e., ISO 3087;
- b) details necessary for the identification of the sample;
- c) result of the test;
- d) reference number of the result;
- e) any characteristics noticed during the determination, and any operation not specified in this International Standard which may have had an influence on the results.

## Annex A (normative)

### Determination of moisture content of adhesive or wet iron ores

#### Introduction

When it is difficult to conduct sieving, crushing and dividing owing to a sample being adhesive or excessively wet, the sample may be pre-dried until preparation can be conducted without difficulty.

In this case, the moisture content of the lot shall be obtained by using the pre-drying method according to the procedure specified in this annex. In handling the test sample and weighing the initial mass and pre-dried mass of the test sample, attention shall be paid to ensuring the measurement precision of the pre-dried moisture content.

**A.1** Determine the initial mass of the test sample.

**A.2** Spread the test sample in a uniform thickness and dry it in air or in a drying apparatus at a temperature no higher than 105 °C. The choice of temperature and time for this pre-drying stage shall not exceed a point where an ore is likely to reabsorb moisture during subsequent processing.

**A.3** After pre-drying, again determine the mass of the test sample.

**A.4** Calculate the pre-dried moisture content,  $w_p$ , expressed as a percentage by mass, of the test sample using equation (A.1).

$$w_p = \frac{m'_1 - m'_2}{m'_1} \times 100 \quad (\text{A.1})$$

where

$m'_1$  is the initial mass, in grams, of the test sample;

$m'_2$  is the mass, in grams, of the test sample after pre-drying.

**A.5** Prepare the test portions for moisture measurement from the pre-dried sample according to the procedure in ISO 3082.

**A.6** Determine the drying loss of the test portion in accordance with 7.2 and calculate the additional moisture content, expressed as a percentage by mass, in accordance with 9.1.

**A.7** Calculate the total (as received) moisture content,  $w_{pd}$ , expressed as a percentage by mass, of the test sample using equation (A.2).

$$w_{pd} = w_p + \frac{100 - w_p}{100} \times w_d \quad (\text{A.2})$$

where  $w_d$  is the additional moisture content obtained in accordance with 9.1 after pre-drying, expressed as a percentage by mass.

**A.8** Determine the moisture content, as a percentage by mass, of the lot in accordance with 9.2.

**A.9** If the mass of the moisture sample is not large, the entire quantity of the sample may be dried in order to conduct the moisture determination according to the method specified in the body of this International Standard.

## Annex B (normative)

### Corrections for sprinkled water and/or rain-water

#### Introduction

Nowadays, in many countries, strict environmental regulations must be observed in the iron ore and steel industry. When water is sprinkled over iron ore during loading and/or unloading operations to prevent dust evolution, the moisture content of a lot shall be corrected, according to the procedure specified in this annex, for the mass of water sprinkled.

This annex also describes a method for correcting the moisture content of a lot containing rain water.

#### B.1 General

**B.1.1** Water is sprinkled for the following reasons:

- a) environmental regulations at loading and/or unloading ports;
- b) difficulty of handling iron ores due to ore characteristics, weather conditions, handling equipment, etc.

**B.1.2** Correction for rain-water shall be made whenever rainfall occurs during the loading or unloading operations, and the moisture content of the lot is known to have been affected.

#### B.2 Corrections for sprinkled water

##### B.2.1 General

In the case of unloading of a lot, sprinkled water refers to water sprinkled (or sprayed) in the vessel holds and/or on any sections extending to a point where samples are taken. In the case of loading of a lot, sprinkled water refers to water sprinkled in the holds and/or on the loading conveyors located after the point where moisture samples are taken.

Two methods of correction for sprinkled water are mentioned in this clause. One refers to water added before the sampling point during unloading operations, the other to water added after the sampling point during loading operations.

##### B.2.2 Measurement of sprinkled water

The measurement of sprinkled water shall be made with a volumenometer having an accuracy of  $\pm 5\%$ . The volume obtained shall be converted to a mass,  $m_3$ , in tonnes, by multiplying by the density of the sprinkled water.

NOTE Fresh water is assumed to have a density of  $1 \text{ t/m}^3$ .

### B.2.3 Mass of lot

The mass of the lot,  $m_4$ , in tonnes, as received or as despatched without sprinkled water or rain water, or the mass of the lot,  $m_5$ , in tonnes as received or as despatched containing sprinkled water or rain water, should be determined by draught survey or by other internationally recognized means, such as weightometer or weigh hopper.

NOTE In the examples given in B.2.4, B.2.5, B.3.6, B.3.7, B.4 and B.5 below, it is assumed that the mass of the lot has been determined by draught survey. In these instances, the determination of mass is conducted either before any sprinkled water or rain-water is added (unloading operations) or after all sprinkled water or rain-water has been added (loading operations).

If a weightometer or weigh hopper is used, special care must be taken to ensure corrections take into account the relative position of the weighing device and the sampling point. For example, during unloading operations, if sampling is conducted immediately after the weighing device, no corrections for sprinkled water or rain-water are necessary. However, corrections may be necessary if the sampling point is remote from the weighing device.

### B.2.4 Calculation of moisture content corrected for sprinkled water added during unloading operations prior to taking moisture samples

The moisture content of the lot,  $w_s$ , expressed as a percentage by mass, corrected for sprinkled water, is given by equation (B.1) and reported to the first decimal place.

$$w_s = \bar{w} - (100 - \bar{w}) \frac{m_3}{m_4} f \quad (\text{B.1})$$

where

$\bar{w}$  is the mean value of the moisture content, expressed as a percentage by mass, of a sample taken containing sprinkled water, calculated to the second decimal place;

$m_3$  is the mass, in tonnes, of sprinkled water;

$m_4$  is the mass, in tonnes, of the lot as received without sprinkled water, as determined in B.2.3;

$f$  is a pre-determined factor to correct for water lost during sprinkling.

NOTE In determining a suitable  $f$  factor the following factors should be considered on a case-by-case basis:

- a) atmospheric conditions
  - humidity;
  - air temperature;
  - wind effects;
  - rainfall;
- b) ore type / ore characteristics
  - sizing;
  - mineralogy;
  - porosity / texture;
  - moisture content;
- c) sprinkler arrangement / geometry;
- d) chemical reagents / additives in water.

### B.2.5 Calculation of moisture content corrected for sprinkled water added during loading operations after taking moisture samples

The moisture content of the lot,  $w_s$ , expressed as a percentage by mass, corrected for sprinkled water, is given by equation (B.2) and reported to the first decimal place.

$$w_s = \bar{w} + (100 - \bar{w}) \frac{m_3}{m_5} f \quad (\text{B.2})$$

where

$\bar{w}$  is the mean value of the moisture content, expressed as a percentage by mass, of a sample taken prior to sprinkled water, calculated to the second decimal place;

$m_3$  is the mass, in tonnes, of sprinkled water;

$m_5$  is the mass, in tonnes, of the lot containing sprinkled water, as determined in B.2.3;

$f$  refer to note in B.2.4.

## B.3 Corrections for rain-water

### B.3.1 General

The moisture content of the lot shall be determined from the as-tested moisture content by allowing for the influx of rain-water into the vessel's hold(s) and/or on to the handling equipment during both loading and unloading operations.

Two methods of correction for rain-water are mentioned in this clause. One refers to rain-water influx before the sampling point during unloading operations, the other to rain-water influx after the sampling point during loading operations.

### B.3.2 Effective area caught in the rain

The effective area exposed to the rain shall be calculated by summation of the areas specified below, rounded to the nearest square metre.

- Hatch(es)* The open area, in square metres, of the hatch(es) through which the lot is exposed to the rain, shall be calculated on the basis of the drawings provided on board the carrying vessel.
- Surge hopper(s)* The open area, in square metres, of the hopper(s) used during handling the lot and exposed to the rain, shall be calculated on the basis of drawings of the hopper(s).
- Belt conveyor(s)* The open area, in square metres, of the belt conveyor(s) shall be calculated by multiplying the effective belt width by the length exposed to the rain during transportation of the lot between the vessel and the point where moisture samples are taken.

### B.3.3 Duration of rainy periods

The duration of rainy periods shall be determined from the time of the opening of the hatches to completion of sampling.

### B.3.4 Amount of rain-water

The amount of rain-water shall be determined by means of an approved rain gauge placed close to the loading or the unloading port. The amount of rain-water shall be measured to the nearest millimetre.

### B.3.5 Mass of rain-water

The mass,  $m_R$ , in tonnes, of rain-water is given by equation (B.3), and rounded off to the nearest unit.

$$m_R = \frac{AR\rho}{1000} \quad (\text{B.3})$$

where

$A$  is the effective area, in square metres, exposed to the rain as calculated in B.3.2;

$R$  is the quantity, in millimetres, of rain-water obtained in B.3.4;

$\rho$  is the density, expressed in tonnes per cubic metre, of rain-water (usually  $\rho = 1 \text{ t/m}^3$ ).

### B.3.6 Calculation of moisture content corrected for rain-water ingress during unloading operations prior to taking moisture samples

When a lot is partially or totally exposed to the during unloading operations prior to taking moisture samples, the moisture content,  $w_R$ , expressed as a percentage by mass, of the lot corrected for rain-water is given by equation (B.4) and reported to the first decimal place.

$$w_R = \bar{w} - (100 - \bar{w}) \frac{m_R}{m_4} \quad (\text{B.4})$$

where

$\bar{w}$  is the mean value of the moisture content, expressed as a percentage by mass, of a sample taken containing rain-water, calculated to the second decimal place;

$m_R$  is the mass, in tonnes, of rain-water;

$m_4$  is the mass, in tonnes, of the lot as received without rain-water, as determined in B.2.3.

### B.3.7 Calculation of moisture content corrected for rain-water ingress during loading operations after taking moisture samples

When a lot is partially or totally exposed to rain during loading operations after taking moisture samples, the moisture content,  $w_R$ , expressed as a percentage by mass, of the lot corrected for rain-water is given by equation (B.5) and reported to the first decimal place.

$$w_R = \bar{w} + (100 - \bar{w}) \frac{m_R}{m_5} \quad (\text{B.5})$$

where

$\bar{w}$  is the mean value of the moisture content, expressed as a percentage by mass, of a sample taken prior to rain, calculated to the second decimal place;

$m_R$  is the mass, in tonnes, of rain-water;

$m_5$  is the mass, in tonnes, of the lot containing rain-water, as determined in B.2.3.

#### B.4 Corrections for both sprinkled water and rain-water ingress during unloading operations prior to taking moisture samples

The corrected moisture content,  $w_o$ , expressed as a percentage by mass, of a lot which has been wetted with both sprinkled water and rain-water prior to taking moisture samples is given by equation (B.6) and reported to the first decimal place.

$$w_o = \bar{w} - (100 - \bar{w}) \frac{(m_3 f + m_R)}{m_4} \quad (\text{B.6})$$

where  $f$ ,  $m_3$ ,  $m_4$ ,  $m_R$  and  $\bar{w}$  are as previously defined.

#### B.5 Corrections for both sprinkled water and rain-water ingress during loading operations after taking moisture samples

The corrected moisture content,  $w_o$ , expressed as a percentage by mass, of a lot which has been wetted with both sprinkled water and rain-water after taking moisture samples is given by equation (B.7) and reported to the first decimal place.

$$w_o = \bar{w} + (100 - \bar{w}) \frac{(m_3 f + m_R)}{m_5} \quad \dots(\text{B.7})$$

where  $f$ ,  $m_3$ ,  $m_5$ ,  $m_R$  and  $\bar{w}$  are as previously defined.

STANDARDSISO.COM : Click to view the full PDF of ISO 3087:1998

## Annex C (informative)

### Precision of moisture measurement

This International Standard assumes that single test results have the precision shown as  $\beta_{PM}$  in table C.1

When two test portions have been prepared from a single test sample and subjected to moisture measurement in the same laboratory, the test results will generally agree to within the repeatability limit which is given as  $r$  in table 3 and which may be calculated as  $\sqrt{2} \beta_{PM}$ .

**Table C.1 — Precision of moisture measurement**

Average moisture content $\bar{w}$ [% (m/m)]	Precision $\beta_{PM}$ (absolute %)
$\bar{w} \leq 3$	$\pm 0,14$
$3 < \bar{w} \leq 6$	$\pm 0,18$
$6 < \bar{w}$	$\pm 0,22$

## Annex D (informative)

### Examples of test reports

Four examples of test reports are shown in tables D.1, D.2, D.3 and D.4. Table D.1 is a test report for moisture measurement on a test portion. Table D.2 is mainly used for the calculation of moisture content of a lot from partial samples obtained by mass basis sampling, while table D.3 is used for time basis sampling. Table D.4 is a test report for determination of moisture content of a lot on four test portions taken from the gross sample.

**Table D.1 — Example of a test report for values of moisture measurement on a test portion**

Type of iron ore:			
Identity and quantity of lot:			
Sample No.:	Minimum mass of test portion: 5 kg	Nominal top size of test portion: 22,4 mm	Date:
Total mass before drying (g)	(1)	6 015	
Mass of drying pan (g)	(2)	950	
Initial mass of test portion (g)	(3) = (1) – (2)	5 065	
Value of 0,05% of initial mass of test portion (g)	(4) = $\frac{(3)}{2\ 000}$	2,5	
		mass	difference *
Total mass after 4 h drying (g)	(5)	5 805	
Total mass after further 1 h drying (g)	(6)	5 795	(5) – (6) :10
Total mass after another 1 h drying (g)	(7)	5 793	(6) – (7) :2
Final drying loss (g)	(8) = (1) – (7)	222	
Value of moisture measurement, $w$ , (%)	(9) = $\frac{(8)}{(3)} \times 100$	4,38	
Remarks:	Method of weighing (see 7.2)		
Assayer:			
* The difference (5) – (6) was 10 g and exceeded (4), consequently another 1 h drying was conducted. The difference (6) – (7) became 2 g and was less than (4). Therefore, the drying of this test portion was terminated.			