



Manganese ores — Determination of active oxygen content, expressed as manganese dioxide — Volumetric method

Minerais de manganèse — Dosage de l'oxygène actif, exprimé en dioxyde de manganèse — Méthode volumétrique

Second edition — 1980-06-15

STANDARDSISO.COM : Click to view the full PDF of ISO 312:1980

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards institutes (ISO member bodies). The work of developing International Standards is carried out through ISO technical committees. Every member body interested in a subject for which a technical committee has been set up has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work.

Draft International Standards adopted by the technical committees are circulated to the member bodies for approval before their acceptance as International Standards by the ISO Council.

International Standard ISO 312 was developed by Technical Committee ISO/TC 65, *Manganese and chromium ores*.

This second edition was submitted directly to the ISO Council, in accordance with clause 5.10.1 of part 1 of the Directives for the technical work of ISO. It cancels and replaces the first edition (i.e. ISO 312-1974), which had been approved by the member bodies of the following countries :

Austria	India	Romania
Bulgaria	Ireland	South Africa, Rep. of
Chile	Italy	Spain
Czechoslovakia	Japan	United Kingdom
France	Netherlands	USSR
Germany, F.R.	Poland	
Hungary	Portugal	

No member body had expressed disapproval of the document.

Manganese ores — Determination of active oxygen content, expressed as manganese dioxide — Volumetric method

1 Scope and field of application

This International Standard specifies a volumetric method, by reduction with ammonium iron(II) sulphate, for the determination of the active oxygen content (conventionally expressed as manganese dioxide) of manganese ores.

← It should be read in conjunction with ISO 4297.

2 Reference

ISO 4297, *Manganese ores and concentrates — Methods of chemical analysis — General instructions*.

3 Principle

Dissolution of a test portion in an excess of a standard solution of ammonium iron(II) sulphate in sulphuric acid, to reduce the manganese dioxide present in the test portion. Back-titration of the excess of ammonium iron(II) sulphate with standard volumetric potassium dichromate solution in the presence of sodium diphenylamine sulphonate as indicator.

4 Reagents

4.1 Phosphoric acid, ρ 1,7 g/ml.

4.2 Ammonium iron(II) sulphate, 60 g/l solution.

Dissolve 60 g of ammonium iron(II) sulphate $[(\text{NH}_4)_2\text{Fe}(\text{SO}_4 \cdot 6\text{H}_2\text{O})]$ in sulphuric acid, diluted (1 + 7), and dilute to 1 l with the same acid.

4.3 Potassium dichromate, 8,780 g/l standard volumetric solution.

4.3.1 Preparation of the solution

Dissolve 8,780 g of potassium dichromate, recrystallized and dried at 180 to 290 °C, in 100 ml of water. Transfer the solution quantitatively to a 1 l one-mark volumetric flask, dilute to the mark and mix.

4.3.2 Standardization of the solution

Take three test portions from a standard sample of manganese ore having a known manganese dioxide content approximately the same as that of the sample to be analysed and pass them through all stages of the analysis (7.5).

The titre of the potassium dichromate solution is given by the formula

$$T = \frac{B \times m}{V \times 100}$$

where

T is the titre of the potassium dichromate solution, expressed as grams of manganese dioxide corresponding to 1 ml of the solution;

B is the manganese dioxide content, as a percentage by mass, of the standard sample of manganese ore;

m is the mass, in grams, of the test portion from the standard sample;

V is the volume, in millilitres, of potassium dichromate solution used.

Take as the titre the average of the three results.

4.4 Sodium diphenylamine sulphonate, 0,8 g/l solution.

Dissolve 0,8 g of powdered sodium diphenylamine sulphonate $(\text{C}_6\text{H}_5\text{NHC}_6\text{H}_4 \cdot \text{SO}_3\text{Na})$ in a small volume of water and dilute with water to 1 l.

Store the solution in a brown glass bottle.

5 Apparatus

Ordinary laboratory apparatus and

5.1 Conical flask, 300 ml capacity, fitted with a stopper with two outflow pipes (see figure).