

---

**INTERNATIONAL STANDARD**



**3290**

---

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

---

**Rolling bearings — Bearing parts — Balls for rolling bearings**

*Roulements — Éléments de roulements — Billes pour roulements*

First edition — 1975-09-01

STANDARDSISO.COM : Click to view the full PDF of ISO 3290:1975

---

UDC 621.822.71

Ref. No. ISO 3290-1975 (E)

Descriptors : rolling bearings, ball bearings, balls, specifications, diameters.

Price based on 8 pages

## FOREWORD

ISO (the International Organization for Standardization) is a worldwide federation of national standards institutes (ISO Member Bodies). The work of developing International Standards is carried out through ISO Technical Committees. Every Member Body interested in a subject for which a Technical Committee has been set up has the right to be represented on that Committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work.

Draft International Standards adopted by the Technical Committees are circulated to the Member Bodies for approval before their acceptance as International Standards by the ISO Council.

International Standard ISO 3290 was drawn up by Technical Committee ISO/TC 4, *Rolling bearings*, and circulated to the Member Bodies in April 1974.

It has been approved by the Member Bodies of the following countries :

Australia	Italy	Switzerland
Austria	Japan	Thailand
Bulgaria	Netherlands	Turkey
Canada	Poland	U.S.A.
France	Romania	U.S.S.R.
Germany	South Africa, Rep. of	Yugoslavia
Hungary	Spain	
India	Sweden	

This International Standard has also been approved by the International Union of Railways (UIC).

The Member Body of the following country expressed disapproval of the document on technical grounds :

United Kingdom

# Rolling bearings — Bearing parts — Balls for rolling bearings

## 1 SCOPE AND FIELD OF APPLICATION

This International Standard specifies requirements for finished steel balls for rolling bearings.

## 2 DEFINITIONS, SYMBOLS AND EXPLANATIONS

**2.1 nominal ball diameter,  $D_w$**  : The diameter value which is used for the purpose of general identification of a ball size.

**2.2 single diameter of a ball,  $D_{ws}$**  : The distance between two parallel planes tangent to the surface of the ball.

**2.3 mean diameter of a ball,  $D_{wm}$**  : The arithmetic mean of the largest and the smallest actual single diameters of the ball.

**2.4 ball diameter variation,  $V_{D_{ws}}$**  : The difference between the largest and smallest actual single diameters of one ball.

**2.5 deviation from spherical form** : The greatest radial distance in any radial plane between a sphere circumscribed around the ball surface and any point on the ball surface.

Information regarding the measurement of the deviation from spherical form is given in annex B.

**2.6 lot** : A definite quantity of balls manufactured under conditions which are presumed uniform and which is considered as an entity.

**2.7 lot mean diameter,  $D_{wmL}$**  : The arithmetic mean of the mean diameter of the largest ball and that of the smallest ball in the lot.

**2.8 lot diameter variation,  $V_{D_{wL}}$**  : The difference between the mean diameter of the largest ball and that of the smallest ball in the lot.

**2.9 ball grade** : A specific combination of dimensional, form, surface roughness, and sorting tolerances.

A ball grade is identified by a number.

**2.10 ball gauge,  $S$**  : The amount by which a lot mean diameter should differ from the nominal ball diameter, this amount being one of an established series.

Each ball gauge is a whole multiple of the ball gauge interval established for the ball grade in question. See also annex A.

A ball gauge, in combination with the ball grade and nominal diameter, should be considered as the most exact ball size specification to be used by a customer for ordering purposes.

**2.11 deviation from ball gauge,  $\Delta S$**  : The difference between the lot mean diameter and the sum of the nominal diameter and the ball gauge. See also annex A.

$$\Delta S = D_{wmL} - (D_w + S)$$

**2.12 ball subgauge** : The amount, of an established series of amounts, which is nearest to the actual deviation from a ball gauge.

Each ball subgauge is a whole multiple of the ball subgauge interval established for the ball grade in question. See also annex A.

The ball subgauge, in combination with the nominal ball diameter and the ball gauge, is used by ball manufacturers to denote the lot mean diameter and should not be used by customers for ordering purposes.

**2.13 surface roughness** : All those irregularities of the surface which are conventionally defined within a section of the area where deviations of form and waviness are eliminated.

The surface roughness tolerance values given in table 2 refer to the arithmetical mean deviation,  $R_a$ , from the mean line of the profile, evaluated according to the method specified in ISO/R 468, *Surface roughness*.

**2.14 hardness** : The measure of resistance to penetration as determined by specific methods.

### 3 REQUIREMENTS

#### 3.1 Ball size

The preferred nominal ball diameters are given in table 1.

#### 3.2 Quality of geometry and surface

Table 2 comprises the applicable tolerances for :

- ball diameter variation;
- deviation from spherical form;
- surface roughness.

It is recognized that other characteristics, such as waviness and surface appearance, are also essential for the quality of balls for rolling bearings. In the absence of internationally established practice in this field, the specifications and tolerances for such characteristics are subject to agreement between customer and supplier.

#### 3.3 Sorting accuracy and ball gauges

Table 3 comprises the applicable values for :

- maximum lot diameter variation;
- gauge interval;
- preferred gauges;
- subgauge interval;
- subgauges.

#### 3.4 Ball grade application

The preferred range of ball sizes to which the different ball grades should be applied is given in table 4.

#### 3.5 Hardness

Hardness values and the measuring method shall be agreed upon between customer and supplier.

STANDARDSISO.COM : Click to view the full PDF of ISO 3290:1975

TABLE 1 — Preferred ball sizes

Nominal ball diameter $D_w$		Diameter for subgauge 0 of gauge 0		Nominal ball diameter $D_w$		Diameter for subgauge 0 of gauge 0	
mm	in	mm	in	mm	in	mm	in
0,3		0,300 00	0.011 810	9		9,000 00	0.354 330
	1/64	0,396 88	0.015 625		23/64	9,128 12	0.359 375
0,4		0,400 00	0.015 750		3/8	9,525 00	0.375 000
0,5		0,500 00	0.019 680		25/64	9,921 87	0.390 625
	0.020	0,508 00	0.020 000	10		10,000 00	0.393 700
0,6		0,600 00	0.023 620		13/32	10,318 75	0.406 250
	0.025	0,635 00	0.025 000	11		11,000 00	0.433 070
0,7		0,700 00	0.027 560		7/16	11,112 50	0.437 500
	1/32	0,793 75	0.031 250	11,5		11,500 00	0.452 756
0,8		0,800 00	0.031 496		29/64	11,509 38	0.453 125
1		1,000 00	0.039 370		15/32	11,906 25	0.468 750
	3/64	1,190 63	0.046 875	12		12,000 00	0.472 440
1,2		1,200 00	0.047 240		31/64	12,303 12	0.484 375
1,5		1,500 00	0.059 060		1/2	12,700 00	0.500 000
	1/16	1,587 50	0.062 500	13		13,000 00	0.511 810
	5/64	1,984 38	0.078 125		17/32	13,493 75	0.531 250
2		2,000 00	0.078 740	14		14,000 00	0.551 180
	3/32	2,381 25	0.093 750		9/16	14,287 50	0.562 500
2,5		2,500 00	0.098 420	15		15,000 00	0.590 550
	7/64	2,778 00	0.109 375		19/32	15,081 25	0.593 750
3		3,000 00	0.118 110		5/8	15,875 00	0.625 000
	1/8	3,175 00	0.125 000	16		16,000 00	0.629 920
3,5		3,500 00	0.137 800		21/32	16,668 75	0.656 250
	9/64	3,571 87	0.140 625	17		17,000 00	0.669 290
	5/32	3,968 75	0.156 250		11/16	17,462 50	0.687 500
4		4,000 00	0.157 480	18		18,000 00	0.708 660
	11/64	4,365 63	0.171 875		23/32	18,256 25	0.718 750
4,5		4,500 00	0.177 160	19		19,000 00	0.748 030
	3/16	4,762 50	0.187 500		3/4	19,050 00	0.750 000
5		5,000 00	0.196 850	20		20,000 00	0.781 250
5,5		5,500 00	0.216 540		25/32	19,843 75	0.781 250
	7/32	5,556 25	0.218 750	20		20,000 00	0.787 400
	15/64	5,953 12	0.234 375		13/16	20,637 50	0.812 500
6		6,000 00	0.236 220	21		21,000 00	0.826 770
	1/4	6,350 00	0.250 000		27/32	21,431 25	0.843 750
6,5		6,500 00	0.255 900	22		22,000 00	0.866 140
	17/64	6,746 88	0.265 625		7/8	22,225 00	0.875 000
7		7,000 00	0.275 590	23		23,000 00	0.905 510
	9/32	7,143 75	0.281 250		29/32	23,018 75	0.906 250
7,5		7,500 00	0.295 280		15/16	23,812 50	0.937 500
	19/64	7,540 63	0.296 875	24		24,000 00	0.944 880
	5/16	7,937 50	0.312 500		31/32	24,606 25	0.968 750
8		8,000 00	0.314 960	25		25,000 00	0.984 250
8,5		8,500 00	0.334 640		1	25,400 00	1,000 000
	11/32	8,731 25	0.343 750	26		26,000 00	1.023 620

TABLE 1 (concluded)

Nominal ball diameter $D_w$		Diameter for subgauge 0 of gauge 0	
mm	in	mm	in
28	1 1/16	26,987 50	1.062 500
	1 1/8	28,000 00	1.102 360
30	1 3/16	28,575 00	1.125 000
	1 1/4	30,000 00	1.181 100
32	1 5/16	30,162 50	1.187 500
	1 1/2	31,750 00	1.250 000
34	1 3/8	32,000 00	1.259 840
	1 5/8	33,337 50	1.312 500
35	1 7/16	34,000 00	1.338 580
	1 1/2	34,925 00	1.375 000
36	1 3/4	35,000 00	1.377 950
	1 13/16	36,000 00	1.417 320
38	1 7/16	36,512 50	1.437 500
	1 1/2	38,000 00	1.496 060
40	1 1/2	38,100 00	1.500 000
	1 9/16	39,687 50	1.562 500
45	1 5/8	40,000 00	1.574 800
	1 11/16	41,275 00	1.625 000
45	1 3/4	42,862 50	1.687 500
	1 13/16	44,450 00	1.750 000
50	1 7/8	45,000 00	1.771 650
	1 15/16	46,037 50	1.812 500
55	2	47,625 00	1.875 000
	2 1/8	49,212 50	1.937 500
60	2	50,000 00	1.968 500
	2 1/8	50,800 00	2.000 000
65	2 1/4	53,975 00	2.125 000
	2 3/8	55,000 00	2.165 354
65	2 1/2	57,150 00	2.250 000
	2 7/8	60,000 00	2.362 205
70	3	60,325 00	2.375 000
	3 1/8	63,500 00	2.500 000
75	3 1/4	65,000 00	2.559 055
	3 3/8	66,675 00	2.625 000
80	3 1/2	69,850 00	2.750 000
	3 5/8	73,025 00	2.875 000
85	4	76,200 00	3.000 000
	4 1/8	79,375 00	3.125 000
90	4 1/4	82,550 00	3.250 000
	4 3/8	85,725 00	3.375 000
95	4 1/2	88,900 00	3.500 000
	4 7/8	92,075 00	3.625 000
100	5	95,250 00	3.750 000
	5 1/8	98,425 00	3.875 000
105	5 1/4	101,600 00	4.000 000
	5 3/8	104,775 00	4.125 000
110	5 1/2	107,950 00	4.250 000
	5 7/8	111,125 00	4.375 000
115	6	114,300 00	4.500 000
	6 1/8		

TABLE 2 — Form and surface roughness tolerances

Grade	Ball diameter variation $V_{Dws}$	Deviation from spherical form	Surface roughness $R_a$
Maximum values in micrometres			
3	0,08	0,08	0,012
5	0,13	0,13	0,02
10	0,25	0,25	0,025
16	0,4	0,4	0,032
20	0,5	0,5	0,04
28	0,7	0,7	0,05
40	1	1	0,08
100	2,5	2,5	0,125
200	5	5	0,2
Maximum values in microinches			
3	3	3	0.5
5	5	5	0.8
10	10	10	1
16	16	16	1.25
20	20	20	1.6
28	28	28	2
40	40	40	3.2
100	100	100	5
200	200	200	8

TABLE 3 – Sorting tolerances and gauges

Grade	Lot diameter variation $V_{D_{wL}}$ max.	Gauge interval	Preferred gauges	Subgauge interval	Subgauges
Values in micrometres					
3	0,13	0,5	- 5, ... - 0,5, 0, + 0,5, ... + 5	0,1	- 0,2, - 0,1, 0, + 0,1, + 0,2
5	0,25	1	- 5, ... - 1, 0, + 1, ... + 5	0,2	- 0,4, - 0,2, 0, + 0,2, + 0,4
10	0,5	1	- 9, ... - 1, 0, + 1, ... + 9	0,2	- 0,4, - 0,2, 0, + 0,2, + 0,4
* 16	0,8	2	- 10, ... - 2, 0, + 2, ... + 10	0,4	- 0,8, - 0,4, 0, + 0,4, + 0,8
* 20	1	2	- 10, ... - 2, 0, + 2, ... + 10	0,4	- 0,8, - 0,4, 0, + 0,4, + 0,8
* 28	1,4	2	- 12, ... - 2, 0, + 2, ... + 12	0,4	- 0,8, - 0,4, 0, + 0,4, + 0,8
40	2	4	- 16, ... - 4, 0, + 4, ... + 16	0,8	- 1,6, - 0,8, 0, + 0,8, + 1,6
100	5	10	- 40, ... - 10, 0, + 10, ... + 40	2	- 4, - 2, 0, + 2, + 4
200	10	15	- 60, ... - 15, 0, + 15, ... + 60	3	- 6, - 3, 0, + 3, + 6
Values in microinches					
3	5	20	- 200, ... - 20, 0, + 20, ... + 200	4	- 8, - 4, 0, + 4, + 8
5	10	40	- 200, ... - 40, 0, + 40, ... + 200	8	- 16, - 8, 0, + 8, + 16
10	20	40	- 360, ... - 40, 0, + 40, ... + 360	8	- 16, - 8, 0, + 8, + 16
* 16	32	80	- 400, ... - 80, 0, + 80, ... + 400	16	- 32, - 16, 0, + 16, + 32
* 20	40	80	- 400, ... - 80, 0, + 80, ... + 400	16	- 32, - 16, 0, + 16, + 32
* 28	56	80	- 480, ... - 80, 0, + 80, ... + 480	16	- 32, - 16, 0, + 16, + 32
40	80	160	- 640, ... - 160, 0, + 160, ... + 640	32	- 64, - 32, 0, + 32, + 64
100	200	400	- 1 600, ... - 400, 0, + 400, ... + 1 600	80	- 160, - 80, 0, + 80, + 160
200	400	600	- 2 400, ... - 600, 0, + 600, ... + 2 400	120	- 240, - 120, 0, + 120, + 240

\* In exceptional cases and after agreement between customer and manufacturer, half the gauge and subgauge interval values may be used for grades 16, 20 and 28.

TABLE 4 – Applicability of ball grades


Grade	Preferred range of nominal ball diameters to which the grade is applicable			
	mm		in	
	over	incl.	over	incl.
3	—	12	—	1/2
5	—	12	—	1/2
10	—	25	—	1
16	—	25	—	1
20	—	38	—	1 1/2
28	—	38	—	1 1/2
40	—	50	—	2
100	—	all	—	all
200	—	all	—	all

ANNEX A


ILLUSTRATION OF GAUGES AND SORTING PRINCIPLES

A.1 GAUGE AND SUBGAUGE



Example 1 : Grade 3, values in microinches



Example 2 : Grade 5, values in micrometres



A.2 LOT AND GAUGE DEVIATION



## ANNEX B

## MEASUREMENT OF DEVIATION FROM SPHERICAL FORM

**B.1 METHOD USING ROUNDNESS MEASURING INSTRUMENT**

Considering the wide range of sizes of steel balls for rolling bearings, from 0,3 mm to 114,3 mm (4 1/2 in), the measurement of deviation from spherical form may be a difficult and slow process requiring special equipment. In practice it is usually measured by a numerical evaluation of the ball profile, in two or three equatorial planes at 90° to each other, as recorded on a polar chart which shows the measured profiles. The measured profile is a graphical representation of the ball's radial deviations, highly magnified, which are recorded as either the ball or a contacting stylus is precisely rotated about the ball axis. The accuracy of spindle rotation and the sensitivity of the transducer should be within 0,025  $\mu\text{m}$  ( $10^{-6}$  in). Because of the high radial magnification, some care must be taken in interpreting the polar charts, and there are several commonly used procedures for finding the radial separation of the measured profile from a perfect circle. The minimum circumscribed circle method is relatively simple and is generally satisfactory for ball profiles, as is also the assumption that two or three equatorial profiles at 90° to each other are a good indication of deviation from spherical form.

**B.2 METHOD USING VEE-BLOCK MEASUREMENTS**

Deviation from spherical form in steel balls for rolling bearings may result in equatorial profiles having two or more waves or radial deviations from a perfect circle. Measuring single diameters of a ball will give a good indication of out-of-roundness for two waves or even numbers of waves but may fail to detect or properly measure out-of-roundness having odd numbers of waves. For medium and large balls it is practical to use a Vee-block measuring device, arranged as shown in the figure, to measure the out-of-roundness of the profile having odd numbers of waves. The angle of the Vee has a pronounced influence on the indicator reading and no one angle is adequate for all waviness. The most practical Vee angles appear to be 90° and 120° and the magnification factor for the ratio of the indicator reading to the actual wave height or deviation from spherical form is shown in the table below the sketch. To determine the deviation from spherical form, divide the indicator reading by this factor.

When the number of waves in the profile is unknown, which is most usual, readings in three planes at 90° to each other should be taken on a single diameter (two-point) measuring device and on both the 90° and 120° Vee-block (three-point) measuring devices. Dividing the highest reading obtained with either Vee-block measuring device by a factor of 2 to determine the deviation from spherical form for odd numbers of waves is considered acceptable.