



**International
Standard**

ISO 3882

**Metallic and other inorganic
coatings — Review of methods of
measurement of thickness**

*Revêtements métalliques et autres revêtements inorganiques —
Revue des méthodes de mesurage de l'épaisseur*

**Fourth edition
2024-01**

STANDARDSISO.COM : Click to view the full PDF of ISO 3882:2024

STANDARDSISO.COM : Click to view the full PDF of ISO 3882:2024



COPYRIGHT PROTECTED DOCUMENT

© ISO 2024

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Overview	1
5 Non-destructive methods	2
5.1 Split beam microscope (light section) method, ISO 2128.....	2
5.2 Magnetic methods, ISO 2178 and ISO 2361.....	2
5.3 Eddy current methods, ISO 2360 and ISO 21968.....	2
5.4 X-ray spectrometric method, ISO 3497.....	3
5.5 Beta backscatter method, ISO 3543.....	3
6 Destructive methods	4
6.1 Microscopical (optical) method, ISO 1463.....	4
6.2 Fizeau multiple-beam interferometry method, ISO 3868.....	4
6.3 Profilometric method, ISO 4518.....	4
6.4 Scanning electron microscope method, ISO 9220.....	4
6.5 Dissolution methods.....	4
6.5.1 Coulometric method, ISO 2177.....	4
6.5.2 Gravimetric (strip and weigh) method, ISO 10111.....	5
6.5.3 Gravimetric (analytical) method, ISO 10111.....	5
Annex A (informative) Typical measuring application and range	6
Bibliography	9

STANDARDSISO.COM : Click to view the full PDF of ISO 3882:2024

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO document should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents. ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 107, *Metallic and other inorganic coatings*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 262, *Metallic and other inorganic coatings, including for corrosion protection and corrosion testing of metals and alloys*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This fourth edition cancels and replaces the third edition (ISO 3882:2003), which has been technically revised.

The main changes are as follows:

- editorial revisions;
- restructuring of the document;
- former Tables 2 and 3 moved to [Annex A](#);
- new subclause [6.5.1.2](#) for the STEP method;
- review of measurement uncertainties;
- phase-sensitive eddy current, as described in ISO 21968, added to measurement methods and [Tables A.1](#) and [A.2](#).

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

This document summarizes the various methods used for the measurement of coating thickness and describes their working principles. Methods of measuring coating thickness are either destructive or non-destructive (see [Table 1](#)). The information given in [Annex A, Table A.1](#) will assist in the choice of typical instrumental methods suitable for thickness measurements. For all instrumental methods, manufacturers' instructions contain useful information on the correct handling of the instruments.

The thickness ranges covered by the different methods depend on the coating materials, thickness of the coating, substrates and instruments used (see [Annex A, Table A.2](#)); for example, although X-ray spectrometry can be used to measure the thickness of a chromium coating, thicknesses of 20 μm or more cannot be measured with sufficient precision. Similarly, while magnetic methods can be used to measure the thickness of a gold coating over a magnetic steel substrate, many magnetic instruments do not have the sensitivity to measure accurately thicknesses of gold coatings less than 2 μm .

Where a referee method is required, the appropriate coating specification can contain useful information on the preferred method.

STANDARDSISO.COM : Click to view the full PDF of ISO 3882:2024

[STANDARDSISO.COM](https://standardsiso.com) : Click to view the full PDF of ISO 3882:2024

Metallic and other inorganic coatings — Review of methods of measurement of thickness

1 Scope

This document reviews methods for measuring the thickness of metallic and other inorganic coatings on both metallic and non-metallic substrates (see [Tables 1](#), [A.1](#) and [A.2](#)). It is limited to tests already specified, or to be specified, in International Standards and excludes certain tests that are used for special applications.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 2064, *Metallic and other inorganic coatings — Definitions and conventions concerning the measurement of thickness*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 2064 apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

4 Overview

[Table 1](#) summarizes the methods of measuring coating thickness that are discussed in this document.

Table 1 — Methods of measuring coating thickness

Non-destructive		Destructive	
Split beam microscope (light section)	ISO 2128 ^a	Microscopical (optical)	ISO 1463
Magnetic	ISO 2178 and ISO 2361	Fizeau multiple-beam interferometry	ISO 3868 ^b
Eddy current — amplitude-sensitive	ISO 2360	Profilometric (stylus and optical)	ISO 4518 ^b
— phase-sensitive	ISO 21968		
X-ray spectrometric	ISO 3497	Scanning electron microscope	ISO 9220
Beta backscatter	ISO 3543	Dissolution methods:	
		Gravimetric strip and weigh method and gravimetric analytical method	ISO 10111
		Coulometric method	ISO 2177
		STEP method	ISO 16866
^a Can be destructive in some applications.			
^b Can be non-destructive in some applications.			

5 Non-destructive methods

5.1 Split beam microscope (light section) method, ISO 2128

This equipment, originally designed for the measurement of surface roughness, is used for measuring the thickness of transparent and translucent coatings, in particular anodic oxide coatings on aluminium. A light beam is projected on to the surface at an angle of 45°. Part of the beam is reflected from the surface of the coating and the rest penetrates the coating and is reflected from the coating-metal substrate interface. The distance that separates the two images observed in the eyepiece of the microscope is proportional to the thickness of the coating and can be measured by means of a Vernier screw that controls a calibrated graticule. The method can be used where sufficient light is reflected from the coating-metal substrate interface to give a clear image in the microscope. For transparent or translucent coatings, such as anodic oxide films, this method is non-destructive.

For measuring the thickness of opaque coatings, a small area of the coating is removed; in this application, the method is destructive. The step between the surface of the coating and the basis metal produces a deflection of the light beam that gives an absolute measure of the coating thickness.

The method is not suitable for hard anodic coatings or for coatings that are very thin (less than 2 µm thick), very thick (greater than 100 µm thick) or rough. It is not suitable for coatings on heavily shot-blasted surfaces. Other methods, such as eddy current (see ISO 2360), interference microscope (see ISO 3868) and microscopical (see ISO 1463), can be applicable for thickness measurement where the split beam microscope method cannot be used.

The method is best suited to small parts because of the ease with which they can be set up on the microscope stage.

The measurement uncertainty of the method is usually less than 10 % of the thickness.

5.2 Magnetic methods, ISO 2178 and ISO 2361

Instruments for these methods measure either the magnetic attraction between a magnet and the basis metal, as influenced by the presence of the coating (see ISO 2361), or the reluctance of a magnetic flux path passing through the coating and the basis metal (see ISO 2178).

All instruments using magnetic methods are sensitive to the magnetic condition and properties of the test specimen, surface curvature, surface cleanliness, surface roughness and thickness of the basis metal and of the coating. Additionally, different materials can look the same but have different permeability, μ_r . Usually, this effect is determined by calibration at the test specimen.

These methods are limited in practice to non-magnetic coatings on a magnetic substrate (see ISO 2178) and to electroplated nickel coatings on a magnetic or non-magnetic substrate (see ISO 2361).

The measurement uncertainty of the method is less than 10 % of the thickness or 1,5 µm, whichever is the greater.

5.3 Eddy current methods, ISO 2360 and ISO 21968

ISO 2360 describes an amplitude-sensitive method and is based on differences in electrical conductivity between coatings and substrates. The method is used primarily for measuring the thickness of non-conductive coatings on non-magnetic metals and of single layer metal coatings on non-conductors. If this method is used for measuring thicknesses of metallic coatings on metallic substrates, great care is necessary if acceptable results are to be obtained. In the latter case, the phase-sensitive method as described in ISO 21968 is more suitable. The phase-sensitive eddy current method is also more suitable for metallic coatings on non-conductive base materials than the amplitude-sensitive method. Furthermore, within certain limits it can deal with non-magnetic metallic coatings on magnetic base materials and with magnetic coatings on non-conductive or conductive base materials.

The method is ideal for rapid determination of anodic coating thickness measurements on aluminium and its alloys and is well suited for use in field measurements. For autocatalytic nickel coatings, this method

gives erratic measurements due to variations in conductivity of the coatings with changes in phosphorous content.

The measurement uncertainty of the method is usually less than 10 % of the thickness or 0,5 μm , whichever is the greater.

5.4 X-ray spectrometric method, ISO 3497

This method uses emission and absorption X-ray spectrometry for determining the mass per unit area of metallic coatings, which, provided that the test specimen is of uniform density, is directly proportional to the thickness. In principle, the method can also determine the composition of an alloy coating. Within its physical limitations, it can also analyse superimposed coatings.

X-rays are made to irradiate a fixed area of the coated surface, and the intensity of the secondary radiation emitted by the coating or by the substrate and attenuated by the coating is measured. A correlation exists between the intensity of the X-rays and the coating thickness. This is either established using calibration standards or calculated by the so-called fundamental parameter method and calibration standards are only needed to ensure traceability and to adjust in some cases the calculated characteristic.

This method's accuracy is reduced:

- when constituents of the coating are present in the basis metal, and vice versa;
- when more than two coatings are superimposed;
- when the chemical composition of a coating varies from that of the calibration standard.

The method is not applicable above a certain thickness that depends on the atomic numbers and densities of the materials involved. It also needs a minimum mass per area to deliver results with acceptably low uncertainty.

For autocatalytic nickel coatings, this method is only recommended for deposits in the as-plated condition. The phosphorus content of the coating should be known in order to enable calculation of the thickness of the deposit. However, instruments working with an evacuated chamber, as well as instruments having an SDD detector and working with short working distances and large collimators or capillary optics, can determine the phosphorous content and measure the thickness of the coating in two consecutive measurements, which run in practice quasi as one measurement, using different acceleration voltages for both tasks. As the matrix effect due to the distribution of phosphorus in layers of the coating also affects the measurement uncertainty, the calibration standards shall be made under the same conditions as those of the production process.

Instruments capable of measuring the thickness of a coating with an uncertainty of less than 10 % of the thickness are commercially available.

5.5 Beta backscatter method, ISO 3543

This method uses radio isotopes that emit beta rays and detectors that measure the intensity of those beta rays backscattered by the test specimen. The intensity of the backscattered beta rays will be between two values, namely the backscatter intensity of the coating and that of the basis metal. The measurement is only possible if the atomic number of the coating material is sufficiently different from that of the substrate. The instrument is calibrated using calibration standards having the same coating and substrate as the specimen to be measured. The measured intensity of the beta rays that are backscattered by the test specimen is used to calculate the mass per unit area of the coating. If the test specimen has a uniform density, this intensity of the backscattered rays is directly proportional to the thickness.

This method can be used for both thin and heavy coatings, the minimum and maximum measurable coating thickness being a function of the coating material density.

A measurement uncertainty of less than 10 % of the measuring values over a wide range of coating thickness can be achieved using this method. Depending on the measuring time, the precision of the measuring values can be increased.

6 Destructive methods

6.1 Microscopical (optical) method, ISO 1463

In this method, coating thickness is measured on a magnified image of a cross-section of the coating using an optical microscope.

The measurement uncertainty of this method is less than 10 % of the thickness subject to a minimum error of 0,8 μm . However, with careful preparation of the specimen and the application of suitable instruments, this method is capable of providing a measurement uncertainty of 0,4 μm under reproducible conditions.

6.2 Fizeau multiple-beam interferometry method, ISO 3868

By completely dissolving a small area of the coating without attacking the substrate, or by masking an area before plating, a step is formed from the surface of the coating to that of its substrate. The height of this step is measured with a multiple-beam interferometer.

This method is particularly useful for measuring the thickness of very thin opaque metal coatings. It is not suitable for vitreous enamel coatings. This method is essentially a laboratory technique and is useful for measuring the thickness of coatings on standards used for calibrating non-destructive test instruments, such as beta backscatter and X-ray spectrometry instruments, especially for standards with rather thin (sub-micron) coatings.

This method provides an absolute measure of the microscopic vertical surface variation ranging from 0,002 μm to 0,2 μm . The measurement uncertainty is $\pm 0,001 \mu\text{m}$.

6.3 Profilometric method, ISO 4518

By masking during the coating process or by dissolving a small area of the coating without attacking the substrate, a step is formed from the surface of the substrate to that of the coating. A stylus is drawn across this step and its height is determined by electronically measuring and recording the motion of the stylus. Alternatively, optical profilometers such as confocal microscopes or interference microscopes can be used to measure the step height.

Available commercial instruments allow measurements to be made over the range 0,01 mm to 0,000 02 mm (20 nm).

The measurement uncertainty of this method is less than 10 % of the thickness.

6.4 Scanning electron microscope method, ISO 9220

In this method, coating thickness is measured on a magnified image of a cross-section of the coating using a scanning electron microscope. The measurement is made on a calibrated digital image provided by the SEM's software.

The measurement uncertainty is less than 10 % of the thickness or 0,1 μm , whichever is the greater.

6.5 Dissolution methods

6.5.1 Coulometric method, ISO 2177

6.5.1.1 General

The mass per unit area of a metallic coating is determined by measuring the quantity of electric charge consumed in dissolving the coating from a precisely defined area when the sample is connected as anode in a suitable electrolyte under suitable conditions. Provided that the coating of the test specimen has a uniform density thereof, the mass per unit area is directly proportional to the thickness. The method works according to Faraday's law.

The change in potential that occurs when the underlying material is reached serves to indicate the end-point of the dissolution. The method is applicable to metallic coatings on both metallic and non-metallic substrates.

The measurement uncertainty of the method is usually less than 10 % of the thickness.

6.5.1.2 STEP method, ISO 16866

A special variant of coulometry is the simultaneous thickness and electrochemical potential determination (STEP) test. The basic physical principle is the same as described in [6.5.1.1](#). It is used if there are several Ni layers on top of each other. The special feature of the STEP method is that an additional silver electrode is used. This electrode is sensitive enough to detect the small potential difference between the individual nickel layers.

The layer thickness is determined manually from the course of the electrode potential.

6.5.2 Gravimetric (strip and weigh) method, ISO 10111

In this method, the coating mass is determined by weighing the sample before and after dissolving the coating without attacking the substrate or by weighing the coating after dissolving the substrate without attack of the coating. The coating shall be of uniform density.

The mass of the coating divided by the density and the area of the coating gives the average coating thickness.

The limitation of this method is that it does not indicate the presence of bare spots or sites with thicknesses lower than the specified minimum in the measuring areas. Additionally, the single value obtained from each measuring area is the mean thickness over that area; there can be no further mathematical analysis of this single value, for example for statistical process control purposes.

The measurement uncertainty of this method is less than 5 % of the thickness over a wide range of thicknesses.

6.5.3 Gravimetric (analytical) method, ISO 10111

In this method, the coating mass is determined by dissolving the coating, with or without dissolving the substrate material, and determining the quantity of coating metal by chemical analysis.

The mass of the coating divided by the density and the area of the coating gives the average coating thickness.

The limitations of the method are as follows:

- it is not reliable if the same metal is present in the coating and in the substrate or in the basis metal;
- it does not indicate the presence of bare spots or sites with thicknesses lower than the specified minimum in the measuring areas;
- the single value obtained from each measuring area is the mean thickness over that area; there can be no further mathematical analysis of this single value, for example for statistical process control purposes.

The measurement uncertainty of this method is normally less than 5 % of the thickness over a wide range of thicknesses.

Annex A
(informative)

Typical measuring application and range

[Table A.1](#) provides an overview of the applicability of typical instrumental methods for coating thickness measurement. It provides general guidance only. The applicability of a method can be a function of an individual instrument and of other variables such as coating and substrate thickness. For details of the methods, reference should be made to the appropriate clauses of this document as well as to the relevant International Standard for each method of measurement. Where proprietary instruments are used, special care should be exercised to ensure that specific manufacturer's instructions and procedures are followed, particularly in matters concerning calibration.

STANDARDSISO.COM : Click to view the full PDF of ISO 3882:2024