

---

---

**Road vehicles — Safety glazing materials —  
Test methods for resistance to radiation,  
high temperature, humidity, fire and  
simulated weathering**

*Véhicules routiers — Vitrages de sécurité — Méthodes d'essai de  
résistance au rayonnement, aux températures élevées, à l'humidité, au feu  
et aux conditions climatiques simulées*



## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 3.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 3917 was prepared by Technical Committee ISO/TC 22, *Road vehicles*, Subcommittee SC 11, *Safety glazing materials*.

This third edition cancels and replaces the second edition (ISO 3917:1992), which has been technically revised.

STANDARDSISO.COM : Click to view the full PDF of ISO 3917:1999

© ISO 1999

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization  
Case postale 56 • CH-1211 Genève 20 • Switzerland  
Internet iso@iso.ch

Printed in Switzerland

# Road vehicles — Safety glazing materials — Test methods for resistance to radiation, high temperature, humidity, fire and simulated weathering

## 1 Scope

This International Standard specifies test methods for resistance to radiation, high temperature, humidity, fire and simulated weathering, relating to the safety requirements for all safety glazing materials in a road vehicle, whatever the type of glass or the material of which they are composed.

## 2 Normative references

The following normative documents contain provisions which, through reference in this text, constitute provisions of this International Standard. For dated references, subsequent amendments to, or revisions of, any of these publications do not apply. However, parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the normative documents indicated below. For undated references, the latest edition of the normative document referred to applies. Members of ISO and IEC maintain registers of currently valid International Standards.

ISO 3536:1999, *Road vehicles — Safety glazing materials — Vocabulary.*

ISO 3537:1999, *Road vehicles — Safety glazing materials — Mechanical tests.*

ISO 3538:1997, *Road vehicles — Safety glazing materials — Test methods for optical properties.*

ISO 3795:1989, *Road vehicles, and tractors and machinery for agriculture and forestry — Determination of burning behaviour of interior materials.*

ISO 4892-1:1999, *Plastics — Methods of exposure to laboratory light sources — Part 1: General guidance.*

ISO 4892-2:1994, *Plastics — Methods of exposure to laboratory light sources — Part 2: Xenon-arc sources.*

ISO 4892-4:1994, *Plastics — Methods of exposure to laboratory light sources — Part 4: Open-flame carbon-arc lamp.*

ISO 15082:1999, *Road vehicles — Tests for rigid plastic safety glazing materials.*

## 3 Terms and definitions

For the purposes of this International Standard, the terms and definitions given in ISO 3536 apply.

## 4 Test conditions

Unless otherwise specified, the test shall be carried out under the following conditions:

- ambient temperature:  $20\text{ °C} \pm 5\text{ °C}$ ;
- atmospheric pressure: 86 kPa to 106 kPa (860 mbar to 1 060 mbar);
- relative humidity:  $(60 \pm 20)\%$ .

## 5 Application of test

For certain types of safety glazing material, it is not necessary to carry out all the tests specified in this International Standard when the results, according to the purpose of testing, can be predicted with certainty from knowledge of the properties of the safety glazing material concerned.

## 6 Radiation test

### 6.1 Principle

Determination of whether exposure to radiation over an extended period of time produces any appreciable decrease in regular luminous transmittance or any pronounced discoloration of the safety glazing material.

### 6.2 Apparatus

**6.2.1 Radiation source**, consisting of a medium pressure mercury arc lamp with a tubular quartz bulb of ozone-free type; the bulb axis shall be vertical. The nominal dimensions of the lamp shall be 360 mm in length by 9,5 mm in diameter. The arc length shall be  $300\text{ mm} \pm 14\text{ mm}$ . The lamp shall be operated at  $750\text{ W} \pm 50\text{ W}$ .

Any other source of radiation which produces the same effect as the lamp specified above may be used. To check that the effects of another source are the same, a comparison shall be made by measuring the amount of energy emitted within a wavelength range of 300 nm to 450 nm, all other wavelengths being removed by the use of suitable filters. The alternative source shall then be used with these filters.

In the case of safety glazing material for which there is no satisfactory correlation between this test and the conditions of use, it will be necessary to review the test conditions.

**6.2.2 Power supply transformer and capacitor**, which shall be capable of supplying to the lamp (6.2.1) a starting peak voltage of 1 100 V minimum and an operating voltage of  $500\text{ V} \pm 50\text{ V}$ .

**6.2.3 Device for mounting and rotating the test specimens** at 1 r/min to 5 r/min about the centrally located radiation source in order to ensure even exposure.

### 6.3 Test specimen

The size of the test specimens shall be 76 mm × 300 mm.

### 6.4 Procedure

Measure the regular luminous transmittance, determined according to ISO 3538, of three test specimens before exposure. Protect a portion of each test specimen from the radiation, and then position the test specimen in the test apparatus 230 mm from, and with its 300 mm dimension parallel to, the lamp axis. Maintain the temperature of the test specimens at  $45\text{ °C} \pm 5\text{ °C}$  throughout the test.

The surface of each test specimen which would represent the outside face of the safety glazing material when mounted on the vehicle shall face the lamp. For the type of lamp specified in 6.2.1, the exposure time shall be 100 h.

After exposure, measure the luminous transmittance again on each test specimen in the exposed area.

## 6.5 Expression of results

The results of the luminous transmission measurement of the exposed test specimen shall be compared with the values obtained for unexposed test specimens of the same material. The deviation shall be expressed as a percentage.

Changes in colour shall be evaluated:

- either by examining the test specimens placed upon a white background and comparing the exposed area with the area which was protected from the radiation;
- or by measuring the trichromatic coordinates of the test specimen before and after ageing and by calculating the difference between two colours according to the CIE<sup>1)</sup> prescriptions.

## 7 High temperature test

### 7.1 Principle

Determination of whether the safety glazing material will withstand exposure to high temperatures over an extended period of time without its appearance becoming substantially altered.

### 7.2 Procedure

Heat one or more test specimens of at least 300 mm × 300 mm to 100 °C  $\pm$  2 °C. Maintain this temperature for a period of 2 h, then allow the test specimen(s) to cool to room temperature.

If the safety glazing material has both external surfaces of inorganic material, the test may be carried out by immersing the test specimen vertically in water boiling at 100 °C  $\pm$  2 °C for the specified period of time, care being taken to avoid undue thermal shock.

If specimens are cut from windscreens, one edge of the test specimen shall be part of an edge of the windscreen.

### 7.3 Expression of results

The resistance of the safety glazing material to high temperatures shall be evaluated with reference to bubbles or other defects produced in the test specimen by the test described in 7.2.

Any defects within 15 mm of an uncut edge, 25 mm from a cut edge or within 10 mm of any cracks which may develop shall be disregarded.

Any test specimen in which cracks develop to an extent which might confuse the results shall be discarded and another test specimen shall be tested in its place.

## 8 Humidity test

### 8.1 Principle

Determination of whether the safety glazing material will successfully withstand the effects of humidity in the atmosphere over an extended period of time.

### 8.2 Procedure

Keep one or more test specimens of at least 300 mm × 300 mm vertically for two weeks in a closed container in which the temperature is maintained at 50 °C  $\pm$  2 °C and the relative humidity at (95  $\pm$  4) %.

---

<sup>1)</sup> International Commission on Illumination

These test conditions should exclude any condensation on test specimens.

In the event that several test specimens are tested at the same time, adequate spacing shall be provided between the test specimens.

Precautions shall be taken to prevent condensate from the walls and ceiling of the test chamber from falling on the test specimens.

If the test specimens are cut from windscreens, one edge of the test specimen shall be part of an edge of the windscreen.

### 8.3 Expression of results

The resistance to humidity shall be evaluated visually by reference to change in the appearance of the safety glazing material after testing, i.e.:

- separation of materials;
- loss of transparency according to ISO 3538.

A waiting period of 48 h after exposure prior to evaluation is permitted, if necessary.

The changes shall be assessed over the whole test specimen, except within 10 mm of the uncut edges or within 15 mm of the cut edges.

## 9 Burning behaviour test

### 9.1 Principle

Determination of the behaviour of the safety glazing material under the action of a small flame.

The method used shall be that specified in ISO 3795. Test plastic safety glazing materials according to ISO 15082.

### 9.2 Expression of results

The burning behaviour of the safety glazing material shall be evaluated by reference to the burning rate.

## 10 Resistance to simulated weathering

### 10.1 Principle

Determination of whether safety glazing materials, of which at least one surface is plastic, will successfully withstand exposure to simulated weathering conditions.

### 10.2 Exposure apparatus

#### 10.2.1 Light sources

Two types of light sources are included in this International Standard, the long arc xenon and open flame carbon arc lamps. Either light source may be used for this test. Because of spectral differences between the xenon arc and open flame carbon arc, however, test results from the two light sources may or may not correlate, depending on the materials under test.

### 10.2.2 Long arc xenon lamp

The exposure apparatus<sup>2)</sup> shall use a long arc xenon lamp as the source of irradiation, which shall comply with ISO 4892-2:1994, 4.1.2, method A (artificial weathering).

The long arc xenon lamp is advantageous in that it can, when correctly filtered and maintained, yield a spectrum most closely approximating that of natural sunlight. To this end, the quartz xenon burner tube shall be fitted with suitable borosilicate glass optical filter(s)<sup>3)</sup>. The xenon lamps employed shall be operated from a suitable 50 Hz or 60 Hz power supply through suitable reactance transformers and electrical equipment.

The exposure apparatus shall include equipment necessary for measuring and/or controlling the following:

- a) irradiance;
- b) black panel temperature;
- c) water spray;
- d) operating schedule or cycle.

The exposure apparatus shall be made from inert materials which do not contaminate the water employed in the test.

Irradiance shall be measured at the test specimen surface and shall be controlled according to the recommendations of the exposure apparatus manufacturer.

Total ultraviolet<sup>4)</sup> radiance exposure, in joules per square metre, shall be measured or computed and shall be considered the primary measure of test specimen exposure.

### 10.2.3 Open flame carbon arc lamp

The exposure apparatus<sup>5)</sup> shall use an open flame carbon arc lamp as the source of irradiation, which shall comply with ISO 4892-4:1994, 4.1, Table 1, Type 1 filter.

The open flame carbon arc yields a spectrum which is substantially different from natural sunlight. In that portion of the ultraviolet and visible spectrum, between 350 nm and 450 nm, concentration of energy in the cyanogen bands causes the open flame carbon arc to exceed greatly the spectral irradiance of natural sunlight. Except for this region, the open flame carbon arc has a spectral power distribution approximating natural sunlight.

The open flame carbon arc lamps employed shall be operated at  $50\text{ V} \pm 2\text{ V}$  of discharge voltage and  $60\text{ A} \pm 2\text{ A}$  of discharge current. They shall consist of carbon electrodes, of 22 h or 60 h in continuous illumination life.

Total exposure time shall be the primary measure of test specimen exposure. Measurement or computation of total ultraviolet radiance exposure is optional.

## 10.3 Test specimens

The dimensions of the test specimen shall normally be those specified in the appropriate test method for the property or properties to be measured after exposure.

---

<sup>2)</sup> Such as Atlas Ci Series, Heraeus Xenotest Series, or Suga WWL-X Series. These are tradenames. This information is given for the convenience of users of this International Standard and does not constitute an endorsement by ISO of the product named. Equivalent products may be used if they can be shown to lead to the same results.

<sup>3)</sup> Borosilicate glass filters such as Corning 7740, Corning 7746 Pyrex, Atlas Type S, and Atlas Suprex have been found satisfactory. These are tradenames [see footnote 6)].

<sup>4)</sup> Total ultraviolet is considered to be all radiation of wavelength less than 400 nm.

<sup>5)</sup> Such as Suga WEL-SUN-Series or Atlas XW Series. These are tradenames [see footnote 6)].

The number of test specimens for each test condition or exposure stage shall be determined, in addition to those required for visual evaluations as specified in 10.5 by the number required by the test methods.

It is recommended that visual evaluations be conducted on the largest test specimens tested.

## 10.4 Procedure

**10.4.1** Measure, in accordance with ISO 3538, the luminous transmission of the test specimen(s) to be exposed. Measure, in accordance with ISO 3537, the resistance to abrasion of the plastic surface(s) of the control specimen(s). That face of each test specimen which would represent the surface glazed to the exterior of the road vehicle shall face the lamp.

Other exposure conditions shall be as specified in 10.4.2 to 10.4.11.

**10.4.2** In accordance with ISO 4892, the irradiance shall not vary more than  $\pm 10\%$  over the whole test specimen area.

**10.4.3** At appropriate intervals, clean lamp filters by washing with detergent and water. Xenon arc filters shall be replaced according to the recommendations of the equipment manufacturer. Open flame carbon arc filters should be replaced after 2 000 h of use, or when pronounced discoloration or milkiness develops, whichever occurs first. It is recommended that two of the filters be replaced at each 500 h interval.

**10.4.4** The temperature within the exposure apparatus during the dry portion of the cycle shall be controlled by circulation of sufficient air to maintain a constant black panel temperature.

In the xenon arc exposure apparatus, this temperature shall be  $70\text{ °C} \pm 3\text{ °C}$  as indicated by a black standard thermometer <sup>6)</sup> or equivalent. In the open flame carbon arc exposure apparatus, this temperature shall be  $63\text{ °C} \pm 3\text{ °C}$  as indicated by a black panel thermometer <sup>7)</sup> or equivalent. The black panel or black standard thermometer shall be mounted in the test specimen rack and readings shall be taken at the point where maximum heat is developed due to light exposure.

**10.4.5** The relative humidity within the exposure apparatus shall be controlled at  $(50 \pm 5)\%$  during the dry portions of the cycle.

**10.4.6** The deionized water used in the spray cycle shall contain less than  $1\text{ }\mu\text{g/g}$  silicon dioxide solids and shall leave no permanent deposit or residue on the test specimens which would interfere with subsequent measurements.

**10.4.7** The alkalinity (pH) of the water shall be between 6,0 and 8,0 and the conductivity shall be less than  $5\text{ }\mu\text{S}$ .

**10.4.8** The temperature of the water in the line where it enters the exposure apparatus shall be the ambient water temperature.

**10.4.9** The water shall strike the test specimens in the form of a fine spray in sufficient volume to wet the test specimens uniformly, immediately upon impact.

Water spray shall be directed only against the test specimen surface facing the light source. No recirculation of the spray water or immersion of the test specimens in the water is permitted.

**10.4.10** The test specimens shall be rotated about the arc in order to provide uniform distribution of the light. All positions in the exposure apparatus shall be filled with test specimens or surrogates to ensure that a uniform temperature distribution is maintained. Test specimens shall be held in frames with backs exposed to the cabinet environment. However, reflections from cabinet walls shall not be permitted to strike the back surface of specimens.

---

<sup>6)</sup> The black standard thermometer is described in ISO 4892-1:1999, 5.2.2.1.

<sup>7)</sup> The black panel thermometer is described in ISO 4892-1:1999, 5.2.2.2.