

INTERNATIONAL
STANDARD

ISO
4045

IULTCS/IUC 11

Third edition
2018-05

**Leather — Chemical tests —
Determination of pH and difference
figure**

*Cuir — Essais chimiques — Détermination du pH et de l'indice de
différence*

STANDARDSISO.COM : Click to view the full PDF of ISO 4045:2018



Reference numbers
ISO 4045:2018(E)
IULTCS/IUC 11:2018(E)

© ISO 2018

STANDARDSISO.COM : Click to view the full PDF of ISO 4045:2018



COPYRIGHT PROTECTED DOCUMENT

© ISO 2018

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	1
5 Reagents	1
6 Apparatus	2
7 Sampling and preparation of the samples	2
8 Procedure	2
8.1 Preparation of the extract	2
8.2 Calibration of the pH meter	3
8.3 Determination of the pH value	3
8.4 Determination of the difference figure	3
9 Test report	3

STANDARDSISO.COM : Click to view the full PDF of ISO 4045:2018

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html

This document was prepared by the Chemical Tests Commission of the International Union of Leather Technologists and Chemists Societies (IUC Commission, IULTCS) in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 289, *Leather*, the secretariat of which is held by UNI, in accordance with the agreement on technical cooperation between ISO and CEN (Vienna Agreement).

It is based on IUC 11 published in *J. Soc. Leather Tech. Chem.*, **49**, pp. 25–29, 1965, and declared an official method of the IULTCS in 1965.

IULTCS, originally formed in 1897, is a world-wide organization of professional leather societies to further the advancement of leather science and technology. IULTCS has three Commissions, which are responsible for establishing international methods for the sampling and testing of leather. ISO recognizes IULTCS as an international standardizing body for the preparation of test methods for leather.

This third edition cancels and replaces the second edition (ISO 4045:2008), which has been technically revised as follows:

- change in title to include “and difference figure”;
- [5.1](#) and [6.1](#) have been revised;
- [Clause 7](#) has been revised: two samples are only prepared when there is enough leather;
- [8.1](#) has been revised to more clearly explain the procedure;
- [8.2](#) has been added (previously part of the next clause);
- [8.3](#) and [8.4](#) (previously [8.2](#) and [8.3](#)) have been revised and the previous title of [8.4](#) deleted;
- [Clause 9](#) b) and d) have been revised.

Leather — Chemical tests — Determination of pH and difference figure

1 Scope

This document specifies a method for determining the pH value and the difference figure of an aqueous leather extract. It is applicable to all types of leather.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 2418, *Leather — Chemical, physical and mechanical and fastness tests — Sampling location*

ISO 3696, *Water for analytical laboratory use — Specification and test methods*

ISO 4044, *Leather — Chemical tests — Preparation of chemical test samples*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.1 difference figure

difference between the pH value of a solution and that of its tenfold dilution

Note 1 to entry: The difference figure is a measure of the strength of acids and bases and can never exceed a value of 1. The difference figure amounts to 0,70 to 1,00 when a solution contains a free strong acid (or a free strong base). The ionization of weak acids and bases increases with greater dilution, and therefore the difference figure can only act as a criterion for the presence of free strong acid or base in aqueous extracts with pH values below 4 or above 10.

4 Principle

Preparation of an aqueous extract from a test portion of the leather and measurement of the pH of the extract, using a pH meter. In cases where the pH value obtained is below 4,00 or above 10,00, the pH value of a tenfold dilution of the aqueous extract is also determined.

5 Reagents

5.1 **Water**, minimum grade 3 in accordance with ISO 3696.

5.2 Buffer solution, for calibrating the electrode system.

It is preferable to purchase a commercially available standard buffer solution for measurement as recommended by the pH meter manufacturer. The length of time for which buffer solutions will keep depends on their composition and the method of use. Control of the accuracy of the buffer solution is therefore indispensable. Used buffer solution shall be discarded.

6 Apparatus

6.1 Suitable shaker, rotating shaker with a frequency of (50 ± 10) r/min or other suitable shaker after validation.

6.2 pH meter, with glass electrode, with a measuring range of 0 pH units to 14 pH units, graduated in 0,01 pH units. The electrode system shall be calibrated prior to each series of measurements against the buffer solution (5.2).

Aqueous extracts of heavily fat-liquored leather may in time make the electrode membrane dirty. In such cases, the membrane shall be lightly rubbed with a piece of cotton wool dipped in acetone or the electrode should be suspended in a 1:1 water:acetone mixture. After cleaning, the membrane should again be thoroughly soaked in water.

6.3 Analytical balance, capable of weighing to an accuracy of 0,01 g.

6.4 Wide mouthed flask, with leak-proof stopper, capacity 250 ml.

6.5 Measuring cylinder, capacity 100 ml, graduated in 1 ml divisions.

6.6 Volumetric flask, capacity 100 ml.

6.7 Pipette, capacity 10 ml.

7 Sampling and preparation of the samples

Sample in accordance with ISO 2418. If sampling in accordance with ISO 2418 is not possible, then details about sampling shall be given in the test report. Prepare the leather sample in accordance with ISO 4044.

Samples should be analysed in duplicate, if it is possible.

8 Procedure

8.1 Preparation of the extract

Weigh $(5,0 \pm 0,1)$ g of the test sample into the wide-mouthed flask (6.4) and using the measuring cylinder (6.5) add (100 ± 1) ml of water (5.1) at (20 ± 2) °C. Shake well by hand for about 30 s so that the test portion is uniformly wet. Shake mechanically in the shaker (6.1) for between 6,0 h and 6,5 h. Allow the extract to settle. Decant and take the liquid phase for pH measurement, ensuring that there are no suspended solids.

If difficulty is experienced in decanting the extract from the slurry, it may be strained through a clean, dry, non-absorbent mesh (for example, nylon cloth or a coarse sintered glass filter) or centrifuged.