
International Standard



4074/3

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

**Rubber condoms —
Part 3 : Determination of width**

*Préservatifs masculins en caoutchouc —
Partie 3 : Détermination de la largeur*

First edition — 1980-07-01

STANDARDSISO.COM : Click to view the full PDF of ISO 4074-3:1980

UDC 615.477.86

Ref. No. ISO 4074/3-1980 (E)

Descriptors : rubber products, contraceptives, dimensional measurement, width.

Price based on 1 page

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards institutes (ISO member bodies). The work of developing International Standards is carried out through ISO technical committees. Every member body interested in a subject for which a technical committee has been set up has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work.

Draft International Standards adopted by the technical committees are circulated to the member bodies for approval before their acceptance as International Standards by the ISO Council.

International Standard ISO 4074/3 was developed by Technical Committee ISO/TC 157, *Mechanical contraceptives*, and was circulated to the member bodies in January 1979.

It has been approved by the member bodies of the following countries :

Canada	Mexico	Thailand
Czechoslovakia	Netherlands	Turkey
Denmark	Poland	United Kingdom
France	Romania	USA
India	South Africa, Rep. of	USSR
Korea, Rep. of	Sweden	

No member body expressed disapproval of the document.

STANDARDSISO.COM: Click to view the full PDF of ISO 4074-3:1980

Rubber condoms — Part 3 : Determination of width

1 Scope and field of application

This part of ISO 4074 specifies a method for the determination of the width of rubber condoms.

2 Principle

Free hanging of the unrolled condom over the edge of a ruler and observation of its width.

3 Equipment

A steel ruler, with a scale divided into millimetres.

4 Procedure

4.1 Unroll the condom and lay it flat over the edge of the ruler, allowing it to hang freely.

4.2 Measure to the nearest millimetre the width of the condom at any point up to 85 mm from the open end. For condoms having a bulbous portion near the closed end measure also the width of this portion.

5 Test report

The test report shall include the following particulars :

- a) the identification of the sample;
- b) the width noted in accordance with 4.2;
- c) the date of testing.