
**Glass-reinforced thermosetting
plastics (GRP) pipes — Determination
of the apparent axial long-term
modulus of pipes subject to beam
bending**

*Tubes en plastiques thermodurcissables renforcés de verre (PRV) —
Détermination du module axial apparent à long terme de tubes
soumis à la flexion de poutre*

STANDARDSISO.COM : Click to view the full PDF file ISO 4152:2021



STANDARDSISO.COM : Click to view the full PDF of ISO 4152:2021



COPYRIGHT PROTECTED DOCUMENT

© ISO 2021

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword.....	iv
Introduction.....	v
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	1
4 Principle.....	1
5 Apparatus.....	1
6 Test piece.....	3
7 Number of test pieces.....	3
8 Determination of the dimensions of the test piece.....	3
8.1 Outside diameter, d_o	3
8.2 Mean wall thickness, e	3
8.3 Inner diameter, d_i	4
8.4 Length.....	4
9 Conditioning.....	4
10 Procedure.....	4
10.1 Preparation of test piece.....	4
10.2 Preparation of supporting frame.....	4
10.3 Mounting of test piece.....	4
10.4 Mounting of displacement meters and zero readings.....	5
10.5 Filling of test sample.....	5
10.6 Monitoring deflection.....	5
11 Calculating creep modulus.....	5
12 Test report.....	6
Bibliography.....	7

STANDARDSISO.COM : Click to view the full PDF of ISO 4152:2021

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 138, *Plastics pipes, fittings and valves for the transport of fluids*, Subcommittee SC 6, *Reinforced plastics pipes and fittings for all applications*.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

The apparent axial long-term modulus of pipes subject to beam bending of pipes manufactured according to ISO 23856 is required for designing pipe systems installed aboveground in accordance with ISO/TS 10986.

The modulus is used to calculate deflections and rotations of pipes installed on two or more supports.

STANDARDSISO.COM : Click to view the full PDF of ISO 4152:2021

[STANDARDSISO.COM](https://standardsiso.com) : Click to view the full PDF of ISO 4152:2021

Glass-reinforced thermosetting plastics (GRP) pipes — Determination of the apparent axial long-term modulus of pipes subject to beam bending

1 Scope

This document specifies a method for determining the apparent axial long-term modulus of pipes subject to beam bending deflection between vertically supported end-couplers, which allow rotation of the pipe relative to the couplers.

In conjunction with ISO 10928, this document expresses the results of the test as an apparent axial long-term modulus for use in the calculation of mid-span beam deflection and end rotation of GRP pipes as specified in ISO/TS 10986.

Test conditions and requirements are specified in the referring standard.

For practical reasons, the test method is not suited for diameters greater than DN 600.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 10928:2016, *Plastics piping systems — Glass-reinforced thermosetting plastics (GRP) pipes and fittings — Methods for regression analysis and their use*

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

4 Principle

A pipe sample is mounted on supports at the ends and filled with water. The deflection is measured both at mid-span and at the supports. The deflections measured at the supports is subtracted from the deflection measured at the centre to obtain a flexural deflection to be used to compute the modulus. The displacements are measured at pipe springlines to minimize errors caused by pipe cross-section deformation.

The deflection is monitored over time, and the apparent axial long-term modulus computed. The 50-year modulus is computed from the extrapolated deflection after 10 000 h of testing.

5 Apparatus

5.1 Supporting frame, comprising two parallel steel beams, four floor supports, and two circular end closures (see [Figure 1](#) for typical test set-up). The beams shall be sufficiently stiff such that no visible


deformation shall occur during the test. Each section shall have a length equal to the length of the test piece plus at least 100 mm.

The end closures shall simulate a realistic coupling with rubber seals and shall remain leak tight during the duration of the test. One of the end closures shall have fittings for filling the pipe and both end closures shall be fitted with air bleeding holes. The end closures shall be welded or bolted to the steel beams, such that no rotation of the end closures occurs during the test (see Figure 2).

5.2 Bracket supports, to be glued to the test sample at spring-line. The brackets serve as contact points for the displacement meters (5.4). A total of six brackets are required for the test.

5.3 Dimensional measuring devices, to measure the dimensions of the test piece, i.e. length, diameter, and wall thickness. Each device shall be calibrated to an accuracy of within $\pm 1\%$.


5.4 Displacement measuring devices, with continuous monitoring and a suitable data acquisition system. The whole system shall be calibrated to an accuracy of $\pm 1\%$. Six devices are required for the test.



Key

- | | | | |
|---|-------------------------|---|-----------------|
| 1 | end closure | 4 | floor support |
| 2 | displacement transducer | 5 | test piece |
| 3 | steel beam | 6 | bracket support |

Figure 1 — Typical test set-up along the pipe

**Key**

- | | | | |
|---|------------------|---|-----------------------|
| 1 | end closure | 5 | air bleeding fittings |
| 2 | steel beam | 6 | rubber seal |
| 3 | floor support | 7 | mounting bracket |
| 4 | filling fittings | | |

Figure 2 — Typical detail of end closure

6 Test piece

The sample length shall be chosen such that the axial beam bending stresses at mid-span are equal to the planned allowable stress for the pipe under installation conditions within $\pm 10\%$.

The relation of data generated in this test to the planned pipe installation shall be described in the referring standard.

7 Number of test pieces

The number of test pieces shall be as specified in the referring standard.

8 Determination of the dimensions of the test piece

8.1 Outside diameter, d_o

Measure the external diameter of the test piece at three locations: the centre of the pipe and at a distance of one sixth of the sample length from the centre in each direction. Calculate the mean value of d_o as the arithmetic average of the three measured values.

8.2 Mean wall thickness, e

Measure the wall thickness of the test piece at six equally spaced locations around the circumference at each end. Calculate the mean wall thickness, e , as the arithmetic average of the twelve measured values.

8.3 Inner diameter, d_i

Calculate the inner diameter, d_i , of the test piece by subtracting two times the mean wall thickness from the mean value of the outside diameter, d_o .

8.4 Length

Determine and mark the position of the crown of the pipe (e.g. by use of a level). Determine and mark the position of the spring-line at the pipe-ends and at the centre by measuring from the crown down to one quarter of the circumference in each direction. Measure the length of the test piece at spring-line on each side.

9 Conditioning

Unless otherwise specified by the referring standard, the test pieces and the water used in the test shall be stored under testing conditions for at least 24 h prior to testing.

10 Procedure

10.1 Preparation of test piece

Glue the bracket supports onto the test piece at the springlines. Two shall be placed at mid-span of the pipe, while two are placed at each end. These shall be at a certain distance, l , from the supporting seal. See [Formula \(1\)](#):

$$l = 2 (e d_m)^{0,5} \quad (1)$$

where

- l is the distance between the supporting seal and the measurement point of the bracket close to the end;
- e is the pipe thickness;
- d_m is the mean diameter.

10.2 Preparation of supporting frame

Drill two bolt holes on each end of the steel beams and place the beams on the support. The end closures shall be bolted onto the beams. This can be achieved by welding brackets with bolt holes to the end closures. The bolt holes shall fit to the bolt holes on the steel beams (see [Figure 2](#)). The rotated pipe ends (from test load) shall not come in contact with the end-closure ends during test.

This shall be assured by:

- choosing the correct distance between end-closures relative to the pipe length;
- obtaining equal spacing between the pipe-end and end-closure end at both sides of the test set-up;
- measuring distance between end-closures and position marks on the pipe showing the position of the pipe end relative to the end-closures.

10.3 Mounting of test piece

Place the end-closures onto the pipe. Mount the end-closures to the support frame by bolting or welding them onto the steel beams.

10.4 Mounting of displacement meters and zero readings

Mount the displacement meters onto the steel beams and connect them to a data acquisition system, if applicable.

Within 1 h after the pipe has been mounted in the supporting frame, zero readings shall be taken from all the meters.

NOTE Since it can be difficult to complete all mounting within 1 h, the supporting frame can be rotated 90° around the centreline during the preparations and then the frame placed back in position when ready.

10.5 Filling of test sample

After the zero readings have been taken, fill the sample with water through the fittings on the end closure until all air has been bled from the sample. The filling time should be less than 1 h.

10.6 Monitoring deflection

During filling, the deflection shall be measured continuously. The deflections at the time when the sample is full shall be noted. This is the initial deflection. Thereafter, the deflections shall be measured at least once every day for 10 000 h.

11 Calculating creep modulus

Compute the veritable deflection by subtracting the average of the measured end deflections from the measured centre deflections. Compute the extrapolated 50-year deflection by using method A in ISO 10928:2016.

The initial modulus, E_i , shall be calculated by [Formula \(2\)](#).

$$E_i = \frac{5 q L^4}{384 I \Delta_i} \quad (2)$$

where

q is the load from the weight of the water in the pipe, in N/mm;

L is the span length in mm between the end supports of the pipe, i.e. between the location of the gasket seals;

I is the second moment of area of the pipe cross section

$$I = \frac{\pi}{64} (d_o^4 - d_i^4)$$

where:

d_o is the outer diameter, in mm;

d_i is the inner diameter, in mm;

Δ_i is the initial deflection, in mm.