

---

# International Standard



# 4382/2

---

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

---

## ● Plain bearings — Copper alloys — Part 2 : Wrought copper alloys for solid plain bearings

*Paliers lisses — Alliages de cuivre — Partie 2 : Alliages de cuivre corroyés pour paliers lisses massifs*

First edition — 1981-12-15

STANDARDSISO.COM : Click to view the full PDF of ISO 4382-2:1981

---

UDC 669.35.018.24-13

Ref. No. ISO 4382/2-1981 (E)

Descriptors : bearing alloys, copper alloys, designation, chemical composition, mechanical properties, physical properties.

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards institutes (ISO member bodies). The work of developing International Standards is carried out through ISO technical committees. Every member body interested in a subject for which a technical committee has been set up has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work.

Draft International Standards adopted by the technical committees are circulated to the member bodies for approval before their acceptance as International Standards by the ISO Council.

International Standard ISO 4382/2 was developed by Technical Committee ISO/TC 123, *Plain bearings*, and was circulated to the member bodies in September 1978.

It has been approved by the member bodies of the following countries :

Chile	Korea, Rep. of	Spain
Czechoslovakia	Libyan Arab Jamahiriya	Sweden
France	Mexico	USA
Germany, F.R.	Netherlands	USSR
India	New Zealand	Yugoslavia
Ireland	Poland	
Italy	South Africa, Rep. of	

The member body of the following country expressed disapproval of the document on technical grounds :

United Kingdom

This International Standard has been drawn up in close cooperation with ISO/TC 26, *Copper and copper alloys*.

# Plain bearings — Copper alloys — Part 2 : Wrought copper alloys for solid plain bearings

## 1 Scope and field of application

This part of ISO 4382 specifies requirements for wrought copper alloys for use in solid plain bearings, particularly for bushes. It gives a limited selection of alloys currently available for general purposes.

## 2 References

ISO/R 400, *Tensile testing of copper and copper alloys.*

ISO/R 401, *Tensile testing of copper and copper alloy tubes of circular section.*

ISO 4379, *Plain bearings — Solid copper alloy bushes — Dimensions and tolerances.*

ISO 4384/2, *Plain bearings — Hardness testing on bearing metals — Part 2 : Solid materials.*<sup>1)</sup>

## 3 Requirements

### 3.1 Chemical composition

The chemical composition shall be within the limits specified in table 1, where single figures denote maximum values.

The chemical analysis is decisive for the acceptance of the bearing metals.

### 3.2 Material properties

Material properties shall be according to table 1.

The Brinell hardness is regarded as the test and acceptance value. All other indicated values are mean values and are regarded as typical values for the designer. In view of the range of possible alloy compositions, relatively large deviations from the indicated values must be expected in individual cases.

## 4 Designation

Example : Designation of a bearing metal having the symbol CuSn8P and a minimum Brinell hardness of 120 :

**Bearing metal ISO 4382 — CuSn8P — HB 120**

1) At present at the stage of draft.

Table 1 – Wrought copper alloys

Chemical elements and properties	Chemical composition, % (m/m)								
	CuSn8P		CuZn31Si1		CuZn37Mn2Al2Si		CuAl9Fe4Ni4		
Cu	90,0 to 92,5		66,0 to 70,0		57,0 to 60,0		78,0 to 87,0		
Sn	7,5 to 9,0		—		0,5		0,2		
Zn	0,3		28,5 to 33,3		32,0 to 40,0		0,5		
Al	—		—		1,0 to 2,5		8,0 to 11,0		
Ni	0,3		0,5		0,25 <sup>1)</sup>		2,5 to 5,0		
Fe	0,1		0,4		0,6		2,5 to 4,5		
Si	—		0,7 to 1,3		0,3 to 1,3		0,1		
Mn	—		—		1,5 to 3,5		3,0		
Pb	0,05		0,8		0,8		0,1		
P	0,1 to 0,4		—		—		—		
Total others	0,2		0,5		0,5		0,5		
Material properties of specimen									
<b>Brinell hardness</b> <sup>2)</sup> HB2,5/62,5/10, min.	80	120	140	160	100	135	160	150	160
<b>Tensile strength</b> $R_m$ N/mm <sup>2</sup> ≈	400	470	520	580	440	510	560	600	700
<b>Elongation</b> $A$ % ≈	55	40	25	10	30	15	10	15	15
<b>0,2 % Proof stress</b> $R_{p0,2}$ N/mm <sup>2</sup> ≈	200	300	400	480	250	350	450	300	400
<b>Elastic modulus</b> $E$ kN/mm <sup>2</sup> ≈	115			105			100		118
<b>Thermal expansion</b> $\alpha_l$ 10 <sup>-6</sup> /K ≈	17			18			19		16
<b>Thermal conductivity</b> $\lambda$ at 15 °C W/(m·K) ≈	59			67			65		27
<b>Density</b> $\rho$ kg/dm <sup>3</sup> ≈	8,8			8,4			8,1		7,6

1) The maximum of nickel may be raised to 2 % by agreement between supplier and purchaser.

2) For hardness testing see ISO 4384/2.

Table 2 — Guide for uses of bearing metals

Bearing alloys	Characteristics and principle uses
<b>CuSn8P</b>	For hardened shafts with any combination of high load, high sliding velocity, impact loading or pounding; when there is adequate lubrication and good alignment. Hardness should be chosen to suit working conditions.
<b>CuZn31Si1</b>	For hardened shafts with any combination of high load, moderate to high sliding velocity, impact loading or pounding; when there is adequate lubrication and good alignment. Hardness should be chosen to suit working conditions.
<b>CuZn37Mn2Al2Si</b>	High wear resistance; tolerant of poor lubrication; hardened shafts essential.
<b>CuAl9Fe4Ni4</b>	Very hard alloy for structural components under sliding conditions. Suitable for marine environments. Hardened shafts essential. Relatively poor embeddability.

STANDARDSISO.COM :: Click to view the full PDF of ISO 4382-2:1981

STANDARDSISO.COM : Click to view the full PDF of ISO 4382-2:1981