

INTERNATIONAL STANDARD

ISO
4437

First edition
1988-01-15



INTERNATIONAL ORGANIZATION FOR STANDARDIZATION
ORGANISATION INTERNATIONALE DE NORMALISATION
МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ

Buried polyethylene (PE) pipes for the supply of gaseous fuels — Metric series — Specification

*Canalisations enterrées en polyéthylène (PE) pour réseaux de distribution de combustibles
gazeux — Série métrique — Spécifications*

STANDARDSISO.COM : Click to view the full PDF of ISO 4437:1988

Contents	Page
1 Scope and field of application	1
2 References	1
3 Material	1
4 Performance requirements	1
4.1 Effects of gas constituents on the hydrostatic strength	1
4.2 Hydrostatic strength	1
4.3 Properties after weathering	2
5 General requirements for manufactured pipes	2
5.1 Dimensions	2
5.2 Pipe properties	3
6 Test methods	3
6.1 Density of material	3
6.2 Dimensional measurements	3
6.3 Surface finish	3
6.4 Effect of gas constituents on the hydrostatic strength	4
6.5 Hydrostatic strength	4
6.6 Properties after weathering	5
6.7 Heat reversion	5
6.8 Tensile strength at yield and elongation at break	5
6.9 Resistance to internal hydraulic pressure	5
7 Marking	5
 Annexes	
A Additional specifications	6
B Squeeze-off technique	7
C Some current countries using pipe series and minimum wall thickness	8

Buried polyethylene (PE) pipes for the supply of gaseous fuels — Metric series — Specification

1 Scope and field of application

This International Standard specifies the required physical properties of pipes of polyethylene (PE) intended to be used for the supply of gaseous fuels. In addition, it specifies some general properties of the material from which these pipes are made.

This International Standard also lays down dimensional requirements and acceptable pressure ratings for pipes.

When using polyethylene pipes for the transport of gaseous fuels, the presence of other constituents in the gas must be taken into account, as, at a certain level of concentration, these constituents could impair the properties of the pipe.

2 References

ISO 161-1, *Thermoplastics pipes for the transport of fluids — Nominal outside diameters and nominal pressures — Part 1: Metric series.*

ISO 1167, *Plastics pipes for the transport of fluids — Determination of the resistance to internal pressure.*

ISO/R 1183, *Plastics — Methods for determining the density and relative density (specific gravity) of plastics excluding cellular plastics.*

ISO 1872, *Polyethylene thermoplastic materials — Designation.*¹⁾

ISO 2506, *Polyethylene pipes (PE) — Longitudinal reversion — Test methods and specification.*

ISO 3126, *Plastics pipes — Measurement of dimensions.*

ISO 3607, *Polyethylene (PE) pipes — Tolerances on outside diameters and wall thicknesses.*

ISO 4065, *Thermoplastics pipes — Universal wall thickness table.*

ISO 4607, *Plastics — Methods of exposure to natural weathering.*

ISO 6259, *Polyethylene (PE) pipes — Determination of tensile properties.*²⁾

3 Material

3.1 The base material from which the pipe is produced shall be polyethylene to which shall be added only those antioxidants, UV stabilizers and pigments necessary for the manufacture of pipes to the specification and to its end use including weldability. (See annex A, clause A.3.) The nominal density of the base material, when determined in accordance with 6.1, shall be greater than 930 kg/m³.³⁾

All additives shall be uniformly dispersed.⁴⁾

3.2 Clean rework, generated from a manufacturer's own production of pipe to this specification, may be used, if it is derived from the same resin as used for the relevant production.

3.3 When tested by the method described in 6.5, the material, tested as pipe, shall meet the requirements of 4.2.1, 4.2.2 and 4.2.3.

From the data obtained, the manufacturer shall state whether the material conforms with the requirements of type A, B or C (see table 1).

4 Performance requirements

4.1 Effects of gas constituents on the hydrostatic strength

When tested by the method described in 6.4, the pipe shall withstand a hoopstress of 2 MPa at 80 °C for at least 30 h. The test shall be carried out on 32, 40 or 50 mm SDR 11 (or S 5) pipe.

4.2 Hydrostatic strength⁵⁾

4.2.1 Long-term hydrostatic strength at 20 °C

When tested in accordance with 6.5.1, the material in pipe form shall be shown to have a 95 % lower confidence limit of the

1) For the purposes of this International Standard, this reference is specifically to the 1972 edition.

2) At present at the stage of draft.

3) A PE of density greater than 930 kg/m³ corresponds to classification 3, 4 or 5 in accordance with clause 3 of ISO 1872. (See 6.1.)

4) Specifications and test methods are being developed.

5) These requirements are tentative and subject to revision.

5.1.3 Tolerances

5.1.3.1 Wall thickness

The maximum permissible variation between the nominal wall thickness, e , and the wall thickness at any point, e_i , shall be in accordance with ISO 3607.

5.1.3.2 Mean outside diameter¹⁾

The maximum permissible variation between the mean outside diameter, d_m , and the nominal outside diameter, d_e , for normal tolerance pipe shall be in accordance with ISO 3607, and for close tolerance pipe as given in table 3 (see 6.2 and annex A, clause A.4).

Table 3 – Dimensions for close and normal tolerance pipe

Dimensions in millimetres

Outside diameter nom.	Tolerance	
	min. CT	normal
20	+0,3 0	+0,3 0
25		
32		
40	+0,4 0	+0,4 0
50		+0,5 0
63		+0,6 0
75	+0,5 0	+0,7 0
90	+0,6 0	+0,9 0
110		+1 0
125		+1,2 0
140	+0,8 0	+1,3 0
160	+1 0	+1,5 0
180	+1,2 0	+1,7 0
200	+1,3 0	+1,8 0
225	+1,4 0	+2,1 0
250	+1,5 0	+2,3 0

5.1.3.3 Roundness

The roundness shall be specified by agreement between user and manufacturer.

1) This clause is provisional : tolerances are under study.

5.2 Pipe properties

5.2.1 Surface finish

The internal and external surfaces of the pipe shall be clean, smooth and reasonably free from grooving or other defects (see 6.3), which might impair its functional properties.

The ends shall be cleanly cut and square with the pipe axis.

5.2.2 Heat reversion

When tested by the method described in 6.7, at no point around the pipe shall the length change by more than 3 %.

On inspection after testing, the pipe shall show no faults such as cracks, cavities and blisters.

5.2.3 Tensile strength at yield

When tested by the method described in 6.8, the tensile strength at yield at 23 °C for each of the specimens tested shall not be less than the values stated in table 4.

Table 4 – Tensile strength at yield

Type	B and C	A
Minimum tensile strength at yield, MPa	15	19

5.2.4 Elongation at break

When tested by the method described in 6.8, the elongation at break at 23 °C for each of the specimens tested shall not be less than 350 %.

5.2.5 Resistance to internal hydraulic pressure

When tested by the method described in 6.9, the time to failure shall not be less than the values stated in table 1 for the type declared in 3.3.

6 Test methods

6.1 Density of material

The nominal density shall be determined in accordance with ISO/R 1183 and the sample shall be prepared in accordance with ISO 1872.

6.2 Dimensional measurements

Dimensions shall be measured in accordance with ISO 3126.

6.3 Surface finish

The internal and external surfaces of the pipe shall be visually examined without magnification.