
**Paints and varnishes — Pull-off test
for adhesion**

Peintures et vernis — Essai de traction

STANDARDSISO.COM : Click to view the full PDF of ISO 4624:2023



STANDARDSISO.COM : Click to view the full PDF of ISO 4624:2023



COPYRIGHT PROTECTED DOCUMENT

© ISO 2023

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword.....	iv
Introduction.....	v
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	1
4 Principle.....	2
5 Apparatus.....	2
6 Adhesives.....	5
7 Sampling.....	6
8 Test panels.....	6
8.1 Substrate.....	6
8.2 Preparation and coating.....	6
8.3 Drying and conditioning.....	6
8.4 Thickness of coating.....	6
9 Procedure.....	6
9.1 Number of determinations.....	6
9.2 Ambient conditions.....	6
9.3 Adhesive.....	6
9.4 Test assemblies.....	7
9.4.1 Method A: General method (using two dollies) for testing both rigid and deformable substrates.....	7
9.4.2 Method B: Method for testing from one side only, using a single dolly (suitable for rigid substrates only).....	7
9.4.3 Method C: Method using dollies, one as a painted substrate.....	8
9.5 Measurement.....	9
9.5.1 Breaking strength.....	9
9.5.2 Nature of the fracture.....	9
10 Calculation and expression of results.....	9
10.1 Breaking strength.....	9
10.2 Nature of failure.....	10
10.3 Example.....	10
11 Precision.....	10
12 Test report.....	10
Bibliography.....	12

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO document should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents. ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 35, *Paints and varnishes*, Subcommittee SC 9, *General test methods for paints and varnishes*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 139 *Paints and varnishes*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This fourth edition cancels and replaces the third edition (ISO 4624:2016), which has been technically revised.

The main changes are as follows:

- [Clause 3](#) on terms and definitions has been added;
- for the use of this method on concrete, larger dolly of up to 100 mm have been added to [5.2](#);
- requirement concerning the adhesive in relation to substrate or coating material has been added in [Clause 6](#) (last sentence).
- additional information has been added to the single dolly method in [9.4.2](#);
- the normative references have been updated.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

This document describes methods for assessing the adhesion of a single coating or a multi-coat system of paint, varnish or a related product by measuring the minimum tensile stress necessary to detach or to rupture the coating in a direction perpendicular to the substrate.

The test result is influenced not only by the mechanical properties of the system under test, but also by the nature and preparation of the substrate, the method of paint application, the drying conditions of the coating, the temperature, the humidity and other factors like the type of test instrument which has been used.

ISO 2409 can also be used for the evaluation of adhesion characteristics.

STANDARDSISO.COM : Click to view the full PDF of ISO 4624:2023

[STANDARDSISO.COM](https://standardsiso.com) : Click to view the full PDF of ISO 4624:2023

Paints and varnishes — Pull-off test for adhesion

1 Scope

This document specifies three methods for determining the adhesion by carrying out a pull-off test on a single coating or a multi-coat system of paint, varnish or related product.

These methods include:

- method A: using two dollies, suitable for testing both rigid and deformable substrates;
- method B: testing from one side only, using a single dolly, suitable for rigid substrates only;
- method C: using dollies, one as a painted substrate.

These test methods have been found useful in comparing the adhesion behaviour of different coatings. It is most useful in providing relative ratings for a series of coated panels exhibiting significant differences in adhesion.

The test can be applied using a wide range of substrates. Different procedures are given according to whether the substrate is deformable, e.g. thin metal, plastics and wood, or rigid, e.g. thick concrete and metal plates. To avoid distortion of the substrate during the tensile test, it is common to use a sandwich construction. For example, for special purposes, the coating can be applied directly to the face of a test dolly.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1513, *Paints and varnishes — Examination and preparation of test samples*

ISO 1514, *Paints and varnishes — Standard panels for testing*

ISO 2808, *Paints and varnishes — Determination of film thickness*

ISO 3270, *Paints and varnishes and their raw materials — Temperatures and humidities for conditioning and testing*

ISO 4618, *Paints and varnishes — Vocabulary*

ISO 15528, *Paints, varnishes and raw materials for paints and varnishes — Sampling*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 4618 apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

4 Principle

The product or system under test is applied at uniform thickness to flat panels of uniform surface texture.

After drying/curing the coating system, dollies are bonded directly to the surface of the coated and cured panel using an adhesive.

After curing the adhesive, the bonded dolly assemblies are placed in a suitable tensile tester. The bonded assemblies are subjected to a controlled tensile test (pull-off test), and the force required to break the coating/substrate bond is measured.

To avoid possible distortion of the substrate during the tensile test, dollies with a diameter smaller than the 2 cm diameter used for steel substrates may be used to reduce the force introduced.

The test result is the tensile stress necessary to break the weakest interface (adhesive failure) or the weakest component (cohesive failure) of the test assembly. Mixed adhesive/cohesive failures may also occur.


5 Apparatus

5.1 Tensile tester, suitable for carrying out the chosen procedure specified in [Clause 9](#). The tensile stress shall be applied in a direction perpendicular to the plane of the coated substrate and shall be increased at a substantially uniform rate, not greater than 1 MPa/s¹⁾ such that failure of the test assembly occurs within 90 s. Suitable designs for applying the tensile stress are shown in [Figures 1](#) and [2](#).

Instead of a tensile tester, other types of pull-off adhesion testers (mechanically, pneumatically, hydraulically or hand-driven) may be used provided that they give similar results. The type of instrument shall be reported in the test report, because hand-driven/mechanical/hydraulic instruments are reported to produce widely different results.

NOTE The results can be influenced by the test assembly used. Furthermore, the results are not reproducible unless coaxial alignment of the tensile forces is ensured.


1) 1 MPa/s = 1 MN/(m²·s).

**Key**

- 1 support
- 2 ball joint
- 3 dollies
- 4 coating
- 5 substrate

NOTE These methods are described in [9.4.1](#) and [9.4.3](#).

Figure 1 — Example of a suitable test apparatus for the two-dolly methods (methods A and C)



Key

- 1 coating
- 2 test piece
- 3 dolly
- 4 ball-and-socket sliding joint
- 5 support (suitably designed to allow for joint assembly)
- 6 ball-and-socket sliding joint

NOTE This test apparatus is described in [9.4.2](#).

Figure 2 — Example of a suitable test apparatus for the one-dolly method (method B)

5.2 Test dollies, each consisting of a steel or aluminium cylindrical-faced testing body, specifically designed to be used with the tensile tester. Each dolly has a rigid, flat face for bonding the adhesive/coating at one end and a facility for connecting the pull-off tester at the other. Each dolly has a nominal diameter of 20 mm and sufficient thickness to ensure freedom from distortion during the test. It is recommended that the height of each dolly is not less than half its diameter. The faces of each dolly shall be machined perpendicular to its axis before use.

Dollies with a diameter of 7 mm for example, may be used when the method for testing adhesion from one side only is used and when there is a danger of distortion of the substrate (see [9.4.2](#)). If dollies smaller in diameter are used, more measurements shall be made to improve the precision. When using 7 mm dollies, 10 measurements have been shown to be practicable. The diameter of the dollies shall be recorded in the test report.


Use of this method on concrete typically uses a larger dolly of up to 100 mm. Use of a larger dolly is beneficial on concrete coatings as the force applied during the test provides values closer to the maximum tensile strength of most concrete.

5.3 Centring device, for ensuring proper coaxial alignment of the test assembly during the adhesion process of the two-dolly methods described in [9.4.1](#) (method A) and [9.4.3](#) (method C). A suitable design is shown in [Figure 3](#).

5.4 Cutting device, such as a sharp knife, for cutting through the cured adhesive and the paint coating to the substrate, round the circumference of the dolly.

Depending on the mechanical properties of the paint system (e.g. brittleness), cutting through the cured adhesive and the paint film to the substrate can have a big influence on the adhesion of the paint system. It is permitted, if specified or agreed between the interested parties, not to cut when the paint systems are less than 150 µm in layer thickness. If cuts around the dolly have been made, this shall be mentioned in the test report and the type of cutting tool shall also be mentioned.

When using small dollies, cutting often is difficult and is normally not carried out. Experience has shown that an increasing number of small dollies has an advantage concerning precision compared to the cut combined with the 20 mm dollies.



Key

- 1 test assembly aligned for adhesion process (see 5.3)
- 2 centring pin

Figure 3 — Example of a suitable centring device for 20 mm-diameter dollies

6 Adhesives

Special attention is required in selecting suitable adhesives to be used in the test. To produce failure of the coating, it is essential that the cohesive and bonding properties of the adhesive are greater than those of the coating under test.

Preliminary screening of adhesives shall be carried out in order to determine their suitability for use. Suitable adhesives and, if applicable, their unmixed components, shall cause little or no visible change in the coating under test when left in contact with the coating for a period equivalent to the curing time of the adhesive.

Adhesives which give the highest results, which means the most coating-substrate adhesive failure or coating failure, are preferred.

In most cases, cyanoacrylate, two-component solventless epoxide and peroxide-catalysed polyester adhesives have been found suitable. In special tests under highly humid conditions, the curing time of the adhesive should be as short as possible. The use of two-pack quick-drying epoxy adhesive is preferable in these situations.

Where failure is mainly associated with the adhesive at tensions less than 5 MPa, the use of another type of adhesive can enable more useful results to be obtained.

The adhesive may not interact with the substrate or the coating material under test.

7 Sampling

Take a representative sample of the product to be tested (or of each product in case of a multi-coat system) as specified in ISO 15528.

Examine and prepare the sample for testing as specified in ISO 1513.

8 Test panels

8.1 Substrate

Select the substrate from one of those described in ISO 1514, using where possible the same type of material that will be used in practice. The substrate panels shall be plane and free from distortion.

8.2 Preparation and coating

Prepare each test panel in accordance with that pre-treatment method which is intended to be carried out on the original surface. The chosen pre-treatment shall be reported in the test report.

8.3 Drying and conditioning

Dry (or stove) and age, if applicable, each coated test panel for the specified time and under the specified conditions. Before testing, condition the coated panels at (23 ± 2) °C and a relative humidity of (50 ± 5) % as specified in ISO 3270, for a minimum period of 16 h.

8.4 Thickness of coating

The thickness of the coating shall be specified and agreed between the interested parties. Determine the thickness, in micrometres, of the dried coating by one of the procedures specified in ISO 2808.

9 Procedure

9.1 Number of determinations

Carry out at least six determinations, i.e. using at least six test assemblies (see [9.4](#)).

9.2 Ambient conditions

Carry out the test at (23 ± 2) °C and a relative humidity of (50 ± 5) %, as specified in ISO 3270.

9.3 Adhesive

Prepare and apply the adhesive (see [Clause 6](#)) in accordance with the manufacturer's instructions. Use the minimum quantity of adhesive required to produce a firm, continuous and even bond between the components of the test assembly. Remove any excess adhesive immediately if possible.

9.4 Test assemblies


9.4.1 Method A: General method (using two dollies) for testing both rigid and deformable substrates

If the test piece is too large, use an area cut from the coated substrate (disc of minimum diameter 30 mm or square of minimum side 30 mm). Take care not to distort the test piece. Apply the adhesive evenly to the surfaces of two freshly-cleaned dollies (5.2) of equal diameter.

Place the test piece between the adhesive-coated faces of the dollies such that the dollies are coaxially aligned in the centre of the test piece, as shown in Figure 4. Align the test assembly in the centring device (5.3) and maintain the alignment for a period equal to the curing time of the adhesive. In special tests under highly humid conditions, the curing time of the adhesive shall be as short as possible, the use of two-pack quick-drying epoxy adhesive is preferable in these situations. At the end of this period, carefully use the cutting device (5.4) to cut around the circumference of the dollies through to the substrate, unless otherwise specified or agreed (see 5.4).

The adhesion at the adhesive/coating interface may be improved by lightly abrading the surface of the dried coating and the surface of the test dolly before application of the adhesive.

In the method for deformable substrates, if a poor adhesive bond is expected between the uncoated face of the substrate and the dolly, coat both faces of the substrate with the product under test.



Key


- 1 dolly coated with adhesive
- 2 substrate painted on one or both sides

Figure 4 — Test assembly for sandwich method with substrate painted on one or both sides

9.4.2 Method B: Method for testing from one side only, using a single dolly (suitable for rigid substrates only)

Apply the adhesive evenly to the uncoated, freshly-cleaned surface of a dolly (5.2). Place the adhesive-coated face of the dolly in contact with the coating, for a period equal to the curing time of the adhesive (see 9.4.1). At the end of this period, carefully use the cutting device (5.4) to cut around the circumference of the dolly through to the substrate, unless otherwise specified or agreed.

Place the outer ring in position and test as indicated in Figure 5.



Key


- 1 outer ring
- 2 dolly coated with adhesive
- 3 paint coating
- 4 substrate

Figure 5 — Test assembly for rigid substrates

The test assembly shall be so that the substrate cannot deform during the test. Different options are possible, such as using a thicker substrate.

9.4.3 Method C: Method using dollies, one as a painted substrate

Apply the adhesive evenly to the uncoated, freshly-cleaned surface of a dolly. Place the adhesive-coated surface of the dolly in contact with the surface of a second dolly coated with the product under test, as shown in [Figure 6](#), and align the test assembly in the centring device ([5.3](#)) for a period equal to the curing time of the adhesive.



Key

- 1 painted dolly
- 2 paint film
- 3 adhesive
- 4 dolly coated with adhesive

Figure 6 — Test assembly using dollies only

9.5 Measurement

9.5.1 Breaking strength

Immediately after the period allowed for the curing of the adhesive, place the test assembly in the pull-off adhesion tester (5.1), taking care to align the dollies so that the tensile force is applied uniformly across the test area, without any bending moment. Apply a tensile stress, increasing at a rate not greater than 1 MPa/s, perpendicular to the plane of the coated substrate such that failure of the test assembly occurs within 90 s of initial application of the stress.

Record the tensile stress required to break the test assembly. Repeat the pull-off test for each test assembly prepared (see 9.1).

9.5.2 Nature of the fracture

Visually inspect the fracture surfaces to establish the nature of the fracture, and assess the type of fracture as follows:

- A is cohesive failure of substrate;
- A/B is adhesive failure between substrate and first coat;
- B is cohesive failure of first coat;
- B/C is adhesive failure between first and second coats;
- n is cohesive failure of the n^{th} coat of a multicoat system;
- n/m is adhesive failure between the n^{th} coat and the m^{th} coat of a multicoat system;
- /Y is adhesive failure between final coat and adhesive;
- Y is cohesive failure of adhesive;
- Y/Z is adhesive failure between adhesive and dolly.

Estimate the area of fracture as a percentage to the nearest 10 % for each type of fracture.

Where consistency of bonding failure is not achieved, review both the preparation and application of the coating; for inconsistent failure of the adhesive, see [Clause 6](#) and [9.4.1](#). Repeat the series of tests using at least six more test assemblies.

10 Calculation and expression of results

10.1 Breaking strength

The breaking strength, σ , in megapascals, for each test assembly is given by [Formula \(1\)](#):

$$\sigma = \frac{F}{A} \quad (1)$$

where

- F is the breaking force, in newtons;
- A is the area of the dolly, in square millimetres.

In the case of dollies of diameter 20 mm, the breaking strength, in megapascals, is given by [Formula \(2\)](#).

$$\sigma = \frac{4F}{400\pi} = \frac{F}{314} \quad (2)$$

Calculate the mean of all determinations to the nearest whole number. In case of more than one measurement, express the number of measurements, the mean result, the highest and the lowest result.

10.2 Nature of failure

Evaluate the cumulated area of the six dollies (see [9.1](#)) and express the result as the estimated mean percentage area and type of fracture in the system under test, in accordance with [9.5.2](#).

10.3 Example

The pull-off test result can be expressed as follows:

20 MPa, 30 % B, 70 % B/C

This means that:

- a paint system breaks at a mean tensile stress of 20 MPa;
- examination of the area on each side of the site of separation reveals a mean of approximately 30 % of the dolly area associated with cohesive failure of the first coat;
- 70 % of the dolly area associated with intercoat results in adhesive failure between the first and second coats.

11 Precision

No relevant precision data are currently available.

Users of this document should be aware that, because of the subjective assessment of the point at which detachment occurs and the nature of the failure, precision data will only give an indication of the accuracy of the method.

However, the method has been found to be useful in comparing the adhesion of different coatings. It is most useful in providing relative ratings for a series of coated panels exhibiting significant differences in adhesion.

12 Test report

The test report shall contain at least the following information:

- a) all details necessary to identify the product(s) tested;
- b) a reference to this document, i.e. ISO 4624:2023;
- c) the details of the preparation of the test panels, including
 - 1) the material, the thickness and the surface preparation of the substrate (see [8.1](#)),
 - 2) the method of application of the coating material to the substrate, including the duration and conditions of drying between coats in the case of a multi-coat system (see [8.2](#)),
 - 3) the duration and conditions of drying (or stoving) and ageing (if applicable) of the coating before testing (see [8.3](#)), and