



# Rubber compounding ingredients — Silica, precipitated, hydrated —

## Part 1: Non-rubber tests

### TECHNICAL CORRIGENDUM 2

*Ingrédients de mélange du caoutchouc — Silices hydratées précipitées —*

*Partie 1: Essais sur le produit brut*

*RECTIFICATIF TECHNIQUE 2*

Technical Corrigendum 2 to ISO 5794-1:2005 was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 3, *Raw materials (including latex) for use in the rubber industry*.

---

Page 25

Replace G.6.3.3 and G.6.3.4 by the following text:

#### **G.6.3.3 Separation using a syringe**

**G.6.3.3.1** Fill a suitable syringe with 20 cm<sup>3</sup> of the silica suspension.

**G.6.3.3.2** Fix the filter to the syringe and push the test portion through the filter.

**G.6.3.3.3** Take a portion of the filtrate for titration (see G.6.4).