

---

---

**Implants for surgery — Metallic  
materials —**

Part 5:  
**Wrought cobalt-chromium-tungsten-  
nickel alloy**

*Implants chirurgicaux — Produits à base de métaux —*

*Partie 5: Alliage corroyé à base de cobalt, de chrome, de tungstène et  
de nickel*

STANDARDSISO.COM : Click to view the full PDF of ISO 5832-5:2005



**PDF disclaimer**

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

STANDARDSISO.COM : Click to view the full PDF of ISO 5832-5:2005

© ISO 2005

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 5832-5 was prepared by Technical Committee ISO/TC 150, *Implants for surgery*, Subcommittee SC 1, *Materials*.

This third edition cancels and replaces the second edition (ISO 5832-5:1993), which has been technically revised.

ISO 5832 consists of the following parts, under the general title *Implants for surgery — Metallic materials*:

- *Part 1: Wrought stainless steel*
- *Part 2: Unalloyed titanium*
- *Part 3: Wrought titanium 6-aluminium 4-vanadium alloy*
- *Part 4: Cobalt-chromium-molybdenum casting alloy*
- *Part 5: Wrought cobalt-chromium-tungsten-nickel alloy*
- *Part 6: Wrought cobalt-nickel-chromium-molybdenum alloy*
- *Part 7: Forgeable and cold-formed cobalt-chromium-nickel-molybdenum-iron alloy*
- *Part 8: Wrought cobalt-nickel-chromium-molybdenum-tungsten-iron alloy*
- *Part 9: Wrought high nitrogen stainless steel*
- *Part 11: Wrought titanium 6-aluminium 7-niobium alloy*
- *Part 12: Wrought cobalt-chromium-molybdenum alloy*

## Introduction

No known surgical implant material has ever been shown to be completely free of adverse reactions in the human body. However, long-term clinical experience of the use of the material referred to in this part of ISO 5832 has shown that an acceptable level of biological response can be expected, if the material is used in appropriate applications.

STANDARDSISO.COM : Click to view the full PDF of ISO 5832-5:2005

# Implants for surgery — Metallic materials —

## Part 5: Wrought cobalt-chromium-tungsten-nickel alloy

### 1 Scope

This part of ISO 5832 specifies the characteristics of, and corresponding test methods for, wrought cobalt-chromium-tungsten-nickel alloy for use in the manufacture of surgical implants.

NOTE The tensile properties of a sample obtained from a finished product made of this alloy might not necessarily comply with those specified in this part of ISO 5832.

### 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 643, *Steels — Micrographic determination of the apparent grain size*

ISO 4967:1998, *Steel — Determination of content of nonmetallic inclusions — Micrographic method using standard diagrams*

ISO 6892, *Metallic materials — Tensile testing at ambient temperature*

### 3 Chemical composition

The analysis of a representative sample of the alloy when determined as specified in Clause 6 shall comply with the chemical composition specified in Table 1.

Table 1 — Chemical composition

Element	Compositional limits
	mass fraction %
Chromium	19 to 21
Tungsten	14 to 16
Nickel	9 to 11
Iron	≤ 3
Carbon	≤ 0,15
Silicon	≤ 1
Manganese	≤ 2
Sulfur	0,03
Phosphorus	0,04
Cobalt	Balance

## 4 Microstructure

### 4.1 Grain size index

Samples shall be prepared and etched for examination by any recognized technique. The grain size measured in accordance with ISO 643 shall be 5 or finer.

NOTE ISO 643 is given as a reference even though the material dealt with in this part of ISO 5832 is not iron-based.

### 4.2 Inclusion content

A longitudinal sample suitably polished shall be examined in accordance with ISO 4967, Method A, and shall not exhibit inclusions in excess of those specified in Table 2.

Table 2 — Inclusion content limits

Type of inclusion	Inclusion content: thin <sup>a</sup>
A — Sulfides	1
B — Aluminates	3
C — Silicates	1
D — Oxides (globular)	3
<sup>a</sup> Thick inclusions are allowed until 0,5.	

## 5 Tensile properties

The tensile properties of the alloy, determined as specified in Clause 6, shall be in accordance with the requirements of Table 3.

The level of mechanical properties for material in other than the annealed condition shall be specified in the purchase order.

Table 3 — Tensile properties

Condition	Tensile strength MPa	0,2 % offset proof stress MPa	Percentage elongation %
Annealed	≥ 860	≥ 310	≥ 30

## 6 Test methods

The test methods to be used in determining compliance with the requirements of this part of ISO 5832 shall be those given in Table 4.

Representative test pieces for the determination of tensile properties shall be prepared in accordance with ISO 6892.