
**Metallic and other inorganic
coatings — Electrodeposited coatings
of chromium for engineering purposes**

*Revêtements métalliques et autres revêtements inorganiques —
Dépôts électrolytiques de chrome pour usages industriels*

STANDARDSISO.COM : Click to view the full PDF of ISO 6158:2018



STANDARDSISO.COM : Click to view the full PDF of ISO 6158:2018



COPYRIGHT PROTECTED DOCUMENT

© ISO 2018

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 Information to be supplied by the purchaser to the processor	2
5 Designation	3
5.1 General.....	3
5.2 Designation specification.....	3
5.3 Designation of basis metal.....	3
5.4 Designation of heat treatment requirements.....	4
5.5 Designation of type and thickness of metal coating.....	4
5.6 Examples of designations.....	5
6 Requirements	5
6.1 Special test specimens.....	5
6.2 Appearance.....	5
6.3 Surface finish.....	6
6.4 Thickness.....	6
6.5 Hardness.....	6
6.6 Adhesion.....	6
6.7 Porosity.....	7
6.8 Stress relief heat treatment prior to coating.....	7
6.9 Hydrogen-embrittlement-relief heat treatment.....	7
6.10 Peening of metal parts.....	7
6.11 Use of undercoats.....	8
6.12 Stripping.....	8
6.13 Corrosion resistance/multilayer chromium plating.....	8
6.14 Surface roughness of electroplated metallic chromium coating.....	8
7 Sampling	8
Annex A (informative) Typical thickness of metallic chromium coatings specified in engineering applications	9
Annex B (normative) Thickness test methods for electroplated metallic chromium and other metallic coatings	10
Annex C (normative) Determination of cracks and pores in metallic chromium coatings	11
Annex D (normative) Classification of different quality/grate of roughness of electrodeposited metallic chromium coatings	12
Bibliography	13

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 107, *Metallic and other inorganic coatings*, Subcommittee SC 3, *Electrodeposited coatings and related finishes*.

This fourth edition cancels and replaces the third edition (ISO 6158:2011), which has been technically revised. The main changes compared with the previous edition are as follows:

- the Scope has been corrected;
- in [Clause 4](#), additional required information on special technical and engineering (surface) purposes for the electrodeposited metallic chromium coating has been added;
- in [5.2](#), additional information on surface roughness grade/quality for designation has been added;
- in [5.2](#), additional information for the description of the necessary final surface roughness of the complete finished parts given by the purchaser has been added;
- in [5.6](#), object temperature during heat treatment has been added;
- in [5.6](#), an example of designation with additional information on the final surface roughness of the completed parts has been added;
- in [6.1](#), important information for receiving reliable test results has been added;
- in [6.11](#), important information for the pretreatment of chromium plating has been added;
- in [6.13](#), information for corrosion resistance has been added;
- in [6.14](#) and [Annex D](#), information on surface roughness and structure has been added.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

Electrodeposited chromium coatings are frequently deposited from hexavalent chromium solutions similar to those used for electroplating. Engineering chromium coatings, however, are generally thicker than decorative ones. Regular or conventional chromium is the type most frequently specified, but microporous, microcracked or specially profiled surfaces and duplex chromium are also applied to achieve oil-retaining or non-sticking surfaces, or to improve corrosion resistance. These properties are the main reason for using metallic chromium coatings for engineering purposes. Summarized electrodeposited coatings of metallic chromium for engineering purposes have in total more than 35 coating and process properties simultaneously.

Electrodeposited chromium coatings for engineering applications are most often applied directly to the basis metal to increase wear and abrasion resistance, to increase fretting resistance, to reduce static and kinetic friction, to reduce galling and seizing, to increase corrosion resistance, and to build up undersize or worn parts. For protection against severe corrosion, nickel or other metallic undercoats may be applied prior to the electrodeposition of chromium, or the corrosion resistance of the chromium coating may be increased by alloying, e.g. with molybdenum.

STANDARDSISO.COM : Click to view the full PDF of ISO 6158:2018

[STANDARDSISO.COM](https://standardsiso.com) : Click to view the full PDF of ISO 6158:2018

Metallic and other inorganic coatings — Electrodeposited coatings of chromium for engineering purposes

WARNING — This document calls for the use of substances and/or procedures that may be injurious to health if adequate safety measures are not taken. This document does not address any health hazards, safety or environmental matters associated with its use. It is the responsibility of the user of this document to establish appropriate health, safety and environmentally acceptable practices.

1 Scope

This document specifies requirements for electroplated coatings of metallic chromium, with or without undercoats, on ferrous and non-ferrous metals for engineering purposes. The coating designation provides a means of specifying the thickness of chromium appropriate for typical engineering applications.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1463, *Metallic and oxide coatings — Measurement of coating thickness — Microscopical method*

ISO 2064, *Metallic and other inorganic coatings — Definitions and conventions concerning the measurement of thickness*

ISO 2080, *Metallic and other inorganic coatings — Surface treatment, metallic and other inorganic coatings — Vocabulary*

ISO 3497, *Metallic coatings — Measurement of coating thickness — X-ray spectrometric methods*

ISO 3543, *Metallic and non-metallic coatings — Measurement of thickness — Beta backscatter method*

ISO 3882, *Metallic and other inorganic coatings — Review of methods of measurement of thickness*

ISO 4516, *Metallic and other inorganic coatings — Vickers and Knoop microhardness tests*

ISO 4519, *Electrodeposited metallic coatings and related finishes — Sampling procedures for inspection by attributes*

ISO 4526, *Metallic coatings — Electroplated coatings of nickel for engineering purposes*

ISO 9227, *Corrosion tests in artificial atmospheres — Salt spray tests*

ISO 9587, *Metallic and other inorganic coatings — Pretreatment of iron or steel to reduce the risk of hydrogen embrittlement*

ISO 9588, *Metallic and other inorganic coatings — Post-coating treatments of iron or steel to reduce the risk of hydrogen embrittlement*

ISO 10309, *Metallic coatings — Porosity tests — Ferroxy test*

ISO 10587, *Metallic and other inorganic coatings — Test for residual embrittlement in both metallic-coated and uncoated externally-threaded articles and rods — Inclined wedge method*

ISO 12686, *Metallic and other inorganic coatings — Automated controlled shot-peening of metallic articles prior to nickel, autocatalytic nickel or chromium plating, or as a final finish*

ISO 15724, *Metallic and other inorganic coatings — Electrochemical measurement of diffusible hydrogen in steels — Barnacle electrode method*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 2064, ISO 2080, ISO 3882, ISO 9587, ISO 9588 and ISO 12686 apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

4 Information to be supplied by the purchaser to the processor

When ordering articles to be processed in accordance with this document, the purchaser shall provide the following essential information in writing, for example, in the contract or purchase order, or on the engineering drawings:

- a) the designation (see [Clause 5](#));
- b) the nominal composition or specification, and metallurgical condition of the basis metal including hardness (see [5.3](#)); in the case of reclaimed articles, it may not be possible to supply this information, and it may, therefore, be difficult to guarantee the quality of the coating;
- c) the nature, condition and finish of the basis metal if they are likely to affect the serviceability and/or appearance of the coating (see [6.3](#));
- d) the significant surface, indicated by drawings of the articles or by suitably marked samples (see [6.2](#));
- e) the requirements for special test specimens (see [6.1](#));
- f) the appearance and surface finish of the metallic chromium coating, e.g. as-plated, ground or machined (see [6.2](#) and [6.3](#)); alternatively, samples showing the appearance and required finish shall be supplied or approved by the purchaser, and used for comparison purposes (see [6.2](#));
- g) the necessity for any treatment to induce compressive stress, e.g. peening before or after electroplating (see [6.10](#));
- h) any special requirements for, or restrictions on, pretreatment, e.g. vapour blasting instead of acid pretreatment;
- i) positions, where unavoidable, contact marks and the type, size and number of other defects that are acceptable (see [6.2](#)) per unit area to be mentioned;
- j) requirements for undercoats (see [5.5](#) and [6.11](#)) and stripping (see [6.12](#));
- k) the test method to be used to measure thickness (see [6.4](#)) and additional segments of the surface where minimum thickness requirements apply;
- l) the adhesion and porosity requirements, and test methods (see [6.6](#) and [6.7](#), respectively);
- m) the tensile strength of parts and the requirement for stress-relief heat treatment before electroplating (see [6.8](#));

- n) requirements for any embrittlement-relief heat treatment after electroplating, and for hydrogen embrittlement testing (see [6.9](#));
- o) the sampling plan and acceptance levels (see [Clause 7](#));
- p) any additional information, e.g. any special requirements for adhesion (see [6.6](#));
- q) additional information belonging to the required surface roughness and structure (for special technical and engineering purposes (see [6.14](#) and [Annex D](#)).

5 Designation

5.1 General

The designation shall appear on engineering drawings, in the purchase order, the contract or in the detailed product specification.

The designation specifies, in the order given, the basis metal, the specific alloy (optional), stress relief requirements, the type and thickness of undercoats, the type and thickness of the electroplated metallic chromium coating, and post-treatments such as heat treatment to reduce susceptibility to hydrogen embrittlement.

5.2 Designation specification

The designation shall comprise the following:

- a) the term “Electrodeposited coating”;
- b) the number of this document, i.e. ISO 6158;
- c) a hyphen;
- d) the chemical symbol of the basis metal (see [5.3](#)), e.g. Fe (iron or steel);
- e) a solidus (/);
- f) stress relief (SR) designation (see [5.4](#));
- g) a solidus (/);
- h) chemical symbols for the metallic chromium coating, as well as coatings applied prior to chromium electroplating, separated by solidi for each stage in the coating sequence in the order of application; double solidi or separators (//) to be used to indicate that a step has been omitted or is not a requirement;
- i) a number indicating the minimum thickness, in micrometres, of the coating(s) followed by a solidus (/);
- j) hydrogen-embrittlement-relief (ER) designation (see [5.4](#)), followed by a solidus (/);
- k) a number indicating the quality/grate of the final surface roughness (see [6.14](#)).

See [5.6](#) for examples of designations.

5.3 Designation of basis metal

The basis metal shall be designated by its chemical symbol, or its principal constituent if it is an alloy.

For example:

- a) Fe for iron and steel;

- b) Zn for zinc alloys;
- c) Cu for copper and copper alloys;
- d) Al for aluminium and aluminium alloys.

To ensure proper surface preparation and hence adherence of the coating to the substrate, it is essential to identify the specific alloy and its metallurgical condition (tempered, nitrided, etc.).

It is recommended that the specific alloy be identified by its standard designation following the chemical symbol of the basis metal; for example, its UNS number, or the national or regional equivalent, may be placed between the symbols < > (see Bibliography).

EXAMPLE Fe<G43400> is the UNS designation for a high-strength steel.

5.4 Designation of heat treatment requirements

The heat treatment requirements shall be in brackets and designated as follows:

- a) the letters SR for heat treatment for stress relief purposes; the letters ER for heat treatment for the purpose of reducing susceptibility to hydrogen embrittlement; the letters HT for heat treatment for other purposes;
- b) in parenthesis, the minimum temperature, in degrees Celsius;
- c) the duration of the heat treatment, in hours;

EXAMPLE [SR(210)1] designates stress relief heat treatment at 210 °C for 1 h (temperature of the plated object).

- d) when heat treatment prior to or after electrodeposition is specified, the requirements shall be included in the designation (see 5.6).

5.5 Designation of type and thickness of metal coating

The electrodeposited metallic chromium coating shall be designated by the symbols given in Table 1 placed after a number giving the specified minimum local thickness of the coating, in micrometres. Annex A provides information on the typical thickness of metallic chromium specified in engineering applications.

EXAMPLE Cr50hr designates a regular hard chromium coating that is 50 µm thick.

Table 1 — Symbols for different types of chromium

Type of chromium	Symbol
Regular hard chromium	hr
Hard chromium from mixed acid solutions	hm
Microcracked hard chromium	hc
Microporous hard chromium	hp
Duplex chromium	hd
Special types of chromium	hs

Nickel undercoats shall be designated in accordance with ISO 4526, i.e. the symbol sf for sulfur-free nickel coatings, sc for sulfur-containing nickel coatings, or pd for sulfur-free nickel coatings containing submicron particles dispersed throughout the nickel matrix shall be used to designate the type of nickel undercoat by placing the appropriate symbol after the number giving the specified minimum local thickness of the coating, in micrometres.

EXAMPLE Ni10sf designates an electrodeposited nickel undercoat 10 µm thick prepared from a solution that does not introduce sulfur into the deposit.

5.6 Examples of designations

The examples of designations below describe the heat treatment and electroplating steps in the order that they are performed. The standard designation of the basis material is placed immediately after the chemical symbol for steel, Fe. It is especially important to know the standard designation of a metal or alloy that is difficult to prepare for electroplating and that is susceptible to hydrogen embrittlement.

For ordering purposes, the detailed product specification shall not only comprise the designation, but shall also include clear written statements of other requirements that are essential for the serviceability of a particular product (see [Clause 4](#)).

An example of an electrodeposited coating of regular hard chromium 50 µm thick (Cr50hr) deposited on mild steel (Fe), ignoring omission of any step (double solidi), is as follows:

Electrodeposited coating ISO 6158 – Fe/Cr50hr

An example of an electrodeposited coating of porous, electrodeposited chromium that is 250 µm thick (Cr250hp) on an aluminium alloy (Al), is as follows:

Electrodeposited coating ISO 6158 – Al/Cr250hp

An example of an electrodeposited coating of regular hard chromium 50 µm thick (Cr50hr) deposited on steel (Fe) over an undercoat of sulfur-free nickel 10 µm thick (Ni10sf), is as follows:

Electrodeposited coating ISO 6158 – Fe/Ni10sf/Cr50hr

An appropriate designation of an electrodeposited coating of regular hard chromium 50 µm thick (Cr50hr) deposited on steel that is stress relieved prior to electroplating at 210 °C for 2 h temperature of the electrodeposited object and roughness quality grade 1 and heat treated after electroplating for embrittlement-relief purposes at 210 °C for 22 h is as follows:

Electrodeposited coating ISO 6158 – Fe/[SR(210)2]/Cr50hr/[ER(210)22]/1

6 Requirements

6.1 Special test specimens

Special test specimens are often used to measure adhesion, thickness, porosity, corrosion, hardness and other properties when the coated articles are not suitable for the test, or if it is not practical to submit the coated articles to destructive tests because the parts are few in number or too expensive. Special test specimens shall be of the same material, shall be in the same metallurgical condition, and shall have the same surface condition and quality to avoid the possibility of influencing the electrodeposition by mechanical treatment (grinding and so on) as the coated articles. They shall be representative of the metallic undercoats and shall be processed along with the coated articles that they represent.

The use of special or representative test specimens to determine that the requirements of this document have been satisfied, the number of test specimens to be used, the material from which they shall be made, and their shape and size shall be specified by the purchaser [see [Clause 4 e](#)].

6.2 Appearance

The metallic chromium coating on the significant surface shall be bright or lustrous and, when visually inspected, shall be free from pits, blisters, exfoliation or other defects detrimental to the final finish. Nodular growths elsewhere than at the extreme edges of coatings are not permitted on articles used in the as-plated condition, or on the surface of ground articles. Imperfections and variations that arise from surface conditions of the basis metal (scratches, pores, roll marks, inclusions) and that persist in the finish, despite the observance of good metal finishing practice, shall not be cause for rejection. The purchaser shall specify limits for the tolerable defects on the finished and unfinished product [see [Clause 4 i](#)].

Approved samples of artefacts shall be used for comparison purposes [see [Clause 4 f](#)].

Electroplated articles shall be free from cracks, visible, if needed, with corrected vision. Coatings thicker than 50 µm shall be free from macro-cracks extending to the basis metal.

If parts are electroplated and subsequently ground to size, the grinding shall never be done dry, but with the proper coolant and with a sufficiently light touch to prevent cracking. Macro-cracking, visually observed, with unaided or corrected vision, but without magnification after grinding, shall be a cause for rejection.

Blisters or cracks that are visible and that result from heat treatment or grinding procedures performed by the electroplater shall be cause for rejection.

6.3 Surface finish

This document does not specify requirements for the surface condition of the basis metal prior to electroplating.

Because the appearance and serviceability of coatings depends on the surface condition of the basis metal, agreement shall be reached between the interested parties that the surface finish of the basis metal is satisfactory for electroplating [see Bibliography and [Clause 4 b](#), [c](#) and [f](#)].

The surface finish of the metallic chromium coating might be, for example, as-plated, ground or machined. Alternatively, samples showing the required finish shall be supplied or approved by the purchaser, and used for comparison purposes [see [Clause 4 f](#)].

For ground finishes, a surface roughness value, R_a , of 0,4 µm is termed a commercial finish and 0,2 µm is termed a good commercial finish.

6.4 Thickness

The coating thickness specified in the designation shall be the minimum local thickness. The minimum local thickness of an electrodeposited coating shall be measured on any point that can be touched by a ball 20 mm in diameter, unless otherwise specified by the purchaser [see [Clause 4 k](#)].

The minimum local thickness of electrodeposited metallic chromium, nickel or other metallic undercoats shall be measured by one of the methods described in [Annex B](#), unless specified otherwise by the purchaser [see [Clause 4 k](#)].

In cases of dispute, the coulometric method shall be used for measuring the thickness of metallic chromium coatings less than 10 µm thick, and the microscopical method shall be used for measuring the thickness of metallic chromium coatings and undercoats 10 µm and above [see [Clause 4 k](#)].

Although there are no technical limitations to the thickness of the metallic chromium coating that can be electroplated, there are practical limitations caused by the size and geometry of the articles that make it difficult to achieve smooth surfaces and uniformity of deposit thickness, especially as the metallic chromium thickness is increased. The electroplating operation may have to be interrupted at intermediate stages of processing to hone or machine the coated surface so as to meet appearance and surface roughness requirements. The honed or machined surface shall be properly prepared (see [6.12](#)) prior to resumption of electroplating to ensure adhesion between coatings of metallic chromium. Auxiliary anodes may have to be employed to achieve uniformity of deposit thickness and coverage.

6.5 Hardness

When hardness is specified, it shall be measured by the method given in ISO 4516.

6.6 Adhesion

A bend test on a representative sample, electroplated with 25 µm of chromium, is applied as a test of the effectiveness of the process. A review of methods of testing adhesion is given in ISO 2819, which includes

a thermal shock test that has been found applicable in certain cases. For thick deposits of metallic chromium (greater than 25 µm), a grinding test is useful for detecting poor adhesion [see [Clause 4 l](#)].

It is the responsibility of the electroplater to ensure that the method for surface preparation prior to electroplating results in coatings that are adherent to the basis metal (see [6.3](#)). See [6.4](#) regarding the need for proper surface preparation to ensure adhesion of metallic chromium to metallic chromium.

6.7 Porosity

Electroplated ferrous articles (or special test specimens) shall be subjected to the ferroxyl test described in ISO 10309, or to an alternative porosity test specified by the purchaser. The part fails if more than the number of pores per part or per unit area exceeds that agreed between the purchaser and the electroplater [see [Clause 4 l](#)].

When porous, cracked or other types of discontinuous metallic chromium coatings are specified, the determination of the number of pores and cracks in the metallic chromium shall be carried out using an optical microscope of suitable magnification or using the method given in [Annex C](#), when applicable [see [Clause 4 l](#)].

The method given in [Annex C](#) may not be applicable to thick metallic chromium coatings where cracks or pores do not extend to the basis metal or to a nickel undercoat.

6.8 Stress relief heat treatment prior to coating

When specified by the purchaser, steel parts that have an ultimate tensile strength equal to or greater than 1 000 MPa (31 HRC) and that contain tensile stresses caused by machining, grinding, straightening or cold-forming operations shall be given a stress relief heat treatment prior to cleaning and metal deposition. The procedures and classes for stress relief heat treatment shall be in accordance with the procedures and classes from ISO 9587 or as specified by the purchaser [see [Clause 4 m](#)].

Steels with oxide or scale shall be cleaned before application of the coatings. For high strength steels, non-electrolytic alkaline and anodic alkaline cleaners, as well as mechanical cleaning procedures, are preferred to avoid the risk of producing hydrogen embrittlement during cleaning operations. The possibility of overheating shall be considered in the case of mechanical cleaning of high-strength steels (tensile strength >1 400 MPa).

6.9 Hydrogen-embrittlement-relief heat treatment

Steel parts having an ultimate tensile strength equal to or greater than 1 000 MPa (31 HRC), as well as surface-hardened parts, shall receive hydrogen-embrittlement-relief heat treatment in accordance with the procedures and classes of ISO 9588 or as specified by the purchaser [see [Clause 4 n](#)].

The effectiveness of the embrittlement-relief treatment shall be determined by a test method specified by the purchaser [see [Clause 4 n](#)] or by the test methods described in ISO 10587 and ISO 15724.

6.10 Peening of metal parts

If peening prior to or after electroplating is specified by the purchaser, it shall be performed in accordance with ISO 12686. The method of measuring shot peening intensity is also described in ISO 12686 [see [Clause 4 g](#)].

Shot peening prior to electroplating can minimize the reduction in fatigue strength that occurs when high-strength steels are electroplated with chromium, and is recommended for parts subjected to repeated applications of complex load patterns in service. Other factors that affect fatigue strength include thickness, which shall be kept as thin as is compatible with the expected service conditions. The compressive stresses resulting from controlled shot peening increase corrosion resistance and resistance to stress corrosion cracking.

6.11 Use of undercoats

When specified by the purchaser [see [Clause 4 j](#))], nickel or other metallic undercoats may be applied, and hydrogen-embrittlement-relief treatment [see [Clause 4 n](#)) and [6.9](#)], if required, shall be carried out after electroplating of the metallic undercoats (before chromium plating) in accordance with the procedures and classes of ISO 9588. Electrolytic nickel undercoats shall conform to ISO 4526.

6.12 Stripping

Stripping and re-plating is permitted, but coatings on parts having an ultimate tensile strength equal to or greater than 1 000 MPa (31 HRC), which are stripped in acid, shall be given embrittlement-relief treatment (see [6.9](#)) before subsequent electroplating. Embrittlement-relief treatment after stripping may not be necessary if the parts are stripped anodically in an alkaline solution [see [Clause 4 n](#))].

With previously electroplated parts where the chromium has been worn through, or where grinding has exposed the basis metal, or the undercoat (if present), better results are often obtained by stripping the remaining chromium completely.

When the chromium on the surface is sound, however, the surface may be finished to approximate the requirements of the final product, for example, by grinding with a diamond wheel coated with aluminium oxide. After degreasing and anodically cleaning in an alkaline solution followed by thorough rinsing, the initial coating of metallic chromium may be activated by anodic etching at 6 V in the chromium electroplating solution for 10 s to 20 s, and then making the part cathodic, initially at 3 V and then slowly increasing the voltage so that gassing and electrodeposition commence in 30 s to 60 s, and full current is reached in 5 min.

6.13 Corrosion resistance/multilayer chromium plating

The high corrosion resistance of an electrodeposited metallic chromium coating is generated for engineering purposes and is one of the most important properties. The corrosion resistance shall be ensured by chromium thickness higher than 50 µm and shall be tested in accordance with ISO 9227, ascertained as hours of resistance against base material modification.

The corrosion resistance of the metallic chromium deposit can be varied by deposition parameters and also by the structure of the electrodeposited chromium coating. An additional improvement of its corrosion resistance can be achieved by multilayer chromium electroplating. In this case, at least two or (preferred for engineering purposes) three metallic chromium coatings are generated using different parameters during electroplating. The electroplating of each of these two or three metallic chromium coatings is done by variation in current density and/or temperature. This direct variation during electroplating of the coatings generates an intended crack-building mechanism. Therefore, it is important to achieve at least 150 µm of chromium thickness to avoid cracks going down to the base metal. The increased number of intended generated cracks in the metallic chromium coating reduces anodic corrosion current density and therefore corrosion resistance increases.

6.14 Surface roughness of electroplated metallic chromium coating

To fulfil all customer requirements, a metallic chromium coating, generated by electrodeposition for engineering purposes, shall have definite surface roughness and stated surface structure and shall be defined by the purchaser. Surface roughness and surface structure can vary from very rough ($R_{\max} \geq 50 \mu\text{m}$) up to mirror polished ($R_{\max} \leq 0,025 \mu\text{m}$). The surface profile of the metallic chromium coating with definite structure can vary between spherical calotte and totally jagged. For classification of these wide ranges of roughness measurements, see Table D.1.

7 Sampling

The method of sampling shall be selected from the procedures specified in ISO 4519. The acceptance levels shall be as specified by the purchaser [see [Clause 4 o](#))].

Annex A (informative)

Typical thickness of metallic chromium coatings specified in engineering applications

Table A.1 — Typical thickness of metallic chromium coatings specified in engineering applications

Typical thickness μm	Application
≥ 2 to ≤ 10	To reduce friction and for light wear resistance
> 10 to ≤ 30	For moderate wear resistance
> 30 to ≤ 60	For adhesive wear resistance
> 60 to ≤ 120	For severe wear resistance
> 120 to ≤ 250	For severe wear, abrasion and erosion resistance
> 250	For repair

STANDARDSISO.COM : Click to view the full PDF of ISO 6158:2018

Annex B (normative)

Thickness test methods for electroplated metallic chromium and other metallic coatings

B.1 General

ISO 3882 reviews methods of measuring the thickness of metallic and inorganic coatings.

B.2 Destructive tests

B.2.1 Microscopical method

Use the method specified in ISO 1463. The microscopical method shall be used for measuring the thickness of metallic chromium coatings and undercoats 10 μm and above.

B.2.2 Coulometric method

The coulometric method specified in ISO 2177 may be used to measure the total thickness of the metallic chromium deposits, as well as the thickness of a metallic under-layer, when present, at any point on the significant surface which can be touched by a ball 20 mm in diameter. In cases of dispute, the coulometric method shall be used for measuring the thickness of metallic chromium coatings less than 10 μm thick (see [6.4](#)).

B.2.3 Scanning electron microscope method

The scanning electron microscope method specified in ISO 9220 may be used to measure metallic chromium thickness and the thickness of under-layers.

B.3 Non-destructive tests

B.3.1 Magnetic method

The magnetic method specified in ISO 2178 may be used when the basis metal is magnetic.

B.3.2 Beta backscatter method

Use the method specified in ISO 3543. This method is suitable for measuring the thickness of metallic chromium coatings on aluminium and aluminium alloys, magnesium and magnesium alloys, titanium and titanium alloys, and non-metals.

B.3.3 X-ray spectrometric method

Use the method specified in ISO 3497. This method is also known as the X-ray fluorescence method.