



**International
Standard**

ISO 6626-1

**Internal combustion engines —
Piston rings —**

**Part 1:
Coil spring loaded oil control rings
made of cast iron**

*Moteurs à combustion interne — Segments de piston —
Partie 1: Anneaux de contrôle de l'huile à ressort hélicoïdal en fonte*

**First edition
2024-07**

STANDARDSISO.COM : Click to view the full PDF of ISO 6626-1:2024



COPYRIGHT PROTECTED DOCUMENT

© ISO 2024

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword	v
Introduction	vi
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Overview	1
5 Piston ring types and designation	2
5.1 Types DSF-C, DSF-CNP, SSF, GSF, DSF, DSF-NG and SSF-L — General features and dimensions.....	2
5.2 Type DSF-C — Coil-spring loaded bevelled edge oil control ring, chromium plated and profile ground.....	2
5.2.1 General features and dimensions.....	2
5.2.2 Example designation of a type DSF-C piston ring in accordance with this document.....	3
5.3 Type DSF-CNP — Coil-spring loaded bevelled edge oil control ring, chromium plated not profile ground.....	3
5.3.1 General features and dimensions.....	3
5.3.2 Example designation of a type DSF-CNP piston ring in accordance with this document.....	4
5.4 Type SSF — Coil-spring loaded slotted oil control ring.....	4
5.4.1 General features and dimensions.....	4
5.4.2 Example designation of a type SSF piston ring in accordance with this document.....	5
5.5 Type GSF — Coil-spring loaded double bevelled oil control ring.....	5
5.5.1 General features and dimensions.....	5
5.5.2 Example designation of a type GSF piston ring in accordance with this document.....	6
5.6 Type DSF — Coil-spring loaded bevelled edge oil control ring.....	6
5.6.1 General features and dimensions.....	6
5.6.2 Example designation of a type DSF piston ring in accordance with this document.....	7
5.7 Type DSF-NG — Coil-spring loaded bevelled edge oil control ring (face geometry similar to type DSF-C or type DSF-CNP).....	7
5.7.1 General features and dimensions.....	7
5.7.2 Example designation of a type DSF-NG piston ring in accordance with this document.....	8
5.8 Type SSF-L — Coil-spring loaded slotted oil control ring with $h_1 = 4,75$ mm (3/16 in) ring width and 0,6 mm nominal land width.....	8
5.8.1 General features and dimensions.....	8
5.8.2 Example designation of a type SSF-L piston ring in accordance with this document.....	9
6 Common features	9
6.1 Oil drainage by slots or holes.....	9
6.1.1 Arrangement of slots.....	9
6.1.2 Slot length.....	11
6.1.3 Arrangement of holes.....	11
6.1.4 Diameter and number of holes.....	11
6.2 Plating thickness — DSF-C and DSF-CNP Coil-spring loaded oil control rings.....	11
6.3 Peripheral edges at gap of chromium plated oil control rings.....	12
6.4 Spring groove and land offsets.....	12
7 Coil springs	12
7.1 Types of coil spring.....	12
7.2 Latch pin and location of small pitch in the coil spring.....	14
7.3 Coil spring excursion (extended gap).....	14
7.4 Position of coil spring gap and fixing.....	15

ISO 6626-1:2024(en)

7.5	Material	15
8	Tangential force and nominal contact pressure	15
8.1	Tangential force, F_t	15
8.1.1	Force factors	15
8.1.2	General tangential force, F_t	16
8.1.3	Actual tangential force, F_t , and tolerance	16
8.1.4	Normalized tangential force, F_N	16
8.2	Nominal contact pressure, p_o	16
9	Dimensions	16
Annex A (informative) Historical classes of nominal contact pressure, p_o		78
Bibliography		80

STANDARDSISO.COM : Click to view the full PDF of ISO 6626-1:2024

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents. ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 22, *Road vehicles*, Subcommittee SC 34, *Propulsion, powertrain and powertrain fluids*.

This first edition cancels and replaces ISO 6626:1989, which has been technically revised.

The main changes are as follows:

- classes of nominal contact pressure were moved to [Annex A](#) and the normalized tangential force was introduced;
- verification and correction of figures;
- update of dimension [Tables 8 to 25](#).

A list of all parts in the ISO 6626 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

The ISO 6626 series is one of a set of International Standards dealing with piston rings for reciprocating internal combustion engines. Others are the ISO 6621 series, ISO 6622, ISO 6623, ISO 6624, ISO 6625, the ISO 6626 series, and ISO 6627.

The common features and dimensional tables presented in this document constitute a broad range of variables. When selecting a particular ring type, the designer should bear in mind the conditions under which it will be required to operate.

It is also important that the designer refer to the specifications and requirements of ISO 6621-3 and ISO 6621-4 before completing selection.

STANDARDSISO.COM : Click to view the full PDF of ISO 6626-1:2024

Internal combustion engines — Piston rings —

Part 1: Coil spring loaded oil control rings made of cast iron

1 Scope

This document specifies the essential dimensional features of coil-spring loaded oil control rings made of cast iron, types DSF-C, DSF-CNP, SSF, GSF, DSF, DSF-NG and SSF-L. It is applicable to piston rings in sizes from 60 mm up to and including 200 mm for reciprocating internal combustion engines for road vehicles and other applications.

2 Normative references

The following documents are referred to in the text in such a way that some or all their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 6621-1, *Internal combustion engines — Piston rings — Part 1: Vocabulary*

ISO 6621-4, *Internal combustion engines — Piston rings — Part 4: General specifications*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 6621-1 apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

4 Overview

Coil-spring loaded oil control ring types are specified in [Figures 1](#) to [8](#). Their common features and the features' dimensions are specified in [Tables 1](#) to [5](#) and shown in [Figures 9](#) to [11](#). Essential features of coil springs are shown in [Figures 12](#) to [16](#). [Table 7](#) specifies different classes of contact pressure. [Tables 8](#) to [19](#) give the dimensions and forces of coil-spring loaded oil control rings.

The normal range for axial width of coil-spring loaded oil control rings (3 mm to 8 mm inclusive) is divided into 0,5 mm or 1,0 mm increments. In [Tables 20](#) to [25](#), dimensions are given for coil-spring loaded oil control rings with an axial width of 4,75 mm (i.e. 3/16 inch) for existing applications in inch units.

For the cast iron part, the recommended material is Class 10 in accordance with ISO 6621-3. For special applications, material Classes 20 to 50 may be used.

Variation from these in face design and spring groove may be used, as recommended by individual manufacturers, in plain or chromed versions.

5 Piston ring types and designation

5.1 Types DSF-C, DSF-CNP, SSF, GSF, DSF, DSF-NG and SSF-L — General features and dimensions

See [Figure 1](#) and [Tables 8](#) to [25](#). [Figure 1](#) is applicable to [Figures 2](#) to [8](#). [Figures 2](#) to [8](#) show detailed cross sections corresponding to [Figure 1](#).





Figure 1 — Types DSF-C, DSF-CNP, SSF, GSF, DSF, DSF-NG and SSF-L

NOTE Gap chamfer s_3 is for coated rings only.

5.2 Type DSF-C — Coil-spring loaded bevelled edge oil control ring, chromium plated and profile ground

5.2.1 General features and dimensions

See [Figure 2](#) and [Tables 8](#), [9](#) and [20](#).



Key

- 1 reference plane
- a See [Table 3](#).
- b See [Table 4](#).
- c See [Table 5](#).
- d Angles α and β to be agreed between manufacturer and customer. Angles can be different (historical value is 35°).

Figure 2 — Type DSF-C

5.2.2 Example design of a type DSF-C piston ring in accordance with this document


EXAMPLE Coil-spring loaded bevelled edge oil control ring, chromium plated and profile ground (DSF-C), of nominal diameter $d_1 = 124$ mm (124), nominal ring width $h_1 = 3,5$ mm (3,5), a land width $h_5 = 0,25$ mm (0,25), made of grey cast iron, non-heat treated, material subclass 11 (MC11), having a selected closed gap of 0,20 mm min. (S020), a chromium layer thickness on the lands of 0,15 mm (CR3), phosphated on all cast iron surfaces to depth of 0,002 mm min. (PO), reduced slot length (WK), a coil-spring with reduced heat set (WF), and a variable pitch with coil-diameter d_7 ground (CSE), with tangential force F_t in accordance with the nominal contact pressure of 1,5 N/mm² (PN1,5) and the ring marked with the manufacturer's mark (MM). Parameters in parenthesis are used in the ISO ring designation:

Piston ring ISO 6626-1 DSF-C - 124 × 3,5 × 0,25 - MC11 / S020 CR3 PO WK WF CSE PN1,5 MM

5.3 Type DSF-CNP — Coil-spring loaded bevelled edge oil control ring, chromium plated not profile ground

5.3.1 General features and dimensions

See [Figure 3](#) and [Tables 10, 11](#) and [21](#).



Key

- 1 reference plane
- a See [Table 3](#).
- b See [Table 4](#).
- c See [Table 5](#).
- d Angles α and β to be agreed between manufacturer and customer. Angles can be different (historical value is 35°).
- e Before plating.

Figure 3 — Type DSF-CNP

5.3.2 Example designation of a type DSF-CNP piston ring in accordance with this document


EXAMPLE Coil-spring loaded bevelled edge oil control ring, chromium plated, not profile ground (DSF-CNP) of nominal diameter $d_1 = 100$ mm (100), nominal ring width $h_1 = 4,0$ mm (4,0), a land width $h_5 = 0,40$ mm (0,40), made of grey cast iron, non-heat treated, material subclass 12 (MC12), constant spring pitch (CSN) and tangential force F_t in accordance with the nominal contact pressure of $P_0 = 1,0$ N/mm² (PN1,0). Parameters in parenthesis are used in the ISO ring designation:

Piston ring ISO 6626-1 DSF-CNP - 100 × 4 × 0,40 - MC12 / CSN PN1,0

5.4 Type SSF — Coil-spring loaded slotted oil control ring

5.4.1 General features and dimensions

See [Figure 4](#) and [Table 12](#), [13](#) and [22](#).



Key

- 1 reference plane
- a See [Table 4](#).
- b See [Table 5](#).

Figure 4 — Type SSF

5.4.2 Example designation of a type SSF piston ring in accordance with this document


EXAMPLE Coil-spring loaded slotted oil control ring with rectangular groove (SSF) of nominal diameter $d_1 = 80$ mm (80), nominal ring width $h_1 = 4$ mm (4,0), a land width $h_5 = 0,70$ mm (0,70), made of grey cast iron, non-heat treated, material subclass 12 (MC12), constant spring pitch (CSN) and tangential force F_t in accordance with the nominal contact pressure of $P_0 = 1,0$ N/mm² (PN1,0). Parameters in parenthesis are used in the ISO ring designation:

Piston ring ISO 6626-1 SSF- 80 × 4,0 × 0,70 - MC12 / CSN PN1,0

5.5 Type GSF — Coil-spring loaded double bevelled oil control ring

5.5.1 General features and dimensions

See [Figure 5](#) and [Tables 14](#), [15](#) and [23](#). Top side marking is mandatory and shall be performed in accordance with ISO 6621-4.



Key

- 1 reference plane
- 2 top side identification mark
- a See [Table 4](#).
- b See [Table 5](#).

Figure 5 — Type GSF

5.5.2 Example designation of a type GSF piston ring in accordance with this document


EXAMPLE Coil-spring loaded double bevelled oil control ring (GSF) of nominal diameter $d_1 = 75$ mm (75), nominal ring width $h_1 = 3,5$ mm (3,5), a land width $h_5 = 0,35$ mm (0,35), made of grey cast iron, non-heat treated, material subclass 12 (MC12), with constant spring pitch (CSN) and tangential force F_t in accordance with the nominal contact pressure of $P_0 = 1,0$ N/mm² (PN1,0). Parameters in parenthesis are used in the ISO ring designation:

Piston ring ISO 6626-1 GSF- 75 × 3,5 × 0,35 - MC12 / CSN PN1,0

5.6 Type DSF — Coil-spring loaded bevelled edge oil control ring

5.6.1 General features and dimensions

See [Figure 6](#) and [Tables 14](#), [15](#) and [23](#).



Key

- 1 reference plane
- a See [Table 4](#).
- b See [Table 5](#).

Figure 6 — Type DSF

5.6.2 Example designation of a type DSF piston ring in accordance with this document


EXAMPLE Coil-spring loaded bevelled edge oil control ring (DSF) of nominal diameter $d_1 = 90$ mm (90), nominal ring width $h_1 = 3,5$ mm (3,5), a land width $h_5 = 0,35$ mm (0,35), made of grey cast iron, non-heat treated, material subclass 12 (MC12), with constant spring pitch (CSN) and tangential force F_t in accordance with the nominal contact pressure of $P_0 = 1,0$ N/mm² (PN1,0). Parameters in parenthesis are used in the ISO ring designation:

Piston ring ISO 6626-1 DSF- 90 × 3,5 × 0,35 - MC12 / CSN PN1,0

5.7 Type DSF-NG — Coil-spring loaded bevelled edge oil control ring (face geometry similar to type DSF-C or type DSF-CNP)

5.7.1 General features and dimensions

See [Figure 7](#) and [Tables 16, 17](#) and [24](#).



Key

- 1 reference plane
- a See [Table 4](#).
- b See [Table 5](#).
- c Angles α and β to be agreed between manufacturer and customer. Angles can be different (historical value is 35°).

Figure 7 — Type DSF-NG

5.7.2 Example designation of a type DSF-NG piston ring in accordance with this document


EXAMPLE Coil-spring loaded bevelled edge oil control ring (DSF-NG, face geometry similar to type DSF-C or type DSF-CNP) of nominal diameter $d_1 = 140$ mm (140), nominal ring width $h_1 = 4,5$ mm (4,5), a land width $h_5 = 0,40$ mm (0,40), made of grey cast iron, non-heat treated, material subclass 12 (MC12), constant spring pitch (CSN) and tangential force F_t in accordance with the nominal contact pressure of $P_0 = 1,0$ N/mm² (PN1,0). Parameters in parenthesis are used in the ISO ring designation:

Piston ring ISO 6626-1 DSF-NG - 140 × 4,5 × 0,40 - MC12 / CSN PN1,0

5.8 Type SSF-L — Coil-spring loaded slotted oil control ring with $h_1 = 4,75$ mm (3/16 in) ring width and 0,6 mm nominal land width

5.8.1 General features and dimensions

See [Figure 8](#) and [Tables 18, 19](#) and [25](#).



Key

- 1 reference plane
- a See [Table 4](#).
- b See [Table 5](#).
- c Angles α and β to be agreed between manufacturer and customer. Angles can be different (historical value is 35°).

Figure 8 — Type SSF-L

5.8.2 Example designation of a type SSF-L piston ring in accordance with this document

EXAMPLE Coil-spring loaded slotted oil control ring with rectangular groove at periphery and V-shaped groove beneath (SSF-L) of nominal diameter $d_1 = 80$ mm (80), nominal ring width $h_1 = 4,75$ mm (4,75), made of grey cast iron, non-heat treated, material subclass 12 (MC12), constant spring pitch (CSN) and tangential force F_t in accordance with the nominal contact pressure of $P_0=1,0$ N/mm² (PN1,0). Parameters in parenthesis are used in the ISO ring designation:


Piston ring ISO 6626-1 SSF-L - 80 × 4,75 - MC12 / CSN PN1,0

6 Common features


6.1 Oil drainage by slots or holes

6.1.1 Arrangement of slots


[Figure 9](#) shows the arrangement of oil drainage slots and [Table 1](#) gives the cutter diameter.




a) 8 slots for $60 \text{ mm} \leq d_1 < 80 \text{ mm}$



b) 10 slots for $80 \text{ mm} \leq d_1 < 115 \text{ mm}$



c) 12 slots for $115 \text{ mm} \leq d_1 < 150 \text{ mm}$



d) 14 slots for $150 \text{ mm} \leq d_1 \leq 200 \text{ mm}$

Figure 9 — Arrangement of slots

Table 1 — Cutter diameter

Dimensions in millimeters

Nominal diameter d_1	Cutter diameter d_5 max.
$60 \leq d_1 < 150$	60
$150 \leq d_1 \leq 200$	75

6.1.2 Slot length

6.1.2.1 Standard slot length

Slot length, w_1 , shall be equal to bridge length, w_2 .

The maximum difference between w_1 and w_2 shall be 4 mm.

6.1.2.2 Reduced slot length — Code WK

Oil control rings with reduced slot length will retain the same number of slots and the same angular spacing. The maximum difference between w_1 and w_2 for the standard slot length does not apply.

See [Table 2](#).

Table 2 — Reduced slot length

Dimensions in millimeters

d_1	w_1 (range of nominal values)
$60 \leq d_1 < 80$	6 ... 11
$80 \leq d_1 < 115$	8 ... 13
$115 \leq d_1 < 150$	10 ... 15
$150 \leq d_1 \leq 200$	12 ... 18

6.1.3 Arrangement of holes

Arrangement of holes is shown in [Figure 10](#). Deviating arrangements shall be agreed between manufacturer and customer.




Figure 10 — Arrangement of holes

6.1.4 Diameter and number of holes

The diameter, d_{15} , and number, n , of holes shall be agreed between manufacturer and customer.

6.2 Plating thickness — DSF-C and DSF-CNP Coil-spring loaded oil control rings

See [Figure 11](#) and [Table 3](#).




Figure 11 — Plating thickness

Table 3 — Plating thickness

Dimensions in millimeters

Code	Thickness ^a min.
CR1	0,05
CR2	0,10
CR3	0,15

^a For plating thickness tolerances, see ISO 6621-4.

6.3 Peripheral edges at gap of chromium plated oil control rings

For features and their dimensions, see ISO 6621-4.

6.4 Spring groove and land offsets

See [Figures 2](#) to [8](#) and [Tables 4](#) and [5](#).

Table 4 — Permitted land offset

Dimensions in millimetres

Ring width h_1	t
$3 \leq h_1 < 5$	0,015
$5 \leq h_1 \leq 8$	0,025

Table 5 — Permitted spring groove offset

Dimensions in millimetres

Ring width h_1	v
$h_1 < 3,5$	0,3
$h_1 \geq 3,5$	0,4

7 Coil springs

7.1 Types of coil spring

All values in the dimensional tables of [Clause 9](#) are based on cylindrical coil-springs made of round wire. The three designs shown in [Figures 12](#) to [14](#) are common. The use of different spring designs may be agreed

between manufacturer and customer. Changed spring groove configurations and dimensions can then be necessary.






Figure 12 — Type CSN coil spring with constant pitch



Key

1 approximately $0,8 \times d_8$

Figure 13 — Type CSG coil spring with constant pitch (coil diameter, d_7 , ground)



Key


1 approximately $0,8 \times d_8$

Figure 14 — Type CSE coil spring with variable pitch (coil diameter, d_7 , ground)

7.2 Latch pin and location of small pitch in the coil spring

Figure 15 illustrates the location of the small pitch area of the coil spring relative to the spring gap.

Dimensions in millimeters



Key

- 1 spring gap
- 2 area with small pitch
- a Latch pin free length.
- b Latch pin fixed length.

Figure 15 — Position of area with small pitch

7.3 Coil spring excursion (extended gap)

Coil spring excursion, f_1 , is the distance between the ends of the ring gap, with unstressed ring, measured in the middle of the spring groove (see Figure 16). The maximum value of f_1 is given in Table 6.




Figure 16 — Coil spring excursion

Table 6 — Coil spring excursion

Dimensions in millimeters

Nominal diameter d_1	f_1 max.
$60 \leq d_1 < 125$	$0,13 \times d_1$
$125 \leq d_1 \leq 200$	$0,12 \times d_1$

7.4 Position of coil spring gap and fixing

The spring gap shall be approximately 180° from the gap and the spring gap ends fixed with a connecting or latch pin.

7.5 Material

Coil springs are made of materials as shown in ISO 6621-3, subclasses MC62 (valve spring wire), MC64 (Chromium-Silicon steel), MC67 (stainless steel) and MC68 (piano wire).

Springs are available with two different heat set resistance levels (loss of tangential force under load and temperature):

- standard heat resistance;
- reduced heat set, code WF.

For test conditions and the permissible loss of tangential forces, see ISO 6621-5.

8 Tangential force and nominal contact pressure

8.1 Tangential force, F_t

The tangential force, F_t , of coil-spring loaded oil control rings is mainly determined by the force of the spring. The cast iron part itself has a very small tangential force due to its low radial wall thickness and the decreased ratio “total free gap/nominal diameter”.

Only the tangential force measurement method can be used because of the flexible design of the cast iron part of the coil-spring loaded oil control rings.

8.1.1 Force factors

Because of the small contribution of the cast iron part in the tangential force, force factors are not necessary when additional features, materials, or both (other than grey cast iron with modulus of elasticity of 100 GN/m²) are being used.

8.1.2 General tangential force, F_t

The tangential force, F_t , of a spring loaded oil control ring is determined by:

- nominal diameter, d_1 , in millimetres,
- land width, h_5 , in millimeters,
- required nominal contact pressure, p_0 , in N/mm^2 , calculated using the formula:

$$F_t = \frac{1}{2} \cdot d_1 \cdot 2 \cdot h_5 \cdot p_0$$

The land width, h_5 , depends on the ring type, nominal diameter, and ring width. Recommended values for land width, h_5 , are mentioned for every ring type in [Clause 9](#). Other values may be agreed between manufacturer and customer.

8.1.3 Actual tangential force, F_t , and tolerance

The actual tangential force of a spring-loaded oil control ring can be calculated with the tabulated normalized tangential force, F_t/d_1 , given in [Table 7](#), according to the required nominal contact pressure, p_0 , using the formula:

$$F_t = (F_N) \cdot d_1$$

The tolerance on F_t is the actual value $F_t \pm 20\%$. Actual values of tangential force shall be rounded up or down in accordance with ISO 6621-4.

8.1.4 Normalized tangential force, F_N

The normalized tangential forces, $F_N (= F_t/d_1)$, for different nominal contact pressure, p_0 , are given in [Table 7](#).

Table 7 — Normalized tangential forces, F_N

Code	P_0 [N/mm ²]	0,2	0,25	0,28	0,30	0,35	0,40	0,50	0,60	0,70	0,80	0,90	1,10	1,30	1,60
PN2,5	2,5	0,50	0,63	0,70	0,75	0,88	1,00	1,25	1,50	1,75	2,00	2,25	2,75	3,25	4,00
PN2,0	2,0	0,40	0,50	0,56	0,60	0,70	0,80	1,00	1,20	1,40	1,60	1,80	2,20	2,60	3,20
PN1,5	1,5	0,30	0,38	0,42	0,45	0,53	0,60	0,75	0,90	1,05	1,20	1,35	1,65	1,95	2,40
PN1,0	1,0	0,20	0,25	0,28	0,30	0,35	0,40	0,50	0,60	0,70	0,80	0,90	1,10	1,30	1,60
PN0,5	0,5	0,10	0,13	0,14	0,15	0,18	0,20	0,25	0,30	0,35	0,40	0,45	0,55	0,65	0,80

8.2 Nominal contact pressure, p_0

New contact pressure classes are introduced and have replaced the classes of nominal contact pressure used in ISO 6626:1989, which are shown in [Annex A](#) for reference.

The nominal contact pressure, p_0 , must be chosen to suit the application and requirements regarding oil consumption and friction losses. The range of the usual nominal contact pressure, p_0 , is given in [Table 7](#). Varying values may be agreed between manufacturer and customer.

9 Dimensions

The dimensions are shown in [Tables 8 to 25](#). Land spacing B_3 shall be agreed between manufacturer and customer.

Table 8 — Width dimensions of DSF-C oil control rings

Dimensions in millimeters

Nominal diameter	Radial thickness over coil spring a_{12} Tolerance for h_1 shown in column				Ring width h_1 column					Closed gap s_1	Radial wall thickness a_1 for h_1 shown in column					Land width h_5 for all h_1 Recommended range
	1	2	3	4	1	2	3	4	Tolerance		1	2	3	4	Tolerance	
$60 \leq d_1 < 65$	-	3,5 0 0,25	3,5 0 0,25	3,7 0 0,25	-	3	3,5	4	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,2 +0,2 0	-	2,4	2,4	2,5	$\pm 0,15$ within a ring 0,15 max.	0,20-0,4 $\pm 0,07$
$65 \leq d_1 < 70$	-	3,6 0 0,25	3,7 0 0,25	3,7 0 0,25	-	3	3,5	4	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,2 +0,2 0	-	2,45	2,5	2,5	$\pm 0,15$ within a ring 0,15 max.	0,20-0,4 $\pm 0,07$
$70 \leq d_1 < 75$	-	3,6 0 0,25	3,8 0 0,25	3,9 0 0,25	-	3	3,5	4	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,2 +0,2 0	-	2,55	2,6	2,6	$\pm 0,15$ within a ring 0,15 max.	0,20-0,4 $\pm 0,07$
$75 \leq d_1 < 80$	-	3,7 0 0,25	3,9 0 0,25	4 0 0,25	-	3	3,5	4	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,25 +0,25 0	-	2,6	2,7	2,7	$\pm 0,15$ within a ring 0,15 max.	0,20-0,4 $\pm 0,07$
$80 \leq d_1 < 85$	3,8 0 0,25	4 0 0,25	4,1 0 0,25	4,1 0 0,25	3	3,5	4	4,5	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,25 +0,25 0	2,7	2,7	2,8	2,8	$\pm 0,15$ within a ring 0,15 max.	0,25-0,4 $\pm 0,07$
$85 \leq d_1 < 90$	3,9 0 0,25	4 0 0,25	4,1 0 0,25	4,1 0 0,25	3	3,5	4	4,5	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,25 +0,25 0	2,8	2,8	2,9	2,9	$\pm 0,15$ within a ring 0,15 max.	0,25-0,4 $\pm 0,07$

NOTE For intermediate sizes (e.g. repair sizes), the radial thickness of the next smaller nominal diameter applies.

Table 8 (continued)

Nominal diameter	Radial thickness over coil spring a_{12} Tolerance for h_1 shown in column				Ring width h_1 column					Closed gap s_1	Radial wall thickness a_1 for h_1 shown in column					Land width h_5 for all h_1 Recommended range
	d_1	1	2	3	4	1	2	3	4		Tolerance	1	2	3	4	
$90 \leq d_1 < 95$	3,9 0 -	4,1 0 -	4,2 0 -	4,2 0 -	3	3,5	4	4,5	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,3 +0,25 0	2,85	2,9	2,95	3	$\pm 0,15$ within a ring 0,15 max.	0,25-0,4 $\pm 0,07$
$95 \leq d_1 < 100$	4 0 -	4,1 0 -	4,2 0 -	4,2 0 -	3	3,5	4	4,5	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,3 +0,25 0	2,95	3	3,05	3,1	$\pm 0,15$ within a ring 0,15 max.	0,25-0,4 $\pm 0,07$
$100 \leq d_1 < 105$	4,2 0 -	4,4 0 -	4,5 0 -	4,7 0 -	3,5	4	4,5	5	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,3 +0,25 0	3,05	3,1	3,15	3,2	$\pm 0,20$ within a ring 0,2 max.	0,25-0,4 $\pm 0,07$
$105 \leq d_1 < 110$	4,2 0 -	4,4 0 -	4,5 0 -	4,7 0 -	3,5	4	4,5	5	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,3 +0,25 0	3,1	3,15	3,2	3,3	$\pm 0,20$ within a ring 0,2 max.	0,25-0,4 $\pm 0,07$
$110 \leq d_1 < 115$	4,3 0 -	4,5 0 -	4,6 0 -	4,8 0 -	3,5	4	4,5	5	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,35 +0,30 0	3,2	3,25	3,3	3,4	$\pm 0,20$ within a ring 0,2 max.	0,25-0,4 $\pm 0,07$
$115 \leq d_1 < 120$	4,4 0 -	4,6 0 -	4,7 0 -	4,9 0 -	3,5	4	4,5	5	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,35 +0,30 0	3,3	3,35	3,4	3,5	$\pm 0,20$ within a ring 0,2 max.	0,25-0,4 $\pm 0,07$

NOTE For intermediate sizes (e.g. repair sizes), the radial thickness of the next smaller nominal diameter applies.

Table 8 (continued)

Nominal diameter	Radial thickness over coil spring a_{12} Tolerance for h_1 shown in column				Ring width h_1 column					Closed gap s_1	Radial wall thickness a_1 for h_1 shown in column					Land width h_5 for all h_1 Recommended range
	d_1	1	2	3	4	1	2	3	4		Tolerance	1	2	3	4	
$120 \leq d_1 < 125$	4,4 0 - 0,25	4,6 0 - 0,25	4,8 0 - 0,25	5 0 - 0,25	3,5	4	4,5	5	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,35 +0,30 0	3,4	3,45	3,5	3,6	$\pm 0,20$ within a ring 0,2 max.	0,25-0,4 $\pm 0,07$
$125 \leq d_1 < 130$	4,7 0 - 0,25	4,9 0 - 0,25	5 0 - 0,25	5,2 0 - 0,25	4	4,5	5	6	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,4 +0,3 0	3,5	3,6	3,7	3,8	$\pm 0,15$ within a ring 0,15 max.	0,25-0,5 $\pm 0,07$
$130 \leq d_1 < 135$	4,7 0 - 0,25	4,9 0 - 0,25	5,1 0 - 0,25	5,3 0 - 0,25	4	4,5	5	6	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,4 +0,3 0	3,5	3,6	3,7	3,8	$\pm 0,15$ within a ring 0,15 max.	0,25-0,5 $\pm 0,07$
$135 \leq d_1 < 140$	4,9 0 - 0,25	5,1 0 - 0,25	5,3 0 - 0,25	5,5 0 - 0,25	4	4,5	5	6	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,4 +0,3 0	3,6	3,7	3,8	3,9	$\pm 0,20$ within a ring 0,2 max.	0,25-0,5 $\pm 0,07$
$140 \leq d_1 < 145$	4,9 0 - 0,25	5,1 0 - 0,25	5,3 0 - 0,25	5,5 0 - 0,25	4	4,5	5	6	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,4 +0,3 0	3,7	3,8	3,9	4	$\pm 0,20$ within a ring 0,2 max.	0,25-0,5 $\pm 0,07$
$145 \leq d_1 < 150$	4,9 0 - 0,25	5,1 0 - 0,25	5,3 0 - 0,25	5,5 0 - 0,25	4	4,5	5	6	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,4 +0,3 0	3,8	3,9	4	4,1	$\pm 0,20$ within a ring 0,2 max.	0,25-0,5 $\pm 0,07$

NOTE For intermediate sizes (e.g. repair sizes), the radial thickness of the next smaller nominal diameter applies.

Table 8 (continued)

Nominal diameter	Radial thickness over coil spring a_{12} Tolerance for h_1 shown in column				Ring width h_1 column					Closed gap s_1	Radial wall thickness a_1 for h_1 shown in column					Land width h_5 for all h_1 Recommended range
	d_1	1	2	3	4	1	2	3	4		Tolerance	1	2	3	4	
$150 \leq d_1 < 155$	5,4 0 - 0,25	5,4 0 - 0,25	5,5 0 - 0,25	5,5 0 - 0,25	4,5	5	6	7	-0,010 -0,035 For phosphated PO surface: -0,005 -0,035	0,45 +0,35 0	3,9	4	4,1	4,2	±0,20 within a ring 0,2 max.	0,25-0,5 ±0,07 0,6 ±0,09
$155 \leq d_1 < 160$	5,4 0 - 0,25	5,4 0 - 0,25	5,5 0 - 0,25	5,5 0 - 0,25	4,5	5	6	7	-0,010 -0,035 For phosphated PO surface: -0,005 -0,035	0,45 +0,35 0	3,9	4	4,1	4,2	±0,20 within a ring 0,2 max.	0,25-0,5 ±0,07 0,6 ±0,09
$160 \leq d_1 < 165$	5,4 0 - 0,25	5,6 0 - 0,25	5,8 0 - 0,25	6 0 - 0,25	4,5	5	6	7	-0,010 -0,035 For phosphated PO surface: -0,005 -0,035	0,45 +0,35 0	4	4,2	4,3	4,4	±0,20 within a ring 0,2 max.	0,25-0,5 ±0,07 0,6 ±0,09
$165 \leq d_1 < 170$	5,4 0 - 0,25	5,6 0 - 0,25	5,8 0 - 0,25	6 0 - 0,25	4,5	5	6	7	-0,010 -0,035 For phosphated PO surface: -0,005 -0,035	0,45 +0,35 0	4	4,2	4,3	4,4	±0,20 within a ring 0,2 max.	0,25-0,5 ±0,07 0,6 ±0,09
$170 \leq d_1 < 175$	5,4 0 - 0,25	5,6 0 - 0,25	5,8 0 - 0,25	6 0 - 0,25	4,5	5	6	7	-0,010 -0,035 For phosphated PO surface: -0,005 -0,035	0,45 +0,35 0	4	4,2	4,3	4,4	±0,20 within a ring 0,2 max.	0,25-0,5 ±0,07 0,6 ±0,09
$175 \leq d_1 < 180$	5,8 0 -0,35	6 0 -0,35	6,3 0 -0,35	6,7 0 -0,35	5	6	7	8	-0,010 -0,035 For phosphated PO surface: -0,005 -0,035	0,55 +0,40 0	4,6	4,7	4,8	5	±0,20 within a ring 0,2 max.	0,3-0,5 ±0,07 0,6 ±0,09
$180 \leq d_1 < 185$	5,8 0 -0,35	6 0 -0,35	6,3 0 -0,35	6,7 0 -0,35	5	6	7	8	-0,010 -0,035 For phosphated PO surface: -0,005 -0,035	0,55 +0,40 0	4,6	4,7	4,8	5	±0,20 within a ring 0,2 max.	0,3-0,5 ±0,07 0,6 ±0,09

NOTE For intermediate sizes (e.g. repair sizes), the radial thickness of the next smaller nominal diameter applies.

Table 8 (continued)

Nominal diameter	Radial thickness over coil spring a_{12} Tolerance for h_1 shown in column				Ring width h_1 column					Closed gap s_1	Radial wall thickness a_1 for h_1 shown in column					Land width h_5 for all h_1 Recommended range
	d_1	1	2	3	4	1	2	3	4		Tolerance	1	2	3	4	
$185 \leq d_1 < 190$	6,2 0 -0,4	6,5 0 -0,4	6,7 0 -0,4	7,1 0 -0,4	5	6	7	8	-0,010 -0,035 For phosphated PO surface: -0,005 -0,035	0,55 +0,40 0	4,9	5	5,1	5,3	$\pm 0,20$ within a ring 0,2 max.	0,3-0,5 $\pm 0,07$ 0,6 $\pm 0,09$
$190 \leq d_1 < 195$	6,2 0 -0,4	6,5 0 -0,4	6,7 0 -0,4	7,1 0 -0,4	5	6	7	8	-0,010 -0,035 For phosphated PO surface: -0,005 -0,035	0,55 +0,40 0	4,9	5	5,1	5,3	$\pm 0,20$ within a ring 0,2 max.	0,3-0,5 $\pm 0,07$ 0,6 $\pm 0,09$
$195 \leq d_1 \leq 200$	6,2 0 -0,4	6,5 0 -0,4	6,7 0 -0,4	7,1 0 -0,4	5	6	7	8	-0,010 -0,035 For phosphated PO surface: -0,005 -0,035	0,55 +0,40 0	4,9	5	5,1	5,3	$\pm 0,20$ within a ring 0,2 max.	0,3-0,5 $\pm 0,07$ 0,6 $\pm 0,09$

NOTE For intermediate sizes (e.g. repair sizes), the radial thickness of the next smaller nominal diameter applies.

Table 9 — Groove and spring dimensions of DSF-C oil control rings

Dimensions in millimetres

Nominal diameter	Groove depth a_4 for h_1 shown in column				Groove depth and bridge a_{13} for h_1 shown in column				Coil spring groove diameter d_{14} for h_1 shown in column				Coil spring diameter d_7 for h_1 shown in column				
	d_1	1	2	3	4	1	2	3	4	1	2	3	4	1	2	3	4
$60 \leq d_1 < 65$	-	0,45 $\pm 0,1$	0,45 $\pm 0,1$	0,5 $\pm 0,1$	-	1,5 0 -0,15	1,5 0 -0,15	1,5 0 -0,15	-	2,1 +0,1 0	2,1 +0,1 0	2,3 +0,1 0	-	2 -0,1 0	2 -0,1 0	2,2 -0,1 0	-0,1 0
$65 \leq d_1 < 70$	-	0,45 $\pm 0,1$	0,45 $\pm 0,1$	0,5 $\pm 0,1$	-	1,6 0 -0,15	1,5 0 -0,15	1,5 0 -0,15	-	2,1 +0,1 0	2,3 +0,1 0	2,3 +0,1 0	-	2 -0,1 0	2,2 -0,1 0	2,2 -0,1 0	-0,1 0
$70 \leq d_1 < 75$	-	0,45 $\pm 0,1$	0,45 $\pm 0,1$	0,5 $\pm 0,1$	-	1,6 0 -0,15	1,6 0 -0,15	1,5 0 -0,15	-	2,1 +0,1 0	2,3 +0,1 0	2,5 +0,1 0	-	2 -0,1 0	2,2 -0,1 0	2,4 -0,1 0	-0,1 0
$75 \leq d_1 < 80$	-	0,45 $\pm 0,1$	0,45 $\pm 0,1$	0,5 $\pm 0,1$	-	1,7 0 -0,15	1,7 0 -0,15	1,6 0 -0,15	-	2,1 +0,1 0	2,3 +0,1 0	2,5 +0,1 0	-	2 -0,1 0	2,2 -0,1 0	2,4 -0,1 0	-0,1 0
$80 \leq d_1 < 85$	0,45 $\pm 0,1$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	1,8 0 -0,15	1,8 0 -0,15	1,7 0 -0,15	1,7 0 -0,15	2,1 +0,1 0	2,3 +0,1 0	2,5 +0,1 0	2,5 +0,1 0	2 -0,1 0	2,2 -0,1 0	2,4 -0,1 0	2,4 -0,1 0	-0,1 0
$85 \leq d_1 < 90$	0,45 $\pm 0,1$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	1,9 0 -0,15	1,8 0 -0,15	1,7 0 -0,15	1,7 0 -0,15	2,1 +0,1 0	2,3 +0,1 0	2,5 +0,1 0	2,5 +0,1 0	2 -0,1 0	2,2 -0,1 0	2,4 -0,1 0	2,4 -0,1 0	-0,1 0
$90 \leq d_1 < 95$	0,45 $\pm 0,1$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	1,9 0 -0,15	1,9 0 -0,15	1,8 0 -0,15	1,8 0 -0,15	2,1 +0,1 0	2,3 +0,1 0	2,5 +0,1 0	2,5 +0,1 0	2 -0,1 0	2,2 -0,1 0	2,4 -0,1 0	2,4 -0,1 0	-0,1 0

Table 9 (continued)

Nominal diameter	Groove depth a_4 for h_1 shown in column				Groove depth and bridge a_{13} for h_1 shown in column				Coil spring groove diameter d_{14} for h_1 shown in column				Coil spring diameter d_7 for h_1 shown in column				
	d_1	1	2	3	4	1	2	3	4	1	2	3	4	1	2	3	4
$95 \leq d_1 < 100$	0,45 $\pm 0,1$	0,45 $\pm 0,1$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	2 0 - 0,15	1,9 0 - 0,15	1,8 0 - 0,15	1,8 0 - 0,15	2,1 +0,1 0	2,3 +0,1 0	2,5 +0,1 0	2,5 +0,1 0	2 -0,1 0	2,2 -0,1 0	2,4 -0,1 0	2,4 -0,1 0	2,4 -0,1 0
$100 \leq d_1 < 105n$	0,45 $\pm 0,1$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	2 0 - 0,15	2 0 -0,2	1,9 0 -0,2	1,9 0 -0,2	2,3 +0,1 0	2,5 +0,1 0	2,7 +0,1 0	2,9 +0,1 0	2,2 - 0,1 0	2,4 - 0,1 0	2,6 - 0,1 0	2,8 - 0,1 0	2,8 - 0,1 0
$105 \leq d_1 < 110$	0,45 $\pm 0,1$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	2 0 - 0,15	2 0 -0,2	1,9 0 -0,2	1,9 0 -0,2	2,3 +0,1 0	2,5 +0,1 0	2,7 +0,1 0	2,9 +0,1 0	2,2 - 0,1 0	2,4 - 0,1 0	2,6 - 0,1 0	2,8 - 0,1 0	2,8 - 0,1 0
$110 \leq d_1 < 115$	0,45 $\pm 0,1$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	2,1 0 -0,2	2,1 0 -0,2	2 0 -0,2	2 0 -0,2	2,3 +0,1 0	2,5 +0,1 0	2,7 +0,1 0	2,9 +0,1 0	2,2 - 0,1 0	2,4 - 0,1 0	2,6 - 0,1 0	2,8 - 0,1 0	2,8 - 0,1 0
$115 \leq d_1 < 120$	0,45 $\pm 0,1$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	2,2 0 -0,2	2,2 0 -0,2	2,1 0 -0,2	2,1 0 -0,2	2,3 +0,1 0	2,5 +0,1 0	2,7 +0,1 0	2,9 +0,1 0	2,2 - 0,1 0	2,4 - 0,1 0	2,6 - 0,1 0	2,8 - 0,1 0	2,8 - 0,1 0
$120 \leq d_1 < 125$	0,45 $\pm 0,1$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	2,2 0 -0,2	2,2 0 -0,2	2,2 0 -0,2	2,2 0 -0,2	2,3 +0,1 0	2,5 +0,1 0	2,7 +0,1 0	2,9 +0,1 0	2,2 - 0,1 0	2,4 - 0,1 0	2,6 - 0,1 0	2,8 - 0,1 0	2,8 - 0,1 0
$125 \leq d_1 < 130$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	2,3 0 -0,2	2,3 0 -0,2	2,2 0 -0,2	2,2 0 -0,2	2,5 +0,1 0	2,7 +0,1 0	2,9 +0,1 0	3,1 +0,1 0	2,4 - 0,1 0,1	2,6 - 0,1 0,1	2,8 - 0,1 0,1	3 - 0,1 0,1	3 - 0,1 0,1
$130 \leq d_1 < 135$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	2,3 0 -0,2	2,3 0 -0,2	2,3 0 -0,2	2,3 0 -0,2	2,5 +0,1 0	2,7 +0,1 0	2,9 +0,1 0	3,1 +0,1 0	2,4 - 0,1 0	2,6 - 0,1 0	2,8 - 0,1 0	3,0 - 0,1 0	3,0 - 0,1 0
$135 \leq d_1 < 140$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	2,3 0 -0,2	2,3 0 -0,2	2,3 0 -0,2	2,3 0 -0,2	2,7 +0,1 0	2,9 +0,1 0	3,1 +0,1 0	3,3 +0,15 0	2,6 - 0,1 0	2,8 - 0,1 0	3 - 0,1 0	3,2 - 0,1 0	3,2 - 0,1 0
$140 \leq d_1 < 145$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	2,3 0 -0,2	2,3 0 -0,2	2,3 0 -0,2	2,3 0 -0,2	2,7 +0,1 0	2,9 +0,1 0	3,1 +0,1 0	3,3 +0,15 0	2,6 - 0,1 0	2,8 - 0,1 0	3 - 0,1 0	3,2 - 0,1 0	3,2 - 0,1 0
$145 \leq d_1 < 150$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	2,3 0 -0,2	2,3 0 -0,2	2,3 0 -0,2	2,3 0 -0,2	2,7 +0,1 0	2,9 +0,1 0	3,1 +0,1 0	3,3 +0,15 0	2,6 - 0,1 0	2,8 - 0,1 0	3 - 0,1 0	3,2 - 0,1 0	3,2 - 0,1 0
$150 \leq d_1 < 155$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	2,6 0 - 0,2	2,4 0 - 0,2	2,3 0 - 0,2	2,3 0 - 0,2	2,9 +0,1 0	3,1 +0,15 0	3,3 +0,15 0	3,3 +0,15 0	2,8 0 - 0,1	3 0 - 0,1	3,2 0 - 0,1	3,2 0 - 0,1	3,2 0 - 0,1
$155 \leq d_1 < 160$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	2,6 0 - 0,2	2,4 0 - 0,2	2,3 0 - 0,2	2,3 0 - 0,2	2,9 +0,1 0	3,1 +0,15 0	3,3 +0,15 0	3,3 +0,15 0	2,8 0 - 0,1	3 0 - 0,1	3,2 0 - 0,1	3,2 0 - 0,1	3,2 0 - 0,1
$160 \leq d_1 < 165$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	2,6 0 - 0,2	2,6 0 - 0,2	2,6 0 - 0,2	2,4 0 - 0,2	2,9 +0,1 0	3,1 +0,15 0	3,3 +0,15 0	3,7 +0,15 0	2,8 0 - 0,1	3 0 - 0,1	3,2 0 - 0,1	3,6 0 - 0,1	3,6 0 - 0,1

Table 9 (continued)

Nominal diameter	Groove depth a_4 for h_1 shown in column				Groove depth and bridge a_{13} for h_1 shown in column				Coil spring groove diameter d_{14} for h_1 shown in column				Coil spring diameter d_7 for h_1 shown in column			
	d_1	1	2	3	4	1	2	3	4	1	2	3	4	1	2	3
$165 \leq d_1 < 170$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	2,6 0 - 0,2	2,6 0 - 0,2	2,6 0 - 0,2	2,4 0 - 0,2	2,9 +0,1 0	3,1 +0,15 0	3,3 +0,15 0	3,7 +0,15 0	2,8 0 - 0,1	3 0 - 0,1	3,2 0 - 0,1	3,6 0 - 0,1
$170 \leq d_1 < 175$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	2,6 0 - 0,2	2,6 0 - 0,2	2,6 0 - 0,2	2,4 0 - 0,2	2,9 +0,1 0	3,1 +0,15 0	3,3 +0,15 0	3,7 +0,15 0	2,8 0 - 0,1	3 0 - 0,1	3,2 0 - 0,1	3,6 0 - 0,1
$175 \leq d_1 < 180$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	1,2 $\pm 0,15$	1,5 $\pm 0,15$	2,8 0 - 0,2	2,8 0 - 0,2	2,7 0 - 0,2	2,7 0 - 0,2	3,1 +0,1 0	3,3 +0,15 0	3,7 +0,15 0	4,15 +0,15 0	3 0,1 0	3,2 0 0	3,6 0,1 0	4 - 0,12 0
$180 \leq d_1 < 185$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	1,2 $\pm 0,15$	1,5 $\pm 0,15$	2,8 0 - 0,2	2,8 0 - 0,2	2,7 0 - 0,2	2,7 0 - 0,2	3,1 +0,1 0	3,3 +0,15 0	3,7 +0,15 0	4,15 +0,15 0	3 0,1 0	3,2 0 0	3,6 0,1 0	4 - 0,12 0
$185 \leq d_1 < 190$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	1,2 $\pm 0,15$	1,5 $\pm 0,15$	3 0 - 0,2	2,9 0 - 0,2	2,7 0 - 0,2	2,7 0 - 0,2	3,3 +0,15 0	3,7 +0,15 0	4,15 +0,15 0	4,55 +0,15 0	3,2 0 - 0,1	3,6 0 - 0,1	4 0 - 0,12	4,4 0 - 0,12
$190 \leq d_1 < 195$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	1,2 $\pm 0,15$	1,5 $\pm 0,15$	3 0 - 0,2	2,9 0 - 0,2	2,7 0 - 0,2	2,7 0 - 0,2	3,3 +0,15 0	3,7 +0,15 0	4,15 +0,15 0	4,55 +0,15 0	3,2 0 - 0,1	3,6 0 - 0,1	4 0 - 0,12	4,4 0 - 0,12
$195 \leq d_1 \leq 200$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	1,2 $\pm 0,15$	1,5 $\pm 0,15$	3 0 - 0,2	2,9 0 - 0,2	2,7 0 - 0,2	2,7 0 - 0,2	3,3 +0,15 0	3,7 +0,15 0	4,15 +0,15 0	4,55 +0,15 0	3,2 0 - 0,1	3,6 0 - 0,1	4 0 - 0,12	4,4 0 - 0,12

Table 10 — Width dimensions of DSF-CNP oil control rings

Dimensions in millimetres

Nominal diameter	Radial thickness over coil spring a_{12} for h_1 shown in column				Ring width h_1 column					Closed gap s_1	Radial wall thickness a_1 for h_1 shown in column					Land width h_5 for all h_1
	d_1	1	2	3	4	1	2	3	4		Tolerance	1	2	3	4	
$60 \leq d_1 < 65$	-	3,5 0 -0,25	3,5 0 -0,25	3,7 0 -0,25	-	3	3,5	4	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,2 +0,2 0	-	2,4	2,4	2,5	$\pm 0,15$ within a ring 0,15 max.	0,25-0,4 $\pm 0,12$
$65 \leq d_1 < 70$	-	3,6 0 -0,25	3,7 0 -0,25	3,7 0 -0,25	-	3	3,5	4	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,2 +0,2 0	-	2,45	2,5	2,5	$\pm 0,15$ within a ring 0,15 max.	0,25-0,4 $\pm 0,12$

NOTE For intermediate sizes (e.g. repair sizes), the radial thickness of the next smaller nominal diameter applies.

Table 10 (continued)

Nominal diameter	Radial thickness over coil spring a_{12} for h_1 shown in column				Ring width h_1 column					Closed gap s_1	Radial wall thickness a_1 for h_1 shown in column					Land width h_5 for all h_1 Recommended range
	1	2	3	4	1	2	3	4	Tolerance		1	2	3	4	Tolerance	
$70 \leq d_1 < 75$	-	3,6 0 -0,25	3,8 0 -0,25	3,9 0 -0,25	-	3	3,5	4	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,2 +0,2 0	-	2,55	2,6	2,6	$\pm 0,15$ within a ring 0,15 max.	0,25-0,4 $\pm 0,12$
$75 \leq d_1 < 80$	-	3,7 0 -0,25	3,9 0 -0,25	4 0 -0,25	-	3	3,5	4	0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,25 +0,25 0	-	2,6	2,7	2,7	$\pm 0,15$ within a ring 0,15 max.	0,25-0,4 $\pm 0,12$
$80 \leq d_1 < 85$	3,8 0 -0,25	4 0 -0,25	4,1 0 -0,25	4,1 0 -0,25	3	3,5	4	4,5	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,25 +0,25 0	2,7	2,7	2,8	2,8	$\pm 0,15$ within a ring 0,15 max.	0,25-0,4 $\pm 0,12$
$85 \leq d_1 < 90$	3,9 0 -0,25	4 0 -0,25	4,1 0 -0,25	4,1 0 -0,25	3	3,5	4	4,5	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,25 +0,25 0	2,8	2,8	2,9	2,9	$\pm 0,15$ within a ring 0,15 max.	0,25-0,4 $\pm 0,12$
$90 \leq d_1 < 95$	3,9 0 -0,25	4,1 0 -0,25	4,2 0 -0,25	4,2 0 -0,25	3	3,5	4	4,5	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,3 +0,25 0	2,85	2,9	2,95	3	$\pm 0,15$ within a ring 0,15 max.	0,25-0,4 $\pm 0,12$
$95 \leq d_1 < 100$	4 0 - 0,25	4,1 0 - 0,25	4,2 0 - 0,25	4,2 0 - 0,25	3	3,5	4	4,5	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,3 +0,25 0	2,95	3	3,05	3,1	$\pm 0,15$ within a ring 0,15 max.	0,25-0,4 $\pm 0,12$
$100 \leq d_1 < 105$	4,2 0 - 0,25	4,4 0 - 0,25	4,5 0 - 0,25	4,7 0 - 0,25	3,5	4	4,5	5	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,3 +0,25 0	3,05	3,1	3,15	3,2	$\pm 0,20$ within a ring 0,2 max.	0,25-0,4 $\pm 0,12$
$105 \leq d_1 < 110$	4,2 0 - 0,25	4,4 0 - 0,25	4,5 0 - 0,25	4,7 0 - 0,25	3,5	4	4,5	5	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,3 +0,25 0	3,1	3,15	3,2	3,3	$\pm 0,20$ within a ring 0,2 max.	0,25-0,4 $\pm 0,12$

NOTE For intermediate sizes (e.g. repair sizes), the radial thickness of the next smaller nominal diameter applies.

Table 10 (continued)

Nominal diameter	Radial thickness over coil spring a_{12} for h_1 shown in column				Ring width h_1 column					Closed gap s_1	Radial wall thickness a_1 for h_1 shown in column					Land width h_5 for all h_1 Recommended range		
	d_1	1	2	3	4	1	2	3	4		Tolerance	1	2	3	4		Tolerance	
$110 \leq d_1 < 115$	4,3 0 - 0,25	4,5 0 - 0,25	4,6 0 - 0,25	4,8 0 - 0,25		3,5	4	4,5	5	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,35 +0,30 0		3,2	3,25	3,3	3,4	$\pm 0,20$ within a ring 0,2 max.	0,25-0,4 $\pm 0,12$
$115 \leq d_1 < 120$	4,4 0 - 0,25	4,6 0 - 0,25	4,7 0 - 0,25	4,9 0 - 0,25		3,5	4	4,5	5	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,35 +0,30 0		3,3	3,35	3,4	3,5	$\pm 0,20$ within a ring 0,2 max.	0,25-0,4 $\pm 0,12$
$120 \leq d_1 < 125$	4,4 0 - 0,25	4,6 0 - 0,25	4,8 0 - 0,25	5 0 - 0,25		3,5	4	4,5	5	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,35 +0,30 0		3,4	3,45	3,5	3,6	$\pm 0,20$ within a ring 0,2 max.	0,25-0,4 $\pm 0,12$
$125 \leq d_1 < 130$	4,7 0 - 0,25	4,9 0 - 0,25	5 0 - 0,25	5,2 0 - 0,25		4	4,5	5	6	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,35 +0,30 0		3,5	3,6	3,6	3,7	$\pm 0,20$ within a ring 0,2 max.	0,25-0,4 $\pm 0,12$
$130 \leq d_1 < 135$	4,7 0 - 0,25	4,9 0 - 0,25	5,1 0 - 0,25	5,3 0 - 0,25		4	4,5	5	6	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,4 +0,3 0		3,5	3,6	3,7	3,8	$\pm 0,15$ within a ring 0,15 max.	0,25-0,5 $\pm 0,12$
$135 \leq d_1 < 140$	4,9 0 - 0,25	5,1 0 - 0,25	5,3 0 - 0,25	5,5 0 - 0,25		4	4,5	5	6	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,4 +0,3 0		3,6	3,7	3,8	3,9	$\pm 0,20$ within a ring 0,2 max.	0,25-0,5 $\pm 0,12$
$140 \leq d_1 < 145$	4,9 0 - 0,25	5,1 0 - 0,25	5,3 0 - 0,25	5,5 0 - 0,25		4	4,5	5	6	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,4 +0,3 0		3,7	3,8	3,9	4	$\pm 0,20$ within a ring 0,2 max.	0,25-0,5 $\pm 0,12$
$145 \leq d_1 < 150$	4,9 0 - 0,25	5,1 0 - 0,25	5,3 0 - 0,25	5,5 0 - 0,25		4	4,5	5	6	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,4 +0,3 0		3,8	3,9	4	4,1	$\pm 0,20$ within a ring 0,2 max.	0,25-0,5 $\pm 0,12$

NOTE For intermediate sizes (e.g. repair sizes), the radial thickness of the next smaller nominal diameter applies.

Table 10 (continued)

Nominal diameter	Radial thickness over coil spring a_{12} for h_1 shown in column				Ring width h_1 column					Closed gap s_1	Radial wall thickness a_1 for h_1 shown in column					Land width h_5 for all h_1 Recommended range
	d_1	1	2	3	4	1	2	3	4		Tolerance	1	2	3	4	
$150 \leq d_1 < 155$	5,4 0 - 0,25	5,4 0 - 0,25	5,5 0 - 0,25	5,5 0 - 0,25	4,5	5	6	7	-0,010 -0,035 For phosphated PO surface: -0,005 -0,035	0,45 +0,35 0	3,9	4	4,1	4,2	$\pm 0,20$ within a ring 0,2 max.	0,3-0,6 $\pm 0,12$
$155 \leq d_1 < 160$	5,4 0 - 0,25	5,4 0 - 0,25	5,5 0 - 0,25	5,5 0 - 0,25	4,5	5	6	7	-0,010 -0,035 For phosphated PO surface: -0,005 -0,035	0,45 +0,35 0	3,9	4	4,1	4,2	$\pm 0,20$ within a ring 0,2 max.	0,3-0,6 $\pm 0,12$
$160 \leq d_1 < 165$	5,4 0 - 0,25	5,6 0 - 0,25	5,8 0 - 0,25	6 0 - 0,25	4,5	5	6	7	-0,010 -0,035 For phosphated PO surface: -0,005 -0,035	0,45 +0,35 0	4	4,2	4,3	4,4	$\pm 0,20$ within a ring 0,2 max.	0,3-0,6 $\pm 0,12$
$165 \leq d_1 < 170$	5,4 0 - 0,2	5,6 0 - 0,2	5,8 0 - 0,2	6 0 - 0,2	4,5	5	6	7	-0,010 -0,035 For phosphated PO surface: -0,005 -0,035	0,45 +0,35 0	4	4,2	4,3	4,4	$\pm 0,20$ within a ring 0,2 max.	0,3-0,6 $\pm 0,12$
$170 \leq d_1 < 175$	5,4 0 - 0,2	5,6 0 - 0,2	5,8 0 - 0,2	6 0 - 0,2	4,5	5	6	7	-0,010 -0,035 For phosphated PO surface: -0,005 -0,035	0,45 +0,35 0	4	4,2	4,3	4,4	$\pm 0,20$ within a ring 0,2 max.	0,3-0,6 $\pm 0,12$
$175 \leq d_1 < 180$	5,8 0 - 0,35	6 0 - 0,35	6,3 0 - 0,35	6,7 0 - 0,35	5	6	7	8	-0,010 -0,035 For phosphated PO surface: -0,005 -0,035	0,55 +0,40 0	4,6	4,7	4,8	5	$\pm 0,20$ within a ring 0,2 max.	0,3-0,6 $\pm 0,12$
$180 \leq d_1 < 185$	5,8 0 - 0,35	6 0 - 0,35	6,3 0 - 0,35	6,7 0 - 0,35	5	6	7	8	-0,010 -0,035 For phosphated PO surface: -0,005 -0,035	0,55 +0,40 0	4,6	4,7	4,8	5	$\pm 0,20$ within a ring 0,2 max.	0,3-0,6 $\pm 0,12$
$185 \leq d_1 < 190$	6,2 0 -0,4	6,5 0 -0,4	6,7 0 -0,4	7,1 0 -0,4	5	6	7	8	-0,010 -0,035 For phosphated PO surface: -0,005 -0,035	0,55 +0,40 0	4,9	5	5,1	5,3	$\pm 0,20$ within a ring 0,2 max.	0,3-0,6 $\pm 0,12$

NOTE For intermediate sizes (e.g. repair sizes), the radial thickness of the next smaller nominal diameter applies.

Table 10 (continued)

Nominal diameter	Radial thickness over coil spring a_{12} for h_1 shown in column				Ring width h_1 column					Closed gap s_1	Radial wall thickness a_1 for h_1 shown in column					Land width h_5 for all h_1 Recommended range
	d_1	1	2	3	4	1	2	3	4		Tolerance	1	2	3	4	
$190 \leq d_1 < 195$	6,2 0 -0,4	6,5 0 -0,4	6,7 0 -0,4	7,1 0 -0,4	5	6	7	8	-0,010 -0,035 For phosphated PO surface: -0,005 -0,035	0,55 +0,40 0	4,9	5	5,1	5,3	$\pm 0,20$ within a ring 0,2 max.	0,3-0,6 $\pm 0,12$
$195 \leq d_1 \leq 200$	6,2 0 -0,4	6,5 0 -0,4	6,7 0 -0,4	7,1 0 -0,4	5	6	7	8	-0,010 -0,035 For phosphated PO surface: -0,005 -0,035	0,55 +0,40 0	4,9	5	5,1	5,3	$\pm 0,20$ within a ring 0,2 max.	0,3-0,6 $\pm 0,12$

NOTE For intermediate sizes (e.g. repair sizes), the radial thickness of the next smaller nominal diameter applies.

Table 11 — Groove and spring dimensions of DSF-CNP oil control rings

Dimensions in millimetres

Nominal diameter	Groove depth a_4 for h_1 shown in column				Groove depth and bridge a_{13} for h_1 shown in column				Coil spring groove diameter d_{14} for h_1 shown in column				Coil spring diameter d_7 for h_1 shown in column				
	d_1	1	2	3	4	1	2	3	4	1	2	3	4	1	2	3	4
$60 \leq d_1 < 65$	-	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	-	1,5 0 0,15	1,5 0 0,15	1,5 0 0,15	-	2,1 +0,1 0	2,1 +0,1 0	2,3 +0,1 0	-	2 - 0,1 0	2 - 0,1 0	2,2 - 0,1 0	2,2 - 0,1 0
$65 \leq d_1 < 70$	-	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	-	1,6 0 0,15	1,5 0 0,15	1,5 0 0,15	-	2,1 +0,1 0	2,3 +0,1 0	2,3 +0,1 0	-	2 - 0,1 0	2,2 - 0,1 0	2,2 - 0,1 0	2,2 - 0,1 0
$70 \leq d_1 < 75$	-	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	-	1,6 0 0,15	1,6 0 0,15	1,5 0 0,15	-	2,1 +0,1 0	2,3 +0,1 0	2,5 +0,1 0	-	2 - 0,1 0	2,2 - 0,1 0	2,4 - 0,1 0	2,4 - 0,1 0
$75 \leq d_1 < 80$	-	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	-	1,7 0 0,15	1,7 0 0,15	1,6 0 0,15	-	2,1 +0,1 0	2,3 +0,1 0	2,5 +0,1 0	-	2 - 0,1 0	2,2 - 0,1 0	2,4 - 0,1 0	2,4 - 0,1 0
$80 \leq d_1 < 85$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	1,8 - 0,15	1,8 - 0,15	1,7 - 0,15	1,7 - 0,15	2,1 +0,1 0	2,3 +0,1 0	2,5 +0,1 0	2,5 +0,1 0	2 - 0,1 0	2,2 - 0,1 0	2,4 - 0,1 0	2,4 - 0,1 0	2,4 - 0,1 0
$85 \leq d_1 < 90$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	1,9 - 0,15	1,8 - 0,15	1,7 - 0,15	1,7 - 0,15	2,1 +0,1 0	2,3 +0,1 0	2,5 +0,1 0	2,5 +0,1 0	2 - 0,1 0	2,2 - 0,1 0	2,4 - 0,1 0	2,4 - 0,1 0	2,4 - 0,1 0
$90 \leq d_1 < 95$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	1,9 - 0,15	1,9 - 0,15	1,8 - 0,15	1,8 - 0,15	2,1 +0,1 0	2,3 +0,1 0	2,5 +0,1 0	2,5 +0,1 0	2 - 0,1 0	2,2 - 0,1 0	2,4 - 0,1 0	2,4 - 0,1 0	2,4 - 0,1 0

ISO 6626-1:2024(en)

Table 11 (continued)

Nominal diameter d_1	Groove depth a_4 for h_1 shown in column				Groove depth and bridge a_{13} for h_1 shown in column				Coil spring groove diameter d_{14} for h_1 shown in column				Coil spring diameter d_7 for h_1 shown in column			
	1	2	3	4	1	2	3	4	1	2	3	4	1	2	3	4
$95 \leq d_1 < 100$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	2 0 - 0,15	1,9 0 - 0,15	1,8 0 - 0,15	1,8 0 - 0,15	2,1 +0,1 0	2,3 +0,1 0	2,5 +0,1 0	2,5 +0,1 0	2 - 0,1 0	2,2 - 0,1 0	2,4 - 0,1 0	2,5 - 0,1 0
$100 \leq d_1 < 105$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	2 0 - 0,15	2 0 -0,2	1,9 0 -0,2	1,9 0 -0,2	2,3 +0,1 0	2,5 +0,1 0	2,7 +0,1 0	2,9 +0,1 0	2,2 - 0,1 0	2,4 - 0,1 0	2,6 - 0,1 0	2,8 - 0,1 0
$105 \leq d_1 < 110$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	2 0 - 0,15	2 0 -0,2	1,9 0 -0,2	1,9 0 -0,2	2,3 +0,1 0	2,5 +0,1 0	2,7 +0,1 0	2,9 +0,1 0	2,2 - 0,1 0	2,4 - 0,1 0	2,6 - 0,1 0	2,8 - 0,1 0
$110 \leq d_1 < 115$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	2,1 0 -0,2	2,1 0 -0,2	2 0 -0,2	2 0 -0,2	2,3 +0,1 0	2,5 +0,1 0	2,7 +0,1 0	2,9 +0,1 0	2,2 - 0,1 0	2,4 -0 ,1 0	2,6 - 0,1 0	2,8 - 0,1 0
$115 \leq d_1 < 120$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	2,2 0 -0,2	2,2 0 -0,2	2,1 0 -0,2	2,1 0 -0,2	2,3 +0,1 0	2,5 +0,1 0	2,7 +0,1 0	2,9 +0,1 0	2,2 - 0,1 0	2,4 - 0,1 0	2,6 - 0,1 0	2,8 - 0,1 0
$120 \leq d_1 < 125$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	2,2 0 -0,2	2,2 0 -0,2	2,2 0 -0,2	2,2 0 -0,2	2,3 +0,1 0	2,5 +0,1 0	2,7 +0,1 0	2,9 +0,1 0	2,2 - 0,1 0	2,4 - 0,1 0	2,6 - 0,1 0	2,8 - 0,1 0
$125 \leq d_1 < 130$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	2,3 0 -0,2	2,3 0 -0,2	2,2 0 -0,2	2,2 0 -0,2	2,5 +0,1 0	2,7 +0,1 0	2,9 +0,1 0	3,1 +0,1 0	2,4 0 - 0,1	2,6 0 - 0,1	2,8 0 - 0,1	3 0 - 0,1
$130 \leq d_1 < 135$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	2,3 0 -0,2	2,3 0 -0,2	2,3 0 -0,2	2,3 0 -0,2	2,5 +0,1 0	2,7 +0,1 0	2,9 +0,1 0	3,1 +0,1 0	2,4 - 0,1 0	2,6 - 0,1 0	2,8 - 0,1 0	3 - 0,1 0
$135 \leq d_1 < 140$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	2,3 0 -0,2	2,3 0 -0,2	2,3 0 -0,2	2,3 0 -0,2	2,7 +0,1 0	2,9 +0,1 0	3,1 +0,1 0	3,3 +0,15 0	2,6 0 - 0,1	2,8 - 0,1 0	3 - 0,1 0	3,2 - 0,1 0
$140 \leq d_1 < 145$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	2,3 0 -0,2	2,3 0 -0,2	2,3 0 -0,2	2,3 0 -0,2	2,7 +0,1 0	2,9 +0,1 0	3,1 +0,1 0	3,3 +0,15 0	2,6 - 0,1 0	2,8 - 0,1 0	3 - 0,1 0	3,2 - 0,1 0
$145 \leq d_1 < 150$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	2,3 - 0,2	2,3 - 0,2	2,3 - 0,2	2,3 - 0,2	2,7 +0,1 0	2,9 +0,1 0	3,1 +0,1 0	3,3 +0,15 0	2,6 0 - 0,1	2,8 0 - 0,1	3 0 - 0,1	3,2 0 - 0,1
$150 \leq d_1 < 155$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	1,2 $\pm 0,15$	2,6 0 -0,2	2,4 0 -0,2	2,3 0 -0,2	2,3 0 -0,2	2,9 +0,1 0	3,1 +0,15 0	3,3 +0,15 0	3,3 +0,15 0	2,8 0 - 0,1	3 0 - 0,1	3,2 0 - 0,1	3,2 0 - 0,1
$155 \leq d_1 < 160$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	1,2 $\pm 0,15$	2,6 0 -0,2	2,6 0 -0,2	2,6 0 -0,2	2,4 0 -0,2	2,9 +0,1 0	3,1 +0,15 0	3,3 +0,15 0	3,3 +0,15 0	2,8 0 - 0,1	3 0 - 0,1	3,2 0 - 0,1	3,2 0 - 0,1

Table 11 (continued)

Nominal diameter d_1	Groove depth a_4 for h_1 shown in column				Groove depth and bridge a_{13} for h_1 shown in column				Coil spring groove diameter d_{14} for h_1 shown in column				Coil spring diameter d_7 for h_1 shown in column			
	1	2	3	4	1	2	3	4	1	2	3	4	1	2	3	4
$160 \leq d_1 < 165$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	1,2 $\pm 0,15$	2,6 0 - 0,2	2,6 0 - 0,2	2,6 0 - 0,2	2,4 0 - 0,2	2,9 $+0,1$ 0	3,1 $+0,15$ 0	3,3 $+0,15$ 0	3,7 $+0,15$ 0	2,8 0 - 0,1	3 0 - 0,1	3,2 0 - 0,1	3,6 0 - 0,1
$165 \leq d_1 < 170$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	1,2 $\pm 0,15$	2,6 0 - 0,2	2,6 0 - 0,2	2,6 0 - 0,2	2,4 0 - 0,2	2,9 $+0,1$ 0	3,1 $+0,15$ 0	3,3 $+0,15$ 0	3,7 $+0,15$ 0	2,8 0 - 0,1	3 0 - 0,1	3,2 0 - 0,1	3,6 0 - 0,1
$170 \leq d_1 < 175$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	1,2 $\pm 0,15$	2,6 0 - 0,2	2,6 0 - 0,2	2,6 0 - 0,2	2,4 0 - 0,2	2,9 $+0,1$ 0	3,1 $+0,15$ 0	3,3 $+0,15$ 0	3,7 $+0,15$ 0	2,8 0 - 0,1	3 0 - 0,1	3,2 0 - 0,1	3,6 0 - 0,1
$175 \leq d_1 < 180$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	1,2 $\pm 0,15$	1,5 $\pm 0,15$	2,8 0 - 0,2	2,8 0 - 0,2	2,7 0 - 0,2	2,7 0 - 0,2	3,1 $+0,1$ 0	3,3 $+0,15$ 0	3,7 $+0,15$ 0	4,15 $+0,15$ 0	3 - 0,1	3,2 - 0,1	3,6 -0,1 0	4 - 0,12 0
$180 \leq d_1 < 185$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	1,2 $\pm 0,15$	1,5 $\pm 0,15$	3 0 - 0,2	2,9 0 - 0,2	2,7 0 - 0,2	2,7 0 - 0,2	3,3 $+0,15$ 0	3,7 $+0,15$ 0	4,15 $+0,15$ 0	4,55 $+0,15$ 0	3,2 0 - 0,1	3,6 0 - 0,1	4 0 - 0,12	4,4 0 - 0,12
$185 \leq d_1 < 190$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	1,2 $\pm 0,15$	1,5 $\pm 0,15$	3 0 - 0,2	2,9 0 - 0,2	2,7 0 - 0,2	2,7 0 - 0,2	3,3 $+0,15$ 0	3,7 $+0,15$ 0	4,15 $+0,15$ 0	4,55 $+0,15$ 0	3,2 0 - 0,1	3,6 0 - 0,1	4 0 - 0,12	4,4 0 - 0,12
$190 \leq d_1 < 195$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	1,2 $\pm 0,15$	1,5 $\pm 0,15$	3 0 - 0,2	2,9 0 - 0,2	2,7 0 - 0,2	2,7 0 - 0,2	3,3 $+0,15$ 0	3,7 $+0,15$ 0	4,15 $+0,15$ 0	4,55 $+0,15$ 0	3,2 0 - 0,1	3,6 0 - 0,1	4 0 - 0,12	4,4 0 - 0,12
$195 \leq d_1 \leq 200$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	1,2 $\pm 0,15$	1,5 $\pm 0,15$	3 0 - 0,2	2,9 0 - 0,2	2,7 0 - 0,2	2,7 0 - 0,2	3,3 $+0,15$ 0	3,7 $+0,15$ 0	4,15 $+0,15$ 0	4,55 $+0,15$ 0	3,2 0 - 0,1	3,6 0 - 0,1	4 0 - 0,12	4,4 0 - 0,12

Table 12 — Width dimensions of SSF oil control rings

Dimensions in millimetres

Nominal diameter d_1	Radial thickness over coil spring a_{12} for h_1 shown in column				Ring width h_1 column					Closed gap s_1	Radial wall thickness a_1 for h_1 shown in column					Land width h_5 for all h_1 Recommended range
	1	2	3	4	1	2	3	4	Tolerance		1	2	3	4	Tolerance	
$60 \leq d_1 < 65$	-	3,5 0 - 0,25	3,5 0 - 0,25	3,7 0 - 0,25	-	3	3,5	4	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,2 $+0,2$ 0	-	2,4	2,4	2,5	$\pm 0,15$ within a ring 0,15 max.	0,5-0,7 $\pm 0,1$
$65 \leq d_1 < 70$	-	3,6 0 - 0,25	3,7 0 - 0,25	3,7 0 - 0,25	-	3	3,5	4	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,2 $+0,2$ 0	-	2,45	2,5	2,5	$\pm 0,15$ within a ring 0,15 max.	0,5-0,7 $\pm 0,1$

Table 12 (continued)

Nominal diameter	Radial thickness over coil spring a_{12} for h_1 shown in column				Ring width h_1 column					Closed gap s_1	Radial wall thickness a_1 for h_1 shown in column					Land width h_5 for all h_1 Recommended range
	d_1	1	2	3	4	1	2	3	4		Tolerance	1	2	3	4	
$70 \leq d_1 < 75$	-	3,6 0 - 0,25	3,8 0 - 0,25	3,9 0 - 0,25	-	3	3,5	4	-0,010 -0,030 For phosphate PO surface: -0,005 -0,030	0,2 +0,2 0	-	2,55	2,6	2,6	$\pm 0,15$ within a ring 0,15 max.	0,5-0,7 $\pm 0,1$
$75 \leq d_1 < 80$	-	3,7 0 - 0,25	3,9 0 - 0,25	4 0 - 0,25	-	3	3,5	4	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,25 +0,25 0	-	2,6	2,7	2,7	$\pm 0,15$ within a ring 0,15 max.	0,5-0,7 $\pm 0,1$
$80 \leq d_1 < 85$	3,8 0 -0,25	4 0 - 0,25	4,1 0 - 0,25	4,1 0 - 0,25	3	3,5	4	4,5	-0,010 -0,030 For phosphate PO surface: -0,005 -0,030	0,25 +0,25 0	2,7	2,7	2,8	2,8	$\pm 0,15$ within a ring 0,15 max.	0,5-0,8 $\pm 0,1$
$85 \leq d_1 < 90$	3,9 0 -0,25	4 0 - 0,25	4,1 0 - 0,25	4,1 0 - 0,25	3	3,5	4	4,5	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,25 +0,25 0	2,8	2,8	2,9	2,9	$\pm 0,15$ within a ring 0,15 max.	0,5-0,8 $\pm 0,1$
$90 \leq d_1 < 95$	3,9 0 -0,25	4,1 0 - 0,25	4,2 0 - 0,25	4,2 0 - 0,25	3	3,5	4	4,5	-0,010 -0,030 For phosphate PO surface: -0,005 -0,030	0,3 +0,25 0	2,85	2,9	2,95	3	$\pm 0,15$ within a ring 0,15 max.	0,5-0,8 $\pm 0,1$
$95 \leq d_1 < 100$	4 0 - 0,25	4,1 0 - 0,25	4,2 0 - 0,25	4,2 0 - 0,25	3	3,5	4	4,5	-0,010 -0,030 For phosphate PO surface: -0,005 -0,030	0,3 +0,25 0	2,95	3	3,05	3,1	$\pm 0,15$ within a ring 0,15 max.	0,5-0,8 $\pm 0,1$
$100 \leq d_1 < 105$	4,2 0 - 0,25	4,4 0 - 0,25	4,5 0 -0,25	4,7 0 -0,25	3,5	4	4,5	5	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,3 +0,25 0	3,05	3,1	3,15	3,2	$\pm 0,20$ within a ring 0,2 max.	0,6-0,9 $\pm 0,1$
$105 \leq d_1 < 110$	4,2 0 - 0,25	4,4 0 - 0,25	4,5 0 -0,25	4,7 0 -0,25	3,5	4	4,5	5	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,3 +0,25 0	3,1	3,15	3,2	3,3	$\pm 0,20$ within a ring 0,2 max.	0,6-0,9 $\pm 0,1$

Table 12 (continued)

Nominal diameter	Radial thickness over coil spring a_{12} for h_1 shown in column				Ring width h_1 column					Closed gap s_1	Radial wall thickness a_1 for h_1 shown in column					Land width h_5 for all h_1 Recommended range
	d_1	1	2	3	4	1	2	3	4		Tolerance	1	2	3	4	
$110 \leq d_1 < 115$	4,3 0 - 0,25	4,5 0 - 0,25	4,6 0 - -0,25	4,8 0 - -0,25	3,5	4	4,5	5	-0,010 -0,030 For phosphate PO surface: -0,005 -0,030	0,35 +0,30 0	3,2	3,25	3,3	3,4	$\pm 0,20$ within a ring 0,2 max.	0,6-0,9 $\pm 0,1$
$115 \leq d_1 < 120$	4,4 0 - 0,25	4,6 0 - 0,25	4,7 0 - -0,25	4,9 0 - -0,25	3,5	4	4,5	5	-0,010 -0,030 For phosphate PO surface: -0,005 -0,030	0,35 +0,30 0	3,3	3,35	3,4	3,5	$\pm 0,20$ within a ring 0,2 max.	0,6-0,9 $\pm 0,1$
$120 \leq d_1 < 125$	4,4 0 - 0,25	4,6 0 - 0,25	4,8 0 - -0,25	5 0 - -0,25	3,5	4	4,5	5	-0,010 -0,030 For phosphate PO surface: -0,005 -0,030	0,35 +0,30 0	3,4	3,45	3,5	3,6	$\pm 0,20$ within a ring 0,2 max.	0,6-0,9 $\pm 0,1$
$125 \leq d_1 < 130$	4,7 0 - 0,25	4,9 0 - 0,25	5 0 - -0,25	5,2 0 - -0,25	4	4,5	5	6	-0,010 -0,030 For phosphate PO surface: -0,005 -0,030	0,35 +0,30 0	3,5	3,6	3,6	3,7	$\pm 0,20$ within a ring 0,2 max.	0,6-1,1 $\pm 0,1$
$130 \leq d_1 < 135$	4,7 0 - 0,25	4,9 0 - 0,25	5,1 0 - 0,25	5,3 0 - 0,25	4	4,5	5	6	-0,010 -0,030 For phosphate PO surface: -0,005 -0,035	0,4 +0,3 0	3,5	3,6	3,7	3,8	$\pm 0,15$ within a ring 0,15 max.	0,6-1,1 $\pm 0,1$
$135 \leq d_1 < 140$	4,9 0 - 0,25	5,1 0 - 0,25	5,3 0 - 0,25	5,5 0 - 0,25	4	4,5	5	6	-0,010 -0,030 For phosphate PO surface: -0,005 -0,035	0,4 +0,3 0	3,6	3,7	3,8	3,9	$\pm 0,20$ within a ring 0,2 max.	0,6-1,1 $\pm 0,1$
$140 \leq d_1 < 145$	4,9 0 - 0,25	5,1 0 - 0,25	5,3 0 - 0,25	5,5 0 - 0,25	4	4,5	5	6	-0,010 -0,030 For phosphated PO surface: -0,005 -0,035	0,4 +0,3 0	3,7	3,8	3,9	4	$\pm 0,20$ within a ring 0,2 max.	0,6-1,1 $\pm 0,1$
$145 \leq d_1 < 150$	4,9 0 - 0,25	5,1 0 - 0,25	5,3 0 - 0,25	5,5 0 - 0,25	4	4,5	5	6	-0,010 -0,030 For phosphate PO surface: -0,005 -0,035	0,4 +0,3 0	3,8	3,9	4	4,1	$\pm 0,20$ within a ring 0,2 max.	0,6-1,1 $\pm 0,1$

Table 12 (continued)

Nominal diameter	Radial thickness over coil spring a_{12} for h_1 shown in column				Ring width h_1 column					Closed gap s_1	Radial wall thickness a_1 for h_1 shown in column					Land width h_5 for all h_1 Recommended range
	d_1	1	2	3	4	1	2	3	4		Tolerance	1	2	3	4	
$150 \leq d_1 < 155$	5,4 0 - 0,25	5,4 0 - 0,25	5,5 0 - 0,25	5,5 0 - 0,25	4,5	5	6	7	-0,010 -0,035 For phosphate PO surface: -0,005 -0,035	0,45 +0,35 0	3,9	4	4,1	4,2	$\pm 0,20$ within a ring 0,2 max.	0,7-1,1 $\pm 0,1$ 1,3 $\pm 0,15$
$155 \leq d_1 < 160$	5,4 0 - 0,25	5,4 0 - 0,25	5,5 0 - 0,25	5,5 0 -0,25	4,5	5	6	7	-0,010 -0,035 For phosphate PO surface: -0,005 -0,035	0,45 +0,35 0	3,9	4	4,1	4,2	$\pm 0,20$ within a ring 0,2 max.	0,7-1,1 $\pm 0,1$ 1,3 $\pm 0,15$
$160 \leq d_1 < 165$	5,4 0 - 0,25	5,6 0 - 0,25	5,8 0 - 0,25	6 0 - 0,25	4,5	5	6	7	-0,010 -0,035 For phosphate PO surface: -0,005 -0,035	0,45 +0,35 0	4	4,2	4,3	4,4	$\pm 0,20$ within a ring 0,2 max.	0,7-1,1 $\pm 0,1$ 1,3 $\pm 0,15$
$165 \leq d_1 < 170$	5,4 0 - 0,25	5,6 0 - 0,25	5,8 0 - 0,25	6 0 - 0,25	4,5	5	6	7	-0,010 -0,035 For phosphated PO surface: -0,005 -0,035	0,45 +0,35 0	4	4,2	4,3	4,4	$\pm 0,20$ within a ring 0,2 max.	0,7-1,1 $\pm 0,1$ 1,3 $\pm 0,15$
$170 \leq d_1 < 175$	0,25	0,25	0,25	0,25	4,5	5	6	7	-0,010 -0,035 For phosphated PO surface: -0,005 -0,035	0,45 +0,35 0	4	4,2	4,3	4,4	$\pm 0,20$ within a ring 0,2 max.	0,7-1,1 $\pm 0,1$ 1,3 $\pm 0,15$
$175 \leq d_1 < 180$	5,8 0 - 0,35	6 0 - 0,35	6,3 0 - 0,35	6,7 0 - 0,35	5	6	7	8	-0,010 -0,035 For phosphate PO surface: -0,005 -0,035	0,55 +0,40 0	4,6	4,7	4,8	5	$\pm 0,20$ within a ring 0,2 max.	0,9-1,1 $\pm 0,1$ 1,3-1,6 $\pm 0,15$
$180 \leq d_1 < 185$	5,8 0 - 0,35	6 0 - 0,35	6,3 0 - 0,35	6,7 0 - 0,35	5	6	7	8	-0,010 -0,035 For phosphate PO surface: -0,005 -0,035	0,55 +0,40 0	4,6	4,7	4,8	5	$\pm 0,20$ within a ring 0,2 max.	0,9-1,1 $\pm 0,1$ 1,3-1,6 $\pm 0,15$
$185 \leq d_1 < 190$	6,2 0 -0,4	6,5 0 -0,4	6,7 0 -0,4	7,1 0 -0,4	5	6	7	8	-0,010 -0,035 For phosphate PO surface: -0,005 -0,035	0,55 +0,40 0	4,9	5	5,1	5,3	$\pm 0,20$ within a ring 0,2 max.	0,9-1,1 $\pm 0,1$ 1,3-1,6 $\pm 0,15$
$190 \leq d_1 < 195$	6,2 0 -0,4	6,5 0 -0,4	6,7 0 -0,4	7,1 0 -0,4	5	6	7	8	-0,010 -0,035 For phosphate PO surface: -0,005 -0,035	0,55 +0,40 0	4,9	5	5,1	5,3	$\pm 0,20$ within a ring 0,2 max.	$\pm 0,9-1,1$ $\pm 0,1$ 1,3-1,6 $\pm 0,15$

Table 12 (continued)

Nominal diameter	Radial thickness over coil spring a_{12} for h_1 shown in column				Ring width h_1 column					Closed gap s_1	Radial wall thickness a_1 for h_1 shown in column					Land width h_5 for all h_1 Recommended range
	d_1	1	2	3	4	1	2	3	4		Tolerance	1	2	3	4	
$195 \leq d_1 \leq 200$	6,2 0 -0,4	6,5 0 -0,4	6,7 0 -0,4	7,1 0 -0,4	5	6	7	8	-0,010 -0,035 For phosphate PO surface: -0,005 -0,035	0,55 +0,40 0	4,9	5	5,1	5,3	$\pm 0,20$ within a ring 0,2 max.	$\pm 00,9-1,1$ $\pm 0,1$ $1,3-1,6$ $\pm 0,15$

Table 13 — Groove and spring dimensions of SSF oil control rings

Dimensions in millimetres

Nominal diameter	Groove depth a_4 for h_1 shown in column				Groove depth and bridge a_{13} for h_1 shown in column				Coil spring groove diameter d_{14} for h_1 shown in column				Coil spring diameter d_7 for h_1 shown in column				
	d_1	1	2	3	4	1	2	3	4	1	2	3	4	1	2	3	4
$60 \leq d_1 < 65$	-	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	-	1,5 0 -0,15	1,5 0 0,15	1,5 0 0,15	-	2,1 +0,1 0	2,1 +0,1 0	2,3 +0,1 0	-	2 -0,1 0	2 -0,1 0	2,2 -0,1 0	2,2 -0,1 0
$65 \leq d_1 < 70$	-	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	-	1,6 0 -0,15	1,5 0 0,15	1,5 0 0,15	-	2,1 +0,1 0	2,3 +0,1 0	2,3 +0,1 0	-	2 -0,1 0	2,2 -0,1 0	2,2 -0,1 0	2,2 -0,1 0
$70 \leq d_1 < 75$	-	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	-	1,6 0 -0,15	1,6 0 0,15	1,5 0 0,15	-	2,1 +0,1 0	2,3 +0,1 0	2,5 +0,1 0	-	2 -0,1 0	2,2 -0,1 0	2,4 -0,1 0	2,4 -0,1 0
$75 \leq d_1 < 80$	-	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	-	1,7 0 -0,15	1,7 0 0,15	1,6 0 0,15	-	2,1 +0,1 0	2,3 +0,1 0	2,5 +0,1 0	-	2 -0,1 0	2,2 -0,1 0	2,4 -0,1 0	2,4 -0,1 0
$80 \leq d_1 < 85$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	1,8 0 -0,15	1,8 0 -0,15	1,7 0 0,15	1,7 0 0,15	2,1 +0,1 0	2,3 +0,1 0	2,5 +0,1 0	2,5 +0,1 0	2 -0,1 0	2,2 -0,1 0	2,4 -0,1 0	2,4 -0,1 0	2,4 -0,1 0
$85 \leq d_1 < 90$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	1,9 0 -0,15	1,8 0 -0,15	1,7 0 0,15	1,7 0 0,15	2,1 +0,1 0	2,3 +0,1 0	2,5 +0,1 0	2,5 +0,1 0	2 -0,1 0	2,2 -0,1 0	2,4 -0,1 0	2,4 -0,1 0	2,4 -0,1 0
$90 \leq d_1 < 95$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	1,9 0 -0,15	1,9 0 -0,15	1,8 0 0,15	1,8 0 0,15	2,1 +0,1 0	2,3 +0,1 0	2,5 +0,1 0	2,5 +0,1 0	2 -0,1 0	2,2 -0,1 0	2,4 -0,1 0	2,4 -0,1 0	2,4 -0,1 0
$95 \leq d_1 < 100$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	2 0 0,15	1,9 0 -0,15	1,8 0 -0,15	1,8 0 -0,15	2,1 +0,1 0	2,3 +0,1 0	2,5 +0,1 0	2,5 +0,1 0	2 -0,1 0	2,2 -0,1 0	2,4 -0,1 0	2,4 -0,1 0	2,4 -0,1 0
$100 \leq d_1 < 105$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	2 0 -0,15	2 0 -0,2	1,9 0 -0,2	1,9 0 -0,2	2,3 +0,1 0	2,5 +0,1 0	2,7 +0,1 0	2,9 +0,1 0	2,2 -0,1 0	2,4 -0,1 0	2,6 -0,1 0	2,8 -0,1 0	2,8 -0,1 0

ISO 6626-1:2024(en)

Table 13 (continued)

Nominal diameter	Groove depth a_4				Groove depth and bridge a_{13}				Coil spring groove diameter d_{14}				Coil spring diameter d_7			
	for h_1 shown in column				for h_1 shown in column				for h_1 shown in column				for h_1 shown in column			
d_1	1	2	3	4	1	2	3	4	1	2	3	4	1	2	3	4
$105 \leq d_1 < 115$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	2,1 0 -0,2	2,1 0 -0,2	2 0 -0,2	2 0 -0,2	2,3 +0,1 0	2,5 +0,1 0	2,7 +0,1 0	2,9 +0,1 0	2,2 -0,1 0	2,4 -0,1 0	2,6 -0,1 0	2,8 -0,1 0
$115 \leq d_1 < 120$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	2,2 0 -0,2	2,2 0 -0,2	2,1 0 -0,2	2,1 0 -0,2	2,3 +0,1 0	2,5 +0,1 0	2,7 +0,1 0	2,9 +0,1 0	2,2 -0,1 0	2,4 -0,1 0	2,6 -0,1 0	2,8 -0,1 0
$120 \leq d_1 < 125$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	2,2 0 -0,2	2,2 0 -0,2	2,2 0 -0,2	2,2 0 -0,2	2,3 +0,1 0	2,5 +0,1 0	2,7 +0,1 0	2,9 +0,1 0	2,2 -0,1 0	2,4 -0,1 0	2,6 -0,1 0	2,8 -0,1 0
$125 \leq d_1 < 130$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	2,3 0 -0,2	2,3 0 -0,2	2,2 0 -0,2	2,2 0 -0,2	2,5 +0,1 0	2,7 +0,1 0	2,9 +0,1 0	3,1 +0,1 0	2,4 -0,1 0	2,6 0 -0,1	2,8 0 -0,1	3 0 -0,1
$130 \leq d_1 < 135$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	2,3 0 0,2	2,3 0 0,2	2,3 0 0,2	2,3 0 0,2	2,5 +0,1 0	2,7 +0,1 0	2,9 +0,1 0	3,1 +0,1 0	2,4 - 0	2,6 - 0	2,8 - 0	3 - 0
$135 \leq d_1 < 140$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	2,3 0 0,2	2,3 0 0,2	2,3 0 0,2	2,3 0 0,2	2,7 +0,1 0	2,9 +0,1 0	3,1 +0,1 0	3,3 +0,15 0	2,6 - 0	2,8 - 0	3 - 0	3,2 - 0
$140 \leq d_1 < 145$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	2,3 0 0,2	2,3 0 0,2	2,3 0 0,2	2,3 0 0,2	2,7 +0,1 0	2,9 +0,1 0	3,1 +0,1 0	3,3 +0,15 0	2,6 -0,1 0	2,8 -0,1 0	3 -0,1 0	3,2 -0,1 0
$145 \leq d_1 < 150$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	2,3 0 0,2	2,3 0 0,2	2,3 0 0,2	2,3 0 0,2	2,7 +0,1 0	2,9 +0,1 0	3,1 +0,1 0	3,3 +0,15 0	2,6 - 0,1	2,8 - 0,1	3 - 0,1	3,2 - 0,1
$150 \leq d_1 < 155$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	1,2 $\pm 0,15$	2,6 0 0,2	2,4 0 0,2	2,3 0 0,2	2,3 0 0,2	2,9 +0,1 0	3,1 +0,15 0	3,3 +0,15 0	3,3 +0,15 0	2,8 0 0,1	3 0 0,1	3,2 0 0,1	3,2 0 0,1
$155 \leq d_1 < 160$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	1,2 $\pm 0,15$	2,6 0 -0,2	2,4 0 -0,2	2,3 0 -0,2	2,3 0 -0,2	2,9 +0,1 0	3,1 +0,15 0	3,3 +0,15 0	3,3 +0,15 0	2,8 0 0,1	3 0 0,1	3,2 0 0,1	3,2 0 0,1
$160 \leq d_1 < 165$ \leq	0,7 $\pm 0,1$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	1,2 $\pm 0,15$	2,6 0 0,2	2,6 0 0,2	2,6 0 0,2	2,4 0 0,2	2,9 +0,1 0	3,1 +0,15 0	3,3 +0,15 0	3,7 +0,15 0	2,8 0 0,1	3 0 0,1	3,2 0 0,1	3,6 0 0,1
$165 \leq d_1 < 170$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	1,2 $\pm 0,15$	2,6 0 0,2	2,6 0 0,2	2,6 0 0,2	2,4 0 0,2	2,9 +0,1 0	3,1 +0,15 0	3,3 +0,15 0	3,7 +0,15 0	2,8 0 0,1	3 0 0,1	3,2 0 0,1	3,6 0 0,1
$170 \leq d_1 < 175$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	1,2 $\pm 0,15$	2,6 0 0,2	2,6 0 0,2	2,6 0 0,2	2,4 0 0,2	2,9 +0,1 0	3,1 +0,15 0	3,3 +0,15 0	3,7 +0,15 0	2,8 0 0,1	3 0 0,1	3,2 0 0,1	3,6 0 0,1
$175 \leq d_1 < 180$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	1,2 $\pm 0,15$	1,5 $\pm 0,15$	2,8 0 0,2	2,8 0 0,2	2,7 0 0,2	2,7 0 0,2	3,1 +0,1 0	3,3 +0,15 0	3,7 +0,15 0	4,15 +0,15 0	3 - 0,1	3,2 - 0,1	3,6 -0,1 0	4 - 0,12

Table 13 (continued)

Nominal diameter	Groove depth a_4 for h_1 shown in column				Groove depth and bridge a_{13} for h_1 shown in column				Coil spring groove diameter d_{14} for h_1 shown in column				Coil spring diameter d_7 for h_1 shown in column			
	d_1	1	2	3	4	1	2	3	4	1	2	3	4	1	2	3
$180 \leq d_1 < 185$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	1,2 $\pm 0,15$	1,5 $\pm 0,15$	2,8 0 – 0,2	2,8 0 – 0,2	2,7 0 – 0,2	2,7 0 – 0,2	3,1 +0,1 0	3,3 +0,15 0	3,7 +0,15 0	4,15 +0,15 0	3 – 0,1 0	3,2 – 0,1 0	3,6 –0,1 0	4 – 0,12 0
$185 \leq d_1 < 190$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	1,2 $\pm 0,15$	1,5 $\pm 0,15$	3 0 – 0,2	2,9 0 – 0,2	2,7 0 – 0,2	2,7 0 – 0,2	3,3 +0,15 0	3,7 +0,15 0	4,15 +0,15 0	4,55 +0,15 0	3,2 0 – 0,1	3,6 0 – 0,1	4 0 – 0,12	4,4 0 – 0,12
$190 \leq d_1 < 195$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	1,2 $\pm 0,15$	1,5 $\pm 0,15$	3 0 – 0,2	2,9 0 – 0,2	2,7 0 – 0,2	2,7 0 – 0,2	3,3 +0,15 0	3,7 +0,15 0	4,15 +0,15 0	4,55 +0,15 0	3,2 0 – 0,1	3,6 0 – 0,1	4 0 – 0,12	4,4 0 – 0,12
$195 \leq d_1 \leq 200$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	1,2 $\pm 0,15$	1,5 $\pm 0,15$	3 0 – 0,2	2,9 0 – 0,2	2,7 0 – 0,2	2,7 0 – 0,2	3,3 +0,15 0	3,7 +0,15 0	4,15 +0,15 0	4,55 +0,15 0	3,2 0 – 0,1	3,6 0 – 0,1	4 0 – 0,12	4,4 0 – 0,12

Table 14 — Width dimensions of GSF and DSF oil control rings

Dimensions in millimetres

Nominal diameter	Radial thickness over coil spring a_{12} for h_1 shown in column				Ring width h_1 column				Closed gap	Radial wall thickness a_1 for h_1 shown in column					Land width h_5 for all h_1		
	d_1	1	2	3	4	1	2	3		4	Tolerance	s_1	1	2		3	4
$60 \leq d_1 < 65$	–	3,5 0 – 0,25	3,5 0 –0,25	3,7 0 – 0,25	–	3	3,5	4	–0,010 –0,030 For phosphate PO surface: –0,005 –0,030	0,2 +0,2 0	–	2,4	2,4	2,5	–	±0,15 within a ring 0,15 max.	0,28 ±0,08 0,35–0,4 ±0,1
$65 \leq d_1 < 70$	–	3,6 0 – 0,25	3,7 0 –0,25	3,7 0 – 0,25	–	3	3,5	4	–0,010 –0,030 For phosphated PO surface: –0,005 –0,030	0,2 +0,2 0	–	2,45	2,5	2,5	–	±0,15 within a ring 0,15 max.	0,28 ±0,08 0,35–0,4 ±0,1
$70 \leq d_1 < 75$	–	3,6 0 – 0,25	3,8 0 –0,25	3,9 0 – 0,25	–	3	3,5	4	–0,010 –0,030 For phosphated PO surface: –0,005 –0,030	0,2 +0,2 0	–	2,55	2,6	2,6	–	±0,15 within a ring 0,15 max.	0,28 ±0,08 0,35–0,4 ±0,1

NOTE For intermediate sizes (e.g. repair sizes), the radial thickness of the next smaller nominal diameter applies.

Table 14 (continued)

Nominal diameter	Radial thickness over coil spring a_{12} for h_1 shown in column				Ring width h_1 column					Closed gap s_1	Radial wall thickness a_1 for h_1 shown in column					Land width h_5 for all h_1 Recommended range	
	d_1	1	2	3	4	1	2	3	4		Tolerance	1	2	3	4		Tolerance
$75 \leq d_1 < 80$	-	3,7 0 -	3,9 0 -0,25	4 0 -	4 0 -	-	3	3,5	4	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,25 +0,25 0	-	2,6	2,7	2,7	$\pm 0,15$ within a ring 0,15 max.	0,28 $\pm 0,08$ 0,35-0,4 $\pm 0,1$
$80 \leq d_1 < 85$	3,8 0 -	4 0 -	4,1 0 -0,25	4,1 0 -	4,1 0 -	3	3,5	4	4,5	-0,010 -0,030 For phosphate PO surface: -0,005 -0,030	0,25 +0,25 0	2,7	2,7	2,8	2,8	$\pm 0,15$ within a ring 0,15 max.	0,28 $\pm 0,08$ 0,35-0,4 $\pm 0,1$
$85 \leq d_1 < 90$	3,9 0 -	4 0 -	4,1 0 -0,25	4,1 0 -	4,1 0 -	3	3,5	4	4,5	-0,010 -0,030 For phosphate PO surface: -0,005 -0,030	0,25 +0,25 0	2,8	2,8	2,9	2,9	$\pm 0,15$ within a ring 0,15 max.	0,28 $\pm 0,08$ 0,35 - 0,4 $\pm 0,1$
$90 \leq d_1 < 95$	3,9 0 -	4,1 0 -	4,2 0 -0,25	4,2 0 -	4,2 0 -	3	3,5	4	4,5	0,010 -0,030 For phosphate PO surface: -0,005 -0,030	0,3 +0,25 0	2,85	2,9	2,95	3	$\pm 0,15$ within a ring 0,15 max.	0,28 $\pm 0,08$ 0,35-0,4 $\pm 0,1$
$95 \leq d_1 < 100$	4 0 -	4,1 0 -	4,2 0 -	4,2 0 -	4,2 0 -	3	3,5	4	4,5	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,3 +0,25 0	2,95	3	3,05	3,1	$\pm 0,15$ within a ring 0,15 max.	0,28 $\pm 0,08$ 0,35-0,4 $\pm 0,1$
$100 \leq d_1 < 105$	4,2 0 -	4,4 0 -	4,5 0 -	4,7 0 -	4,7 0 -	3,5	4	4,5	5	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,3 +0,25 0	3,05	3,1	3,15	3,2	$\pm 0,20$ within a ring 0,2 max.	0,35 - 0,4 $\pm 0,1$
$105 \leq d_1 < 110$	4,2 0 -	4,4 0 -	4,5 0 -	4,7 0 -	4,7 0 -	3,5	4	4,5	5	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,3 +0,25 0	3,1	3,15	3,2	3,3	$\pm 0,20$ within a ring 0,2 max.	0,35-0,4 $\pm 0,1$

NOTE For intermediate sizes (e.g. repair sizes), the radial thickness of the next smaller nominal diameter applies.

Table 14 (continued)

Nominal diameter	Radial thickness over coil spring a_{12} for h_1 shown in column				Ring width h_1 column					Closed gap s_1	Radial wall thickness a_1 for h_1 shown in column					Land width h_5 for all h_1 Recommended range
	d_1	1	2	3	4	1	2	3	4		Tolerance	1	2	3	4	
$110 \leq d_1 < 115$	4,3 0 -	4,5 0 -	4,6 0 -	4,8 0 -	3,5	4	4,5	5	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,35 +0,30 0	3,2	3,25	3,3	3,4	$\pm 0,20$ within a ring 0,2 max.	0,35-0,4 $\pm 0,1$
$115 \leq d_1 < 120$	4,4 0 -	4,6 0 -	4,7 0 -	4,9 0 -	3,5	4	4,5	5	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,35 +0,30 0	3,3	3,35	3,4	3,5	$\pm 0,20$ within a ring 0,2 max.	0,35-0,4 $\pm 0,1$
$120 \leq d_1 < 125$	4,4 0 -	4,6 0 -	4,8 0 -	5 0 -	3,5	4	4,5	5	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,35 +0,30 0	3,4	3,45	3,5	3,6	$\pm 0,20$ within a ring 0,2 max.	0,35-0,4 $\pm 0,1$
$125 \leq d_1 < 130$	4,7 0 -	4,9 0 -	5 0 -	5,2 0 -	4	4,5	5	6	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,35 +0,30 0	3,5	3,6	3,6	3,7	$\pm 0,20$ within a ring 0,2 max.	0,4-0,5 $\pm 0,1$
$130 \leq d_1 < 135$	4,7 0 -	4,9 0 -	5 0 -	5,2 0 -	4	4,5	5	6	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,4 +0,3 0	3,5	3,6	3,7	3,8	$\pm 0,15$ within a ring 0,15 max.	0,4-0,5 $\pm 0,1$
$135 \leq d_1 < 140$	4,9 0 -	5,1 0 -	5,3 0 -	5,5 0 -	4	4,5	5	6	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,4 +0,3 0	3,6	3,7	3,8	3,9	$\pm 0,20$ within a ring 0,2 max.	0,4-0,5 $\pm 0,1$

NOTE For intermediate sizes (e.g. repair sizes), the radial thickness of the next smaller nominal diameter applies.

Table 14 (continued)

Nominal diameter d_1	Radial thickness over coil spring a_{12} for h_1 shown in column				Ring width h_1 column					Closed gap s_1	Radial wall thickness a_1 for h_1 shown in column					Land width h_5 for all h_1 Recommended range
	1	2	3	4	1	2	3	4	Tolerance		1	2	3	4	Tolerance	
$140 \leq d_1 < 145$	4,9 0 -	5,1 0 -	5,3 0 -	5,5 0 -	4	4,5	5	6	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,4 +0,3 0	3,7	3,8	3,9	4	±0,20 within a ring 0,2 max.	0,4-0,5 ±0,1
$145 \leq d_1 < 150$	4,9 0 -	5,1 0 -	5,3 0 -	5,5 0 -	4	4,5	5	6	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,4 +0,3 0	3,8	3,9	4	4,0	±0,20 within a ring 0,2 max.	0,4-0,5 ±0,1
$150 \leq d_1 < 155$	5,4 0 -	5,4 0 -	5,5 0 -	5,5 0 -	4,5	5	6	7	-0,010 -0,035 For phosphated PO surface: -0,005 -0,035	0,45 +0,35 0	3,9	4	4,1	4,2	±0,20 within a ring 0,2 max.	0,4-0,5 ±0,1 0,6 ±0,15
$155 \leq d_1 < 160$	5,4 0 -	5,4 0 -	5,5 0 -	5,5 0 -	4,5	5	6	7	-0,010 -0,035 For phosphated PO surface: -0,005 -0,035	0,45 +0,35 0	3,9	4	4,1	4,2	±0,20 within a ring 0,2 max.	0,4-0,5 ±0,1 0,6 ±0,15
$160 \leq d_1 < 165$	5,4 0 -	5,6 0 -	5,8 0 -	6 0 -	4,5	5	6	7	-0,010 -0,035 For phosphated PO surface: -0,005 -0,035	0,45 +0,35 0	4	4,2	4,3	4,4	±0,20 within a ring 0,2 max.	0,4-0,5 ±0,1 0,6 ±0,15

NOTE For intermediate sizes (e.g. repair sizes), the radial thickness of the next smaller nominal diameter applies.

Table 14 (continued)

Nominal diameter	Radial thickness over coil spring a_{12} for h_1 shown in column				Ring width h_1 column					Closed gap s_1	Radial wall thickness a_1 for h_1 shown in column					Land width h_5 for all h_1 Recommended range
	d_1	1	2	3	4	1	2	3	4		Tolerance	1	2	3	4	
$165 \leq d_1 < 170$	5,4 0 -	5,6 0 -	5,8 0 -	6 0 -	4,5	5	6	7	-0,010 -0,035 For phosphated PO surface: -0,005 -0,035	0,45 +0,35 0	4	4,2	4,3	4,4	$\pm 0,20$ within a ring 0,2 max.	0,4-0,5 $\pm 0,1$ 0,6 $\pm 0,15$
$\leq 170 d_1 < 175$	5,4 0 -0,25	5,6 0 -0,25	5,8 0 -0,25	6 0 -0,25	4,5	5	6	7	-0,010 -0,035 For phosphated PO surface: -0,005 -0,035	0,45 +0,35 0						
$175 \leq d_1 < 180$	5,8 0 -	6 0 -	6,3 0 -	6,7 0 -	5	6	7	8	-0,010 -0,035 For phosphated PO surface: -0,005 -0,035	0,55 +0,40 0	4,6	4,7	4,8	5	$\pm 0,20$ within a ring 0,2 max.	0,4-0,5 $\pm 0,1$ 0,6 $\pm 0,15$
$180 \leq d_1 < 185$	5,8 0 -	6 0 -	6,3 0 -	6,7 0 -	5	6	7	8	-0,010 -0,035 For phosphated PO surface: -0,005 -0,035	0,55 +0,40 0	4,6	4,7	4,8	5	$\pm 0,20$ within a ring 0,2 max.	0,4-0,5 $\pm 0,1$ 0,6 $\pm 0,15$
$185 \leq d_1 < 190$	6,2 0 -0,4	6,5 0 -0,4	6,7 0 -0,4	7,1 0 -0,4	5	6	7	8	-0,010 -0,035 For phosphated PO surface: -0,005 -0,035	0,55 +0,40 0	4,9	5	5,1	5,3	$\pm 0,20$ within a ring 0,2 max.	0,4-0,5 $\pm 0,1$ 0,6 $\pm 0,15$
$190 \leq d_1 < 195$	6,2 0 -0,4	6,5 0 -0,4	6,7 0 -0,4	7,1 0 -0,4	5	6	7	8	-0,010 -0,035 For phosphated PO surface: -0,005 -0,035	0,55 +0,40 0	4,9	5	5,1	5,3	$\pm 0,20$ within a ring 0,2 max.	0,4-0,5 $\pm 0,1$ 0,6 $\pm 0,15$
$195 \leq d_1 \leq 200$	6,2 0 -0,4	6,5 0 -0,4	6,7 0 -0,4	7,1 0 -0,4	5	6	7	8	-0,010 -0,035 For phosphated PO surface: -0,005 -0,035	0,55 +0,40 0	4,9	5	5,1	5,3	$\pm 0,20$ within a ring 0,2 max.	0,4-0,5 $\pm 0,1$ 0,6 $\pm 0,15$

NOTE For intermediate sizes (e.g. repair sizes), the radial thickness of the next smaller nominal diameter applies.

Table 15 — Groove and spring dimensions of GSF and DSF oil control rings

Dimensions in millimetres

Nominal diameter	Groove depth a_4 for h_1 shown in column				Groove depth and bridge a_{13} for h_1 shown in column				Coil spring groove diameter d_{14} for h_1 shown in column				Coil spring diameter d_7 for h_1 shown in column				
	d_1	1	2	3	4	1	2	3	4	1	2	3	4	1	2	3	4
$60 \leq d_1 < 65$	-	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	-	1,5 0 0,15	1,5 0 0,15	1,5 0 0,15	-	2,1 $+0,1$ 0	2,1 $+0,1$ 0	2,3 $+0,1$ 0	-	2 0,1 0	2 0,1 0	2,2 - 0	2,2 - 0
$65 \leq d_1 < 70$	-	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	-	1,6 0 0,15	1,5 0 0,15	1,5 0 0,15	-	2,1 $+0,1$ 0	2,3 $+0,1$ 0	2,3 $+0,1$ 0	-	2 0,1 0	2,2 0,1 0	2,2 - 0	2,2 - 0
$70 \leq d_1 < 75$	-	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	-	1,6 0 0,15	1,6 0 0,15	1,5 0 0,15	-	2,1 $+0,1$ 0	2,3 $+0,1$ 0	2,5 $+0,1$ 0	-	2 0,1 0	2,2 0,1 0	2,4 - 0	2,4 - 0
$75 \leq d_1 < 80$	-	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	-	1,7 0 0,15	1,7 0 0,15	1,6 0 0,15	-	2,1 $+0,1$ 0	2,3 $+0,1$ 0	2,5 $+0,1$ 0	-	2 0,1 0	2,2 0,1 0	2,4 - 0	2,4 - 0
$80 \leq d_1 < 85$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	1,8 0 -0,15	1,8 0 0,15	1,7 0 0,15	1,7 0 0,15	2,1 $+0,1$ 0	2,3 $+0,1$ 0	2,5 $+0,1$ 0	2,5 $+0,1$ 0	2 0,1 0	2,2 0,1 0	2,4 0,1 0	2,4 - 0	2,4 - 0
$85 \leq d_1 < 90$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	1,9 0 0,15	1,8 0 0,15	1,7 0 0,15	1,7 0 0,15	2,1 $+0,1$ 0	2,3 $+0,1$ 0	2,5 $+0,1$ 0	2,5 $+0,1$ 0	2 0,1 0	2,2 0,1 0	2,4 0,1 0	2,4 - 0	2,4 - 0
$90 \leq d_1 < 95$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	1,9 0 0,15	1,9 0 0,15	1,8 0 0,15	1,8 0 0,15	2,1 $+0,1$ 0	2,3 $+0,1$ 0	2,5 $+0,1$ 0	2,5 $+0,1$ 0	2 -0,1 0	2,2 0,1 0	2,4 0,1 0	2,4 - 0	2,4 - 0
$95 \leq d_1 < 100$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	2 0 0,15	1,9 0 0,15	1,8 0 0,15	1,8 0 0,15	2,1 $+0,1$ 0	2,3 $+0,1$ 0	2,5 $+0,1$ 0	2,5 $+0,1$ 0	2 0,1 0	2,2 0,1 0	2,4 0,1 0	2,4 - 0	2,4 - 0
$100 \leq d_1 < 105$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	2 0 0,15	2 0 -0,2	1,9 0 -0,2	1,9 0 -0,2	2,3 $+0,1$ 0	2,5 $+0,1$ 0	2,7 $+0,1$ 0	2,9 $+0,1$ 0	2,2 0,1 0	2,4 0,1 0	2,6 0,1 0	2,8 - 0	2,8 - 0
$105 \leq d_1 < 110$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	2 0 0,15	2 0 -0,2	1,9 0 -0,2	1,9 0 -0,2	2,3 $+0,1$ 0	2,5 $+0,1$ 0	2,7 $+0,1$ 0	2,9 $+0,1$ 0	2,2 0,1 0	2,4 0,1 0	2,6 0,1 0	2,8 - 0	2,8 - 0
$110 \leq d_1 < 115$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	2,1 0 -0,2	2,1 0 -0,2	2 0 -0,2	2 0 -0,2	2,3 $+0,1$ 0	2,5 $+0,1$ 0	2,7 $+0,1$ 0	2,9 $+0,1$ 0	2,2 0,1 0	2,4 0,1 0	2,6 0,1 0	2,8 - 0	2,8 - 0
$115 \leq d_1 < 120$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	2,2 0 -0,2	2,2 0 -0,2	2,1 0 -0,2	2,1 0 -0,2	2,3 $+0,1$ 0	2,5 $+0,1$ 0	2,7 $+0,1$ 0	2,9 $+0,1$ 0	2,2 0,1 0	2,4 0,1 0	2,6 0,1 0	2,8 - 0	2,8 - 0
$120 \leq d_1 < 125$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	2,2 0 -0,2	2,2 0 -0,2	2,2 0 -0,2	2,2 0 -0,2	2,3 $+0,1$ 0	2,5 $+0,1$ 0	2,7 $+0,1$ 0	2,9 $+0,1$ 0	2,2 0,1 0	2,4 0,1 0	2,6 0,1 0	2,8 - 0	2,8 - 0

Table 15 (continued)

Nominal diameter	Groove depth a_4 for h_1 shown in column				Groove depth and bridge a_{13} for h_1 shown in column				Coil spring groove diameter d_{14} for h_1 shown in column				Coil spring diameter d_7 for h_1 shown in column			
	d_1	1	2	3	4	1	2	3	4	1	2	3	4	1	2	3
$125 \leq d_1 < 130$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	2,3 0 -0,2	2,3 0 -0,2	2,2 0 -0,2	2,2 0 -0,2	2,5 +0,1 0	2,7 +0,1 0	2,9 +0,1 0	3,1 +0,1 0	2,4 0 - 0,1	2,6 0 - 0,1	2,8 0 - 0,1	3 0 - 0,1
$130 \leq d_1 < 135$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	2,3 0 - 0,2	2,3 0 - 0,2	2,3 0 - 0,2	2,3 0 - 0,2	2,5 +0,1 0	2,7 +0,1 0	2,9 +0,1 0	3,1 +0,1 0	2,4 - 0,1 0	2,6 - 0,1 0	2,8 - 0,1 0	3 - 0,1 0
$135 \leq d_1 < 140$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	2,3 0 - 0,2	2,3 0 - 0,2	2,3 0 - 0,2	2,3 0 - 0,2	2,7 +0,1 0	2,9 +0,1 0	3,1 +0,1 0	3,3 +0,15 0	2,6 - 0,1 0	2,8 - 0,1 0	3 - 0,1 0	3,2 -0,1 0
$140 \leq d_1 < 145$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	2,3 0 - 0,2	2,3 0 - 0,2	2,3 0 - 0,2	2,3 0 - 0,2	2,7 +0,1 0	2,9 +0,1 0	3,1 +0,1 0	3,3 +0,15 0	2,6 - 0,1 0	2,8 - 0,1 0	3 - 0,1 0	3,2 - 0,1 0
$145 \leq d_1 < 150$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	2,3 0 - 0,2	2,3 0 - 0,2	2,3 0 - 0,2	2,3 0 - 0,2	2,7 +0,1 0	2,9 +0,1 0	3,1 +0,1 0	3,3 +0,15 0	2,6 - 0,1 0	2,8 - 0,1 0	3 - 0,1 0	3,2 - 0,1 0
$150 \leq d_1 < 155$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	1,2 $\pm 0,15$	2,6 0 - 0,2	2,4 0 - 0,2	2,3 0 - 0,2	2,3 0 - 0,2	2,9 +0,1 0	3,1 +0,15 0	3,3 +0,15 0	3,3 +0,15 0	2,8 0 - 0,1	3 0 - 0,1	3,2 0 - 0,1	3,2 0 - 0,1
$155 \leq d_1 < 160$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	1,2 $\pm 0,15$	2,6 0 - 0,2	2,6 0 - 0,2	2,6 0 - 0,2	2,4 0 - 0,2	2,9 +0,1 0	3,1 +0,15 0	3,3 +0,15 0	3,3 +0,15 0	2,8 0 - 0,1	3 0 - 0,1	3,2 0 - 0,1	3,2 0 - 0,1
$160 \leq d_1 < 165$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	1,2 $\pm 0,15$	2,6 0 - 0,2	2,6 0 - 0,2	2,6 0 - 0,2	2,4 0 - 0,2	2,9 +0,1 0	3,1 +0,15 0	3,3 +0,15 0	3,7 +0,15 0	2,8 0 - 0,1	3 0 - 0,1	3,2 0 - 0,1	3,6 0 - 0,1
$165 \leq d_1 < 170$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	1,2 $\pm 0,15$	2,6 0 - 0,2	2,6 0 - 0,2	2,6 0 - 0,2	2,4 0 - 0,2	2,9 +0,1 0	3,1 +0,15 0	3,3 +0,15 0	3,7 +0,15 0	2,8 0 - 0,1	3 0 - 0,1	3,2 0 - 0,1	3,6 0 - 0,1
$170 \leq d_1 < 175$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	1,2 $\pm 0,15$	2,6 0 - 0,2	2,6 0 - 0,2	2,6 0 - 0,2	2,4 0 - 0,2	2,9 +0,1 0	3,1 +0,15 0	3,3 +0,15 0	3,7 +0,15 0	2,8 0 - 0,1	3 0 - 0,1	3,2 0 - 0,1	3,6 0 - 0,1
$175 \leq d_1 < 180$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	1,2 $\pm 0,15$	1,5 $\pm 0,15$	2,8 0 -0,2	2,8 0 -0,2	2,7 0 -0,2	2,7 0 -0,2	3,1 +0,1 0	3,3 +0,15 0	3,7 +0,15 0	4,15 +0,15 0	3 -0,1 0	3,2 -0,1 0	3,6 -0,1 0	4 -0,12 0
$180 \leq d_1 < 185$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	1,2 $\pm 0,15$	1,5 $\pm 0,15$	2,8 0 -0,2	2,8 0 -0,2	2,7 0 -0,2	2,7 0 -0,2	3,1 +0,1 0	3,3 +0,15 0	3,7 +0,15 0	4,15 +0,15 0	3 -0,1 0	3,2 -0,1 0	3,6 -0,1 0	4 -0,12 0
$185 \leq d_1 < 190$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	1,2 $\pm 0,1$	1,5 $\pm 0,1$	3 0 -0,2	2,9 0 -0,2	2,7 0 -0,2	2,7 0 -0,2	3,3 +0,15 0	3,7 +0,15 0	4,15 +0,15 0	4,55 +0,15 0	3,2 0 -0,1	3,6 0 -0,1	4 0 -0,12	4,4 0 -0,12
$190 \leq d_1 < 195$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	1,2 $\pm 0,1$	1,5 $\pm 0,1$	3 0 -0,2	2,9 0 -0,2	2,7 0 -0,2	2,7 0 -0,2	3,3 +0,15 0	3,7 +0,15 0	4,15 +0,15 0	4,55 +0,15 0	3,2 0 -0,1	3,6 0 -0,1	4 0 -0,12	4,4 0 -0,12

ISO 6626-1:2024(en)

Table 15 (continued)

Nominal diameter	Groove depth a_4 for h_1 shown in column				Groove depth and bridge a_{13} for h_1 shown in column				Coil spring groove diameter d_{14} for h_1 shown in column				Coil spring diameter d_7 for h_1 shown in column			
	d_1	1	2	3	4	1	2	3	4	1	2	3	4	1	2	3
$195 \leq d_1 \leq 200$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	1,2 $\pm 0,1$	1,5 $\pm 0,1$	3 0 -0,2	2,9 0 -0,2	2,7 0 -0,2	2,7 0 -0,2	3,3 +0,15 0	3,7 +0,15 0	4,15 +0,15 0	4,55 +0,15 0	3,2 0 -0,1	3,6 0 -0,1	4 0 -0,12	4,4 0 -0,12

Table 16 — Width dimensions of DSF-NG oil control rings

Dimensions in millimetres

Nominal diameter	Radial thickness over coil spring a_{12} for h_1 shown in column				Ring width h_1 column					Closed gap s_1	Radial wall thickness a_1 for h_1 shown in column					Land width h_5 for all h_1 Recommended range
	d_1	1	2	3	4	1	2	3	4		Tolerance	1	2	3	4	
$60 \leq d_1 < 65$	-	3,5 0 0,25	3,5 0 0,25	3,7 0 0,25	-	3	3,5	4	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,2 +0,2 0	-	2,4	2,4	2,5	$\pm 0,15$ within a ring 0,15 max.	0,35-0,4 $\pm 0,1$
$65 \leq d_1 < 70$	-	3,6 0 0,25	3,7 0 0,25	3,7 0 0,25	-	3	3,5	4	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,2 +0,2 0	-	2,45	2,5	2,5	$\pm 0,15$ within a ring 0,15 max.	0,35-0,4 $\pm 0,1$
$70 \leq d_1 < 75$	-	3,6 0 0,25	3,8 0 0,25	3,9 0 0,25	-	3	3,5	4	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,2 +0,2 0	-	2,55	2,6	2,6	$\pm 0,15$ within a ring 0,15 max.	0,35-0,4 $\pm 0,1$
$75 \leq d_1 < 80$	-	3,7 0 -0,25	3,9 0 -0,25	4 0 -0,25	-	3	3,5	4	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,25 +0,25 0	-	2,6	2,7	2,7	$\pm 0,15$ within a ring 0,15 max.	0,35-0,4 $\pm 0,1$
$80 \leq d_1 < 85$	-	3,8 0 0,25	4 0 0,25	4,1 0 0,25	3	3,5	4	4,5	-0,010 -0,030 For phosphate PO surface: -0,005 -0,030	0,25 +0,25 0	2,7	2,7	2,8	2,8	$\pm 0,15$ within a ring 0,15 max.	0,35-0,4 $\pm 0,1$

NOTE For intermediate sizes (e.g. repair sizes), the radial thickness of the next smaller nominal diameter applies.

Table 16 (continued)

Nominal diameter	Radial thickness over coil spring a_{12} for h_1 shown in column				Ring width h_1 column					Closed gap s_1	Radial wall thickness a_1 for h_1 shown in column					Land width h_5 for all h_1 Recommended range
	d_1	1	2	3	4	1	2	3	4		Tolerance	1	2	3	4	
$85 \leq d_1 < 90$	3,9 0 - 0,25	4 0 - 0,25	4,1 0 - 0,25	4,1 0 - 0,25	3	3,5	4	4,5	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,25 +0,25 0	2,8	2,8	2,9	2,9	$\pm 0,15$ within a ring 0,15 max.	0,35-0,4 $\pm 0,1$
$90 \leq d_1 < 95$	3,9 0 - 0,25	4,1 0 - 0,25	4,2 0 - 0,25	4,2 0 - 0,25	3	3,5	4	4,5	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,3 +0,25 0	2,85	2,9	2,95	3	$\pm 0,15$ within a ring 0,15 max.	0,35-0,4 $\pm 0,1$
$95 \leq d_1 < 100$	4 0 - 0,25	4,1 0 - 0,25	4,2 0 -0,25	4,2 0 -0,25	3	3,5	4	4,5	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,3 +0,25 0	2,95	3	3,05	3,1	$\pm 0,15$ within a ring 0,15 max.	0,35-0,4 $\pm 0,1$
$100 \leq d_1 < 105$	4,2 0 - 0,25	4,4 0 - 0,25	4,5 0 -0,25	4,7 0 -0,25	3,5	4	4,5	5	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,3 +0,25 0	3,05	3,1	3,15	3,2	$\pm 0,20$ within a ring 0,2 max.	0,35-0,4 $\pm 0,1$
$105 \leq d_1 < 110$	4,2 0 - 0,25	4,4 0 - 0,25	4,5 0 -0,25	4,7 0 -0,25	3,5	4	4,5	5	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030		3,1	3,15	3,2	3,3	$\pm 0,20$ within a ring 0,2 max.	0,35-0,4 $\pm 0,1$
$110 \leq d_1 < 115$	4,3 0 - 0,25	4,5 0 - 0,25	4,6 0 -0,25	4,8 0 -0,25	3,5	4	4,5	5	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,35 +0,30 0	3,2	3,25	3,3	3,4	$\pm 0,20$ within a ring 0,2 max.	0,35-0,4 $\pm 0,1$
$115 \leq d_1 < 120$	4,4 0 - 0,25	4,6 0 - 0,25	4,7 0 -0,25	4,9 0 -0,25	3,5	4	4,5	5	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,35 +0,30 0	3,3	3,35	3,4	3,5	$\pm 0,20$ within a ring 0,2 max.	0,35-0,4 $\pm 0,1$
$120 \leq d_1 < 125$	4,4 0 - 0,25	4,6 0 - 0,25	4,8 0 -0,25	5 0 -0,25	3,5	4	4,5	5	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,35 +0,30 0	3,4	3,45	3,5	3,6	$\pm 0,20$ within a ring 0,2 max.	0,35-0,4 $\pm 0,1$

NOTE For intermediate sizes (e.g. repair sizes), the radial thickness of the next smaller nominal diameter applies.

ISO 6626-1:2024(en)

Table 16 (continued)

Nominal diameter	Radial thickness over coil spring a_{12} for h_1 shown in column				Ring width h_1 column					Closed gap s_1	Radial wall thickness a_1 for h_1 shown in column					Land width h_5 for all h_1 Recommended range
	d_1	1	2	3	4	1	2	3	4		Tolerance	1	2	3	4	
$125 \leq d_1 < 130$	4,7 0 - 0,25	4,9 0 - 0,25	5 0 -0,25	5,2 0 -0,25	4	4,5	5	6	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,35 +0,30 0	3,5	3,6	3,6	3,7	$\pm 0,20$ within a ring 0,2 max.	0,4-0,5 $\pm 0,1$
$130 \leq d_1 < 135$	4,7 0 - 0,25	4,9 0 - 0,25	5 0 - 0,25	5,2 0 - 0,25	4	4,5	5	6	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,4 +0,3 0	3,5	3,6	3,7	3,8	$\pm 0,15$ within a ring 0,15 max.	0,4-0,5 $\pm 0,1$
$135 \leq d_1 < 140$	4,9 0 - 0,25	5,1 0 - 0,25	5,3 0 - 0,25	5,5 0 - 0,25	4	4,5	5	6	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,4 +0,3 0	3,6	3,7	3,8	3,9	$\pm 0,20$ within a ring 0,2 max.	0,4-0,5 $\pm 0,1$
$140 \leq d_1 < 145$	4,9 0 - 0,25	5,1 0 - 0,25	5,3 0 - 0,25	5,5 0 - 0,25	4	4,5	5	6	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,4 +0,3 0	3,7	3,8	3,9	4	$\pm 0,20$ within a ring 0,2 max.	0,4-0,5 $\pm 0,1$
$145 \leq d_1 < 150$	4,9 0 - 0,25	5,1 0 - 0,25	5,3 0 - 0,25	5,5 0 - 0,25	4	4,5	5	6	0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,4 +0,3 0	3,8	3,9	4	4,1	$\pm 0,20$ within a ring 0,2 max.	0,4-0,5 $\pm 0,1$
$150 \leq d_1 < 155$	5,4 0 - 0,25	5,4 0 - 0,25	5,5 0 - 0,25	5,5 0 - 0,25	4,5	5	6	7	-0,010 -0,035 For phosphated PO surface: -0,005 -0,035	0,45 +0,35 0	3,9	4	4,1	4,2	$\pm 0,20$ within a ring 0,2 max.	0,4-0,5 $\pm 0,1$ 0,6 $\pm 0,12$
$154 \leq d_1 < 160$	5,4 0 -0,25	5,4 0 -0,25	5,5 0 -0,25	5,5 0 -0,25	4,5	5	6	7	-0,010 -0,035 For phosphated PO surface: -0,005 -0,035	0,45 +0,35 0	3,9	4	4,1	4,2	$\pm 0,20$ within a ring 0,2 max.	0,4-0,5 $\pm 0,1$ 0,6 $\pm 0,12$

NOTE For intermediate sizes (e.g. repair sizes), the radial thickness of the next smaller nominal diameter applies.

ISO 6626-1:2024(en)

Table 16 (continued)

Nominal diameter	Radial thickness over coil spring a_{12} for h_1 shown in column				Ring width h_1 column					Closed gap s_1	Radial wall thickness a_1 for h_1 shown in column					Land width h_5 for all h_1 Recommended range
	d_1	1	2	3	4	1	2	3	4		Tolerance	1	2	3	4	
$160 \leq d_1 < 165$	5,4 0 - 0,25	5,6 0 - 0,25	5,8 0 - 0,25	6 0 - 0,25	4,5	5	6	7	-0,010 -0,035 For phosphated PO surface -0,005 -0,035	0,45 +0,35 0	4	4,2	4,3	4,4	$\pm 0,20$ within a ring 0,2 max.	0,4-0,5 $\pm 0,1$ 0,6 $\pm 0,12$
$165 \leq d_1 < 170$	5,4 0 - 0,25	5,6 0 - 0,25	5,8 0 - 0,25	6 0 - 0,25	4,5	5	6	7	-0,010 -0,035 For phosphated PO surface -0,005 -0,035	0,45 +0,35 0	4	4,2	4,3	4,4	$\pm 0,20$ within a ring 0,2 max.	0,4-0,5 $\pm 0,1$ 0,6 $\pm 0,12$
$170 \leq d_1 < 175$	5,4 0 - 0,25	5,6 0 - 0,25	5,8 0 - 0,25	6 0 - 0,25	4,5	5	6	7	-0,010 -0,035 For phosphated PO surface -0,005 -0,035	0,45 +0,35 0	4	4,2	4,3	4,4	$\pm 0,20$ within a ring 0,2 max.	0,4-0,5 $\pm 0,1$ 0,6 $\pm 0,12$
$175 \leq d_1 < 180$	5,8 0 - 0,35	6 0 - 0,35	6,3 0 - 0,35	6,7 0 - 0,35	5	6	7	8	-0,010 -0,035 For phosphated PO surface: -0,005 -0,035	0,55 +0,40 0	4,6	4,7	4,8	5	$\pm 0,20$ within a ring 0,2 max.	0,4-0,5 $\pm 0,1$ 0,6 $\pm 0,12$
$180 \leq d_1 < 185$	5,8 0 - 0,35	6 0 - 0,35	6,3 0 - 0,35	6,7 0 - 0,35	5	6	7	8	-0,010 -0,035 For phosphated PO surface: -0,005 -0,035	0,55 +0,40 0	4,6	4,7	4,8	5	$\pm 0,20$ within a ring 0,2 max	0,4-0,5 $\pm 0,1$ 0,6 $\pm 0,12$
$185 \leq d_1 < 190$	6,2 0 -0,4	6,5 0 -0,4	6,7 0 -0,4	7,1 0 -0,4	5	6	7	8	-0,010 -0,035 For phosphated PO surface: -0,005 -0,035	0,55 +0,40 0	4,9	5	5,1	5,3	$\pm 0,20$ within a ring 0,2 max	0,4-0,5 $\pm 0,1$ 0,6 $\pm 0,12$
$190 \leq d_1 < 195$	6,2 0 -0,4	6,5 0 -0,4	6,7 0 -0,4	7,1 0 -0,4	5	6	7	8	-0,010 -0,035 For phosphated PO surface: -0,005 -0,035	0,55 +0,40 0	4,9	5	5,1	5,3	$\pm 0,20$ within a ring 0,2 max	0,4-0,5 $\pm 0,1$ 0,6 $\pm 0,12$

NOTE For intermediate sizes (e.g. repair sizes), the radial thickness of the next smaller nominal diameter applies.

Table 16 (continued)

Nominal diameter	Radial thickness over coil spring a_{12} for h_1 shown in column				Ring width h_1 column					Closed gap s_1	Radial wall thickness a_1 for h_1 shown in column					Land width h_5 for all h_1	
	1	2	3	4	1	2	3	4	Tolerance		1	2	3	4	Tolerance	Recommended range	
$195 \leq d_1 \leq 200$	6,2 0 -0,4	6,5 0 -0,4	6,7 0 -0,4	7,1 0 -0,4	5	6	7	8	-0,035 For phosphated PO surface: -0,005 -0,035	0,55 +0,40 0	4,9	5	5,1	5,3	$\pm 0,20$ within a ring 0,2 max	0,4-0,5 $\pm 0,1$ 0,6 $\pm 0,12$	

NOTE For intermediate sizes (e.g. repair sizes), the radial thickness of the next smaller nominal diameter applies.

Table 17 — Groove and spring dimensions of DSF-NG oil control rings

Dimensions in millimetres

Nominal diameter	Groove depth a_4 for h_1 shown in column				Groove depth and bridge a_{13} for h_1 shown in column				Coil spring groove diameter d_{14} for h_1 shown in column				Coil spring diameter d_7 for h_1 shown in column				
	1	2	3	4	1	2	3	4	1	2	3	4	1	2	3	4	
$60 \leq d_1 < 65$	-	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	-	1,5 0 0,15	1,5 0 0,15	1,5 0 0,15	-	2,1 +0,1 0	2,1 +0,1 0	2,3 +0,1 0	-	2 0,1 0	2 0,1 0	2,2 - 0	2,2 - 0
$65 \leq d_1 < 70$	-	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	-	1,6 0 0,15	1,5 0 0,15	1,5 0 0,15	-	2,1 +0,1 0	2,3 +0,1 0	2,3 +0,1 0	-	2 0,1 0	2,2 0,1 0	2,2 - 0	2,2 - 0
$70 \leq d_1 < 75$	-	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	-	1,6 0 0,15	1,6 0 0,15	1,5 0 0,15	-	2,1 +0,1 0	2,3 +0,1 0	2,5 +0,1 0	-	2 0,1 0	2,2 - 0	2,4 - 0	2,4 0,1 0
$75 \leq d_1 < 80$	-	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	-	1,7 0 0,15	1,7 0 0,15	1,6 0 0,15	-	2,1 +0,1 0	2,3 +0,1 0	2,5 +0,1 0	-	2 0,1 0	2,2 - 0	2,4 - 0	2,4 0,1 0
$80 \leq d_1 < 85$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	1,8 0 0,15	1,8 0 0,15	1,7 0 0,15	1,7 0 0,15	2,1 +0,1 0	2,3 +0,1 0	2,5 +0,1 0	2,5 +0,1 0	2 -0,1 0	2,2 0,1 0	2,4 0,1 0	2,4 - 0	2,4 0,1 0
$85 \leq d_1 < 90$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	1,9 0 0,15	1,8 0 0,15	1,7 0 0,15	1,7 0 0,15	2,1 +0,1 0	2,3 +0,1 0	2,5 +0,1 0	2,5 +0,1 0	2 -0,1 0	2,2 0,1 0	2,4 0,1 0	2,4 - 0	2,4 0,1 0
$90 \leq d_1 < 95$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	1,9 0 0,15	1,9 0 0,15	1,8 0 0,15	1,8 0 0,15	2,1 +0,1 0	2,3 +0,1 0	2,5 +0,1 0	2,5 +0,1 0	2 -0,1 0	2,2 0,1 0	2,4 0,1 0	2,4 - 0	2,4 0,1 0
$95 \leq d_1 < 100$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	2 0 0,15	1,9 0 0,15	1,8 0 0,15	1,8 0 0,15	2,1 +0,1 0	2,3 +0,1 0	2,5 +0,1 0	2,5 +0,1 0	2 -0,1 0	2,2 0,1 0	2,4 0,1 0	2,4 - 0	2,4 0,1 0

ISO 6626-1:2024(en)

Table 17 (continued)

Nominal diameter	Groove depth a_4 for h_1 shown in column				Groove depth and bridge a_{13} for h_1 shown in column				Coil spring groove diameter d_{14} for h_1 shown in column				Coil spring diameter d_7 for h_1 shown in column				
	d_1	1	2	3	4	1	2	3	4	1	2	3	4	1	2	3	4
	$100 \leq d_1 < 105$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	2 0 - 0,15	2 0 -0,2	1,9 0 -0,2	1,9 0 -0,2	2,3 +0,1 0	2,5 +0,1 0	2,7 +0,1 0	2,9 +0,1 0	2,2 - 0,1 0	2,4 - 0,1 0	2,6 - 0,1 0	2,8 - 0,1 0
$105 \leq d_1 < 110$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	2 0 - 0,15	2 0 -0,2	1,9 0 -0,2	1,9 0 -0,2	2,3 +0,1 0	2,5 +0,1 0	2,7 +0,1 0	2,9 +0,1 0	2,2 - 0,1 0	2,4 - 0,1 0	2,6 - 0,1 0	2,8 - 0,1 0	
$110 \leq d_1 < 115$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	2,1 0 -0,2	2,1 0 -0,2	2 0 -0,2	2 0 -0,2	2,3 +0,1 0	2,5 +0,1 0	2,7 +0,1 0	2,9 +0,1 0	2,2 - 0,1 0	2,4 - 0,1 0	2,6 - 0,1 0	2,8 - 0,1 0	
$115 \leq d_1 < 120$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	2,2 0 -0,2	2,2 0 -0,2	2,1 0 -0,2	2,1 0 -0,2	2,3 +0,1 0	2,5 +0,1 0	2,7 +0,1 0	2,9 +0,1 0	2,2 - 0,1 0	2,4 - 0,1 0	2,6 - 0,1 0	2,8 - 0,1 0	
$120 \leq d_1 < 125$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	2,2 0 -0,2	2,2 0 -0,2	2,2 0 -0,2	2,2 0 -0,2	2,3 +0,1 0	2,5 +0,1 0	2,7 +0,1 0	2,9 +0,1 0	2,2 - 0,1 0	2,4 - 0,1 0	2,6 - 0,1 0	2,8 - 0,1 0	
$125 \leq d_1 < 130$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	2,3 0 -0,2	2,3 0 -0,2	2,2 0 -0,2	2,2 0 -0,2	2,5 +0,1 0	2,7 +0,1 0	2,9 +0,1 0	3,1 +0,1 0	2,4 0 - 0,1	2,6 0 - 0,1	2,8 0 - 0,1	3 0 - 0,1	
$130 \leq d_1 < 135$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	2,3 0 - 0,2	2,3 0 - 0,2	2,3 0 - 0,2	2,3 0 - 0,2	2,5 +0,1 0	2,7 +0,1 0	2,9 +0,1 0	3,1 +0,1 0	2,4 - 0,1 0	2,6 - 0,1 0	2,8 - 0,1 0	3 - 0,1 0	
$135 \leq d_1 < 140$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	2,3 0 - 0,2	2,3 0 - 0,2	2,3 0 - 0,2	2,3 0 - 0,2	2,7 +0,1 0	2,9 +0,1 0	3,1 +0,1 0	3,3 +0,15 0	2,6 0 - 0,1	2,8 0 - 0,1	3 0 - 0,1	3,2 0 - 0,1	
$140 \leq d_1 < 145$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	2,3 0 - 0,2	2,3 0 - 0,2	2,3 0 - 0,2	2,3 0 - 0,2	2,7 +0,1 0	2,9 +0,1 0	3,1 +0,1 0	3,3 +0,15 0	2,6 0 - 0,1	2,8 0 - 0,1	3 0 - 0,1	3,2 0 - 0,1	
$145 \leq d_1 < 150$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	2,3 0 - 0,2	2,3 0 - 0,2	2,3 0 - 0,2	2,3 0 - 0,2	2,7 +0,1 0	2,9 +0,1 0	3,1 +0,1 0	3,3 +0,15 0	2,6 0 - 0,1	2,8 0 - 0,1	3 0 - 0,1	3,2 0 - 0,1	
$150 \leq d_1 < 155$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	1,2 $\pm 0,15$	2,6 0 - 0,2	2,4 0 - 0,2	2,3 0 - 0,2	2,3 0 - 0,2	2,9 +0,1 0	3,1 +0,15 0	3,3 +0,15 0	3,3 +0,15 0	2,8 0 - 0,1	3 0 - 0,1	3,2 0 - 0,1	3,2 0 - 0,1	
$155 \leq d_1 < 160$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	1,2 $\pm 0,15$	2,6 0 - 0,2	2,6 0 - 0,2	2,6 0 - 0,2	2,4 0 - 0,2	2,9 +0,1 0	3,1 +0,15 0	3,3 +0,15 0	3,3 +0,15 0	2,8 0 - 0,1	3 0 - 0,1	3,2 0 - 0,1	3,2 0 - 0,1	
$160 \leq d_1 < 165$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	1,2 $\pm 0,15$	2,6 0 - 0,2	2,6 0 - 0,2	2,6 0 - 0,2	2,4 0 - 0,2	2,9 +0,1 0	3,1 +0,15 0	3,3 +0,15 0	3,7 +0,15 0	2,8 0 - 0,1	3 0 - 0,1	3,2 0 - 0,1	3,6 0 - 0,1	

ISO 6626-1:2024(en)

Table 17 (continued)

Nominal diameter	Groove depth a_4 for h_1 shown in column				Groove depth and bridge a_{13} for h_1 shown in column				Coil spring groove diameter d_{14} for h_1 shown in column				Coil spring diameter d_7 for h_1 shown in column				
	d_1	1	2	3	4	1	2	3	4	1	2	3	4	1	2	3	4
$165 \leq d_1 < 170$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	1,2 $\pm 0,15$	2,6 0 -	2,6 0 -	2,6 0 -	2,4 0 -	2,9 +0,1 0	3,1 +0,15 0	3,3 +0,15 0	3,7 +0,15 0	2,8 0 -	3 0 -	3,2 0 -	3,6 0 -	0,1 0,1 0,1
$170 \leq d_1 < 175$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	1,2 $\pm 0,15$	2,6 0 -	2,6 0 -	2,6 0 -	2,4 0 -	2,9 +0,1 0	3,1 +0,15 0	3,3 +0,15 0	3,7 +0,15 0	2,8 0 -	3 0 -	3,2 0 -	3,6 0 -	0,1 0,1 0,1
$175 \leq d_1 < 180$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	1,2 $\pm 0,15$	1,5 $\pm 0,15$	2,8 0 -	2,8 0 -	2,7 0 -	2,7 0 -	3,1 +0,1 0	3,3 +0,15 0	3,7 +0,15 0	4,15 +0,15 0	3 0 -	3,2 -	3,6 -	4 -	0,1 0 0
$180 \leq d_1 < 185$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	1,2 $\pm 0,15$	1,5 $\pm 0,15$	2,8 0 -	2,8 0 -	2,7 0 -	2,7 0 -	3,1 +0,1 0	3,3 +0,15 0	3,7 +0,15 0	4,15 +0,15 0	3 0 -	3,2 -	3,6 -	4 -	0,1 0 0
$185 \leq d_1 < 195$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	1,2 $\pm 0,15$	1,5 $\pm 0,15$	3,0 0 -	2,9 0 -	2,7 0 -	2,7 0 -	3,3 +0,15 0	3,7 +0,15 0	4,15 +0,15 0	4,55 +0,15 0	3,2 0 -	3,6 0 -	4 0 -	4,4 0 -	0,1 0,1 0,12
$195 \leq d_1 \leq 200$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	1,2 $\pm 0,15$	1,5 $\pm 0,15$	3,0 0 -	2,9 0 -	2,7 0 -	2,7 0 -	3,3 +0,15 0	3,7 +0,15 0	4,15 +0,15 0	4,55 +0,15 0	3,2 0 -	3,6 0 -	4 0 -	4,4 0 -	0,1 0,1 0,12

Table 18 — Width dimensions of SSF-L oil control rings

Dimensions in millimetres

Nominal diameter	Radial thickness over coil spring a_{12} for h_1 shown in column				Ring width h_1 column					Closed gap s_1	Radial wall thickness a_1 for h_1 shown in column					Land width h_5 for all h_1 Recommended range
	d_1	1	2	3	4	1	2	3	4		Tolerance	1	2	3	4	
$60 \leq d_1 < 65$	-	3,5 0 -0,25	3,5 0 -0,25	3,7 0 -0,25	-	3	3,5	4	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,2 +0,2 0	-	2,4	2,4	2,5	$\pm 0,15$ within a ring 0,15 max.	0,6 $\pm 0,1$
$65 \leq d_1 < 70$	-	3,6 0 -0,25	3,7 0 -0,25	3,7 0 -0,25	-	3	3,5	4	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,2 +0,2 0	-	2,45	2,5	2,5	$\pm 0,15$ within a ring 0,15 max.	0,6 $\pm 0,1$

NOTE For intermediate sizes (e.g. repair sizes), the radial thickness of the next smaller nominal diameter applies.

Table 18 (continued)

Nominal diameter d_1	Radial thickness over coil spring a_{12} for h_1 shown in column				Ring width h_1 column					Closed gap s_1	Radial wall thickness a_1 for h_1 shown in column					Land width h_5 for all h_1 Recommended range
	1	2	3	4	1	2	3	4	Tolerance		1	2	3	4	Tolerance	
$70 \leq d_1 < 75$	-	3,6 0 -0,25	3,8 0 -0,25	3,9 0 -0,25	-	3	3,5	4	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,2 +0,2 0	-	2,55	2,6	2,6	$\pm 0,15$ within a ring 0,15 max.	0,6 $\pm 0,1$
$75 \leq d_1 < 80$	-	3,7 0 -0,25	3,9 0 -0,25	4 0 -0,25	-	3	3,5	4	0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,25 +0,25 0	-	2,6	2,7	2,7	$\pm 0,15$ within a ring 0,15 max.	0,6 $\pm 0,1$
$80 \leq d_1 < 85$	3,8 0 -0,25	4 0 -0,25	4,1 0 -0,25	4,1 0 -0,25	3	3,5	4	4,5	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,25 +0,25 0	2,7	2,7	2,8	2,8	$\pm 0,15$ within a ring 0,15 max.	0,6 $\pm 0,1$
$85 \leq d_1 < 90$	3,9 0 -0,25	4 0 -0,25	4,1 0 -0,25	4,1 0 -0,25	3	3,5	4	4,5	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,25 +0,25 0	2,8	2,8	2,9	2,9	$\pm 0,15$ within a ring 0,15 max.	0,6 $\pm 0,1$
$90 \leq d_1 < 95$	3,9 0 -0,25	4,1 0 -0,25	4,2 0 -0,25	4,2 0 -0,25	3	3,5	4	4,5	0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,3 +0,25 0	2,85	2,9	2,95	3	$\pm 0,15$ within a ring 0,15 max.	0,6 $\pm 0,1$
$95 \leq d_1 < 100$	4 0 -0,25	4,1 0 0,25	4,2 0 0,25	4,2 0 0,25	3	3,5	4	4,5	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,3 +0,25 0	2,95	3	3,05	3,1	$\pm 0,15$ within a ring 0,15 max.	0,6 $\pm 0,1$
$100 \leq d_1 < 105$	4,2 0 -0,25	4,4 0 0,25	4,5 0 0,25	4,7 0 0,25	3,5	4	4,5	5	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,3 +0,25 0	3,05	3,1	3,15	3,2	$\pm 0,20$ within a ring 0,2 max.	0,6 $\pm 0,1$

NOTE For intermediate sizes (e.g. repair sizes), the radial thickness of the next smaller nominal diameter applies.

Table 18 (continued)

Nominal diameter	Radial thickness over coil spring a_{12} for h_1 shown in column				Ring width h_1 column					Closed gap s_1	Radial wall thickness a_1 for h_1 shown in column					Land width h_5 for all h_1 Recommended range
	d_1	1	2	3	4	1	2	3	4		Tolerance	1	2	3	4	
$105 \leq d_1 < 110$	4,2 0 - 0,25	4,4 0 - 0,25	4,5 0 - 0,25	4,7 0 - 0,25	3,5	4	4,5	5	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,3 +0,25 0	3,1	3,15	3,2	3,3	$\pm 0,20$ within a ring 0,2 max.	0,6 $\pm 0,1$
$110 \leq d_1 < 115$	4,3 0 - 0,25	4,5 0 - 0,25	4,6 0 - 0,25	4,8 0 - 0,25	3,5	4	4,5	5	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,35 +0,30 0	3,2	3,25	3,3	3,4	$\pm 0,20$ within a ring 0,2 max.	0,6 $\pm 0,1$
$114 \leq d_1 < 120$	4,4 0 - 0,25	4,6 0 - 0,25	4,7 0 - 0,25	4,9 0 - 0,25	3,5	4	4,5	5	0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,35 +0,30 0	3,3	3,35	3,4	3,5	$\pm 0,20$ within a ring 0,2 max.	0,6 $\pm 0,1$
$120 \leq d_1 < 125$	4,4 0 - 0,25	4,6 0 - 0,25	4,8 0 - 0,25	5 0 - 0,25	3,5	4	4,5	5	0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,35 +0,30 0	3,4	3,45	3,5	3,6	$\pm 0,20$ within a ring 0,2 max.	0,6 $\pm 0,1$
$125 \leq d_1 < 130$	4,7 0 - 0,25	4,9 0 - 0,25	5 0 - 0,25	5,2 0 - 0,25	4	4,5	5	6	0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,35 +0,30 0	3,5	3,6	3,6	3,7	$\pm 0,20$ within a ring 0,2 max.	0,6 $\pm 0,1$
$130 \leq d_1 < 135$	4,7 0 -0,25	4,9 0 -0,25	5 0 -0,25	5,2 0 -0,25	4	4,5	5	6	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,4 +0,3 0	3,5	3,6	3,7	3,8	$\pm 0,15$ within a ring 0,15 max.	0,6 $\pm 0,1$
$135 \leq d_1 < 140$	4,9 0 -0,25	5,1 0 -0,25	5,3 0 -0,25	5,5 0 -0,25	4	4,5	5	6	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,4 +0,3 0	3,6	3,7	3,8	3,9	$\pm 0,20$ within a ring 0,2 max.	0,6 $\pm 0,1$

NOTE For intermediate sizes (e.g. repair sizes), the radial thickness of the next smaller nominal diameter applies.

Table 18 (continued)

Nominal diameter	Radial thickness over coil spring a_{12} for h_1 shown in column				Ring width h_1 column					Closed gap s_1	Radial wall thickness a_1 for h_1 shown in column					Land width h_5 for all h_1 Recommended range
	d_1	1	2	3	4	1	2	3	4		Tolerance	1	2	3	4	
$140 \leq d_1 < 145$	4,9 0 -0,25	5,1 0 -0,25	5,3 0 -0,25	5,5 0 -0,25	4	4,5	5	6	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,4 +0,3 0	3,7	3,8	3,9	4	$\pm 0,20$ within a ring 0,2 max.	0,6 $\pm 0,1$
$145 \leq d_1 < 150$	4,9 0 -0,25	5,1 0 -0,25	5,3 0 -0,25	5,5 0 -0,25	4	4,5	5	6	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,4 +0,3 0	3,8	3,9	4	4,1	$\pm 0,20$ within a ring 0,2 max.	0,6 $\pm 0,1$
$150 \leq d_1 < 155$	5,4 0 -0,25	5,4 0 -0,25	5,5 0 -0,25	5,5 0 -0,25	4,5	5	6	7	-0,010 -0,035 For phosphated PO surface: -0,005 -0,035	0,45 +0,35 0	3,9	4	4,1	4,2	$\pm 0,20$ within a ring 0,2 max.	0,6 $\pm 0,1$
$155 \leq d_1 < 160$	5,4 0 -0,25	5,4 0 -0,25	5,5 0 -0,25	5,5 0 -0,25	4,5	5	6	7	-0,010 -0,035 For phosphated PO surface: -0,005 -0,035	0,45 +0,35 0	3,9	4	4,1	4,2	$\pm 0,20$ within a ring 0,2 max.	0,6 $\pm 0,1$
$160 \leq d_1 < 165$	5,4 0 -0,25	5,6 0 -0,25	5,8 0 -0,25	6 0 -0,25	4,5	5	6	7	-0,010 -0,035 For phosphated PO surface: -0,005 -0,035	0,45 +0,35 0	4	4,2	4,3	4,4	$\pm 0,20$ within a ring 0,2 max.	0,6 $\pm 0,1$
$165 \leq d_1 < 170$	5,4 0 -0,25	5,6 0 -0,25	5,8 0 -0,25	6 0 -0,25	4,5	5	6	7	-0,010 -0,035 For phosphated PO surface: -0,005 -0,035	0,45 +0,35 0	4	4,2	4,3	4,4	$\pm 0,20$ within a ring 0,2 max.	0,6 $\pm 0,1$

NOTE For intermediate sizes (e.g. repair sizes), the radial thickness of the next smaller nominal diameter applies.

ISO 6626-1:2024(en)

Table 18 (continued)

Nominal diameter d_1	Radial thickness over coil spring a_{12} for h_1 shown in column				Ring width h_1 column					Closed gap s_1	Radial wall thickness a_1 for h_1 shown in column					Land width h_5 for all h_1 Recommended range
	1	2	3	4	1	2	3	4	Tolerance		1	2	3	4	Tolerance	
$170 \leq d_1 < 175$	5,4 0 -0,25	5,6 0 -0,25	5,8 0 -0,25	6 0 -0,25	4,5	5	6	7	-0,010 -0,035 For phosphated PO surface: -0,005 -0,035	0,45 +0,35 0	4	4,2	4,3	4,4	$\pm 0,20$ within a ring 0,2 max.	0,6 $\pm 0,1$
$175 \leq d_1 < 180$	5,8 0 -	6 0 -	6,3 0 -	6,7 0 -	5	6	7	8	-0,010 -0,035 For phosphated PO surface: -0,005 -0,035	0,55 +0,40 0	4,6	4,7	4,8	5	$\pm 0,20$ within a ring 0,2 max.	0,6 $\pm 0,1$
$180 \leq d_1 < 184$	5,8 0 -	6 0 -	6,3 0 -	6,7 0 -	5	6	7	8	-0,010 -0,035 For phosphated PO surface: -0,005 -0,035	0,55 +0,40 0	4,6	4,7	4,8	5	$\pm 0,20$ within a ring 0,2 max.	0,6 $\pm 0,1$
$185 \leq d_1 < 190$	6,2 0 -0,4	6,5 0 -0,4	6,7 0 -0,4	7,1 0 -0,4	5	6	7	8	0,010 -0,035 For phosphated PO surface: -0,005 -0,035	0,55 +0,40 0	4,9	5	5,1	5,3	$\pm 0,20$ within a ring 0,2 max.	0,6 $\pm 0,1$
$190 \leq d_1 < 195$	6,2 0 -0,4	6,5 0 -0,4	6,7 0 -0,4	7,1 0 -0,4	5	6	7	8	0,010 -0,035 For phosphated PO surface: -0,005 -0,035	0,55 +0,40 0	4,9	5	5,1	5,3	$\pm 0,20$ within a ring 0,2 max.	0,6 $\pm 0,1$
$195 \leq d_1 \leq 200$	6,2 0 -0,4	6,5 0 -0,4	6,7 0 -0,4	7,1 0 -0,4	5	6	7	8	-0,035 For phosphated PO surface: -0,005 -0,035	0,55 +0,40 0	4,9	5	5,1	5,3	$\pm 0,20$ within a ring 0,2 max.	0,6 $\pm 0,1$

NOTE For intermediate sizes (e.g. repair sizes), the radial thickness of the next smaller nominal diameter applies.

Table 19 — Groove and spring dimensions of SSF-L oil control rings

Dimensions in millimetres

Nominal diameter	Groove depth a_4 for h_1 shown in column				Groove depth and bridge a_{13} for h_1 shown in column				Coil spring groove diameter d_{14} for h_1 shown in column				Coil spring diameter d_7 for h_1 shown in column				
	d_1	1	2	3	4	1	2	3	4	1	2	3	4	1	2	3	4
$60 \leq d_1 < 65$	-	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	-	1,5 0 - 0,15	1,5 0 - 0,15	1,5 0 - 0,15	-	2,1 +0,1 0	2,1 +0,1 0	2,3 +0,1 0	-	2 - 0,1 0	2 - 0,1 0	2,2 - 0,1 0	2,2 - 0,1 0
$65 \leq d_1 < 70$	-	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	-	1,6 0 - 0,15	1,5 0 - 0,15	1,5 0 - 0,15	-	2,1 +0,1 0	2,3 +0,1 0	2,3 +0,1 0	-	2 - 0,1 0	2,2 - 0,1 0	2,2 - 0,1 0	2,2 - 0,1 0
$70 \leq d_1 < 75$	x	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	-	1,6 0 - 0,15	1,6 0 - 0,15	1,5 0 - 0,15	-	2,1 +0,1 0	2,3 +0,1 0	2,5 +0,1 0	-	2 - 0,1 0	2,2 - 0,1 0	2,4 - 0,1 0	2,4 - 0,1 0
$75 \leq d_1 < 80$	-	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	-	1,7 0 - 0,15	1,7 0 - 0,15	1,6 0 - 0,15	-	2,1 +0,1 0	2,3 +0,1 0	2,5 +0,1 0	-	2 - 0,1 0	2,2 - 0,1 0	2,4 - 0,1 0	2,4 - 0,1 0
$80 \leq d_1 < 85$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	1,8 0 -0,15	1,8 0 - 0,15	1,7 0 - 0,15	1,7 0 - 0,15	2,1 +0,1 0	2,3 +0,1 0	2,5 +0,1 0	2,5 +0,1 0	2 -0,1 0	2,2 - 0,1 0	2,4 - 0,1 0	2,4 - 0,1 0	2,4 - 0,1 0
$85 \leq d_1 < 90$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	1,9 0 -0,15	1,8 0 - 0,15	1,7 0 - 0,15	1,7 0 - 0,15	2,1 +0,1 0	2,3 +0,1 0	2,5 +0,1 0	2,5 +0,1 0	2 -0,1 0	2,2 - 0,1 0	2,4 - 0,1 0	2,4 - 0,1 0	2,4 - 0,1 0
$90 \leq d_1 < 95$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	1,9 0 - 0,15	1,9 0 - 0,15	1,8 0 - 0,15	1,8 0 - 0,15	2,1 +0,1 0	2,3 +0,1 0	2,5 +0,1 0	2,5 +0,1 0	2 -0,1 0	2,2 - 0,1 0	2,4 - 0,1 0	2,4 - 0,1 0	2,4 - 0,1 0
$95 \leq d_1 < 100$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	2 0 - 0,15	1,9 0 - 0,15	1,8 0 -0,15	1,8 0 -0,15	2,1 +0,1 0	2,3 +0,1 0	2,5 +0,1 0	2,5 +0,1 0	2 -0,1 0	2,2 - 0,1 0	2,4 - 0,1 0	2,4 - 0,1 0	2,4 - 0,1 0
$100 \leq d_1 < 105$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	2 0 - 0,15	2 0 -0,2	1,9 0 -0,2	1,9 0 -0,2	2,3 +0,1 0	2,5 +0,1 0	2,7 +0,1 0	2,9 +0,1 0	2,2 - 0,1 0	2,4 - 0,1 0	2,6 - 0,1 0	2,8 - 0,1 0	2,8 - 0,1 0
$105 \leq d_1 < 110$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	2 0 - 0,15	2 0 -0,2	1,9 0 -0,2	1,9 0 -0,2	2,3 +0,1 0	2,5 +0,1 0	2,7 +0,1 0	2,9 +0,1 0	2,2 - 0,1 0	2,4 - 0,1 0	2,6 - 0,1 0	2,8 - 0,1 0	2,8 - 0,1 0
$110 \leq d_1 < 115$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	2,1 0 -0,2	2,1 0 -0,2	2 0 -0,2	2 0 -0,2	2,3 +0,1 0	2,5 +0,1 0	2,7 +0,1 0	2,9 +0,1 0	2,2 - 0,1 0	2,4 - 0,1 0	2,6 - 0,1 0	2,8 - 0,1 0	2,8 - 0,1 0
$115 \leq d_1 < 120$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	2,2 0 -0,2	2,2 0 -0,2	2,1 0 -0,2	2,1 0 -0,2	2,3 +0,1 0	2,5 +0,1 0	2,7 +0,1 0	2,9 +0,1 0	2,2 - 0,1 0	2,4 - 0,1 0	2,6 - 0,1 0	2,8 - 0,1 0	2,8 - 0,1 0
$120 \leq d_1 < 124$	0,5 $\pm 0,1$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	2,2 0 -0,2	2,2 0 -0,2	2,2 0 -0,2	2,2 0 -0,2	2,3 +0,1 0	2,5 +0,1 0	2,7 +0,1 0	2,9 +0,1 0	2,2 - 0,1 0	2,4 - 0,1 0	2,6 - 0,1 0	2,8 - 0,1 0	2,8 - 0,1 0

Table 19 (continued)

Nominal diameter	Groove depth a_4 for h_1 shown in column				Groove depth and bridge a_{13} for h_1 shown in column				Coil spring groove diameter d_{14} for h_1 shown in column				Coil spring diameter d_7 for h_1 shown in column			
	d_1	1	2	3	4	1	2	3	4	1	2	3	4	1	2	3
$125 \leq d_1 < 130$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	2,3 0 -0,2	2,3 0 -0,2	2,2 0 -0,2	2,2 0 -0,2	2,5 +0,1 0	2,7 +0,1 0	2,9 +0,1 0	3,1 +0,1 0	2,4 0 - 0,1	2,6 0 - 0,1	2,8 0 - 0,1	3 0 - 0,1
$130 \leq d_1 < 135$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	2,3 0 - 0,2	2,3 0 - 0,2	2,3 0 - 0,2	2,3 0 - 0,2	2,5 +0,1 0	2,7 +0,1 0	2,9 +0,1 0	3,1 +0,1 0	2,4 - 0,1 0	2,6 - 0,1 0	2,8 - 0,1 0	3 - 0,1 0
$135 \leq d_1 < 140$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	2,3 0 - 0,2	2,3 0 - 0,2	2,3 0 - 0,2	2,3 0 - 0,2	2,7 +0,1 0	2,9 +0,1 0	3,1 +0,1 0	3,3 +0,15 0	2,6 - 0,1 0	2,8 - 0,1 0	3 - 0,1 0	3,2 - 0,1 0
$140 \leq d_1 < 145$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	2,3 0 - 0,2	2,3 0 - 0,2	2,3 0 - 0,2	2,3 0 - 0,2	2,7 +0,1 0	2,9 +0,1 0	3,1 +0,1 0	3,3 +0,15 0	2,6 - 0,1 0	2,8 - 0,1 0	3 - 0,1 0	3,2 - 0,1 0
$145 \leq d_1 < 150$	0,5 $\pm 0,1$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	2,3 0 - 0,2	2,3 0 - 0,2	2,3 0 - 0,2	2,3 0 - 0,2	2,7 +0,1 0	2,9 +0,1 0	3,1 +0,1 0	3,3 +0,15 0	2,6 - 0,1 0	2,8 - 0,1 0	3 - 0,1 0	3,2 - 0,1 0
$150 \leq d_1 < 155$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	1,2 $\pm 0,15$	2,6 0 - 0,2	2,4 0 - 0,2	2,3 0 - 0,2	2,3 0 - 0,2	2,9 +0,1 0	3,1 +0,15 0	3,3 +0,15 0	3,3 +0,15 0	2,8 0 - 0,1	3 0 - 0,1	3,2 0 - 0,1	3,2 0 - 0,1
$155 \leq d_1 < 160$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	1,2 $\pm 0,15$	2,6 0 - 0,2	2,6 0 - 0,2	2,6 0 - 0,2	2,4 0 - 0,2	2,9 +0,1 0	3,1 +0,15 0	3,3 +0,15 0	3,3 +0,15 0	2,8 0 - 0,1	3 0 - 0,1	3,2 0 - 0,1	3,2 0 - 0,1
$160 \leq d_1 < 165$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	1,2 $\pm 0,15$	2,6 0 - 0,2	2,6 0 - 0,2	2,6 0 - 0,2	2,4 0 - 0,2	2,9 +0,1 0	3,1 +0,15 0	3,3 +0,15 0	3,7 +0,15 0	2,8 0 - 0,1	3 0 - 0,1	3,2 0 - 0,1	3,6 0 - 0,1
$165 \leq d_1 < 170$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	1,2 $\pm 0,15$	2,6 0 - 0,2	2,6 0 - 0,2	2,6 0 - 0,2	2,4 0 - 0,2	2,9 +0,1 0	3,1 +0,15 0	3,3 +0,15 0	3,7 +0,15 0	2,8 0 - 0,1	3 0 - 0,1	3,2 0 - 0,1	3,6 0 - 0,1
$170 \leq d_1 < 175$	0,7 $\pm 0,1$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	1,2 $\pm 0,15$	2,6 0 - 0,2	2,6 0 - 0,2	2,6 0 - 0,2	2,4 0 - 0,2	2,9 +0,1 0	3,1 +0,15 0	3,3 +0,15 0	3,7 +0,15 0	2,8 0 - 0,1	3 0 - 0,1	3,2 0 - 0,1	3,6 0 - 0,1
$175 \leq d_1 < 180$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	1,2 $\pm 0,15$	1,5 $\pm 0,15$	2,8 0 - 0,2	2,8 0 - 0,2	2,7 0 - 0,2	2,7 0 - 0,2	3,1 +0,1 0	3,3 +0,15 0	3,7 +0,15 0	4,15 +0,15 0	3 0,1 0	3,2 0,1 0	3,6 0,1 0	4 0,12 0
$180 \leq d_1 < 185$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	1,2 $\pm 0,15$	1,5 $\pm 0,15$	2,8 0 - 0,2	2,8 0 - 0,2	2,7 0 - 0,2	2,7 0 - 0,2	3,1 +0,1 0	3,3 +0,15 0	3,7 +0,15 0	4,15 +0,15 0	3 0,1 0	3,2 0,1 0	3,6 0,1 0	4 0,12 0
$185 \leq d_1 < 190$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	1,2 $\pm 0,15$	1,5 $\pm 0,15$	3 0 - 0,2	2,9 0 - 0,2	2,7 0 - 0,2	2,7 0 - 0,2	3,3 +0,15 0	3,7 +0,15 0	4,15 +0,15 0	4,55 +0,15 0	3,2 0 - 0,1	3,6 0 - 0,1	4 0 - 0,12	4,4 0 - 0,12

Table 19 (continued)

Nominal diameter	Groove depth a_4 for h_1 shown in column				Groove depth and bridge a_{13} for h_1 shown in column				Coil spring groove diameter d_{14} for h_1 shown in column				Coil spring diameter d_7 for h_1 shown in column			
	d_1	1	2	3	4	1	2	3	4	1	2	3	4	1	2	3
$190 \leq d_1 < 195$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	1,2 $\pm 0,15$	1,5 $\pm 0,15$	3 0 - 0,2	2,9 0 - 0,2	2,7 0 - 0,2	2,7 0 - 0,2	3,3 $+0,15$ 0	3,7 $+0,15$ 0	4,15 $+0,15$ 0	4,55 $+0,15$ 0	3,2 0 - 0,1	3,6 0 - 0,1	4 0 - 0,12	4,4 0 - 0,12
$195 \leq d_1 \leq 200$	0,7 $\pm 0,1$	0,9 $\pm 0,1$	1,2 $\pm 0,15$	1,5 $\pm 0,15$	3 0 - 0,2	2,9 0 - 0,2	2,7 0 - 0,2	2,7 0 - 0,2	3,3 $+0,15$ 0	3,7 $+0,15$ 0	4,15 $+0,15$ 0	4,55 $+0,15$ 0	3,2 0 - 0,1	3,7 $+0,15$ 0	4 0 - 0,12	4,4 0 - 0,12

Table 20 — Dimensions of DSF-C oil control rings with special ring width $h_1 = 4,75$ mm (3/16 in)

Dimensions in millimetres

Nominal diameter	Radial thickness over coil spring	Ring width		Closed gap	Radial wall thickness		Land width	Groove depth	Groove depth and bridge	Coil-spring groove diameter	Coil-spring diameter
		h_1	Tolerance		a_1	Tolerance					
d_1	a_{12}	h_1	Tolerance	s_1	a_1	Tolerance	h_5	a_4	a_{13}	d_{14}	d_7
$60 \leq d_1 < 65$	3,7 0 -0,25	4,75	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,2 $+0,2$ 0	2,5	$\pm 0,15$ within a ring 0,15 max.	0,4 $\pm 0,07$	0,5 $\pm 0,1$	1,5 0 -0,15	2,3 $+0,1$ 0	2,2 0 -0,1
$65 \leq d_1 < 70$	3,7 0 -0,25	4,75	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,2 $+0,2$ 0	2,5	$\pm 0,15$ within a ring 0,15 max.	0,4 $\pm 0,07$	0,5 $\pm 0,1$	1,5 0 -0,15	2,3 $+0,1$ 0	2,2 0 -0,1
$70 \leq d_1 < 75$	3,9 0 -0,25	4,75	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,2 $+0,2$ 0	2,6	$\pm 0,15$ within a ring 0,15 max.	0,4 $\pm 0,07$	0,5 $\pm 0,1$	1,5 0 -0,15	2,5 $+0,1$ 0	2,4 0 -0,1
$75 \leq d_1 < 80$	4 0 -0,25	4,75	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,25 $+0,25$ 0	2,7	$\pm 0,15$ within a ring 0,15 max.	0,4 $\pm 0,07$	0,5 $\pm 0,1$	1,6 0 -0,15	2,5 $+0,1$ 0	2,4 0 -0,1
$80 \leq d_1 < 85$	4,1 0 -0,25	4,75	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,25 $+0,25$ 0	2,8	$\pm 0,15$ within a ring 0,15 max.	0,4 $\pm 0,07$	0,5 $\pm 0,1$	1,7 0 -0,15	2,5 $+0,1$ 0	2,4 0 -0,1

Table 20 (continued)

Nominal diameter	Radial thickness over coil spring	Ring width		Closed gap	Radial wall thickness		Land width	Groove depth	Groove depth and bridge	Coil-spring groove diameter	Coil-spring diameter
		h_1	Tolerance		a_1	Tolerance					
$85 \leq d_1 < 90$	a_{12} 4,1 0 -0,25	h_1 4,75	0,010 -0,030 For phosphated PO surface: -0,005 -0,030	s_1 0,25 +0,25 0	a_1 2,9	$\pm 0,15$ within a ring 0,15 max.	h_5 0,4 $\pm 0,07$	a_4 0,5 $\pm 0,1$	a_{13} 1,7 0 -0,15	d_{14} 2,5 +0,1 0	d_7 2,4 0 -0,1
$90 \leq d_1 < 95$	4,2 0 -0,25	4,75	0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,3 +0,25 0	3,0	$\pm 0,15$ within a ring 0,15 max.	0,4 $\pm 0,07$	0,5 $\pm 0,1$	1,8 0 -0,15	2,5 +0,1 0	2,4 0 -0,1
$95 \leq d_1 < 100$	4,2 0 -0,25	4,75	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,3 +0,25 0	3,1	$\pm 0,15$ within a ring 0,15 max.	0,4 $\pm 0,07$	0,7 $\pm 0,1$	1,8 0 -0,15	2,5 +0,1 0	2,4 0 -0,1
$100 \leq d_1 < 105$	4,5 0 -0,25	4,75	0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,3 +0,25 0	3,15	$\pm 0,20$ within a ring 0,20 max.	0,4 $\pm 0,07$	0,7 $\pm 0,1$	1,9 0 -0,2	2,7 +0,1 0	2,6 0 -0,1
$105 \leq d_1 < 110$	4,5 0 -0,25	4,75	0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,3 +0,25 0	3,2	$\pm 0,20$ within a ring 0,20 max.	0,4 $\pm 0,07$	0,7 $\pm 0,1$	1,9 0 -0,2	2,7 +0,1 0	2,6 0 -0,1
$110 \leq d_1 < 115$	4,6 0 -0,25	4,75	0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,35 +0,35 0	3,3	$\pm 0,20$ within a ring 0,20 max.	0,4 $\pm 0,07$	0,7 $\pm 0,1$	2,0 0 -0,2	2,7 +0,1 0	2,6 0 -0,1
$115 \leq d_1 < 120$	4,7 0 -0,25	4,75	0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,35 +0,35 0	3,4	$\pm 0,20$ within a ring 0,20 max.	0,4 $\pm 0,07$	0,7 $\pm 0,1$	2,1 0 -0,2	2,7 +0,1 0	2,6 0 -0,1
$120 \leq d_1 < 125$	4,8 0 -0,25	4,75	0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,35 +0,35 0	3,5	$\pm 0,20$ within a ring 0,20 max.	0,4 $\pm 0,07$	0,7 $\pm 0,1$	2,2 0 -0,2	2,7 +0,1 0	2,6 0 -0,1

ISO 6626-1:2024(en)

Table 20 (continued)

Nominal diameter	Radial thickness over coil spring	Ring width		Closed gap	Radial wall thickness		Land width	Groove depth	Groove depth and bridge	Coil-spring groove diameter	Coil-spring diameter
		h_1	Tolerance		a_1	Tolerance					
d_1	a_{12}	h_1	Tolerance	s_1	a_1	Tolerance	h_5	a_4	a_{13}	d_{14}	d_7
$125 \leq d_1 < 130$	4,9 0 -0,25	4,75	0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,35 +0,35 0	3,6	$\pm 0,20$ within a ring 0,20 max.	0,4 $\pm 0,07$	0,7 $\pm 0,1$	2,3 0 -0,2	2,7 +0,1 0	2,6 0 -0,1
$130 \leq d_1 < 135$	4,9 0 -0,25	4,75	0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,4 +0,35 0	3,6	$\pm 0,20$ within a ring 0,20 max.	0,4 $\pm 0,07$	0,7 $\pm 0,1$	2,3 0 -0,2	2,7 +0,1 0	2,6 0 -0,1
$135 \leq d_1 < 140$	5,1 0 -0,25	4,75	0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,4 +0,35 0	3,7	$\pm 0,20$ within a ring 0,20 max.	0,4 $\pm 0,07$	0,7 $\pm 0,1$	2,5 0 -0,2	2,7 +0,1 0	2,6 0 -0,1
$140 \leq d_1 < 145$	5,1 0 -0,25	4,75	0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,4 +0,35 0	3,8	$\pm 0,20$ within a ring 0,20 max.	0,4 $\pm 0,07$	0,7 $\pm 0,1$	2,5 0 -0,2	2,7 +0,1 0	2,6 0 -0,1
$145 \leq d_1 < 150$	5,1 0 -0,25	4,75	0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,4 +0,35 0	3,9	$\pm 0,20$ within a ring 0,20 max.	0,4 $\pm 0,07$	0,7 $\pm 0,1$	2,5 0 -0,2	2,7 +0,1 0	2,6 0 -0,1
$150 \leq d_1 < 155$	5,4 0 -0,25	4,75	0,010 -0,035 For phosphated PO surface: -0,005 -0,035	0,45 +0,35 0	3,9	$\pm 0,20$ within a ring 0,20 max.	0,4 $\pm 0,07$	0,7 $\pm 0,1$	2,6 0 -0,2	2,9 +0,1 0	2,8 0 -0,1
$155 \leq d_1 < 160$	5,4 0 -0,25	4,75	0,010 -0,035 For phosphated PO surface: -0,005 -0,035	0,45 +0,35 0	3,9	$\pm 0,20$ within a ring 0,20 max.	0,4 $\pm 0,07$	0,7 $\pm 0,1$	2,6 0 -0,2	2,9 +0,1 0	2,8 0 -0,1
$160 \leq d_1 < 165$	5,4 0 -0,25	4,75	0,010 -0,035 For phosphated PO surface: -0,005 -0,035	0,45 +0,35 0	4	$\pm 0,20$ within a ring 0,20 max.	0,4 $\pm 0,07$	0,7 $\pm 0,1$	2,6 0 -0,2	2,9 +0,1 0	2,8 0 -0,1

ISO 6626-1:2024(en)

Table 20 (continued)

Nominal diameter	Radial thickness over coil spring	Ring width		Closed gap	Radial wall thickness		Land width	Groove depth	Groove depth and bridge	Coil-spring groove diameter	Coil-spring diameter
		h_1	Tolerance		a_1	Tolerance					
d_1	a_{12}	h_1	Tolerance	s_1	a_1	Tolerance	h_5	a_4	a_{13}	d_{14}	d_7
$165 \leq d_1 < 170$	5,4 0 -0,25	4,75	0,010 -0,035 For phosphated PO surface: -0,005 -0,035	0,45 +0,35 0	4	$\pm 0,20$ within a ring 0,20 max.	0,4 $\pm 0,07$	0,7 $\pm 0,1$	2,6 0 -0,2	2,9 +0,1 0	2,8 0 -0,1
$170 \leq d_1 < 175$	5,4 0 -0,25	4,75	0,010 -0,035 For phosphated PO surface: -0,005 -0,035	0,45 +0,35 0	4	$\pm 0,20$ within a ring 0,20 max.	0,4 $\pm 0,07$	0,7 $\pm 0,1$	2,6 0 -0,2	2,9 +0,1 0	2,8 0 -0,1
$175 \leq d_1 < 180$	5,8 0 -0,35	4,75	0,010 -0,035 For phosphated PO surface: -0,005 -0,035	0,55 +0,40 0	4,6	$\pm 0,20$ within a ring 0,20 max.	0,4 $\pm 0,07$	0,7 $\pm 0,1$	2,8 0 -0,2	3,1 +0,1 0	3 0 -0,1
$180 \leq d_1 < 185$	5,8 0 -0,35	4,75	0,010 -0,035 For phosphated PO surface: -0,005 -0,035	0,55 +0,40 0	4,6	$\pm 0,20$ within a ring 0,20 max.	0,4 $\pm 0,07$	0,7 $\pm 0,1$	2,8 0 -0,2	3,1 +0,1 0	3 0 -0,1
$185 \leq d_1 < 190$	6,2 0 -0,4	4,75	0,010 -0,035 For phosphated PO surface: -0,005 -0,035	0,55 +0,40 0	4,9	$\pm 0,20$ within a ring 0,20 max.	0,4 $\pm 0,07$	0,7 $\pm 0,1$	3 0 -0,2	3,3 +0,15 0	3,2 0 -0,1
$190 \leq d_1 < 195$	6,2 0 -0,4	4,75	0,010 -0,035 For phosphated PO surface: -0,005 -0,035	0,55 +0,40 0	4,9	$\pm 0,20$ within a ring 0,20 max.	0,4 $\pm 0,07$	0,7 $\pm 0,1$	3 0 -0,2	3,3 +0,15 0	3,2 0 -0,1
$195 \leq d_1 \leq 200$	6,2 0 -0,4	4,75	0,010 -0,035 For phosphated PO surface: -0,005 -0,035	0,55 +0,40 0	4,9	$\pm 0,20$ within a ring 0,20 max.	0,4 $\pm 0,07$	0,7 $\pm 0,1$	3 0 -0,2	3,3 +0,15 0	3,2 0 -0,1

ISO 6626-1:2024(en)

Table 21 — Dimensions of DSF-CNP oil control rings with special ring width $h_1=4,75$ mm (3/16 inch)

Dimensions in millimetres

Nominal diameter	Radial thickness over coil spring	Ring width		Closed gap	Radial wall thickness		Land width	Groove depth	Groove depth and bridge	Coil-spring groove diameter	Coil-spring diameter
		h_1	Tolerance		a_1	Tolerance					
d_1	a_{12}	h_1	Tolerance	s_1	a_1	Tolerance	h_5	a_4	a_{13}	d_{14}	d_7
$60 \leq d_1 < 65$	3,7 0 -0,25	4,75	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,2 +0,2 0	2,5	$\pm 0,15$ within a ring 0,15 max.	0,4 $\pm 0,07$	0,5 $\pm 0,1$	1,5 0 -0,15	2,3 +0,1 0	2,2 0 -0,1
$65 \leq d_1 < 70$	3,7 0 -0,25	4,75	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,2 +0,2 0	2,5	$\pm 0,15$ within a ring 0,15 max.	0,4 $\pm 0,07$	0,5 $\pm 0,1$	1,5 0 -0,15	2,3 +0,1 0	2,2 0 -0,1
$70 \leq d_1 < 75$	3,9 0 -0,25	4,75	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,2 +0,2 0	2,6	$\pm 0,15$ within a ring 0,15 max.	0,4 $\pm 0,07$	0,5 $\pm 0,1$	1,5 0 -0,15	2,5 +0,1 0	2,4 0 -0,1
$75 \leq d_1 < 80$	4 0 -0,25	4,75	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,25 +0,25 0	2,7	$\pm 0,15$ within a ring 0,15 max.	0,4 $\pm 0,07$	0,5 $\pm 0,1$	1,6 0 -0,15	2,5 +0,1 0	2,4 0 -0,1
$80 \leq d_1 < 85$	4,1 0 -0,25	4,75	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,25 +0,25 0	2,8	$\pm 0,15$ within a ring 0,15 max.	0,4 $\pm 0,07$	0,5 $\pm 0,1$	1,7 0 -0,15	2,5 +0,1 0	2,4 0 -0,1
$85 \leq d_1 < 90$	4,1 0 -0,25	4,75	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,25 +0,25 0	2,9	$\pm 0,15$ within a ring 0,15 max.	0,4 $\pm 0,07$	0,5 $\pm 0,1$	1,7 0 -0,15	2,5 +0,1 0	2,4 0 -0,1
$90 \leq d_1 < 95$	4,2 0 -0,25	4,75	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,3 +0,25 0	3,0	$\pm 0,15$ within a ring 0,15 max.	0,4 $\pm 0,07$	0,5 $\pm 0,1$	1,8 0 -0,15	2,5 +0,1 0	2,4 0 -0,1
$95 \leq d_1 < 100$	4,2 0 -0,25	4,75	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,3 +0,25 0	3,1	$\pm 0,15$ within a ring 0,15 max.	0,4 $\pm 0,07$	1,8 0 -0,15	1,8 0 -0,15	2,5 +0,1 0	2,4 0 -0,1

Table 21 (continued)

Nominal diameter	Radial thickness over coil spring	Ring width		Closed gap	Radial wall thickness		Land width	Groove depth	Groove depth and bridge	Coil-spring groove diameter	Coil-spring diameter
d_1	a_{12}	h_1	Tolerance	s_1	a_1	Tolerance	h_5	a_4	a_{13}	d_{14}	d_7
$100 \leq d_1 < 105$	4,5 0 -0,25	4,75	0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,3 +0,25 0	3,15	$\pm 0,20$ within a ring 0,20 max.	0,4 $\pm 0,07$	0,7 $\pm 0,1$	1,9 0 -0,2	2,7 +0,1 0	2,6 0 -0,1
$105 \leq d_1 < 110$	4,5 0 -0,25	4,75	0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,3 +0,25 0	3,2	$\pm 0,20$ within a ring 0,20 max.	0,4 $\pm 0,07$	0,7 $\pm 0,1$	1,9 0 -0,2	2,7 +0,1 0	2,6 0 -0,1
$110 \leq d_1 < 115$	4,6 0 -0,25	4,75	0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,35 +0,35 0	3,3	$\pm 0,20$ within a ring 0,20 max.	0,4 $\pm 0,07$	0,7 $\pm 0,1$	2,0 0 -0,2	2,7 +0,1 0	2,6 0 -0,1
$115 \leq d_1 < 120$	4,7 0 -0,25	4,75	0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,35 +0,35 0	3,4	$\pm 0,20$ within a ring 0,20 max.	0,4 $\pm 0,07$	0,7 $\pm 0,1$	2,1 0 -0,2	2,7 +0,1 0	2,6 0 -0,1
$120 \leq d_1 < 125$	4,8 0 -0,25	4,75	0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,35 +0,35 0	3,5	$\pm 0,20$ within a ring 0,20 max.	0,4 $\pm 0,07$	0,7 $\pm 0,1$	2,2 0 -0,2	2,7 +0,1 0	2,6 0 -0,1
$125 \leq d_1 < 130$	4,9 0 -0,25	4,75	0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,35 +0,35 0	3,6	$\pm 0,20$ within a ring 0,20 max.	0,4 $\pm 0,07$	0,7 $\pm 0,1$	2,3 0 -0,2	2,7 +0,1 0	2,6 0 -0,1
$130 \leq d_1 < 135$	4,9 0 -0,25	4,75	0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,4 +0,35 0	3,6	$\pm 0,20$ within a ring 0,20 max.	0,4 $\pm 0,07$	0,7 $\pm 0,1$	2,3 0 -0,2	2,7 +0,1 0	2,6 0 -0,1

ISO 6626-1:2024(en)

Table 21 (continued)

Nominal diameter	Radial thickness over coil spring	Ring width		Closed gap	Radial wall thickness		Land width	Groove depth	Groove depth and bridge	Coil-spring groove diameter	Coil-spring diameter
d_1	a_{12}	h_1	Tolerance	s_1	a_1	Tolerance	h_5	a_4	a_{13}	d_{14}	d_7
$135 \leq d_1 < 140$	5,1 0 -0,25	4,75	0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,4 +0,35 0	3,7	$\pm 0,20$ within a ring 0,20 max.	0,4 $\pm 0,07$	0,7 $\pm 0,1$	2,5 0 -0,2	2,7 +0,1 0	2,6 0 -0,1
$140 \leq d_1 < 145$	5,1 0 -0,25	4,75	0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,4 +0,35 0	3,8	$\pm 0,20$ within a ring 0,20 max.	0,4 $\pm 0,07$	0,7 $\pm 0,1$	2,5 0 -0,2	2,7 +0,1 0	2,6 0 -0,1
$145 \leq d_1 < 150$	5,1 0 -0,25	4,75	0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,4 +0,35 0	3,9	$\pm 0,20$ within a ring 0,20 max.	0,4 $\pm 0,07$	0,7 $\pm 0,1$	2,5 0 -0,2	2,7 +0,1 0	2,6 0 -0,1
$150 \leq d_1 < 155$	5,4 0 -0,25	4,75	0,010 -0,035 For phosphated PO surface: -0,005 -0,035	0,45 +0,35 0	3,9	$\pm 0,20$ within a ring 0,20 max.	0,4 $\pm 0,07$	0,7 $\pm 0,1$	2,6 0 -0,2	2,9 +0,1 0	2,8 0 -0,1
$155 \leq d_1 < 160$	5,4 0 -0,25	4,75	0,010 -0,035 For phosphated PO surface: -0,005 -0,035	0,45 +0,35 0	3,9	$\pm 0,20$ within a ring 0,20 max.	0,4 $\pm 0,07$	0,7 $\pm 0,1$	2,6 0 -0,2	2,9 +0,1 0	2,8 0 -0,1
$160 \leq d_1 < 165$	5,4 0 -0,25	4,75	0,010 -0,035 For phosphated PO surface: -0,005 -0,035	0,45 +0,35 0	4	$\pm 0,20$ within a ring 0,20 max.	0,4 $\pm 0,07$	0,7 $\pm 0,1$	2,6 0 -0,2	2,9 +0,1 0	2,8 0 -0,1
$165 \leq d_1 < 170$	5,4 0 -0,25	4,75	0,010 -0,035 For phosphated PO surface: -0,005 -0,035	0,45 +0,35 0	4	$\pm 0,20$ within a ring 0,20 max.	0,4 $\pm 0,07$	0,7 $\pm 0,1$	2,6 0 -0,2	2,9 +0,1 0	2,8 0 -0,1

ISO 6626-1:2024(en)

Table 21 (continued)

Nominal diameter	Radial thickness over coil spring	Ring width		Closed gap	Radial wall thickness		Land width	Groove depth	Groove depth and bridge	Coil-spring groove diameter	Coil-spring diameter
		h_1	Tolerance		s_1	a_1					
d_1	a_{12}	h_1	Tolerance	s_1	a_1	Tolerance	h_5	a_4	a_{13}	d_{14}	d_7
170 d_1 <175	5,4 0 -0,25	4,75	0,010 -0,035 For phosphated PO surface: -0,005 -0,035	0,45 +0,35 0	4	$\pm 0,20$ within a ring 0,20 max.	0,4 $\pm 0,07$	0,7 $\pm 0,1$	2,6 0 -0,2	2,9 +0,1 0	2,8 0 -0,1
175 $\leq d_1$ <180	5,8 0 -0,35	4,75	0,010 -0,035 For phosphated PO surface: -0,005 -0,035	0,55 +0,40 0	4,6	$\pm 0,20$ within a ring 0,20 max.	0,4 $\pm 0,07$	0,7 $\pm 0,1$	2,8 0 -0,2	3,1 +0,1 0	3 0 -0,1
180 $\leq d_1$ <185	5,8 0 -0,35	4,75	0,010 -0,035 For phosphated PO surface: -0,005 -0,035	0,55 +0,40 0	4,6	$\pm 0,20$ within a ring 0,20 max.	0,4 $\pm 0,07$	0,7 $\pm 0,1$	2,8 0 -0,2	3,1 +0,1 0	3 0 -0,1
185 $\leq d_1$ <190	6,2 0 -0,4	4,75	0,010 -0,035 For phosphated PO surface: -0,005 -0,035	0,55 +0,40 0	4,9	$\pm 0,20$ within a ring 0,20 max.	0,4 $\pm 0,07$	0,7 $\pm 0,1$	3 0 -0,2	3,3 +0,15 0	3,2 0 -0,1
190 $\leq d_1$ <195	6,2 0 -0,4	4,75	0,010 -0,035 For phosphated PO surface: -0,005 -0,035	0,55 +0,40 0	4,9	$\pm 0,20$ within a ring 0,20 max.	0,4 $\pm 0,07$	0,7 $\pm 0,1$	3 0 -0,2	3,3 +0,15 0	3,2 0 -0,1
195 $\leq d_1 \leq$ 200	6,2 0 -0,4	4,75	0,010 -0,035 For phosphated PO surface: -0,005 -0,035	0,55 +0,40 0	4,9	$\pm 0,20$ within a ring 0,20 max.	0,4 $\pm 0,07$	0,7 $\pm 0,1$	3 0 -0,2	3,3 +0,15 0	3,2 0 -0,1

ISO 6626-1:2024(en)

Table 22 — Dimensions of SSF oil control rings with special ring width $h_1=4,75$ mm (3/16 inch)

Dimensions in millimetres

Nominal diameter	Radial thickness over coil spring	Ring width		Closed gap	Radial wall thickness		Land width	Groove depth	Groove depth and bridge	Coil-spring groove diameter	Coil-spring diameter
		h_1	Tolerance		a_1	Tolerance					
d_1	a_{12}	h_1	Tolerance	s_1	a_1	Tolerance	h_5	a_4	a_{13}	d_{14}	d_7
$60 \leq d_1 < 65$	3,7 0 -0,25	4,75	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,2 +0,2 0	2,5	$\pm 0,15$ within a ring 0,15 max.	0,8 $\pm 0,1$	0,5 $\pm 0,1$	1,5 0 -0,15	2,3 +0,1 0	2,2 0 -0,1
$65 \leq d_1 < 70$	3,7 0 -0,25	4,75	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,2 +0,2 0	2,5	$\pm 0,15$ within a ring 0,15 max.	0,8 $\pm 0,1$	0,5 $\pm 0,1$	1,5 0 -0,15	2,3 +0,1 0	2,2 0 -0,1
$70 \leq d_1 < 75$	3,9 0 -0,25	4,75	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,2 +0,2 0	2,6	$\pm 0,15$ within a ring 0,15 max.	0,8 $\pm 0,1$	0,5 $\pm 0,1$	1,5 0 -0,15	2,5 +0,1 0	2,4 0 -0,1
$75 \leq d_1 < 80$	4 0 -0,25	4,75	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,25 +0,25 0	2,7	$\pm 0,15$ within a ring 0,15 max.	0,8 $\pm 0,1$	0,5 $\pm 0,1$	1,6 0 -0,15	2,5 +0,1 0	2,4 0 -0,1
$80 \leq d_1 < 85$	4,1 0 -0,25	4,75	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,25 +0,25 0	2,8	$\pm 0,15$ within a ring 0,15 max.	0,8 $\pm 0,1$	0,5 $\pm 0,1$	1,7 0 -0,15	2,5 +0,1 0	2,4 0 -0,1
$85 \leq d_1 < 90$	4,1 0 -0,25	4,75	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,25 +0,25 0	2,9	$\pm 0,15$ within a ring 0,15 max.	0,8 $\pm 0,1$	0,5 $\pm 0,1$	1,7 0 -0,15	2,5 +0,1 0	2,4 0 -0,1
$90 \leq d_1 < 95$	4,2 0 -0,25	4,75	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,3 +0,25 0	3,0	$\pm 0,15$ within a ring 0,15 max.	0,8 $\pm 0,1$	0,5 $\pm 0,1$	1,8 0 -0,15	2,5 +0,1 0	2,4 0 -0,1

ISO 6626-1:2024(en)

Table 22 (continued)

Nominal diameter	Radial thickness over coil spring	Ring width		Closed gap	Radial wall thickness		Land width	Groove depth	Groove depth and bridge	Coil-spring groove diameter	Coil-spring diameter
		h_1	Tolerance		a_1	Tolerance					
$95 \leq d_1 < 100$	4,2 0 -0,25	4,75	-0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,3 +0,25 0	3,1	$\pm 0,15$ within a ring 0,15 max.	0,8 $\pm 0,1$	0,7 $\pm 0,1$	1,8 0 -0,15	2,5 +0,1 0	2,4 0 -0,1
$100 \leq d_1 < 105$	4,5 0 -0,25	4,75	0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,3 +0,25 0	3,15	$\pm 0,20$ Within a ring 0,20 max.	0,8 $\pm 0,1$	0,7 $\pm 0,1$	1,9 0 -0,2	2,7 +0,1 0	2,6 0 -0,1
$105 \leq d_1 < 110$	4,5 0 -0,25	4,75	0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,3 +0,25 0	3,2	$\pm 0,20$ Within a ring 0,20 max.	0,8 $\pm 0,1$	0,7 $\pm 0,1$	1,9 0 -0,2	2,7 +0,1 0	2,6 0 -0,1
$110 \leq d_1 < 115$	4,6 0 -0,25	4,75	0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,35 +0,35 0	3,3	$\pm 0,20$ Within a ring 0,20 max.	0,8 $\pm 0,1$	0,7 $\pm 0,1$	2,0 0 -0,2	2,7 +0,1 0	2,6 0 -0,1
$115 \leq d_1 < 120$	4,7 0 -0,25	4,75	0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,35 +0,35 0	3,4	$\pm 0,20$ Within a ring 0,20 max.	0,8 $\pm 0,1$	0,7 $\pm 0,1$	2,1 0 -0,2	2,7 +0,1 0	2,6 0 -0,1
$120 \leq d_1 < 125$	4,8 0 -0,25	4,75	0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,35 +0,35 0	3,5	$\pm 0,20$ Within a ring 0,20 max.	0,8 $\pm 0,1$	0,7 $\pm 0,1$	2,2 0 -0,2	2,7 +0,1 0	2,6 0 -0,1
$125 \leq d_1 < 130$	4,9 0 -0,25	4,75	0,010 -0,030 For phosphated PO surface: -0,005 -0,030	2,7 +0,1 0	3,6	$\pm 0,20$ Within a ring 0,20 max.	0,8 $\pm 0,1$	0,7 $\pm 0,1$	2,3 0 -0,2	2,7 +0,1 0	2,6 0 -0,1
$130 \leq d_1 < 135$	4,9 0 -0,25	4,75	0,010 -0,030 For phosphated PO surface: -0,005 -0,030	0,4 +0,35 0	3,6	$\pm 0,20$ within a ring 0,20 max.	0,8 $\pm 0,1$	0,7 $\pm 0,1$	2,3 0 -0,2	2,7 +0,1 0	2,6 0 -0,1