

---

# International Standard



# 6676

---

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

---

## Acid-grade fluorspar — Determination of total phosphorus content — Molybdophosphate photometric method

*Spaths fluor pour la fabrication de l'acide fluorhydrique — Dosage du phosphore total — Méthode photométrique au molybdophosphate*

First edition — 1981-11-01

STANDARDSISO.COM : Click to view the full PDF of ISO 6676:1981

---

UDC 553.634 : 543.42 : 546.18

Ref. No. ISO 6676-1981 (E)

Descriptors : fluorspar, chemical analysis, determination of content, phosphorus, spectrophotometric analysis.

Price based on 4 pages

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards institutes (ISO member bodies). The work of developing International Standards is carried out through ISO technical committees. Every member body interested in a subject for which a technical committee has been set up has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work.

Draft International Standards adopted by the technical committees are circulated to the member bodies for approval before their acceptance as International Standards by the ISO Council.

International Standard ISO 6676 was developed by Technical Committee ISO/TC 47, *Chemistry*, and was circulated to the member bodies in November 1979.

It has been approved by the member bodies of the following countries :

Australia	Germany, F.R.	Sweden
Austria	Hungary	Switzerland
Belgium	Italy	Thailand
Bulgaria	Korea, Rep. of	United Kingdom
China	Poland	USSR
Czechoslovakia	Portugal	Yugoslavia
Egypt, Arab Rep. of	Romania	
France	South Africa, Rep. of	

The member body of the following country expressed disapproval of the document on technical grounds :

India

# Acid-grade fluorspar — Determination of total phosphorus content — Molybdophosphate photometric method

**WARNING** — Attention is drawn to the dangers involved in the use of chloroform and hydrofluoric acid (see the notes to 4.1 and 4.5).

## 1 Scope and field of application

This International Standard specifies a molybdophosphate photometric method for the determination of the total phosphorus content of acid-grade fluorspar.

The method is applicable to products having total phosphorus contents, expressed as  $\text{PO}_4^{3-}$ , in the range 0,02 to 1,0 % (*m/m*).

## 2 Reference

ISO 565, *Test sieves — Woven metal wire cloth and perforated plate — Nominal sizes of apertures.*

ISO 4282, *Acid-grade fluorspar — Determination of loss in mass at 105 °C.*

## 3 Principle

Removal of silica from a test portion by treating first with hydrofluoric acid solution and then with sulphuric acid solution. Dissolution of the residue and preparation of the test solution. Formation of the yellow molybdophosphate complex and photometric measurement of the absorbance of this complex, after extraction with a mixture of butan-1-ol and chloroform, at a wavelength of about 330 nm.

## 4 Reagents

During the analysis, use only reagents of recognized analytical grade and only distilled water or water of equivalent purity.

### 4.1 Butan-1-ol/chloroform, solvent mixture.

Mix equal volumes of the two reagents.

**NOTE** — Harmful by inhalation. Avoid contact with skin and eyes.

**4.2 Nitric acid**,  $\rho$  approximately 1,40 g/ml, about 68 % (*m/m*) solution.

**4.3 Nitric acid**, approximately 315 g/l solution.

**4.4 Sulphuric acid**,  $\rho$  approximately 1,84 g/ml, about 96 % (*m/m*) solution.

**4.5 Hydrofluoric acid**,  $\rho$  approximately 1,14 g/ml, about 40 % (*m/m*) solution.

**NOTE** — Very toxic by inhalation, in contact with skin and if swallowed. Causes severe burns.

Keep container tightly closed in a well-ventilated place. In case of contact with eyes, rinse immediately with plenty of water and seek medical advice.

Wear suitable protective clothing and gloves. In case of accident or feeling unwell, seek medical advice immediately (show the label where possible).

**4.6 Sodium molybdate dihydrate** ( $\text{Na}_2\text{MoO}_4 \cdot 2\text{H}_2\text{O}$ ), approximately 30 g/l solution.

**4.7 Phosphorus**, standard solution corresponding to 0,100 g of  $\text{PO}_4^{3-}$  per litre.

Dry a little potassium dihydrogenorthophosphate ( $\text{KH}_2\text{PO}_4$ ) by heating in the oven (5.1), controlled at  $105 \pm 2$  °C, for 2 h. Allow to cool in a desiccator. Weigh, to the nearest 0,000 2 g, 0,143 3 g of the dried material, and transfer it quantitatively to a 1 000 ml one-mark volumetric flask. Dissolve in water, dilute to the mark and mix.

1 ml of this standard solution contains 100  $\mu\text{g}$  of  $\text{PO}_4^{3-}$ .

**4.8 Phosphorus**, standard solution corresponding to 0,010 g of  $\text{PO}_4^{3-}$  per litre.

Transfer 100,0 ml of the standard phosphorus solution (4.7) to a 1 000 ml one-mark volumetric flask, dilute to the mark and mix.

1 ml of this standard solution contains 10  $\mu\text{g}$  of  $\text{PO}_4^{3-}$ .

## 5 Apparatus

Ordinary laboratory apparatus and

**5.1 Electric oven**, capable of being controlled at  $105 \pm 2$  °C.

**5.2 Platinum dish**, of diameter approximately 90 mm.

**5.3 Spectrophotometer, or**

**5.4 Photometer**, fitted with filters providing maximum transmission at a wavelength of about 330 nm.

**5.5 Optical cells**, made of silica, and of optical path length 1 cm and 4 or 5 cm.

**6 Test sample**

Use as the test sample the residue obtained in the determination of the loss in mass at 105 °C (see ISO 4282).

**7 Procedure**

**7.1 Test portion**

Grind several grams of the test sample (see clause 6) in an agate mortar until it passes a sieve of aperture size 63 µm (see ISO 565). Dry the ground material for 2 h in the oven (5.1), controlled at 105 ± 2 °C, allow to cool in a desiccator and weigh, to the nearest 0,000 2 g, about 0,1 g into the platinum dish (5.2).

**7.2 Blank test**

Carry out a blank test simultaneously with the determination, following the same procedure and using the same quantities of all reagents as used for the determination, but omitting the test portion.

**7.3 Preparation of calibration graphs**

Prepare as follows calibration graphs for the following ranges of phosphorus content, expressed as PO<sub>4</sub><sup>3-</sup>:

- 0,02 to 0,2 % (m/m) (calibration graph A);
- 0,2 to 1,0 % (m/m) (calibration graph B);

**7.3.1 Preparation of standard colorimetric solutions**

Into each of a series of 500 ml one-mark volumetric flasks, place the volumes of the appropriate standard phosphorus solution (4.7 or 4.8) shown in the following table:

For calibration graph A		For calibration graph B	
Standard phosphorus solution (4.8)	Corresponding mass of PO <sub>4</sub> <sup>3-</sup>	Standard phosphorus solution (4.7)	Corresponding mass of PO <sub>4</sub> <sup>3-</sup>
ml	µg	ml	µg
0*	0	0*	0
2,0	20,0	2,0	200,0
5,0	50,0	4,0	400,0
10,0	100,0	6,0	600,0
15,0	150,0	8,0	800,0
20,0	200,0	10,0	1 000,0

\* Blank test on the reagents for calibration.

Treat each of these solutions as follows.

Dilute to approximately 200 ml with water, add 50 ml of the nitric acid solution (4.3), 50 ml of the sodium molybdate solution (4.6), dilute to the mark with water and mix. Transfer a 100,0 ml aliquot portion to a 200 ml separating funnel, add 20 ml of the solvent mixture (4.1) and shake for about 1 min. Allow the layers to separate and filter the lower layer through a filter paper into a 50 ml one-mark volumetric flask. Repeat the extraction and filtration with a further 20 ml portion of the solvent mixture and finally wash the filter paper with a few millilitres of the solvent mixture, collecting the filtrate in the same flask. Dilute to the mark with the solvent mixture and mix.

**7.3.2 Photometric measurements**

Carry out the measurements using either the spectrophotometer (5.3), at a wavelength of about 330 nm, or with the photometer (5.4) fitted with suitable filters, after having, in each case, adjusted the apparatus to zero absorbance against the solvent mixture (4.1). Use the 4 or 5 cm cells for preparing calibration graph A and the 1 cm cells for preparing calibration graph B.

Deduct the absorbance of the blank test on the reagents for calibration from those of the standard colorimetric solutions (7.3.1).

**7.3.3 Plotting the graphs**

Plot a graph for each range of phosphorus content, having, for example, the masses, expressed in micrograms, of PO<sub>4</sub><sup>3-</sup> contained in 500 ml of the standard colorimetric solutions (7.3.1) as abscissae, and the corresponding nett values of absorbance as ordinates.

**7.4 Determination**

**7.4.1 Preparation of the test solution**

Treat the test portion (7.1) in the platinum dish (5.2) as follows.

Add 10 ml of the hydrofluoric acid solution (4.5), carefully evaporate to dryness on a hot plate in a well-ventilated fume cupboard, and allow to cool. Repeat this operation with a further 10 ml portion of the hydrofluoric acid solution. Add 10 ml of the sulphuric acid solution (4.4) and evaporate until the contents of the dish (5.2) are just moist. Allow to cool.