
International Standard



6722/3

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

**Road vehicles — Unscreened low-tension cables —
Part 3 : Conductor sizes and dimensions**

Véhicules routiers — Câbles basse tension non blindés — Partie 3 : Sections et dimensions des conducteurs

First edition — 1984-12-15

STANDARDSISO.COM : Click to view the full PDF on ISO 6722-3:1984

UDC 621.315.21 : 629.11

Ref. No. ISO 6722/3-1984 (E)

Descriptors : road vehicles, low voltage switchgear, electric cables, dimensions.

Price based on 2 pages

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work.

Draft International Standards adopted by the technical committees are circulated to the member bodies for approval before their acceptance as International Standards by the ISO Council. They are approved in accordance with ISO procedures requiring at least 75 % approval by the member bodies voting.

International Standard ISO 6722/3 was prepared by Technical Committee ISO/TC 22, *Road vehicles*.

STANDARDSISO.COM : Click to view the full PDF of ISO 6722-3:1984

Road vehicles — Unscreened low-tension cables — Part 3: Conductor sizes and dimensions

0 Introduction

ISO 6722 consists of three parts:

- Part 1: General requirements and test methods.
- Part 2: Cable classes, applicable tests and special requirements.
- Part 3: Conductor sizes and dimensions.

1 Scope and field of application

This part of ISO 6722 specifies conductor sizes and lays down the dimensions of unscreened low-tension cables used in road vehicle applications.

2 References

ISO 6722/1, *Road vehicles — Unscreened low-tension cables — Part 1: General requirements and test methods.*

ISO 6722/2, *Road vehicles — Unscreened low-tension cables — Part 2: Cable classes, applicable tests and special requirements.*

3 Cable colour identification

The preferred colours for road vehicle cable insulations are: black, white, blue, orange, brown, green, violet, red, yellow, and grey.

4 Dimensional requirements

The insulated cables covered by this part of ISO 6722 shall conform to the nominal area and maximum resistance values shown in table 1. Other values are given as a guide for constructions where there are no special requirements.

Refer to the annex for current cable sizes that differ from table 1.

Table 1

Nominal conductor area	Approximate number of wires ²⁾	Maximum diameter of single wires ²⁾	Maximum diameter of conductor	Maximum resistance of conductor at 20 °C (mΩ/m)		Nominal insulation thickness ³⁾	Maximum overall cable diameter ³⁾
				Plain copper	Tinned copper		
mm ²		mm	mm			mm	mm
0,05 ¹⁾	7	0,11	0,4	349	356	0,3	1
0,22 ¹⁾	7	0,21	0,7	84,8	86,5	0,3	1,3
0,38 ¹⁾	12	0,21	0,9	54,4	55,5	0,3	1,5
0,5	16	0,21	1,1	37,1	38,2	0,6	2,3
0,75	24	0,21	1,3	24,7	25,4	0,6	2,5
1	32	0,21	1,5	18,5	19,1	0,6	2,7
1,5	30	0,26	1,8	12,7	13,0	0,6	3
2,5	50	0,26	2,2	7,60	7,82	0,7	3,6
4	56	0,31	2,8	4,71	4,85	0,8	4,4
6	84	0,31	3,4	3,14	3,23	0,8	5
10	80	0,41	4,5	1,82	1,85	1,0	6,5
16	126	0,41	6,3	1,16	1,18	1,0	8,3
25	196	0,41	7,8	0,743	0,757	1,3	10,4
35	276	0,41	9,0	0,527	0,538	1,3	11,6
50	396	0,41	10,5	0,368	0,375	1,5	13,5
70	360	0,51	12,5	0,259	0,264	1,5	15,5
95	475	0,51	14,8	0,196	0,200	1,6	18,0
120	608	0,51	16,5	0,153	0,156	1,6	19,7

1) Sizes 0,05, 0,22, and 0,38 mm² are for special applications only.

2) Other conductor constructions are acceptable providing they meet the nominal conductor area and the conductor resistance requirements.

3) For special applications for classes A, B, and C, and certain materials for class C (see ISO 6722/2 for the classes), the nominal insulation thickness and maximum overall cable diameter may be increased as agreed with the user.