



Unplasticized polyvinyl chloride (PVC) fittings with plain sockets for pipes under pressure — Dimensions of sockets — Metric series

Raccords en polychlorure de vinyle (PVC) non plastifié à emboîtements lisses pour tubes sous pression — Dimensions des emboîtements — Série métrique

Second edition — 1975-12-15

STANDARDSISO.COM : Click to view the full PDF of ISO 727:1975

UDC 621.643.4.06 : 678.743.22

Ref. No. ISO 727-1975 (E)

Descriptors : plastic pipes, unplasticized polyvinyl chloride, pressure pipes, pipe fittings, sockets, dimensions

FOREWORD

ISO (the International Organization for Standardization) is a worldwide federation of national standards institutes (ISO Member Bodies). The work of developing International Standards is carried out through ISO Technical Committees. Every Member Body interested in a subject for which a Technical Committee has been set up has the right to be represented on that Committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work.

Draft International Standards adopted by the Technical Committees are circulated to the Member Bodies for approval before their acceptance as International Standards by the ISO Council.

International Standard ISO 727 was drawn up by Technical Committee ISO/TC 138, *Plastics pipes, fittings and valves for the transport of fluids*, and circulated to the Member Bodies in September 1974.

It has been approved by the Member Bodies of the following countries :

Austria	India	Romania
Belgium	Ireland	South Africa, Rep. of
Chile	Israel	Spain
Czechoslovakia	Italy	Sweden
Denmark	Netherlands	Switzerland
Finland	Norway	United Kingdom
France	Poland	U.S.A.
Germany	Portugal	

No Member Body expressed disapproval of the document.

This second edition cancels and replaces the first edition (i.e. ISO 727-1973).

First edition published 1973-09-15
Second edition published 1975-12-15
Corrected and reprinted 1976-01-15

© International Organization for Standardization, 1975 •

Printed in Switzerland

Unplasticized polyvinyl chloride (PVC) fittings with plain sockets for pipes under pressure – Dimensions of sockets – Metric series

1 SCOPE AND FIELD OF APPLICATION

This International Standard specifies the dimensions of plain sockets in unplasticized polyvinyl chloride (PVC) fittings intended for connecting by solvent welding to unplasticized PVC pipe for use under pressure. The resulting joint does not require mechanical anchorage.

The basic dimensions of these fittings are given in ISO 264.

2 REFERENCES

ISO 161/1, *Thermoplastics pipes for the transport of fluids – Outside diameters and nominal pressures – Part 1: Metric series.*

ISO 264, *Unplasticized polyvinyl chloride (PVC) fittings with plain sockets for pipes under pressure – Dimensions of laying lengths – Metric series.*¹⁾

3 SOCKET LENGTH (MINIMUM)




FIGURE – Socket dimensions

The socket length L (see the figure) is given by the expression

$$L = 0,5 d_e + 6 \text{ mm, with a minimum of 12 mm,}$$

where d_e is the outside diameter of the pipe, in accordance with ISO 161/1.

This socket length is applicable for socket fittings for pipes of any diameter under pressure.

4 INSIDE DIAMETER OF SOCKET

The mean inside diameter of a socket shall comply with the requirements of the table.

TABLE – Tolerances on mean inside diameter of socket
Dimensions in millimetres

Outside diameter of pipe Inside diameter of fitting d_e	Tolerances on mean inside diameter of socket	
	Type A for joint with interference	Type B for joint with clearance
10 12 16 20 25	0 -0,15	
32 40 50	0 -0,2	+0,3 +0,1
63 75	0 -0,25	
90		
110 125	0 -0,3	+0,4 +0,1
140 160	0 -0,4	+0,5 +0,2

The mean inside diameter of the socketed portion of the fitting is defined as being the arithmetical mean of two diameters measured perpendicular to each other at the midpoint of the socket depth. The maximum included angle of the socketed portion of the fittings shall not exceed $0^\circ 30'$.

5 OUT-OF-ROUNDNESS TOLERANCES OF SOCKET INSIDE DIAMETER

Maximum out-of-roundness tolerances (maximum diameter – minimum diameter) shall be

- equal to $0,007 d_e$, or
- equal to 0,2 mm if $0,007 d_e < 0,2$ mm.

1) At present at the stage of draft. (Revision of ISO/R 264.)