

# INTERNATIONAL STANDARD

**ISO**  
**7530-6**

First edition  
1990-12-15

---

---

## **Nickel alloys — Flame atomic absorption spectrometric analysis —**

### **Part 6:**

Determination of manganese content

*Alliages de nickel — Analyse par spectrométrie d'absorption atomique  
dans la flamme —*

*Partie 6: Dosage du manganèse*



Reference number  
ISO 7530-6:1990(E)

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 7530-6 was prepared by Technical Committee ISO/TC 155, *Nickel and nickel alloys*.

ISO 7530 consists of the following parts, under the general title *Nickel alloys — Flame atomic absorption spectrometric analysis*:

- Part 1: *General requirements and sample dissolution*
- Part 2: *Determination of cobalt content*
- Part 3: *Determination of chromium content*
- Part 4: *Determination of copper content*
- Part 5: *Determination of iron content*
- Part 6: *Determination of manganese content*
- Part 7: *Determination of aluminium content*
- Part 8: *Determination of silicon content*
- Part 9: *Determination of vanadium content*

© ISO 1990

All rights reserved. No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization  
Case Postale 56 • CH-1211 Genève 20 • Switzerland

Printed in Switzerland

# Nickel alloys — Flame atomic absorption spectrometric analysis —

## Part 6: Determination of manganese content

### 1 Scope

This part of ISO 7530 specifies a flame atomic absorption spectrometric method for the determination of manganese in the range of 0,01 % (*m/m*) to 4 % (*m/m*) in nickel alloys. Typical compositions of some nickel alloys are given in ISO 7530-1, annex B.

The general requirements concerning the apparatus, sampling, dissolution of the test sample, atomic absorption measurements, calculations and test report are given in ISO 7530-1.

### 2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this part of ISO 7530. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this part of ISO 7530 are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 5725:1986, *Precision of test methods — Determination of repeatability and reproducibility for a standard test method by inter-laboratory tests*.

ISO 7530-1:—<sup>1)</sup>, *Nickel alloys — Flame atomic absorption spectrometric analysis — Part 1: General requirements and sample dissolution*.

1) To be published.

### 3 Principle

Dissolution of a test portion in acid and aspiration of the test solution into an air-acetylene flame of an atomic absorption spectrometer.

Measurement of the absorbance of the resonance line energy from the spectrum of manganese and comparison with that of calibration solutions at a wavelength of 279,5 nm.

### 4 Reagents

In addition to the reagents listed in ISO 7530-1, the following special reagents are required.

#### 4.1 Strontium chloride, solution.

Transfer 113,5 g of strontium chloride hexahydrate ( $\text{SrCl}_2 \cdot 6\text{H}_2\text{O}$ ) to a 600 ml beaker, dissolve in 400 ml of hot water (50 °C to 60 °C), cool and transfer to a 1 000 ml one-mark volumetric flask. Make up to the mark with water and mix. The strontium chloride should be free of heavy metals.

#### 4.2 Manganese, standard reference solution (1,000 g/l).

Weigh, to the nearest 0,001 g, 1,000 g of manganese metal of 99,9 % (*m/m*) minimum purity and transfer to a 400 ml beaker. Add 30 ml of hydrochloric acid ( $\rho_{20} = 1,18 \text{ g/ml}$ ) diluted 1 + 1 and 2 ml of nitric acid ( $\rho_{20} = 1,41 \text{ g/ml}$ ). Heat to initiate the reaction and complete dissolution. Add 0,5 ml of hydrogen peroxide (4.4). Cool, transfer to a 1 000 ml one-mark volumetric flask and add 50 ml of hydrochloric acid

( $\rho_{20} = 1,18$  g/ml). Make up to the mark with water, mix and store in a polyethylene bottle.

#### 4.3 Manganese, standard solution (50 mg/l).

Pipette 50 ml of manganese standard reference solution (4.2) into a 1 000 ml one-mark volumetric flask and add 50 ml of hydrochloric acid ( $\rho_{20} = 1,18$  g/ml). Make up to the mark with water, mix and store in a polyethylene bottle.

#### 4.4 Hydrogen peroxide, 300 g/l ( $\rho_{20} = 1,1$ g/ml).

### 5 Apparatus

The apparatus required is specified in clause 5 of ISO 7530-1.

### 6 Sampling and sample preparation

Refer to clause 6 of ISO 7530-1.

### 7 Procedure

#### 7.1 Preparation of test solution

Proceed as directed in 7.1.1 to 7.1.4 of ISO 7530-1. Add 0,25 ml of hydrogen peroxide (4.4) in the final dissolution of the salts.

##### 7.1.1 Primary dilutions

###### 7.1.1.1 Initial dilution for 0,01 % (m/m) to 0,10 % (m/m) manganese

Transfer the test solution (7.1) to a 100 ml one-mark volumetric flask. Add 4 ml of strontium chloride solution (4.1). Make up to the mark with water and mix. Remove any products of hydrolysis by settlement and dry filtration or by centrifuging.

###### 7.1.1.2 Initial dilution for 0,1 % (m/m) to 4,0 % (m/m) manganese

Transfer the test solution (7.1) to a 500 ml one-mark volumetric flask. Add 20 ml of hydrochloric acid ( $\rho_{20} = 1,18$  g/ml). Make up to the mark with water and mix. Remove any products of hydrolysis by settlement and dry filtration or by centrifuging.

##### 7.1.2 Secondary dilutions

###### 7.1.2.1 Secondary dilution for 0,1 % (m/m) to 0,8 % (m/m) manganese

Pipette 50 ml of the solution from 7.1.1.2 into a 100 ml one-mark volumetric flask. Add 4 ml of strontium chloride solution (4.1) and 3 ml of hydrochloric acid ( $\rho_{20} = 1,18$  g/ml). Make up to the mark with water and mix.

###### 7.1.2.2 Secondary dilution for 0,4 % (m/m) to 4 % (m/m) manganese

Pipette 10 ml of the solution from 7.1.1.2 into a 100 ml one-mark volumetric flask. Add 4 ml of strontium chloride solution (4.1) and 5 ml of hydrochloric acid ( $\rho_{20} = 1,18$  g/ml). Make up to the mark with water and mix.

#### 7.2 Reagent blank solution

Carry out a blank test in parallel with the determination, following the same procedure and using the same quantities of all the reagents.

#### 7.3 Manganese calibration solutions

Using pipettes, transfer to each of five 100 ml one-mark volumetric flasks, 0 ml, 5 ml, 10 ml, 15 ml and 20 ml of manganese standard solution (4.3). Add 4 ml of strontium chloride solution (4.1) and 5 ml of hydrochloric acid ( $\rho_{20} = 1,18$  g/ml). Make up to the mark with water and mix.

#### 7.4 Calibration and determination

##### 7.4.1 Atomic absorption measurements

Proceed as directed in 7.4.1 of ISO 7530-1, using a wavelength of 279,5 nm and an air-acetylene flame.

##### 7.4.2 Preparation of calibration graphs

Proceed as directed in 7.4.2 of ISO 7530-1.

#### 7.5 Number of determinations

Carry out the determination at least in duplicate.

### 8 Expression of results

#### 8.1 Calculation

Proceed as directed in 8.1 of ISO 7530-1.

#### 8.2 Precision

##### 8.2.1 Laboratory tests

Eleven laboratories in six countries participated in the testing of this procedure using six samples of nominal composition given in table 1.

##### 8.2.2 Statistical analysis

8.2.2.1 Results were treated according to ISO 5725 as described in 8.2.2 of ISO 7530-1. The results of this analysis are given in table 2.

8.2.2.2 Three laboratories were rejected as Cochran outliers; two for sample 902 and one for samples 3927 and 7049. Also two laboratories were rejected as Dixon stragglers for sample 7049.

## 9 Test report

Refer to clause 9 of ISO 7530-1.

**Table 1 — Nominal composition of test samples [% (m/m)]**

Sample	Al	Co	Cr	Cu	Fe	Mn	Ni	Si	Ti
825	0,2	0,07	21	1,6	30	0,7	Remainder	0,4	1,1
902	0,4	0,05	5	0,04	48	0,4	Remainder	0,35	2,5
3920	0,15	2	19	0,1	3	0,3	Remainder	0,6	2,3
3927	0,1	1	20	0,05	44	0,4	Remainder	0,8	0,6
7013	1,5	17	20	0,2	0,2	0,05	Remainder	0,7	2,4
7049	1	0,01	15	0,15	7	0,8	Remainder	0,3	2,3

**Table 2 — Results of statistical analysis**

Sample reference	Mean % (m/m)	Within-laboratory standard deviation	Between laboratory standard deviation	Repeatability	Reproducibility
825	0,74	0,015	0,027	0,043	0,088
902	0,37	0,003 2	0,017	0,009	0,05 0
3920	0,28	0,003 8	0,009 3	0,011	0,028
3927	0,39	0,005 0	0,016	0,014	0,048
7013	0,058	0,000 7	0,001 6	0,001 9	0,004 8
7049	0,81	0,004 8	0,007 4	0,013	0,025

This page intentionally left blank

STANDARDSISO.COM : Click to view the full PDF of ISO 7530-6:1990