
International Standard



7627/5

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

**Hardmetals — Chemical analysis by flame atomic
absorption spectrometry —
Part 5: Determination of cobalt, iron, manganese,
molybdenum, nickel, titanium and vanadium in contents
from 0,5 to 2 % (m/m)**

Métaux-durs — Analyse chimique par spectrométrie d'absorption atomique dans la flamme — Partie 5: Dosage du cobalt, du fer, du manganèse, du molybdène, du nickel, du titane et du vanadium à des teneurs comprises entre 0,5 et 2 % (m/m)

First edition — 1983-10-15

STANDARDSISO.COM : Click to view the full PDF of ISO 7627-5:1983

UDC 669.018.25 : 643.422

Ref. No. ISO 7627/5-1983 (E)

Descriptors: hardmetals, chemical analysis, determination of content, cobalt, iron, manganese, molybdenum, nickel, titanium, vanadium, atomic absorption spectrometry.

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of developing International Standards is carried out through ISO technical committees. Every member body interested in a subject for which a technical committee has been authorized has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work.

Draft International Standards adopted by the technical committees are circulated to the member bodies for approval before their acceptance as International Standards by the ISO Council.

International Standard ISO 7627/5 was developed by Technical Committee ISO/TC 119, *Powder metallurgy*, and was circulated to the member bodies in August 1982.

It has been approved by the member bodies of the following countries:

Austria	Germany, F.R.	Sweden
Brazil	Italy	Switzerland
Bulgaria	Korea, Rep. of	United Kingdom
China	Norway	USA
Czechoslovakia	Romania	USSR
Egypt, Arab Rep. of	South Africa, Rep. of	
France	Spain	

No member body expressed disapproval of the document.

Hardmetals — Chemical analysis by flame atomic absorption spectrometry — Part 5: Determination of cobalt, iron, manganese, molybdenum, nickel, titanium and vanadium in contents from 0,5 to 2 % (m/m)

1 Scope and field of application

This part of ISO 7627 specifies the method to be used for the determination of cobalt, iron, manganese, molybdenum, nickel, titanium and vanadium contents of hardmetals within the range 0,5 to 2 % (m/m) by flame atomic absorption spectrometry.

General requirements concerning the field of application, principle, interfering elements, apparatus, sampling and test report are given in ISO 7627/1.

NOTE — Determination of element contents in high concentration by the atomic absorption spectrophotometry method yields a wider scattering of results than are obtainable by other methods, i.e. ISO 3909, 4501, 4503 and 4883. See also clause 4.2.

2 Reference

ISO 7627/1, *Hardmetals — Chemical analysis by flame atomic absorption spectrometry — Part 1: General requirements.*

3 Reagents

3.1 Hydrofluoric acid, ρ 1,12 g/ml.

3.2 Nitric acid, ρ 1,42 g/ml.

3.3 Ammonium fluoride, 0,1 g/ml solution.

3.4 Caesium chloride, 0,01 g/ml solution.

3.5 High-purity stock solutions, for calibration purposes for each element to be determined, containing 1,000 g of the element per litre.

NOTE — This value is understood to establish a maximum limit of 1,000 5 g and a minimum limit of 0,999 5 g.

4 Procedure

4.1 Test portion

Weigh, to the nearest 0,001 g, approximately 1 g of the test sample. Transfer it to a 100 ml polytetrafluorethylene beaker or a beaker of other suitable material. Cover the beaker.

4.2 Dissolution of the test portion

Add 10 ml of water, 5 ml of the hydrofluoric acid (3.1), and then 5 ml of the nitric acid (3.2), drop by drop, to the beaker containing the test portion (4.1) and heat gently until the test portion is completely dissolved. Add 10 ml of the caesium chloride solution (3.4) and 10 ml of the ammonium fluoride solution (3.3). Then transfer the solution totally to a 100 ml polypropylene one-mark volumetric flask and dilute to the mark.

4.3 Dilution volume

Prepare the relevant dilution volume for the analysis according to table 1 in the following way.

4.3.1 Dilution volume 100 ml: use the solution in 4.2.

4.3.2 The concentration of the solution may be reduced by a factor of 10 for instruments of higher sensitivity by transferring 10 ml of the solution in 4.2 to a 100 ml polypropylene one-mark volumetric flask. Add 10 ml of the caesium chloride solution (3.4). Add 10 ml of the ammonium fluoride solution (3.3) and dilute to the mark.

4.4 Preparation of calibration and blank solutions

4.4.1 Prepare at least six solutions according to 4.2 with a matrix composition as similar as possible to the test portion to be analysed, but without making up to volume. Then add increasing volumes of properly diluted stock solutions of the elements to be determined according to the concentration ranges to be covered. Make up to 100 ml and mix.