

INTERNATIONAL
STANDARD

ISO
7944

Second edition
1998-06-01

**Optics and optical instruments —
Reference wavelengths**

Optique et instruments d'optique — Longueurs d'onde de référence

STANDARDSISO.COM : Click to view the full PDF of ISO 7944:1998



Reference number
ISO 7944:1998(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 7944 was prepared by Technical Committee ISO/TC 172, *Optics and optical instruments*.

This second edition cancels and replaces the first edition (ISO 7944:1984), which has been technically revised.

STANDARDSISO.COM : Click to view the full PDF of ISO 7944:1998

© ISO 1998

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization
Case postale 56 • CH-1211 Genève 20 • Switzerland
Internet iso@iso.ch

Printed in Switzerland

Optics and optical instruments — Reference wavelengths

1 Scope

This International Standard specifies two reference wavelengths to be used for the characterization of optical materials, optical systems and instruments, as well as ophthalmic lenses. It defines the associated principal refractive indices and principal dispersions, as well as the Abbe numbers with regard to these reference wavelengths and principal dispersions.

2 Reference wavelengths, principal dispersions and Abbe numbers

2.1 General

The reference wavelengths are the mercury e-line 546,07 nm (see 2.2) and the helium d-line 587,56 nm (see 2.3).

For non-ophthalmic applications the mercury e-line shall be the reference wavelength.

Other wavelengths which may be used in addition to these reference wavelengths are given in tables 1, 2 and 3.

NOTE For the future, it is envisaged that only one reference wavelength is to be specified, even for ophthalmic use.

2.2 Mercury e-line 546,07 nm

The associated principal refractive index n_e is the refractive index at the green mercury e-line and the associated principal dispersion is $n_{F'} - n_{C'}$,

where

$n_{F'}$ is the refractive index at the blue cadmium F'-line;

$n_{C'}$ is the refractive index at the red cadmium C'-line.

The Abbe number v_e with regard to this reference wavelength and this principal dispersion is defined as:

$$v_e = \frac{n_e - 1}{n_{F'} - n_{C'}}$$

2.3 Helium d-line 587,56 nm

The associated principal refractive index n_d is the refractive index at the yellow helium d-line and the associated principal dispersion is $n_F - n_C$,

where

n_F is the refractive index at the blue hydrogen F-line;

n_C is the refractive index at the red hydrogen C-line.

The Abbe number V_d with regard to this reference wavelength and this principal dispersion is defined as:

$$V_d = \frac{n_d - 1}{n_F - n_C}$$

Table 1 — Reference wavelengths and recommended wavelengths in the visible and ultraviolet spectral ranges

| Spectral lines | Ultraviolet mercury i-line | Violet mercury h-line | Blue mercury g-line | Blue cadmium F'-line | Blue hydrogen F-line | Green mercury e-line | Yellow helium d-line | Red cadmium C'-line | Red hydrogen C-line | Red helium r-line |
|----------------------------|-------------------------------|--------------------------|------------------------|-------------------------|-------------------------|-------------------------|-------------------------|------------------------|------------------------|----------------------|
| Element | Hg | Hg | Hg | Cd | H | Hg | He | Cd | H | He |
| Wavelength nm | 365,01 ¹⁾ | 404,66 | 435,83 | 479,99 | 486,13 | 546,07 | 587,56 | 643,85 | 656,27 | 706,52 |
| Reference wavelength nm | — | — | — | — | — | 546,07 | 587,56 | — | — | — |
| Principal refractive index | — | — | — | — | — | n_e | n_d | — | — | — |

1) This single line of the Hg-triplet should be used.

Table 2 — Recommended wavelengths in the infrared spectral range

| Element | Rb | Cs | Hg | Hg | Hg | Hg | Hg | Hg | Hg |
|---------------|-------|----------------------|------------------------|----------|---------|---------|---------|---------|---------|
| Wavelength nm | 780,0 | 852,11 ¹⁾ | 1 013,98 ²⁾ | 1 128,66 | 1 395,1 | 1 529,6 | 1 813,1 | 1 970,1 | 2 325,4 |

1) Caesium s-line
2) Mercury t-line

Table 3 — Recommended laser wavelengths

| Active medium | He-Ne | He-Ne | Nd: YAG |
|---------------|-------|-------|---------|
| Wavelength nm | 543,5 | 632,8 | 1064,1 |