

---

---

**Injection containers and accessories —  
Part 1:  
Injection vials made of glass tubing**

*Réipients et accessoires pour produits injectables —  
Partie 1: Flacons en verre étiré*

STANDARDSISO.COM : Click to view the full PDF of ISO 8362-1:2009



**PDF disclaimer**

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

STANDARDSISO.COM : Click to view the full PDF of ISO 8362-1:2009



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2009

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 8362-1 was prepared by Technical Committee ISO/TC 76, *Transfusion, infusion and injection equipment for medical and pharmaceutical use*.

This third edition cancels and replaces the second edition (ISO 8362-1:2003), which has undergone minor revision by including further types of neck finishes for injection vials [model B – neck finish with blow back (European style) and model C – neck finish with blow back (American style)].

ISO 8362 consists of the following parts, under the general title *Injection containers and accessories*:

- *Part 1: Injection vials made of glass tubing*
- *Part 2: Closures for injection vials*
- *Part 3: Aluminium caps for injection vials*
- *Part 4: Injection vials made of moulded glass*
- *Part 5: Freeze drying closures for injection vials*
- *Part 6: Caps made of aluminium-plastics combinations for injection vials*
- *Part 7: Injection caps made of aluminium-plastics combinations without overlapping plastics part*

## Introduction

The purpose of this part of ISO 8362 is to specify the dimensions, capacities, form and requirements of glass vials intended for medical use. Containers made from glass tubing are considered to be suitable for the packaging and storage of injectable preparations until they are administered for medicinal purposes. Such containers may be made from different types of glass which can affect the chemical resistance properties; e.g., those made from borosilicate glass will have a very high level of chemical resistance whereas others made from soda-lime glass will have a lower, but adequate, chemical resistance for the purpose for which they are intended. The chemical resistance of the internal surface of containers made from soda-lime glass can be improved by means of a treatment during production aimed at producing a chemical resistance equal to that of those made from borosilicate glass for single use. This level of chemical resistance is maintained as long as the interior surface is not destroyed by chemical attack, in which case it is reduced to that of untreated soda-lime glass.

Because containers may be made from different types of glass and because it is the chemical behaviour of the internal surface which is important when they are filled with injectable preparations, it is essential to specify test procedures by which this performance can be measured. The procedures recommended in this part of ISO 8362 permit this performance, based on the hydrolytic resistance to be measured and, from the result of measurement, it is possible to classify containers into their correct category. The procedure also allows containers to be tested and to determine, after an intermediate stage, whether the hydrolytic resistance is produced by the composition of the glass as a material or by a treatment of the internal surface.

STANDARDSISO.COM : Click to view the full PDF of ISO 8362-1:2009

# Injection containers and accessories —

## Part 1: Injection vials made of glass tubing

### 1 Scope

This part of ISO 8362 specifies the form, dimensions and capacities of glass vials for injectable preparations. It also specifies the material from which such containers shall be made and the performance requirements of those containers.

This part of ISO 8362 applies to colourless or amber glass containers made from borosilicate or soda-lime glass, made from glass tubing, whether internally surface-treated or not, and intended to be used in the packaging, storage or transportation of products intended for injection.

### 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 719, *Glass — Hydrolytic resistance of glass grains at 98 °C — Method of test and classification*

ISO 720, *Glass — Hydrolytic resistance of glass grains at 121 °C — Method of test and classification*

ISO 1101, *Geometrical Product Specifications (GPS) — Geometrical tolerancing — Tolerances of form, orientation, location and run-out*

ISO 4802-1, *Glassware — Hydrolytic resistance of the interior surfaces of glass containers — Part 1: Determination by titration method and classification*

ISO 4802-2, *Glassware — Hydrolytic resistance of the interior surfaces of glass containers — Part 2: Determination by flame spectrometry and classification*


### 3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 4802-1 and ISO 4808-2 apply.

### 4 Dimensions

The dimensions of injection vials made of glass tubing shall meet the requirements of Figure 1 or Figure 2 or Figure 3, as appropriate, and Table 1; the overflow capacity and mass shall be as shown in Table 1.

Dimensions in millimetres




- a The opening of the vial should have a constant diameter, over the entire distance,  $h_3$ , i.e. it should exhibit a cylindrical shape. A slightly conical shape can be accepted if the following requirements are fulfilled:
  - the truncated cone has the height  $h_3$ ;
  - the larger diameter is located at the flange or as agreed upon;
  - the larger diameter does not exceed the smaller one by more than 0,3 mm.
- b The perpendicularity tolerance  $a$  (as defined in ISO 1101) is a limit for the deviation of the plumb-line through the centre of the bottom part and the axis of the vial at the upper edge of the flange; it is measured at the brim.
- c Edges slightly rounded.

Figure 1 — Typical example of injection vial made of glass tubing containing a neck finish without blow back — Model A

Table 1 — Dimensions, overflow capacity and mass

Size designation of injection vial	Overflow capacity		$a$ mm	$d_1$ mm	$d_2$ mm	$d_3$ mm	$d_4$ mm	$h_1$ mm	$h_2$ mm	$h_3$ mm	$r_1$ mm	$r_2$ mm	$s_1$ mm	$s_2$ mm	$t$ mm	Mass g		
	ml	tol															tol.	$+0,2$ $-0,3$
2R	4	$\pm 0,5$	1	16	$\pm 0,15$	13	10,5	7	35	22	8	2,5	1,5	0,6	0,7	5		
4R	6								45							32	6,1	
6R	10								40							26	8,3	
8R	11,5	$\pm 1$	1,2	22	$\pm 0,2$	16,5	12,6	45	$\pm 0,5$	31	8,5	$\pm 0,5$	3,5	2	1	9,4		
10R	13,5								45							30	10,2	
15R	19								60							45	9	4,0
20R	26	$\pm 1,5$	1,5	30	$\pm 0,25$	17,5	12,6	55	$\pm 0,7$	35	10	$\pm 0,75$	5,5	2,5	1,2	17,4		
25R	32,5							65								45	1	20
30R	37,5							75								55	22,7	

Dimensions in millimetres



<sup>a</sup> The perpendicularity tolerance  $a$  (as defined in ISO 1101) is a limit for the deviation of the plumb-line through the centre of the bottom part and the axis of the vial at the upper edge of the flange; it is measured at the brim.


<sup>b</sup> Edges slightly rounded.

<sup>c</sup> This value should not exceed 0,4 mm in order to avoid the wall becoming too weak. This dimension has not been given as a requirement because it is not possible to measure it adequately.

NOTE Figures 2 and 3 illustrate ideal presentations. The transition to blow back is not sharp-edged but slightly rounded.

**Figure 2 — Typical example of injection vial made of glass tubing containing a neck finish with blow back (European style) — Model B**

Dimensions in millimetres



a The perpendicularity tolerance  $a$  (as defined in ISO 1101) is a limit for the deviation of the plumb-line through the centre of the bottom part and the axis of the vial at the upper edge of the flange; it is measured at the brim.

b Edges slightly rounded.

**Figure 3 — Typical example of injection vial made of glass tubing containing a neck finish with blow back (American style) — Model C**

## 5 Designation

EXAMPLE 1 An injection vial (model A), size 10 (10R), made of amber glass (br) tubing of hydrolytic resistance container class ISO 4802 – HC 1 (1) complying with the requirements specified in this part of ISO 8362 is designated as follows:

**Vial ISO 8362-1 – A – 10R – br – 1**

EXAMPLE 2 An injection vial (model B), size 10 (10R), made of amber glass (br) tubing of hydrolytic resistance container class ISO 4802 – HC 1 (1) complying with the requirements specified in this part of ISO 8362 is designated as follows:

**Vial ISO 8362-1 – B – 10R – br – 1**

EXAMPLE 3 An injection vial (model C), size 15 (15R), made of colourless (cl) glass of hydrolytic resistance container class ISO 4802 – HC 1 (1) complying with the requirements specified in this part of ISO 8362 is designated as follows:

**Vial ISO 8362-1 – C – 15R – cl – 1**