
**Alpine skis and bindings — Binding
mounting area — Requirements and
test methods**

*Skis et fixations de skis alpins — Zone de montage de la fixation —
Exigences de tenue et méthodes d'essai*

STANDARDSISO.COM : Click to view the full PDF of ISO 8364:2017



STANDARDSISO.COM : Click to view the full PDF of ISO 8364:2017



COPYRIGHT PROTECTED DOCUMENT

© ISO 2017, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

	Page
Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Specifications of free space area	2
4.1 Length of free space area (l_z)	2
4.2 Width of the free space area (b_z)	2
5 Geometrical requirements of free space area	3
5.1 Longitudinal profile of the ski surface within the free space area	3
5.2 Transverse profile of the ski surface within the free space area	3
6 Specifications of binding mounting area	4
6.1 Length of binding mounting area (l_b)	4
6.2 Width of binding mounting area	4
6.3 Minimum thickness of binding mounting area	4
7 Strength requirements of binding mounting area	5
7.1 Screw retention strength (F_r)	5
7.2 Stripping resistance (F_s)	5
8 Specifications of the binding	5
8.1 General	5
8.2 Centre-to-centre distances for binding mounting screws	5
8.2.1 Maximum centre-to-centre distance	5
8.2.2 Minimum centre-to-centre distance	6
8.3 Penetration depth of binding screws	6
9 Side walls	6
10 Marking	6
10.1 Marking of the mounting point	6
10.2 Marking of the ski properties	6
11 Apparatus	6
12 Test screws	8
13 Test methods	8
13.1 Sampling and conditioning	8
13.2 General requirements	8
13.3 Retention strength test	9
13.3.1 Mounting of the attachment plate	9
13.3.2 Positioning of the pull-out tests within the binding mounting area	10
13.3.3 Load application	11
13.4 Stripping resistance test	11
14 Test report	11
Annex A (informative) Synoptic tables	13

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 83, *Sports and other recreational facilities and equipment*, Subcommittee SC 04, *Snowsports equipment*.

This fifth edition cancels and replaces the fourth edition (ISO 8364:2007), which has been technically revised.

Alpine skis and bindings — Binding mounting area — Requirements and test methods

1 Scope

This document specifies requirements and test methods for the binding mounting area and free space area, ski bindings and retention devices of alpine skis, in order to optimize the compatibility of the functional unit “ski binding — retention device — boot”.

It contains data for the manufacturer of alpine skis, bindings and retention devices, concerning dimensions, tests and other specifications for the binding mounting area.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 4287, *Geometrical Product Specifications (GPS) — Surface texture: Profile method — Terms, definitions and surface texture parameters*

ISO 5355, *Alpine ski-boots — Requirements and test methods*

ISO 6004, *Alpine skis — Ski binding screws — Requirements*

ISO 6289, *Skis — Vocabulary*

ISO 6506 (all parts), *Metallic materials — Brinell hardness test*

ISO 10045, *Alpine skis — Binding mounting area — Requirements for test screws*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 6289 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <https://www.iso.org/obp>

3.1

mounting point

location on the ski that indicates the position of the boot along the length of the ski for the purpose of mounting the binding, and which corresponds to the boot sole mark established by ISO 5355 for alpine ski-boots

3.2

free space area


area forward and backward from the mounting point, fulfilling minimum flatness requirements in accordance with [Clause 5](#)

Note 1 to entry: See [Figure 1](#).

3.3 binding mounting area

area forward and backward from the mounting point, fulfilling minimum strength requirements in accordance with [Clause 7](#)

Note 1 to entry: See [Figure 1](#).



Key

- l_b length of binding mounting area
- l_z length of free space area
- b_z width of the free space area
- a Mounting point.
- b Free space area.
- c Binding mounting area (width in accordance with [6.2](#)).

Figure 1 — Free space and binding mounting areas

4 Specifications of free space area

4.1 Length of free space area (l_z)

The length of the free space area forward and backward from the mounting point shall be according to the values given in [Table 1](#).

Table 1 — Length of free space area

Group	Length of free space area forward and backward from the mounting point	
	mm	
1	300	
2	270	
3	210	
4	190	

4.2 Width of the free space area (b_z)

The minimum width of the free space area shall be as follows.

- For Groups 1, 2 and 3:
 - 48 mm within an area 100 mm forward and 100 mm backward from the mounting point;


- 53 mm in the remaining part of the free space area.
- For Group 4:
 - 46 mm within an area 100 mm forward and 100 mm backward from the mounting point;
 - 50 mm in the remaining part of the free space area.

5 Geometrical requirements of free space area

5.1 Longitudinal profile of the ski surface within the free space area

Deviations from the straightness of the longitudinal profile from a flat profile are only permissible in the form of a constant curve in the length of the free space area; the tolerance on straightness in this area, the ski base being pressed against a flat surface, is as follows (see [Figure 2](#)):

- Groups 1 and 2: 5 mm;
- Groups 3 and 4: 4 mm.



Key


- l_z length of free space area
- a Groups 1 and 2.
- b Groups 3 and 4.

Figure 2 — Longitudinal profile of the surface

Outside the binding mounting area, within the length of the free space area, a maximum downward deviation of 2 mm from the constant curve is permissible.

5.2 Transverse profile of the ski surface within the free space area

Deviations of straightness of the transverse profile from the flat profile are only permissible in the form of a constant curve across the width of the free space area; the tolerance on straightness within this area is given in [Figure 3](#).



Key
 b_z width of free space area

Figure 3 — Transverse profile of the structure

Beyond the free space area, on the remaining width of the ski, there shall be no elevation beyond the surface of the free space area.

6 Specifications of binding mounting area

6.1 Length of binding mounting area (l_b)

The length of the binding mounting area forward and backward from the mounting point shall be in accordance with the values given in [Table 2](#).

Table 2 — Length of binding mounting area

Group	Length of binding mounting area forward and backward from the mounting point
	mm
1	285
2	240
3	210
4	190


6.2 Width of binding mounting area

The width of the binding mounting area shall be such that it allows the mounting of alpine ski binding screws of nominal diameter 5,5 mm in accordance with ISO 6004, and respects the retention strength requirements in accordance with [7.1](#).

6.3 Minimum thickness of binding mounting area

Within the binding mounting area, a drill hole depth, d' , shall be available (see [Figure 4](#)) as follows:

- Groups 1 and 2: 9,5 mm;
- Groups 3 and 4: 7,5 mm.

**Key**

- d' drill hole depth
 d penetration depth

Figure 4 — Penetration depth, d , of mounting screws

7 Strength requirements of binding mounting area

7.1 Screw retention strength (F_r)

Within the binding mounting area, the minimum value of the screw retention strength for two screws, if the load is applied at ≤ 20 mm/min, shall be as follows:

- Group 1 and Group 2: 2 600 N;
- Group 3: 1 600 N;
- Group 4: 1 300 N.

7.2 Stripping resistance (F_s)

The minimum value of the stripping resistance of the ski shall be 5 Nm for Groups 1 and 2.

NOTE The present state of the art does not allow a stripping resistance of 5 Nm for skis of Groups 3 and 4. It is the responsibility of the ski manufacturer to indicate ski models where caution is required (stripping resistance lower than 5 Nm) when mounting bindings, and to give mounting instructions, such as smaller diameter drilling and manual screw driving.

8 Specifications of the binding

8.1 General

The hole-pattern shall be in accordance with the geometrical requirements according to [8.2](#).

8.2 Centre-to-centre distances for binding mounting screws

8.2.1 Maximum centre-to-centre distance

The maximum centre-to-centre distance in transverse orientation of the binding mounting screws shall be as follows:

- Groups 1 and 2: 42,5 mm;

- Groups 3 and 4: 40,5 mm.

8.2.2 Minimum centre-to-centre distance

For screws which are used for mounting of parts of the binding and retention devices, the centre-to-centre distance shall not be less than the following:

- Groups 1 and 2: 25 mm in the longitudinal direction and 20 mm in all other directions;
- Groups 3 and 4: 20 mm in the longitudinal direction and 15 mm in all other directions.

8.3 Penetration depth of binding screws

In order to ensure the required penetration depth, d , the manufacturer of the binding shall select a suitable length of binding screw, so that after mounting of the binding, the shaft of the screw penetrates the ski, for

- Groups 1 and 2: $d = (8 \pm 0,5)$ mm, and
- Groups 3 and 4: $d = (6 \pm 0,5)$ mm.

To avoid damaging the top layers (damage to the adhesive bond), the diameter of mounting plate holes or countersink facing the ski shall not exceed 8 mm, and drill countersink shall be designed in such a way that its penetration into the top surface of the ski does not exceed 0,6 mm.

Alpine ski binding screws in accordance with ISO 6004 shall be used as mounting elements.

9 Side walls

Side walls shall be designed so that mounting of the binding with commonly used mounting devices is ensured. The basic requirement is that the clamping elements of the mounting device reach at least to the running surface of the ski.

10 Marking

10.1 Marking of the mounting point

A clearly visible mark shall be located on the left side or the top surface of the ski, up to the outer edge for the mounting of the binding. Unless otherwise specified by the ski manufacturer, this mark defines the mounting point in accordance with [3.1](#).

10.2 Marking of the ski properties


A clearly visible mark shall be located on the side or the top surface of the ski.

EXAMPLE "G1".

11 Apparatus

11.1 Retention strength.

Tensile testing machine (with a pull-out device in accordance with [Figure 5](#)) having a minimum load range of 10 000 N.

**Key**

- 1 steel attachment plate
- 2 universal joint
- 3 ski support
- a Thickness according to the penetration depth needed.
- b $a = 25$ mm for Groups 1 and 2; $a = 20$ mm for Groups 3 and 4.

Figure 5 — Tensile testing machine with pull-out device

The pull-out device (see [Figure 5](#)) shall consist of the following components:

- a) a steel attachment plate with two holes of diameter 6 mm; the steel hardness shall be 135 HB30 in accordance with ISO 6506 (all parts);
- b) a universal joint which is connected to the attachment plate and to the clamping device of the test machine;
- c) a ski support with two support rollers.

When using standard test screws in accordance with [Clause 12](#), the following penetration depths, d , shall be reached:

- Groups 1 and 2: $d = (8 \pm 0,5)$ mm;
- Groups 3 and 4: $d = (6 \pm 0,5)$ mm.

11.2 Stripping resistance.

Template, used with a drill bushing, for drilling holes, mounting test screws and determination of stripping torque (see [Figure 6](#) and [13.3.1](#)).

The jig is equipped with a friction plate made of steel with a minimum hardness of 150 HBW 1/30 in accordance with ISO 6506 (all parts), and surface roughness, Ra , of $0,8 \mu\text{m}$ in accordance with ISO 4287.

When using test screws in accordance with [Clause 12](#), the following penetration depths, d , shall be reached:

- Groups 1 and 2: $d = (8 \pm 0,5)$ mm;
- Groups 3 and 4: $d = (6 \pm 0,5)$ mm.

12 Test screws

The screws used for the retention and stripping tests shall be in accordance with ISO 10045.

13 Test methods

13.1 Sampling and conditioning


Carry out the test on three skis which have been at a room temperature of (23 ± 5) °C for a minimum of 24 h, without specific preconditioning of the ski to be tested.

13.2 General requirements

Test the requirements of [Clauses 4](#) to [6](#) and [Clauses 8](#) to [10](#) by measurement and/or sight check.

STANDARDSISO.COM : Click to view the full PDF of ISO 8364:2017

Dimensions in millimetres



Key

- 1 drill template bushing
- 2 drill template
- 3 friction plate
- 4 centering pin
- a Thickness according to the penetration depth needed.

Figure 6 — Drill and test template

13.3 Retention strength test

13.3.1 Mounting of the attachment plate

It is recommended that a drill template be used to ensure exact drill holes, perpendicular to the top surface of the ski, and at the exact distance apart.

Ensure that the dimensions of the drill hole diameters are 4,1 mm H12 or 3,5 mm H12.

If a drill hole diameter of 3,5 mm is to be used, it shall be indicated on the ski by the manufacturer.

The depth of the drill hole, d' , shall be as follows:

- Groups 1 and 2: $(9^{+0,5}_0)$ mm;
- Groups 3 and 4: $(7^{+0,5}_0)$ mm.

Ensure that the drill countersink is in accordance with 8.2, and that the screws are mounted perpendicular to the top surface of the ski in accordance with the ski manufacturer's instructions for mounting the binding.

The tightening torque shall be as follows:

- Groups 1 and 2: $(4 \pm 0,5)$ Nm;
- Groups 3 and 4: $(3 \pm 0,5)$ Nm.

13.3.2 Positioning of the pull-out tests within the binding mounting area

The location of the pull-out tests within binding mounting area is shown in Figure 7. Locations 1 and 2 are those which are specified by this document. Choose locations 3 and 4 at random, but ensure that the distance with respect to the side of the mounting area is as specified in Figure 7. The minimum spacing in the longitudinal direction is as follows:

- Groups 1 and 2: $a = 25$ mm;
- Groups 3 and 4: $a = 20$ mm.

Ensure that the tests are not influenced by the preceding tests. No future test shall be run within 50 mm of a delimited area.