

# INTERNATIONAL STANDARD



# 845

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

## Cellular rubbers and plastics – Determination of apparent density

*Caoutchoucs et plastiques alvéolaires – Détermination de la masse volumique apparente*

First edition – 1977-12-01

STANDARDSISO.COM : Click to view the full PDF of ISO 845:1977



UDC 678-496.8 : 678.01 : 531.755.1

Ref. No. ISO 845-1977 (E)

**Descriptors** : plastics, cellular materials, bulk density, density measurement.

## FOREWORD

ISO (the International Organization for Standardization) is a worldwide federation of national standards institutes (ISO member bodies). The work of developing International Standards is carried out through ISO technical committees. Every member body interested in a subject for which a technical committee has been set up has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work.

Draft International Standards adopted by the technical committees are circulated to the member bodies for approval before their acceptance as International Standards by the ISO Council.

International Standard ISO 845 was developed jointly by Technical Committees ISO/TC 45, *Rubber and rubber products*, and ISO/TC 61, *Plastics*, and was circulated to the member bodies in November 1975.

It has been approved by the member bodies of the following countries :

Australia	Hungary	Romania
Austria	India	South Africa, Rep. of
Belgium	Iran	Spain
Brazil	Israel	Sweden
Canada	Italy	Switzerland
Czechoslovakia	Mexico	Turkey
Finland	Netherlands	United Kingdom
France	New Zealand	U.S.A.
Germany	Poland	U.S.S.R.

No member body expressed disapproval of the document.

This International Standard cancels and replaces both ISO Recommendation R 845-1968 and International Standard ISO 1855-1975, of which documents it constitutes a technical revision.

# Cellular rubbers and plastics – Determination of apparent density

## 1 SCOPE AND FIELD OF APPLICATION

This International Standard specifies a method for determining the apparent density of cellular rubbers and plastics.

## 2 REFERENCE

ISO 1923, *Cellular materials – Determination of linear dimensions*.<sup>1)</sup>

## 3 DEFINITION

For the purpose of this International Standard, the following definition applies :

**apparent density** : Mass per unit volume of the cellular material, at a stated temperature and relative humidity.

## 4 APPARATUS

**4.1 Balance**, capable of determining the mass of the specimen to an accuracy of 0,5 %.

**4.2 Measuring instruments** in accordance with ISO 1923.

## 5 TEST SPECIMENS

### 5.1 Dimensions

The test specimen shall be of a shape such that its volume can be easily calculated. It shall be cut without deforming the original cell structure of the material.

The volume of the test specimen shall be at least 100 cm<sup>3</sup>, but preferably as large as possible commensurate with the apparatus available and with the shape of the original material. The location from which the test specimen is taken and the presence or absence of surface skins shall be recorded.

### 5.2 Number

A minimum of three test specimens shall be tested.

### 5.3 Conditioning

Materials shall not be tested for at least 72 h after manufacture.

The test specimens shall be conditioned for at least 16 h at :

- 23 ± 2 °C, 50 ± 5 % relative humidity; or
- 27 ± 2 °C, 65 ± 5 % relative humidity.

## 6 PROCEDURE

**6.1** Measure the dimensions, in millimetres, of the test specimen, in accordance with ISO 1923. The mean values of a minimum of three separate measurements of each dimension shall be used to calculate the volume of the test specimen.

**6.2** Weigh the test specimen to an accuracy of 0,5 %, expressing its mass in grams.

1) At present at the stage of draft. (Revision of ISO 1923-1972 and ISO/R 1794-1971.)