
**Steel flat products for pressure
purposes — Technical delivery
conditions —**

Part 7:
Stainless steels

*Produits plats en acier pour service sous pression — Conditions
techniques de livraison —*

Partie 7: Aciers inoxydables

STANDARDSISO.COM : Click to view the full PDF of ISO 9328-7:2018



STANDARDSISO.COM : Click to view the full PDF of ISO 9328-7:2018



COPYRIGHT PROTECTED DOCUMENT

© ISO 2018

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Published in Switzerland

Contents

	Page
Foreword.....	iv
Introduction.....	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Classification and designation	1
5 Information to be supplied by the purchaser	2
5.1 Mandatory information.....	2
5.2 Options.....	2
5.3 Example for ordering.....	2
6 Requirements	2
6.1 Steelmaking process.....	2
6.2 Delivery condition.....	2
6.3 Chemical composition and chemical corrosion properties.....	2
6.4 Mechanical properties.....	2
6.5 Surface condition.....	3
6.6 Internal soundness.....	3
6.7 Post-weld heat treatment.....	3
6.8 Dimensions and tolerances.....	3
6.9 Calculation of mass.....	3
6.10 Physical properties.....	3
7 Inspection	3
7.1 Types of inspection and inspection documents.....	3
7.2 Tests to be carried out.....	3
7.3 Re-tests.....	3
8 Sampling	4
8.1 Frequency of testing.....	4
8.2 Selection and preparation of samples and test pieces.....	4
9 Test methods	4
10 Marking	4
Annex A (informative) Steel designations in accordance with this document and designation of comparable steel grades in national or regional standards	30
Annex B (informative) Guidelines for further treatment (including heat treatment) in fabrication	32
Annex C (informative) Post-weld heat treatment	36
Annex D (informative) Preliminary reference data for the tensile strength of austenitic-ferritic steels at elevated temperatures	39
Annex E (informative) Reference data on strength values for 1 % (plastic) creep strain and creep rupture	40
Annex F (informative) Reference data on mechanical properties of austenitic steels at room temperature and at low temperature	47
Annex G (informative) Reference data on some physical properties	49
Annex H (informative) Numbering of steel grades in accordance with ISO 15510	56
Bibliography	58

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 17, *Steel*, Subcommittee SC 10, *Steel for pressure purposes*.

This third edition cancels and replaces the second edition (ISO 9328-7:2011), which has been technically revised. The following changes have been made:

- the term “product thickness” has been replaced with “nominal thickness”;
- new steel grades X1CrNiSi18-5-4, X2CrCuNbTiV22-1, X2CrNiMoN21-9-1, X2CrMnNiN21-5-1 and X2CrNiMnMoCuN24-4-3-2 and all their technical data have been added;
- the technical data in [Table 5](#) have been revised;
- the technical data in [Table 9](#) have been aligned with EN 10028-7.

A list of all the parts in the ISO 9328 series can be found on the ISO website.

Introduction

The International Organization for Standardization (ISO) draws attention to the fact that it is claimed that compliance with this document may involve the use of patents concerning eight steel grades.

ISO takes no position concerning the evidence, validity and scope of this patent right. The holder of this patent right has assured ISO that he/she is willing to negotiate licences under reasonable and non-discriminatory terms and conditions with applicants throughout the world. In this respect, the statement of the holder of this patent right is registered with ISO. Information may be obtained from the following sources.

For steel grades 1.4162 (but also consider footnote ^c in [Table 4](#)) and 1.4662 from:

Outokumpu Stainless AB

SE-77480 AVESTA, Sweden

For steel grades 1.4420 and 1.4622 from:

Outokumpu Oyj

FI-02200 Espoo, Finland

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights other than those identified above. ISO shall not be held responsible for identifying any or all such patent rights.

STANDARDSISO.COM : Click to view the full PDF of ISO 9328-7:2018

[STANDARDSISO.COM](https://standardsiso.com) : Click to view the full PDF of ISO 9328-7:2018

Steel flat products for pressure purposes — Technical delivery conditions —

Part 7: Stainless steels

1 Scope

This document specifies requirements for flat products for pressure purposes made of stainless steels, including austenitic creep-resisting steels, in thicknesses as specified in [Tables 7 to 10](#).

The requirements and definitions of ISO 9328-1 also apply to this document.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 3651-2, *Determination of resistance to intergranular corrosion of stainless steels — Part 2: Ferritic, austenitic and ferritic-austenitic (duplex) stainless steels — Corrosion test in media containing sulfuric acid*

ISO 9328-1:2018, *Steel flat products for pressure purposes — Technical delivery conditions — Part 1: General requirements*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 9328-1 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <https://www.iso.org/obp>

3.1

cryogenic temperature

temperature lower than -75 °C used in the liquefaction of gases

4 Classification and designation

Shall be in accordance with ISO 9328-1.

NOTE 1 Information on the designation of comparable steel grades in national or regional standards is given in [Annex A](#).

NOTE 2 Information on numbering of steel grades is in accordance with ISO 15510.

5 Information to be supplied by the purchaser

5.1 Mandatory information

Shall be in accordance with ISO 9328-1.

5.2 Options

The relevant options of ISO 9328-1 apply.

5.3 Example for ordering

An order of 10 plates made of a steel grade with the name X5CrNi18-10 as specified in this document with nominal dimensions thickness = 8 mm, width = 2 000 mm, length = 5 000 mm and tolerances on dimensions, shape and mass as specified in ISO 18286, with “normal” flatness tolerance in process route 1D (see [Table 6](#)), and with inspection certificate 3.1 as specified in ISO 10474 is designated as follows:

10 plates ISO 18286 – 8 × 2 000 × 5 000 N – Steel ISO 9328-7 – X5 CrNi18-10 + 1D – Inspection certificate 3.1

6 Requirements

6.1 Steelmaking process

Shall be in accordance with ISO 9328-1.

6.2 Delivery condition

The products shall be supplied in the delivery condition specified in the order by reference to the process route given in [Table 6](#) and, where alternatives exist, to the treatment conditions given in [Tables 7](#) to [10](#). Guidelines for further treatment, including heat treatment, are given in [Annex B](#).

6.3 Chemical composition and chemical corrosion properties

6.3.1 The chemical composition requirements given in [Tables 1](#) to [4](#) apply in respect of the chemical composition according to the cast analysis.

6.3.2 The product analysis may deviate from the limiting values for the cast analysis given in [Tables 1](#) to [4](#) by the values listed in [Table 5](#).

6.3.3 Referring to resistance to intergranular corrosion as defined in ISO 3651-2, for ferritic, austenitic and austenitic-ferritic steels, the specifications in [Tables 7](#), [9](#) and [10](#) apply.

NOTE 1 ISO 3651-2 is not applicable for testing martensitic steels.

NOTE 2 The corrosion resistance of stainless steels is very dependent on the type of environment and can therefore not always be clearly ascertained through laboratory tests. It is therefore advisable to draw on the available experience of the use of the steels.

6.4 Mechanical properties

6.4.1 The tensile properties at room temperature and the impact energy at room temperature and at low temperature, as specified in [Tables 7](#) to [10](#), apply for the relevant specified heat treatment condition.

NOTE Austenitic steels are insensitive to brittle fracture in the solution annealed condition. Because they do not have a pronounced transition temperature, which is characteristic of other steels, they are also useful for application at cryogenic temperatures.

6.4.2 The values in [Tables 11](#) to [14](#) apply for the 0,2 % and 1,0 % proof strength at elevated temperatures. Additionally, the values in [Table 15](#) apply for the tensile strength at elevated temperatures of austenitic steels.

Tensile strength values at elevated temperatures for austenitic-ferritic steels are given for guidance in [Annex D](#).

6.4.3 [Annex E](#) provides for the purchaser mean values as preliminary data on the strength for 1 % (plastic) creep strain and creep rupture. These data apply for the solution annealed condition only.

6.4.4 In [Annex F](#), preliminary data on mechanical properties at low temperatures of austenitic steels are listed.

6.5 Surface condition

Shall be in accordance with ISO 9328-1 and [Table 6](#).

6.6 Internal soundness

Shall be in accordance with ISO 9328-1.

6.7 Post-weld heat treatment

Guidelines for the purchaser on post-weld heat treatment are given in [Annex C](#).

6.8 Dimensions and tolerances

Shall be in accordance with ISO 9328-1.

6.9 Calculation of mass

For density of steels, see [Annex G](#).

6.10 Physical properties

Reference data on some physical properties are given in [Annex G](#).

7 Inspection

7.1 Types of inspection and inspection documents

Shall be in accordance with ISO 9328-1.

7.2 Tests to be carried out

Shall be in accordance with [Table 16](#) and ISO 9328-1.

7.3 Re-tests

Shall be in accordance with ISO 9328-1.

8 Sampling

8.1 Frequency of testing

Shall be in accordance with [Table 16](#) and ISO 9328-1.

8.2 Selection and preparation of samples and test pieces

Shall be in accordance with ISO 9328-1.

9 Test methods

Shall be in accordance with ISO 9328-1.

10 Marking

Shall be in accordance with ISO 9328-1.

STANDARDSISO.COM : Click to view the full PDF of ISO 9328-7:2018

Table 1 — Chemical composition (cast analysis)^a of ferritic steels

Steel grade ^b	mass fraction, %										
	C max.	Si max.	Mn max.	P max.	S max.	N max.	Cr	Mo	Nb	Ni	Ti
X2CrNi12	0,030	1,00	1,50	0,040	0,015	0,030	10,5 to 12,5	—	—	0,30 to 1,10	—
X6CrNiTi12	0,08	1,00	1,00	0,040	0,015	—	10,5 to 12,5	—	—	0,50 to 1,50	0,05 to 0,35
X2CrTi17	0,025	0,50	0,50	0,040	0,015	0,015	16,0 to 18,0	—	—	—	0,30 to 0,60
X3CrTi17	0,05	1,00	1,00	0,040	0,015	—	16,0 to 18,0	—	—	—	[4 × (C + N) + 0,15] to 0,80 ^c
X2CrMoTi17-1	0,025	1,00	1,00	0,040	0,015	0,030	16,0 to 18,0	0,80 to 1,40	—	—	0,30 to 0,60
X2CrMoTi18-2	0,025	1,00	1,00	0,040	0,015	0,030	17,0 to 20,0	1,80 to 2,50	—	—	[4 × (C + N) + 0,15] to 0,80 ^c
X6CrMoNb17-1	0,08	1,00	1,00	0,040	0,015	0,040	16,0 to 18,0	0,80 to 1,40	[7 × (C + N) + 0,10] to 1,00	—	—
X2CrTiNb18	0,030	1,00	1,00	0,040	0,015	—	17,5 to 18,5	—	[3 × C + 0,30] to 1,00	—	0,10 to 0,60
X2CrCuNbTiV22-1 _{d,e}	0,030	1,00	0,80	0,040	0,015	0,030	20,0 to 24,0	—	0,10 to 0,70	—	0,10 to 0,70

^a Elements not listed in this table may not be intentionally added to the steel without agreement of the purchaser, except for finishing of the cast. All appropriate precautions are to be taken to avoid the addition of such elements from scrap and other materials used in production, which would impair mechanical properties and the suitability of the steel.

^b Information concerning ISO steel numbers and designations according to other regional or national standards is given in [Annex A](#).

^c The stabilization may be made by use of titanium and/or niobium and/or zirconium. According to the atomic number of these elements and the content of carbon and nitrogen, the equivalence shall, if additional stabilizing with niobium or zirconium is used, be the following:

$$\text{Nb} = \text{Zr} = \frac{7}{4} \text{Ti}$$

^d Patented steel.

^e Other elements: V: 0,03 to 0,50 %; Cu: 0,30 to 0,80 %; Ti + Nb: 8x(C+N) to 0,80 %.

Table 2 — Chemical composition (cast analysis)^a of martensitic steels

Steel grade ^b	mass fraction, %									
	C	Si	Mn	P	S	N	Cr	Mo	Ni	
X3CrNiMo13-4	max. 0,05	max. 0,70	max. 0,50 to 1,00	max. 0,040	max. 0,015	min. 0,020	12,0 to 14,0	0,30 to 1,00	3,5 to 4,5	
X4CrNiMo16-5-1	0,06	0,70	1,50	0,040	0,015	0,020	15,0 to 17,0	0,80 to 1,50	4,0 to 6,0	

^a Elements not listed in this table may not be intentionally added to the steel without the agreement of the purchaser, except for finishing of the cast. All appropriate precautions are to be taken to avoid the addition of such elements from scrap and other materials used in production, which would impair mechanical properties and the suitability of the steel.

^b Information concerning ISO steel numbers and designations according to other regional or national standards is given in [Annex A](#).

SAMPLE ISO.COM : Click to view the full PDF of ISO 9328-7:2018

Table 3 — Chemical composition (cast analysis)^a of austenitic steels

Steel grade ^b	mass fraction, %											Ti	Others	
	C	Si	Mn	P	S	N	Cr	Cu	Mo	Nb	Ni			
Austenitic corrosion-resisting grades														
X2CrNi18-7	≤ 0,030	≤ 1,00	2,00	0,045	0,015	0,10 to 0,20	16,5 to 18,5	—	—	—	6,0 to 8,0	—	—	
X2CrNi18-9	≤ 0,030	≤ 1,00	2,00	0,045	0,015	≤ 0,10	17,5 to 19,5	—	—	—	8,0 to 10,5	—	—	
X2CrNi19-11	≤ 0,030	≤ 1,00	2,00	0,045	0,015	≤ 0,10	18,0 to 20,0	—	—	—	10,0 to 12,0	—	—	
X5CrNi19-9	≤ 0,06	≤ 1,00	2,00	0,045	0,015	0,12 to 0,22	18,0 to 20,0	—	—	—	8,0 to 11,0	—	—	
X2CrNi18-10	≤ 0,030	≤ 1,00	2,00	0,045	0,015	0,12 to 0,22	17,5 to 19,5	—	—	—	8,0 to 11,5	—	—	
X5CrNi18-10	≤ 0,07	≤ 1,00	2,00	0,045	0,015	≤ 0,10	17,5 to 19,5	—	—	—	8,0 to 10,5	—	—	
X6CrNiTi18-10	≤ 0,08	≤ 1,00	2,00	0,045	0,015	—	17,0 to 19,0	—	—	—	9,0 to 12,0	5 × C to 0,70	—	
X6CrNiNb18-10	≤ 0,08	≤ 1,00	2,00	0,045	0,015	—	17,0 to 19,0	—	—	10 × C to 1,00	9,0 to 12,0	—	—	
X1CrNi25-21	≤ 0,020	≤ 0,25	2,00	0,025	0,010	≤ 0,10	24,0 to 26,0	—	—	≤ 0,20	20,0 to 22,0	—	—	
X2CrNiMo17-12-2	≤ 0,030	≤ 1,00	2,00	0,045	0,015	≤ 0,10	16,5 to 18,5	—	—	2,00 to 2,50	10,0 to 13,0	—	—	
X2CrNiMoN17-11-2	≤ 0,030	≤ 1,00	2,00	0,045	0,015	0,12 to 0,22	16,5 to 18,5	—	—	2,00 to 2,50	10,0 to 12,5	—	—	
X5CrNiMo17-12-2	≤ 0,07	≤ 1,00	2,00	0,045	0,015	≤ 0,10	16,5 to 18,5	—	—	2,00 to 2,50	10,0 to 13,0	—	—	
X1CrNiMoN25-22-2	≤ 0,020	≤ 0,70	2,00	0,025	0,010	0,10 to 0,16	24,0 to 26,0	—	—	2,00 to 2,50	21,0 to 23,0	—	—	
X6CrNiMoTi17-12-2	≤ 0,08	≤ 1,00	2,00	0,045	0,015	—	16,5 to 18,5	—	—	2,00 to 2,50	10,5 to 13,5	5 × C to 0,70	—	

^a Elements not listed in this table may not be intentionally added to the steel without the agreement of the purchaser, except for finishing of the cast. All appropriate precautions are to be taken to avoid the addition of such elements from scrap and other materials used in production, which would impair mechanical properties and the suitability of the steel.

^b Information concerning ISO steel numbers and designations according to other regional or national standards is given in [Annex A](#).

^c Patented steel.

Table 3 (continued)

Steel grade ^b	mass fraction, %												Others
	C	Si	Mn	P	S	N	Cr	Cu	Mo	Nb	Ni	Ti	
X6CrNiMoNb17-12-2	≤ 0,08	≤ 1,00	2,00	0,045	0,015	—	16,5 to 18,5	—	2,00 to 2,50	10 × C to 1,00	10,5 to 13,5	—	—
X2CrNiMo17-12-3	≤ 0,030	≤ 1,00	2,00	0,045	0,015	≤ 0,10	16,5 to 18,5	—	2,50 to 3,00	—	10,5 to 13,0	—	—
X2CrNiMoN17-13-3	≤ 0,030	≤ 1,00	2,00	0,045	0,015	0,12 to 0,22	16,5 to 18,5	—	2,50 to 3,00	—	11,0 to 14,0	—	—
X3CrNiMo17-12-3	≤ 0,05	≤ 1,00	2,00	0,045	0,015	≤ 0,10	16,5 to 18,5	—	2,50 to 3,00	—	10,5 to 13,0	—	—
X2CrNiMo18-14-3	≤ 0,030	≤ 1,00	2,00	0,045	0,015	≤ 0,10	17,0 to 19,0	—	2,50 to 3,00	—	12,5 to 15,0	—	—
X2CrNiMoN18-12-4	≤ 0,030	≤ 1,00	2,00	0,045	0,015	0,10 to 0,20	16,5 to 19,5	—	3,0 to 4,0	—	10,5 to 14,0	—	—
X2CrNiMo18-15-4	≤ 0,030	≤ 1,00	2,00	0,045	0,015	≤ 0,10	17,5 to 19,5	—	3,0 to 4,0	—	13,0 to 16,0	—	—
X2CrNiMoN17-13-5	≤ 0,030	≤ 1,00	2,00	0,045	0,015	0,12 to 0,22	16,5 to 18,5	—	4,0 to 5,0	—	12,5 to 14,5	—	—
X1NiCrMoCu31-27-4	≤ 0,020	≤ 0,70	2,00	0,030	0,010	≤ 0,10	26,0 to 28,0	0,70 to 1,50	3,0 to 4,0	—	30,0 to 32,0	—	—
X1NiCrMoCu25-20-5	≤ 0,020	≤ 0,70	2,00	0,030	0,010	≤ 0,15	19,0 to 21,0	1,20 to 2,00	4,0 to 5,0	—	24,0 to 26,0	—	—
X1CrNiSi18-15-4	≤ 0,015	3,7 to 4,5	≤ 2,00	0,025	0,010	≤ 0,10	16,5 to 18,5	—	≤ 0,20	—	14,0 to 16,0	—	—
X2CrNiMoN21-9-1 ^c	≤ 0,03	≤ 1,00	≤ 2,00	0,045	0,015	0,14 to 0,25	19,5 to 21,5	≤ 1,00	0,50 to 1,50	—	8,0 to 9,5	—	—
Austenitic corrosion-resisting grades													
X1CrNiMoCuN25-25-5	≤ 0,020	≤ 0,70	2,00	0,030	0,010	0,17 to 0,25	24,0 to 26,0	1,00 to 2,00	4,7 to 5,7	—	24,0 to 27,0	—	—
X1CrNiMoCuN20-18-7	≤ 0,020	≤ 0,70	1,00	0,030	0,010	0,18 to 0,25	19,5 to 20,5	0,50 to 1,00	6,0 to 7,0	—	17,5 to 18,5	—	—

^a Elements not listed in this table may not be intentionally added to the steel without the agreement of the purchaser, except for finishing of the cast. All appropriate precautions are to be taken to avoid the addition of such elements from scrap and other materials used in production, which would impair mechanical properties and the suitability of the steel.

^b Information concerning ISO steel numbers and designations according to other regional or national standards is given in Annex A.

^c Patented steel.

Table 3 (continued)

Steel grade ^b	mass fraction, %											Others	
	C	Si	Mn	P	S	N	Cr	Cu	Mo	Nb	Ni		Ti
X1NiCrMoCuN25-20-7	≤ 0,020	≤ 0,50	max. 2,00	0,030	0,010	0,15 to 0,25	19,0 to 21,0	0,50 to 1,50	6,0 to 7,0	—	24,0 to 26,0	—	—
X2CrMnNiN17-7-5	< 0,030	≤ 1,00	6,0 to 8,0	0,045	0,015	0,15 to 0,20	16,0 to 17,0	—	—	—	3,5 to 5,5	—	—
X9CrMnNiCu17-8-5-2	≤ 0,10	≤ 1,00	5,5 to 9,5	0,070	0,010	≤ 0,15	16,5 to 18,5	1,00 to 2,50	—	—	4,5 to 5,5	—	—
Austenitic creep-resisting grades													
X3CrNiMoBN17-13-3	≤ 0,04	≤ 0,75	2,00	0,035	0,015	0,10 to 0,18	16,0 to 18,0	—	2,00 to 3,00	—	12,0 to 14,0	—	0,001 5 to 0,005 0 B
X6CrNiTiB18-10	0,04 to 0,08	≤ 1,00	2,00	0,035	0,015	—	17,0 to 19,0	—	—	—	9,0 to 12,0	5 × C to 0,70	0,001 5 to 0,005 0 B
X6CrNi18-10	0,04 to 0,08	≤ 1,00	2,00	0,035	0,015	≤ 0,10	17,0 to 19,0	—	—	—	8,0 to 11,0	—	—
X6CrNi23-13	0,04 to 0,08	≤ 0,70	2,00	0,035	0,015	≤ 0,10	22,0 to 24,0	—	—	—	12,0 to 15,0	—	—
X6CrNi25-20	0,04 to 0,08	≤ 0,70	2,00	0,035	0,015	≤ 0,10	24,0 to 26,0	—	—	—	19,0 to 22,0	—	—

^a Elements not listed in this table may not be intentionally added to the steel without the agreement of the purchaser, except for finishing of the cast. All appropriate precautions are to be taken to avoid the addition of such elements from scrap and other materials used in production, which would impair mechanical properties and the suitability of the steel.

^b Information concerning ISO steel numbers and designations according to other regional or national standards is given in Annex A.

^c Patented steel.

Table 3 (continued)

Steel grade ^b	mass fraction, %												
	C	Si	Mn max.	P max.	S max.	N	Cr	Cu	Mo	Nb	Ni	Ti	Others
X5NiCrAlTi31-20 (+RA)	0,03 to 0,08	≤ 0,70	1,50	0,015	0,010	≤ 0,03	19,0 to 22,0	≤ 0,50	—	≤ 0,10	30,0 to 32,5	0,20 to 0,50	0,20 to 0,50 Al Al + Ti: ≤ 0,70 ≤ 0,50 Co Ni + Co: 30,0 to 32,5
X8NiCrAlTi32-21	0,05 to 0,10	≤ 0,70	1,50	0,015	0,010	≤ 0,03	19,0 to 22,0	≤ 0,50	—	—	30,0 to 34,0	0,25 to 0,65	0,25 to 0,65 Al ≤ 0,50 Co Ni + Co: 30,0 to 34,0
X8CrNiNb16-13	0,04 to 0,10	0,30 to 0,60	1,50	0,035	0,015	—	15,0 to 17,0	—	—	10 × C to 1,20	12,0 to 14,0	—	—

^a Elements not listed in this table may not be intentionally added to the steel without the agreement of the purchaser, except for finishing of the cast. All appropriate precautions are to be taken to avoid the addition of such elements from scrap and other materials used in production, which would impair mechanical properties and the suitability of the steel.

^b Information concerning ISO steel numbers and designations according to other regional or national standards is given in [Annex A](#).

^c Patented steel.

Table 4 — Chemical composition (cast analysis)^a of austenitic-ferritic steels

Steel grade ^b	mass fraction, %										
	C max.	Si max.	Mn max.	P max.	S max.	N	Cr	Cu	Mo	Ni	W
X2CrNiN23-4	0,030	1,00	2,00	0,035	0,015	0,05 to 0,20	22,0 to 24,0	0,10 to 0,60	0,10 to 0,60	3,5 to 5,5	—
X2CrNiN22-2c	0,030	1,00	2,00	0,040	0,010	0,16 to 0,28	21,0 to 23,8	—	≤ 0,45	1,5 to 2,9	—
X2CrNiMoN22-5-3	0,030	1,00	2,00	0,035	0,015	0,10 to 0,22	21,0 to 23,0	—	2,50 to 3,5	4,5 to 6,5	—
X2CrNiMoCuN25-6-3	0,030	0,70	2,00	0,035	0,015	0,20 to 0,30	24,0 to 26,0	1,00 to 2,50	3,0 to 4,0	6,0 to 8,0	—
X2CrMnNiN21-5-1 ^c	0,040	1,00	4,0 to 6,0	0,035	0,005	0,20 to 0,25	21,0 to 22,0	0,10 to 0,80	0,10 to 0,80	1,35 to 1,90 ^d	—
X2CrNiMoN25-7-4	0,030	1,00	2,00	0,035	0,015	0,24 to 0,35	24,0 to 26,0	—	3,0 to 4,5	6,0 to 8,0	—
X2CrNiMoCuWN25-7-4	0,030	1,00	1,00	0,035	0,015	0,20 to 0,30	24,0 to 26,0	0,50 to 1,00	3,0 to 4,0	6,0 to 8,0	0,50 to 1,00
X2CrMnNiN21-5-1 ^c	0,040	1,00	4,0 to 6,0	0,035	0,005	0,20 to 0,25	21,0 to 22,0	0,10 to 0,80	0,10 to 0,80	1,35 to 1,90 ^e	—
X2CrNiMnMoCuN24-4-3-2 ^c	0,030	0,70	2,50 to 4,0	0,035	0,005	0,20 to 0,30	23,0 to 25,0	0,10 to 0,80	1,00 to 2,00	3,0 to 4,5	—

^a Elements not listed in this table may not be intentionally added to the steel without the agreement of the purchaser, except for finishing of the cast. All appropriate precautions are to be taken to avoid the addition of such elements from scrap and other materials used in production, which would impair mechanical properties and the suitability of the steel.

^b Information concerning ISO steel numbers and designations according to other regional or national standards is given in Annex A.

^c Patented steel.

^d Steel grade 1.4162 is patented steel up to a max. limit of Ni of 1,70 %.

^e This steel grade is patented steel up to a max. limit of Ni of 1,70 %.

Table 5 — Permissible product analysis tolerances on the limiting values given in Tables 1 to 4 for the cast analysis

Element	Specified value in the cast analysis in Tables 1 to 4 % by mass	Permissible deviation ^a of the product analysis % by mass
C	≤ 0,030	+0,005
	> 0,030 to ≤ 0,10	±0,01
Si	≤ 1,00	+0,05
	> 1,00 to ≤ 3,00	±0,10
	> 3,00 to ≤ 4,50	±0,15
Mn	≤ 1,00	+0,03
	> 1,00 to ≤ 2,50	+0,04
P	≤ 0,045	+0,005
	> 0,045 to ≤ 0,070	+0,010
S	≤ 0,015	+0,003
N	≤ 0,35	±0,01
Al	≤ 0,65	±0,10
Cr	≥ 10,5 to < 15,0	±0,15
	≥ 15,0 to ≤ 20,0	±0,20
	> 20,0 to ≤ 28,0	±0,25
Cu	≤ 1,00	±0,07
	> 1,00 to ≤ 2,50	±0,10
Mo	≤ 0,60	±0,03
	> 0,60 to ≤ 1,75	±0,05
	≥ 1,75 to < 7,0	±0,10
Nb	≤ 1,00	±0,05
Ni	≤ 1,00	±0,03
	> 1,00 to ≤ 5,0	±0,07
	> 5,0 to ≤ 10,0	±0,10
	> 10,0 to ≤ 20,0	±0,15
	> 20,0 to ≤ 34,0	±0,20
B	≥ 0,001 5 to ≤ 0,005 0	±0,000 3
Co	≤ 0,50	±0,05
Ti	≤ 0,08	±0,05
W	≤ 1,00	±0,05

^a If several product analyses are carried out on one cast, and the contents of an individual element determined lie outside the permissible range of the chemical composition specified for the cast analysis, then it is only allowed to exceed the permissible maximum value or to fall short of the permissible minimum value, but not both for one cast.

Table 6 — Type of process route of sheet, plate and strip^a

	Abbreviation ^b	Type of treatment	Surface finish	Notes
Hot rolled	1C	Hot rolled, heat treated, not descaled	Covered with the rolling scale	Suitable for parts which will be descaled or machined in subsequent production or for certain heat-resisting applications.
	1E	Hot rolled, heat treated, mechanically descaled	Free of scale	The type of mechanical descaling, e.g. coarse grinding or shot blasting, depends on the steel grade and the product, and is left to the manufacturer's discretion, unless otherwise agreed.
	1D	Hot rolled, heat treated, pickled	Free of scale	Usually standard for most steel types to ensure good corrosion resistance; also common finish for further processing. It is permissible for grinding marks to be present. Not as smooth as 2D or 2B.
Cold rolled	2C	Cold rolled, heat treated, not descaled	Smooth with scale from heat treatment	Suitable for parts which will be descaled or machined in subsequent production or for certain heat-resisting applications.
	2E	Cold rolled, heat treated, mechanically descaled	Rough and dull	Usually applied to steels with a scale which is very resistant to pickling solutions. May be followed by pickling.
	2D	Cold rolled, heat treated, pickled	Smooth	Finish for good ductility, but not as smooth as 2B or 2R.
	2B	Cold rolled, heat treated, pickled, skin passed	Smoother than 2D	Most common finish for most steel types to ensure good corrosion resistance, smoothness and flatness. Also a common finish for further processing. Skin passing may be by tension levelling.
	2R	Cold rolled, bright annealed ^c	Smooth, bright, reflective	Smoother and brighter than 2B. Also a common finish for further processing.
Special finishes	1G or 2G	Ground ^d	See footnote ^e .	Grade of grit or surface roughness can be specified. Unidirectional texture, not very reflective.
	1J or 2J	Brushed ^d or dull polished ^d	Smoother than ground. See footnote ^e .	Grade of brush or surface roughness can be specified. Unidirectional texture, not very reflective.

^a Not all process routes and surface finishes are available for all steels.

^b First digit: 1 = hot rolled, 2 = cold rolled.

^c May be skin passed.

^d One surface only, unless otherwise agreed at the time of enquiry and order.

^e Within each finish description, the surface characteristics can vary, and more specific requirements may need to be agreed between the manufacturer and purchaser (e.g. grade of grit or surface roughness).

Table 6 (continued)

	Abbreviation ^b	Type of treatment	Surface finish	Notes
Special finishes	1K or 2K	Satin polished ^d	See footnote e.	Additional specific requirements to a "J" type finish, in order to achieve adequate corrosion resistance for marine and external architectural applications. Transverse $R_a < 0,5 \mu\text{m}$ with clean cut surface finish.
	1P or 2P	Bright polished ^d	See footnote e.	Mechanical polishing. Process or surface roughness can be specified. Non-directional finish, reflective with high degree of image clarity.
	2F	Cold rolled, heat treated, skin passed on roughened rolls	Uniform non-reflective matt surface	Heat treatment by bright annealing or by annealing and pickling.
<p>a Not all process routes and surface finishes are available for all steels.</p> <p>b First digit: 1 = hot rolled, 2 = cold rolled.</p> <p>c May be skin passed.</p> <p>d One surface only, unless otherwise agreed at the time of enquiry and order.</p> <p>e Within each finish description, the surface characteristics can vary, and more specific requirements may need to be agreed between the manufacturer and purchaser (e.g. grade of grit or surface roughness).</p>				

STANDARDSISO.COM : Click to view the full PDF of ISO 9328-7:2018

Table 7 — Mechanical properties at room temperature for ferritic steels in the annealed condition (see Table B.1) and resistance to intergranular corrosion

Steel grade	Product form ^a	Thickness		0,2 % proof strength		Tensile strength	Elongation after fracture		Resistance to intergranular corrosion ^d		Impact energy (ISO-V)
		mm max.	mm	MPa min. (long.)	MPa min. (tr.)		R_m MPa	$A_{80}^{b,c}$ < 3 mm thick % min. (long. + tr.)	A_c ≥ 3 mm thick % min. (long. + tr.)	in the delivery condition	
X2CrNi12	C	8		280	320	450 to 650	20		no	no	no
	H	13,5		250	280		18				
	P	25		280	320		23				
X6CrNiTi12	C	8		280	320	450 to 650	20		no	no	50
	H	13,5		250	280		18				
	P	25		280	320		23				
X2CrTi17	C	4		180	200	380 to 530	24		yes	yes	—e
X3CrTi17	C	4		230	240	420 to 600	23		yes	yes	—e
X2CrMoTi17-1	C	4		200	220	400 to 550	23		yes	yes	—e
X2CrMoTi18-2	C	4		300	320	420 to 640	20		yes	—	—e
X6CrMoNb17-1	C	4		280	300	480 to 560	25		yes	yes	—e
X2CrTiNb18	C	4		230	250	430 to 630	18		yes	yes	—e
X2CrCuNbTiV22-1	C	4		280	300	430 to 630	22		yes	yes	27

^a C = cold-rolled strip; H = hot-rolled strip; P = hot-rolled plate.

^b The values are related to test pieces with a gauge length of 80 mm and a width of 20 mm. Test pieces with a gauge length of 50 mm and a width of 12,5 mm may also be used.

^c The values are related to test pieces with a gauge length of $5,65\sqrt{S_0}$.

^d When tested in accordance with ISO 3651-2.

^e Because of the small maximum nominal thickness, t [the requirement to prepare impact test pieces applies for $t \geq 6$ mm, see ISO 9328-1:2018, 8.2.2.3 c)], no verifiable values can be specified.

Table 8 — Tensile properties at room temperature and impact energy at 20 °C and at -20 °C for martensitic steels in the quenched and tempered condition (see Table B.2)

Steel grade	Product form ^a	Thickness	0,2 % proof strength $R_{p0,2}$	Tensile strength R_m	Elongation after fracture A^b	Impact energy (ISO-V) KV_2	
	mm max.	MPa min.	MPa		≥ 3 mm thick % min. (long. + tr.)	at 20 °C (long. + tr.)	at -20 °C (tr.)
X3CrNiMo13-4	P	75	650	780 to 980	14	70	40
X4CrNiMo16-5-1	P	75	680	840 to 980	14	55	40

^a P = hot-rolled plate.

^b The values apply for test pieces with a gauge length of $5,65\sqrt{S_0}$.

STANDARDSISO.COM : Click to view the full PDF of ISO 9328-7:2018

Table 9 — Tensile properties at room temperature and impact energy at 20 °C and at –20 °C of austenitic steels in the solution annealed condition^a (see Table B.3) and resistance to intergranular corrosion

Steel grade	Product form ^b	Thickness mm max.	0,2 % proof strength		1,0 % proof strength		Tensile strength R_m MPa	Elongation after fracture		Impact energy (ISO-V)		Resistance to intergranular corrosion ^f	
			$R_{p0,2}$	$R_{p0,2}$ MPa min. (tr.) ^c	$R_{p1,0}$	$R_{p1,0}$ MPa min. (tr.) ^c		A_{80^d} < 3 mm thick	A_{80^d} ≥ 3 mm thick	at 20 °C (long.)	KV_2 > 10 mm thick J min. at –20 °C (tr.)	in the delivery condition	in the sensitized condition
Austenitic corrosion-resisting grades													
X2CrNi18-7	C	8	350	380	380	650 to 850	35	40	90	60	60	yes	yes
	H	13,5	330	370	370		40	60	60	60	60	yes	yes
	P	75	330	370	370		40	60	60	60	60	yes	yes
X2CrNi18-9	C	8	220	250	250	520 to 700	45	45	100	60	60	yes	yes
	H	13,5	200	240	240		45	45	100	60	60	yes	yes
	P	75	200	240	240		45	45	100	60	60	yes	yes
X2CrNi19-11	C	8	220	250	250	520 to 700	45	45	100	60	60	yes	yes
	H	13,5	200	240	240		45	45	100	60	60	yes	yes
	P	75	200	240	240		45	45	100	60	60	yes	yes
X5CrNi19-9	C	8	290	320	320	550 to 750	40	40	100	60	60	(yes) ^h	no ⁱ
	H	13,5	270	310	310		40	40	100	60	60	(yes) ^h	no ⁱ
	P	75	270	310	310		40	40	100	60	60	(yes) ^h	no ⁱ
X2CrNi18-10	C	8	290	320	320	550 to 750	40	40	100	60	60	yes	yes
	H	13,5	270	310	310		40	40	100	60	60	yes	yes
	P	75	270	310	310		40	40	100	60	60	yes	yes
X5CrNi18-10	C	8	230	260	260	540 to 750	45 ^f	45 ^f	100	60	60	(yes) ^h	no ⁱ
	H	13,5	210	250	250		45 ^f	45 ^f	100	60	60	(yes) ^h	no ⁱ
	P	75	210	250	250		45 ^f	45 ^f	100	60	60	(yes) ^h	no ⁱ
X6CrNiTi18-10	C	8	220	250	250	520 to 720	40	40	100	60	60	yes	yes
	H	13,5	200	240	240		40	40	100	60	60	yes	yes
	P	75	200	240	240		40	40	100	60	60	yes	yes

Table 9 (continued)

Steel grade	Product form ^b	Thickness mm max.	0,2 % proof strength		1,0 % proof strength		Tensile strength		Elongation after fracture		Impact energy (ISO-V)		Resistance to intergranular corrosion ^f	
			$R_{p0,2}$	MPa min. (tr.) ^c	$R_{p1,0}$	MPa	R_m	MPa	A_{80}^d < 3 mm thick	A_e ≥ 3 mm thick	at 20 °C (long.) (tr.)	KV_2 > 10 mm thick J min.	at -20 °C (tr.)	in the delivery condition
X6CrNiNb18-10	H	13,5	200		240	520 to 720	40	40	100	60	40	yes	yes	
	P	75	200		240	500 to 700								
X1CrNi25-21	P	75	200		240	470 to 670	40	40	100	60	60	yes	yes	
	C	8	240		270	530 to 680	40	40	100	60	60	yes	yes	
X2CrNiMo17-12-2	H	13,5	220		260	520 to 670	45	45						
	P	75	220		260	520 to 670	45	45						
X2CrNiMoN17-11-2	C	8	300		330	580 to 780								
	H	13,5	280		320	580 to 780	40	40	100	60	60	yes	yes	
X1CrNiMoN25-22-2	P	75	280		320	510 to 710	40	40	100	60	60	yes	yes	
	P	75	250		290	540 to 740	40	40	100	60	60	yes	yes	
X5CrNiMo17-12-2	C	8	240		270	530 to 680	40	40						
	H	13,5	220		260	520 to 670	45	45	100	60	60	(yes) ⁱ	no ⁱ	
X6CrNiMoTi17-12-2	P	75	220		260	520 to 670	45	45	100	60	60	yes	yes	
	C	8	240		270	540 to 690	40	40						
X2CrNiMo17-12-3	H	13,5	220		260	520 to 670	40	40	100	60	60	yes	yes	
	P	75	220		260	520 to 670	45	45	100	60	60	yes	yes	
X2CrNiMoN17-13-3	C	8	300		330	580 to 780	35	35						
	H	13,5	280		320	580 to 780	40	40	100	60	60	yes	yes	
X3CrNiMo17-13-3	P	75	280		320	550 to 700	40	40	100	60	60	(yes) ^h	no ⁱ	
	C	8	240		270	550 to 700	40	40	100	60	60	(yes) ^h	no ⁱ	
	H	13,5	220		260	550 to 700	40	40	100	60	60	(yes) ^h	no ⁱ	

Table 9 (continued)

Steel grade	Product form ^b	Thickness mm max.	0,2 % proof strength		1,0 % proof strength		Tensile strength R_m MPa	Elongation after fracture		Impact energy (ISO-V)		Resistance to intergranular corrosion ^f	
			$R_{p0,2}$ MPa min. (tr.) ^c	$R_{p1,0}$ MPa min. (tr.) ^c	$R_{p1,0}$ MPa min. (tr.) ^c	$R_{p1,0}$ MPa min. (tr.) ^c		A_{80^d} < 3 mm thick % min. (tr.) ^c	A_{e^e} ≥ 3 mm thick % min. (tr.) ^c	KV_2 > 10 mm thick J min. at 20 °C (long.) (tr.)	KV_2 > 10 mm thick J min. at -20 °C (tr.)	in the delivery condition	in the sensitized condition
X2CrNiMo18-14-3	P	75	220	260	260	530 to 730	40	40					
	C	8	240	270	270	550 to 700	40	40					
	H	13,5	220	260	260	520 to 670	45	45	100	60	60	yes	yes
X2CrNiMoN18-12-4	P	75	220	260	260	570 to 770	35	35					
	C	8	290	320	320	570 to 770	35	35					
	H	13,5	270	310	310	540 to 740	40	40	100	60	60	yes	yes
X2CrNiMo18-15-4	P	75	270	310	310	540 to 740	40	40					
	C	8	240	270	270	550 to 700	35	35					
	H	13,5	220	260	260	520 to 720	40	40	100	60	60	yes	yes
X2CrNiMoN17-13-5	P	75	220	260	260	520 to 720	40	40					
	C	8	290	320	320	580 to 780	35	35					
	H	13,5	270	310	310	580 to 780	40	40	100	60	60	yes	yes
X1NiCrMoCu31-27-4	P	75	270	310	310	500 to 700	40	40					
	C	8	220	260	260	530 to 730	35	35					
	H	13,5	240	270	270	520 to 720	40	40	100	60	60	yes	yes
X1NiCrMoCu25-20-5	P	75	220	260	260	520 to 720	40	40					
	C	8	290	330	330	600 to 800	40	40					
	H	13,5	220	260	260	650 to 850	35	35	100	60	60	yes	yes
X1CrNiMoCuN25-25-5	P	75	290	330	330	600 to 800	40	40					
	C	8	320	350	350	650 to 850	40	40					
	H	13,5	300	340	340	600 to 800	40	40	100	60	60	yes	yes
X1CrNiMoCuN20-18-7	P	75	300	340	340	600 to 800	40	40					
	C	7	300	340	340	600 to 800	40	40	120	100	100	yes	yes
	H	13	300	340	340	600 to 800	40	40	120	100	100	yes	yes
X1NiCrMoCuN25-20-7	P	75	300	340	340	650 to 850	40	40					
	C	8	320	350	350	650 to 850	40	40					
	H	13,5	300	340	340	600 to 800	40	40	100	60	60	yes	yes

Table 9 (continued)

Steel grade	Product form ^b	Thickness mm max.	0,2 % proof strength $R_{p0,2}$	1,0 % proof strength $R_{p1,0}$	Tensile strength R_m	Elongation after fracture		Impact energy (ISO-V)		Resistance to intergranular corrosion ^f		
						$R_{p0,2}$ MPa min. (tr.) ^c	$R_{p1,0}$ MPa min. (tr.) ^c	A_{80^d} < 3 mm thick % min. (tr.) ^c	A_e ≥ 3 mm thick % min. (tr.) ^c	KV_2 > 10 mm thick J min. at 20 °C (long.) (tr.)	at -20 °C (tr.)	in the delivery condition
X2CrMnNi17-7-5	C	8,0	330	380	650 to 850	40	45	1	60	60	yes	yes
	H	13,5	300	370		45	60	60	60	60	yes	yes
	P	75,0	300	370		45	60	60	60	60	yes	no
X9CrMnNiCu17-8-5-2	C	8,0	230	250	540 to 850	45	45	100	60	60	yes	no
	H	13,5	230	250	520 to 830	40	40	100	60	60	yes	yes
	P	75,0	210	240	520 to 830	35	35	100	60	60	yes	yes
X1CrNiSi18-15-4	P	75	220	260	530 to 730	40	40	100	60	60	yes	yes
	C	8	350	380	650 to 850	35	35	100	60	60	yes	yes
	H	13,5	350	380	650 to 850	40	40	100	60	60	yes	yes
X2CrNiMoN21-9-1	P	75	320	350	630 to 830	40	40	100	60	60	yes	yes
	C	8	300	330	580 to 780	35	40	100	60	60	yes	yes
	H	13,5	260	300	550 to 750	40	40	100	60	60	yes	yes
X3CrNiMoBN17-13-3	P	75	260	300	550 to 750	40	40	100	60	60	yes	yes
	C	8	220	250	510 to 710	40	40	100	60	60	yes	yes
	H	13,5	200	240	510 to 710	45 ^g	45 ^g	100	60	60	no	no
X6CrNiTiB18-10	P	75	200	240	490 to 690	45	45	100	60	60	no	no
	C	8	230	260	530 to 740	35	35	100	60	60	no	no
	H	13,5	210	250	510 to 710	35	35	100	60	60	no	no
X6CrNi18-10	P	75	190	230	530 to 730	40	40	100	60	60	yes	yes
	C	8	230	260	530 to 740	45 ^g	45 ^g	100	60	60	no	no
	H	13,5	210	250	510 to 710	45	45	100	60	60	no	no
X6CrNi23-13	P	75	200	240	530 to 730	35	35	100	60	60	no	no
	C	8	220	250	530 to 730	40	40	100	60	60	yes	yes
	H	13,5	200	240	510 to 710	45	45	100	60	60	no	no
X6CrNi23-13	P	75	200	240	510 to 710	45	45	100	60	60	no	no
	C	8	220	250	530 to 730	40	40	100	60	60	yes	yes
	H	13,5	200	240	510 to 710	45	45	100	60	60	no	no
X6CrNi23-13	P	75	200	240	510 to 710	45	45	100	60	60	no	no
	C	8	220	250	530 to 730	40	40	100	60	60	yes	yes
	H	13,5	200	240	510 to 710	45	45	100	60	60	no	no

Austenitic creep-resisting grades

Table 9 (continued)

Steel grade	Product form ^b	Thickness mm max.	0,2 % proof strength		1,0 % proof strength		Tensile strength R_m MPa	Elongation after fracture		Impact energy (ISO-V)		Resistance to intergranular corrosion ^f	
			$R_{p0,2}$ MPa min. (tr.) ^c	$R_{p1,0}$ MPa min. (tr.) ^c	A_{80}^d < 3 mm thick % min. (tr.) ^c	A_e ≥ 3 mm thick % min. (tr.) ^c		KV_2 J min. at 20 °C (long.) (tr.)		at -20 °C (tr.)		in the delivery condition	in the sensitized condition
X6CrNi25-20	H	13,5	200	240	510 to 710	35	35	100	60	—	no	no	
	P	75	200	240		35	35	100	60	—	no	no	
X5NiCrAlTi31-20	P	75	170	200	500 to 750	30	30	120	80	—	yes	no	
X5NiCrAlTi31-20+RAj	P	75	210	240	500 to 750	30	30	120	80	—	yes	no	
X8NiCrAlTi32-21	P	75	170	200	500 to 750	30	30	120	80	—	yes	no	
X8CrNiNb16-13	P	75	200	240	510 to 690	35	35	100	60	—	yes	yes	

a The solution treatment may be omitted if the conditions for hot working and subsequent cooling are such that the requirements for the mechanical properties of the product and the resistance to intergranular corrosion as defined in ISO 3651-2 are obtained.

b C = cold-rolled strip; H = hot-rolled strip; P = hot-rolled plate.

c If, in the case of strip in rolling widths < 300 mm, longitudinal test pieces are taken, the minimum values are reduced as follows:

- proof strength: minus 15 MPa;
- elongation for constant gauge length: minus 5 %;
- elongation for proportional gauge length: minus 2 %.

d The values are related to test pieces with a gauge length of 80 mm and a width of 20 mm; test pieces with a gauge length of 50 mm and a width of 12,5 mm may also be used.

e The values are related to test pieces with a gauge length of $5,65\sqrt{S_0}$.

f When tested in accordance with ISO 3651-2.

g For stretcher-levelled material, the minimum value is 5 % lower.

h Normally for thicknesses up to 6 mm.

i Resistance to intergranular corrosion is given for thicknesses up to 6 mm in the welded condition.

j +RA = recrystallizing annealed condition.

Table 10 — Tensile properties at room temperature and impact energy at 20 °C and at -40 °C of austenitic-ferritic steels in the solution annealed condition (see Table B.4) and resistance to intergranular corrosion

Steel grade	Product form ^a	Thickness mm max.	0,2 % proof strength		Tensile strength R_m MPa	Elongation after fracture		Impact energy (ISO-V)		Resistance to intergranular corrosion ^d		
			$R_{p0,2}$ MPa min.	width (long.) < 300 mm (tr.) ≥ 300 mm mm		A_{80} < 3 mm thick ^b % min.	A ≥ 3 mm thick ^c % min.	at 20 °C (long.) (tr.)	at -40 °C (tr.)	in the delivery condition	in the sensitized condition	
X2CrMnNiN21-5-1	C	6,4	515	530	700 to 900	25	30	80	80	50		
	H	10	465	480	680 to 900	30	30	80	80	50	yes	yes
	P	80	435	450	650 to 900	30	30	60	40	40		
X2CrNiN23-4	C	8	405	420	630 to 850	20	20					
	H	13,5	385	400				120	90	40	yes	yes
	P	75	385	400	600 to 800	25	25					
X2CrNiN22-2	C	6,4	515	530	700 to 900	20	30	80	80	50		
	H	10	465	480	680 to 900	30	30					
	P	75	435	435	650 to 850	30	30	60	60	27 ^e	yes	yes
X2CrNiMoN22-5-3	C	8	485	500	700 to 950	20	20					
	H	13,5	445	460		25	25	150	100	40	40	40
	P	75	445	460	640 to 840	25	25					
X2CrNiMoCuN25-6-3	C	8	495	510	690 to 940	20	20					
	H	13,5	475	490				150	90	yes	yes	yes
	P	75	475	490	690 to 890	25	25					

^a C = cold-rolled strip; H = hot-rolled strip; P = hot-rolled plate.

^b The values are related to test pieces with a gauge length of 80 mm and a width of 20 mm; test pieces with a gauge length of 50 mm and a width of 12,5 mm may also be used.

^c The values are related to test pieces with a gauge length of $5,65\sqrt{S_0}$.

^d When tested in accordance with ISO 3651-2.

^e For thickness under 12 mm.

Table 10 (continued)

Steel grade	Product form ^a	Thickness mm max.	0,2 % proof strength		Tensile strength R_m MPa	Elongation after fracture		Impact energy (ISO-V)		Resistance to intergranular corrosion ^d	
			$R_{p0,2}$ MPa min.	width (long.) < 300 mm > 300 mm (tr.) mm		A_{80} < 3 mm thick ^b % min. (long. + tr.)	A ≥ 3 mm thick ^c % min. (long. + tr.)	at 20 °C (long.)	at -40 °C (tr.)	in the delivery condition	in the sensitized condition
X2CrNiMoN25-7-4	C	8	535	550	750 to 1 000	20	20	150	90	yes	yes
	H	13,5	515	530	730 to 930	20	20				
	P	75	515	530	730 to 930	25	25	150	90	40	yes
X2CrNiMoCuWN25-7-4	C	6,4	515	530	700 to 900	25	30	80	80	50	
	H	10	465	480	680 to 900	30	30	80	80	50	yes
	P	75	435	450	650 to 850	30	30	60	40	27	
X2CrMnNiN21-5-1	C	6,4	550	550	750 to 900	20	25	80	80	40	
	H	13	550	550	750 to 900	25	25	80	80	40	yes
	P	50	480	480	680 to 900	—	25	60	60	40	40

^a C = cold-rolled strip; H = hot-rolled strip; P = hot-rolled plate.

^b The values are related to test pieces with a gauge length of 80 mm and a width of 20 mm; test pieces with a gauge length of 50 mm and a width of 12,5 mm may also be used.

^c The values are related to test pieces with a gauge length of $5,65\sqrt{S_0}$.

^d When tested in accordance with ISO 3651-2.

^e For thickness under 12 mm.

Table 11 — Minimum values for the 0,2 % proof strength of ferritic steels at elevated temperatures in the annealed condition (see Table B.1)

Steel grade	Minimum 0,2 % proof strength $R_{p0,2}$, MPa at a temperature (in °C) of							
	50 ^a	100	150	200	250	300	350	400
X2CrNi12	265	240	235	230	220	215	—	—
X6CrNiTi12	—	300	270	250	245	225	215	—
X2CrTi17	198	195	180	170	160	155	—	—
X3CrTi17	223	195	190	185	175	165	155	—
X2CrMoTi17-1	—	250	240	230	220	210	205	200
X2CrMoTi18-2	294	250	240	230	220	210	205	—
X6CrMoNb17-1	289	270	265	250	235	215	205	—
X2CrTiNb18	242	230	220	210	205	200	180	—
X2CrCuNbTiV22-1	260	240	230	220	205	200	180	170

^a Determined by linear interpolation.

Table 12 — Minimum values for the 0,2 % proof strength of martensitic steels at elevated temperatures in the quenched and tempered condition (see Table B.2)

Steel grade	Minimum 0,2 % proof strength $R_{p0,2}$, MPa at a temperature (in °C) of						
	50 ^a	100	150	200	250	300	350
X3CrNiMo13-4	627	590	575	560	545	530	515
X4CrNiMo16-5-1	672	660	640	620	600	580	—

^a Determined by linear interpolation.

Table 13 — Minimum values for the 0,2 % and 1,0 % proof strength of austenitic steels at elevated temperatures in the solution annealed condition (see Table B.3)

Steel grade	Minimum 0,2 % proof strength, $R_{p0,2}$, MPa										Minimum 1,0 % proof strength, $R_{p1,0}$, MPa													
	at a temperature (in °C) of										at a temperature (in °C) of													
	50 ^a	100	150	200	250	300	350	400	450	500	550	600	50 ^a	100	150	200	250	300	350	400	450	500	550	600
X2CrNiN18-7	309	265	200	185	180	170	165	—	—	—	—	—	—	235	215	210	200	195	—	—	—	—	—	—
X2CrNi18-9	180	147	132	118	108	100	94	89	85	81	80	—	218	181	162	147	137	127	121	116	112	109	108	—
X2CrNi19-11	180	147	132	118	108	100	94	89	85	81	80	—	218	181	162	147	137	127	121	116	112	109	108	—
X5CrNiN19-9	246	205	175	157	145	136	130	125	121	119	118	—	284	240	210	187	175	167	161	156	152	149	147	—
X2CrNiN18-10	246	205	175	157	145	136	130	125	121	119	118	—	284	240	210	187	175	167	161	156	152	149	147	—
X5CrNi18-10	190	157	142	127	118	110	104	98	95	92	90	—	228	191	172	157	145	135	129	125	122	120	120	—
X6CrNiTi18-10	191	176	167	157	147	136	130	125	121	119	118	—	228	208	196	186	177	167	161	156	152	149	147	—
X6CrNiNb18-10	191	177	167	157	147	136	130	125	121	119	118	—	229	211	196	186	177	167	161	156	152	149	147	—
X1CrNi25-21	181	150	140	130	120	115	110	105	—	—	—	—	217	180	170	160	150	140	135	130	—	—	—	—
X2CrNiMo17-12-2	200	166	152	137	127	118	113	108	103	100	98	—	237	199	181	167	157	145	139	135	130	128	127	—
X2CrNiMoN17-11-2	254	211	185	167	155	145	140	135	131	128	127	—	292	246	218	198	183	175	169	164	160	158	157	—
X5CrNiMo17-12-2	204	177	162	147	137	127	120	115	112	110	108	—	242	211	191	177	167	156	150	144	141	139	137	—
X1CrNiMoN25-22-2	229	195	170	160	150	140	135	—	—	—	—	—	266	225	205	190	180	170	165	—	—	—	—	—
X6CrNiMoTi17-12-2	207	185	177	167	157	145	140	135	131	129	127	—	244	218	206	196	186	175	169	164	160	158	157	—
X6CrNiMoNb17-12-2	207	185	177	167	157	145	140	135	131	129	127	—	244	218	206	196	186	175	169	164	160	158	157	—
X2CrNiMo17-12-3	200	166	152	137	127	118	113	108	103	100	98	—	237	199	181	167	157	145	139	135	130	128	127	—
X2CrNiMoN17-13-3	254	211	185	167	155	145	140	135	131	129	127	—	292	246	218	198	183	175	169	164	160	158	157	—
X3CrNiMo17-13-3	204	177	162	147	137	127	120	115	112	110	108	—	252	211	191	177	167	156	150	144	141	139	137	—
X2CrNiMo18-14-3	199	165	150	137	127	119	113	108	103	100	98	—	237	200	180	165	153	145	139	135	130	128	127	—
X2CrNiMoN18-12-4	248	211	185	167	155	145	140	135	131	129	127	—	286	246	218	198	183	175	169	164	160	158	157	—
X2CrNiMo18-15-4	202	172	157	147	137	127	120	115	112	110	108	—	240	206	188	174	167	156	148	144	140	138	136	—
X2CrNiMoN17-13-5	253	225	200	185	175	165	155	150	—	—	—	—	289	255	230	210	200	190	180	175	—	—	—	—
X1NiCrMoCu31-27-4	209	190	175	160	155	150	145	135	125	120	115	—	245	220	205	190	185	180	175	165	155	150	145	—
X1NiCrMoCu25-20-5	214	205	190	175	160	145	135	125	115	110	105	—	251	235	220	205	190	175	165	155	145	140	135	—
X1CrNiMoCuN25-25-5	271	240	220	200	190	180	175	170	—	—	—	—	307	270	250	230	220	210	205	200	—	—	—	—
X1CrNiMoCuN20-18-7	274	230	205	190	180	170	165	160	153	148	—	—	314	270	245	225	212	200	195	190	184	180	—	—
X1NiCrMoCuN25-20-7	274	230	210	190	180	170	165	160	130	120	105	—	314	270	245	225	215	205	195	190	160	150	135	—
X2CrMnNiN17-7-5	246	205	175	127	120	110	104	100	95	92	90	—	284	240	210	157	145	135	129	125	122	120	120	—

^a Determined by linear interpolation.

Table 13 (continued)

Steel grade	Minimum 0,2 % proof strength, $R_{p0,2}$, MPa															Minimum 1,0 % proof strength, $R_{p1,0}$, MPa														
	at a temperature (in °C) of															at a temperature (in °C) of														
	50a	100	150	200	250	300	350	400	450	500	550	600	50a	100	150	200	250	300	350	400	450	500	550	600						
X9CrMnNiCu17-8-5-2	190	160	150	125	120	110	104	100	95	92	90	—	230	200	180	157	145	135	129	125	122	120	—							
X1CrNiSi18-15-4	205	185	160	145	135	125	120	115	—	—	—	—	240	210	190	175	165	155	150	—	—	—	—							
X2CrNiMoN21-9-1	280	230	210	190	180	170	165	160	155	150	147	—	320	270	250	225	210	195	190	185	180	170	—							
Austenitic creep-resisting grades																														
X3CrNiMoBN17-13-3	239	205	187	170	159	148	141	134	130	127	124	121	277	240	220	200	189	178	171	164	160	157	154	151						
X6CrNiTiB18-10	186	162	152	142	137	132	127	123	118	113	108	103	225	201	191	181	176	172	167	162	157	152	147	142						
X6CrNi23-13	177	140	128	116	108	100	94	91	86	85	84	82	219	185	167	154	146	139	132	126	123	121	118	114						
X6CrNi25-20	177	140	128	116	108	100	94	91	86	85	84	82	219	185	167	154	146	139	132	126	123	121	118	114						
X5NiCrAlTi31-20	159	140	127	115	105	95	90	85	82	80	75	75	185	160	147	135	125	115	110	105	102	100	95	95						
X5NiCrAlTi31-20+RA	199	180	170	160	152	145	137	130	125	120	115	110	227	205	193	180	172	165	160	155	150	145	140	135						
X8NiCrAlTi32-21	159	140	127	115	105	95	90	85	82	80	75	75	185	160	147	135	125	115	110	105	102	100	95	95						
X8CrNiNb16-13	191	175	166	157	147	137	132	128	123	118	118	113	227	205	195	186	176	167	162	157	152	147	147	142						

^a Determined by linear interpolation.

STANDARDS.PK.COM Click to view the full PDF of ISO 9328-7:2018

Table 14 — Minimum values for the 0,2 % proof strength of austenitic-ferritic steels at elevated temperatures in the solution annealed condition (see Table B.4)

Steel grade	Minimum 0,2 % proof strength $R_{p0,2}$, MPa at a temperature (in °C) of				
	50 ^a	100	150	200	250
X2CrNiN23-4	374	330	300	280	265
X2CrNiN22-2 ^b	430	380	350	330	320
X2CrMnNiN21-5-1 ^{b,c}	430	380	350	330	320
X2CrNiMoN22-5-3	422	360	335	315	300
X2CrNiMoCuN25-6-3	475	450	420	400	380
X2CrNiMoN25-7-4	500	450	420	400	380
X2CrNiMoCuWN25-7-4	500	450	420	400	380
X2CrMnNiN21-5-1 ^b	430	380	350	330	320
X2CrNiMnMoCuN24-4-3-2 ^b	—	385	345	325	315

^a Determined by linear interpolation.

^b Patented steel.

^c The values in table are valid only for product forms C and H. Corresponding values for quarto plate, P, are: 430, 380, 340, 310 and 290 MPa for thicknesses, $t \leq 15$ mm; 415, 365, 325, 295 and 275 MPa for thicknesses $15 \text{ mm} < t \leq 40$ mm; and 400, 350, 310, 280 and 260 MPa for thicknesses $40 \text{ mm} < t \leq 75$ mm.

Table 15 — Minimum values for the tensile strength of austenitic steels at elevated temperatures in the solution annealed condition (see Table B.3)

Steel grade	Minimum tensile strength R_m , MPa, at a temperature (in °C) of											
	50 ^a	100	150	200	250	300	350	400	450	500	550	600
Austenitic corrosion-resisting grades												
X2CrNiN18-7	605	530	490	460	450	440	430	—	—	—	—	—
X2CrNi18-9	466	410	380	360	350	340	340	—	—	—	—	—
X2CrNi19-11	466	410	380	360	350	340	340	—	—	—	—	—
X5CrNi19-9	527	490	460	430	420	410	410	—	—	—	—	—
X2CrNi18-10	527	490	460	430	420	410	410	—	—	—	—	—
X5CrNi18-10	494	450	420	400	390	380	380	380	370	360	330	—
X6CrNiTi18-10	477	440	410	390	385	375	375	375	370	360	330	—
X6CrNiNb18-10	476	435	400	370	350	340	335	330	320	310	300	—
X1CrNi25-21	459	440	425	410	390	385	380	—	—	—	—	—
X2CrNiMo17-12-2	486	430	410	390	385	380	380	380	—	360	—	—
X2CrNiMoN17-11-2	557	520	490	460	450	440	435	—	—	—	—	—
X5CrNiMo17-12-2	486	430	410	390	385	380	380	—	—	—	—	—
X1CrNiMoN25-22-2	521	490	475	460	450	440	435	—	—	—	—	—
X6CrNiMoTi17-12-2	490	440	410	390	385	375	375	375	370	360	330	—
X6CrNiMoNb17-12-2	490	440	410	390	385	375	375	375	370	360	330	—
X2CrNiMo17-12-3	486	430	410	390	385	380	380	380	—	360	—	—
X2CrNiMoN17-13-3	557	520	490	460	450	440	435	435	—	430	—	—
X3CrNiMo17-13-3	504	460	440	420	415	410	410	410	—	390	—	—
X2CrNiMo18-14-3	482	420	400	380	375	370	370	—	—	—	—	—

^a Determined by linear interpolation.

^b The tensile strength values also apply for the recrystallizing annealed condition (+RA).

Table 15 (continued)

Steel grade	Minimum tensile strength R_m , MPa, at a temperature (in °C) of											
	50 ^a	100	150	200	250	300	350	400	450	500	550	600
X2CrNiMoN18-12-4	525	500	470	440	430	420	415	415	415	410	390	—
X2CrNiMo18-15-4	486	430	410	390	385	380	380	—	—	—	—	—
X2CrNiMoN17-13-5	557	520	490	460	450	440	435	—	—	—	—	—
X1NiCrMoCu31-27-4	485	460	445	430	410	400	395	—	—	—	—	—
X1NiCrMoCu25-20-5	512	500	480	460	450	440	435	—	—	—	—	—
X1CrNiMoCuN25-25-5	581	550	535	520	500	480	475	—	—	—	—	—
X1CrNiMoCuN20-18-7	637	615	587	560	542	525	517	510	502	495	—	—
X1NiCrMoCuN25-20-7	612	550	535	520	500	480	475	—	—	—	—	—
X2CrMnNiN17-7-5	527	490	460	430	420	410	400	380	370	360	330	—
X9CrMnNiCu17-8-5-2	500	450	420	400	390	380	380	380	370	360	330	—
X1CrNiSi18-15-4	515	490	470	450	435	420	410	400	—	—	—	—
X2CrNiMoN21-9-1	615	565	535	505	495	480	475	465	455	445	425	—
Austenitic creep-resisting grades												
X3CrNiMoBN17-13-3	529	495	472	450	440	430	425	420	410	400	385	365
X6CrNiTiB18-10	460	410	390	370	360	350	345	340	335	330	320	300
X6CrNi18-10	484	440	410	390	385	375	375	375	370	360	330	300
X6CrNi23-13	495	470	450	430	420	410	405	400	385	370	350	320
X6CrNi25-20	495	470	450	430	420	410	405	400	385	370	350	320
X5NiCrAlTi31-20 ^b	487	465	445	435	425	420	418	415	415	415	—	—
X8NiCrAlTi32-21	487	465	445	435	425	420	418	415	415	415	—	—
X8CrNiNb16-13	493	465	440	420	400	385	375	370	360	350	340	320
^a Determined by linear interpolation. ^b The tensile strength values also apply for the recrystallizing annealed condition (+RA).												

Table 16 — Tests to be carried out, test units and extent of testing

Test	Test status ^a	Test unit	Product form		Number of test pieces per test sample
			Strip and sheet cut from strip in rolling width (C,H)	Rolled plate (P)	
Chemical analysis	m	Cast	Cast analysis ^b		
Tensile test at room temperature	m	Cast, thickness $\pm 10\%$, heat treatment batch	1 test sample from each coil	<p>a) Plates ≤ 20 mm (≤ 15 mm)^c thickness: Plates processed under identical conditions may be collected in a batch comprising not more than 20 plates. One test sample per batch shall be taken from heat-treated plates up to 15 m in length. One test sample shall be taken from each end of the longest plate in the batch where heat-treated plates are longer than 15 m. However, see ISO 9328-1:2018, Table 2, footnote a.</p> <p>b) Plates >20 mm (>15 mm)^c thickness: Each single plate; one test sample shall be taken from heat-treated plates up to 15 m long and one sample shall be taken from each end of heat-treated plates longer than 15 m. However, see ISO 9328-1:2018, Table 2, footnote a.</p>	1
Tensile test at elevated temperature ^d	o		To be agreed at the time of enquiry and order.		1
Impact test at room temperature	m ^e		To be agreed at the time of enquiry and order.		3
Impact test at low temperature	o		To be agreed at the time of enquiry and order.		3
Resistance to intergranular corrosion	o		To be agreed at the time of enquiry and order.		1
Other tests	o	See ISO 9328-1.			

^a Tests marked with an “m” (mandatory) shall be carried out as acceptance tests. In all cases, those marked with an “o” (optional) shall be carried out as acceptance tests only if agreed at the time of enquiry and order.

^b A product analysis may be agreed at the time of enquiry and order; the extent of testing shall be specified at the same time.

^c Limit value for martensitic, ferritic and austenitic-ferritic steels.

^d See ISO 9328-1:2018, 9.3.

^e For ferritic, martensitic and austenitic-ferritic grades > 6 mm thickness, and for austenitic grades for cryogenic service > 20 mm thickness; optional for austenitic grades for other applications (see ISO 9328-1:2018, Table 1).

Annex A (informative)

Steel designations in accordance with this document and designation of comparable steel grades in national or regional standards

**Table A.1 — Steel designations in accordance with this document^a and designation of
comparable^b steel grades in national or regional standards**

Steel designation in			
ISO 9328-7	EN 10028-7 ^c	ASTM A959	JIS
Ferritic steels			
X2CrNi12	1.4003	S41003	—
X6CrNiTi12	1.4516	S40975	—
X2CrTi17	1.4520		—
X3CrTi17	1.4510	S43035	SUS 430LX
X2CrMoTi17-1	1.4513		SUS 436L
X2CrMoTi18-2	1.4521	S44400	SUS 444
X6CrMoNb17-1	1.4526	S43600	—
X2CrTiNb18	1.4509		—
X2CrCuNbTiV22-1	1.4622	S44330	—
Martensitic steels			
X3CrNiMo13-4	1.4313	S41500	SUS F6NM
X4CrNiMo16-5-1	1.4418	—	—
Austenitic corrosion-resisting steels			
X2CrNiN18-7	1.4318	S30153	SUS 301L
X2CrNi18-9	1.4307	S30403	SUS 304L
X2CrNi19-11	1.4306	S30403	SUS 304L
X5CrNiN19-9	1.4315	S30451	SUS 304N1
X2CrNiN18-10	1.4311	S30453	SUS 304LN
X5CrNi18-10	1.4301	S30400	SUS 304
X6CrNiTi18-10	1.4541	S32100	SUS 321
X6CrNiNb18-10	1.4550	S34700	SUS 347
X1CrNi25-21	1.4335	S31002	—
X2CrNiMo17-12-2	1.4404	S31603	SUS 316L
X2CrNiMoN17-11-2	1.4406	S31653	SUS 316LN
X5CrNiMo17-12-2	1.4401	S31600	SUS 316
X1CrNiMoN25-22-2	1.4466	S31050	—
^a In accordance with ISO/TS 4949. ^b “Comparable” covers both identical or similar steel grades but does not necessarily imply “substitutable”. ^c In addition to the steel name (identical to the corresponding steel name used in this document), the listed steel number is specified. ^d Steel name in ISO 15510: X3CrNiMo17-12-3.			

Table A.1 (continued)

Steel designation in			
ISO 9328-7	EN 10028-7 ^c	ASTM A959	JIS
X6CrNiMoTi17-12-2	1.4571	S31635	SUS316TI
X6CrNiMoNb17-12-2	1.4580	S31640	—
X2CrNiMo17-12-3	1.4432	S31603	SUS 316L
X2CrNiMoN17-13-3	1.4429	S31653	SUS 316LN
X3CrNiMo17-13-3 ^d	1.4436	S31600	SUS 316
X2CrNiMo18-14-3	1.4435	S31603	SUS 316L
X2CrNiMoN18-12-4	1.4434	S31753	SUS 317LN
X2CrMnNiN17-7-5	1.4371	S20153	—
X9CrMnNiCu17-8-5-2	1.4618	S20100	—
X2CrNiMo18-15-4	1.4438	S31703	SUS 317L
X2CrNiMoN17-13-5	1.4439	S31726	—
X1NiCrMoCu31-27-4	1.4563	N08028	—
X1NiCrMoCu25-20-5	1.4539	N08904	SUS 890L
X1CrNiMoCuN25-25-5	1.4537	N08932	—
X1CrNiMoCuN20-18-7	1.4547	S31254	SUS 312L
X1NiCrMoCuN25-20-7	1.4529	N08926	—
X2CrNiMoN21-9-1	1.4420	—	—
Austenitic creep-resisting steels			
X3CrNiMoBN17-13-3	1.4910	—	—
X6CrNiTiB18-10	1.4941	S32109	—
X6CrNi18-10	1.4948	S30409	SUS 304H
X6CrNi23-13	1.4950	S30908	SUS 309S
X6CrNi25-20	1.4951	S31008	SUS 310S
X5NiCrAlTi31-20(+RA)	1.4958 (+RA)	—	—
X8NiCrAlTi32-21	1.4959	—	—
X8CrNiNb16-13	1.4961	—	—
Austenitic-ferritic steels			
X2CrNiN23-4	1.4362	S32304	—
X2CrNiN22-2	1.4062	S32202	—
X2CrNiMoN22-5-3	1.4462	S32205	SUS 329J3L
X2CrNiMoCuN25-6-3	1.4507	S32550	—
X2CrNiMoN25-7-4	1.4410	S32750	—
X2CrNiMoCuWN25-7-4	1.4501	S32760	—
X2CrMnNiN21-5-1	1.4162	S32101	—
X2CrNiMnMoCuN24-4-3-2	1.4662	S82441	—
^a In accordance with ISO/TS 4949. ^b “Comparable” covers both identical or similar steel grades but does not necessarily imply “substitutable”. ^c In addition to the steel name (identical to the corresponding steel name used in this document), the listed steel number is specified. ^d Steel name in ISO 15510: X3CrNiMo17-12-3.			

Annex B (informative)

Guidelines for further treatment (including heat treatment) in fabrication

- B.1** The guidelines given in [Tables B.1](#) to [B.4](#) are intended for hot forming and heat treatment.
- B.2** Thermal cutting may adversely affect edge areas; they should be machined.
- B.3** Scale and annealing colours produced during hot forming, heat treatment or welding may adversely affect the corrosion resistance. They should be removed as far as possible before use, e.g. by pickling or grinding.
- B.4** For further information, see appropriate documents, e.g. EN 1011-3.

Table B.1 — Guidelines on the temperature for hot forming and heat treatment^a of ferritic stainless steels

Steel grade	Hot forming		Heat treatment symbol ^b	Annealing	
	Temperature °C	Type of cooling		Temperature ^c °C	Type of cooling
X2CrNi12	1 100 to 800	air	+A	700 to 750	air, water
X6CrNiTi12				790 to 850	
X2CrTi17				820 to 880	
X3CrTi17				770 to 830	
X2CrMoTi17-1				790 to 850	
X2CrMoTi18-2				820 to 880	
X6CrMoNb17-1				800 to 860	
X2CrTiNb18				870 to 930	
X2CrCuNbTiV22-1				870 to 930	

^a The temperatures of annealing should be agreed for simulated heat-treated test pieces.

^b +A = annealed.

^c If heat treatment is carried out in a continuous furnace, the upper part of the range specified is usually preferred, or even exceeded.

Table B.2 — Guidelines on the temperature for hot forming and heat treatment^a of martensitic stainless steels

Steel grade	Hot forming		Heat Treatment symbol ^b	Quenching		Tempering Temperature °C
	Temperature °C	Type of cooling		Temperature ^c °C	Type of cooling	
X3CrNiMo13-4	1 150 to 900	air	+QT	950 to 1 050	oil, air, water	560 to 640
X4CrNiMo16-5-1			+QT	900 to 1 000		570 to 650

^a The temperatures of quenching and tempering should be agreed for simulated heat-treated test pieces.

^b +QT = Quenched and tempered.

^c If heat treatment is carried out in a continuous furnace, the upper part of the range specified is usually preferred, or even exceeded.

Table B.3 — Guidelines on the temperature for hot forming and heat treatment^a of austenitic stainless steels

Steel grade	Hot forming		Heat treatment symbol ^b	Solution annealing ^c (but see footnote g)	
	Temperature °C	Type of cooling		Temperature ^{d,e} °C	Type of cooling
Austenitic corrosion-resisting grades					
X2CrNi18-7	1 150 to 850	air	+AT	1 020 to 1 100	
X2CrNi18-9				1 000 to 1 100	
X2CrNi19-11				1 000 to 1 100	
X5CrNi19-9				1 000 to 1 100	
X2CrNi18-10				1 000 to 1 100	
X5CrNi18-10				1 000 to 1 100	
X6CrNiTi18-10				1 000 to 1 100	
X6CrNiNb18-10				1 020 to 1 120	
X1CrNi25-21				1 030 to 1 110	
X2CrNiMo17-12-2				1 030 to 1 110	
X2CrNiMoN17-11-2				1 030 to 1 110	
X1CrNiMoN25-22-2				1 070 to 1 150	
X5CrNiMo17-12-2				1 030 to 1 110	
X6CrNiMoTi17-12-2				1 030 to 1 110	
X6CrNiMoNb17-12-2				1 030 to 1 110	

^a The temperatures of annealing should be agreed for simulated heat-treated test pieces.

^b +AT = solution annealed, +RA = recrystallizing annealed.

^c The solution treatment may be omitted if the conditions for hot working and subsequent cooling are such that the requirements for mechanical properties of the product and the resistance to intergranular corrosion, as defined in ISO 3651-2, are obtained and provided these requirements are met, even after appropriate subsequent solution annealing.

^d If heat treatment is carried out in a continuous furnace, the upper part of the range specified is usually preferred, or even exceeded.

^e The lower end of the range specified for solution annealing should be aimed at for heat treatment as part of further processing, because otherwise the mechanical properties might be affected. If the temperature of hot forming does not drop below the lower temperature for solution annealing, a temperature of 980 °C is adequate as a lower limit for Mo-free steels, a temperature of 1 000 °C for steels with Mo contents up to 3 % and a temperature of 1 020 °C for steels with Mo contents exceeding 3 %.

^f Cooling is sufficiently rapid.

^g Recrystallizing annealing.

^h After solution annealing, the grain size in accordance with ISO 643 shall be 1 to 5.

Table B.3 (continued)

Steel grade	Hot forming		Heat treatment ^b symbol	Solution annealing ^c (but see footnote g)		
	Temperature °C	Type of cooling		Temperature ^{d,e} °C	Type of cooling	
X2CrNiMo17-12-3	1 150 to 850	air	+AT	1 030 to 1 110	water, air ^f	
X2CrNiMoN17-13-3				1 030 to 1 110		
X3CrNiMo17-13-3				1 030 to 1 110		
X2CrNiMo18-14-3				1 030 to 1 110		
X2CrNiMoN18-12-4				1 070 to 1 150		
X2CrNiMo18-15-4				1 070 to 1 150		
X2CrNiMoN17-13-5				1 060 to 1 140		
X1NiCrMoCu31-27-4				1 070 to 1 150		
X1NiCrMoCu25-20-5				1 060 to 1 140		
X1CrNiMoCuN25-25-5				1 120 to 1 180		
X1CrNiMoCuN20-18-7				1 140 to 1 200		
X1NiCrMoCuN25-20-7				1 120 to 1 180		
X2CrMnNiN17-7-5				1 000 to 1 100		
X9CrMnNiCu17-8-5-2				1 000 to 1 100		
X1CrNiSi18-15-4				1 100 to 1 160		
X2CrNiMoN21-9-1				1 030 to 1 110		
Austenitic creep-resisting grades						
X3CrNiMoBN17-13-3	1 150 to 850	air	+AT	1 020 to 1 100	water, air ^f	
X6CrNiTiB18-10				1 050 to 1 110		
X6CrNi18-10				1 050 to 1 110		
X6CrNi23-13				1 050 to 1 150		
X6CrNi25-20				1 050 to 1 150		
X5NiCrAlTi31-20				1 100 to 1 200		
X5NiCrAlTi31-20+RA	1 150 to 850	air	+RA	920 to 1 000 ^g	water, air ^f	
X8NiCrAlTi32-21				+AT		1 100 to 1 200 ^h
X8CrNiNb16-13				1 050 to 1 110		
<p>^a The temperatures of annealing should be agreed for simulated heat-treated test pieces.</p> <p>^b +AT = solution annealed, +RA = recrystallizing annealed.</p> <p>^c The solution treatment may be omitted if the conditions for hot working and subsequent cooling are such that the requirements for mechanical properties of the product and the resistance to intergranular corrosion, as defined in ISO 3651-2, are obtained and provided these requirements are met, even after appropriate subsequent solution annealing.</p> <p>^d If heat treatment is carried out in a continuous furnace, the upper part of the range specified is usually preferred, or even exceeded.</p> <p>^e The lower end of the range specified for solution annealing should be aimed at for heat treatment as part of further processing, because otherwise the mechanical properties might be affected. If the temperature of hot forming does not drop below the lower temperature for solution annealing, a temperature of 980 °C is adequate as a lower limit for Mo-free steels, a temperature of 1 000 °C for steels with Mo contents up to 3 % and a temperature of 1 020 °C for steels with Mo contents exceeding 3 %.</p> <p>^f Cooling is sufficiently rapid.</p> <p>^g Recrystallizing annealing.</p> <p>^h After solution annealing, the grain size in accordance with ISO 643 shall be 1 to 5.</p>						

Table B.4 — Guidelines on the temperature for hot forming and heat treatment^a of austenitic-ferritic steels

Steel grade	Hot forming		Heat treatment Symbol ^b	Solution annealing ^c	
	Temperature °C	Type of cooling		Temperature ^d °C	Type of cooling
Standard grades					
X2CrNiN23-4	1 150 to 950	air	+AT	1 000 ± 50	water, air
X2CrNiMoN22-5-3				1 060 ± 40	
X2CrNiN22-2	1 100 to 950			1 040 ± 60	
X2CrMnNiN21-5-1	1 100 to 900			1 050 ± 30	
X2CrNiMnMoCuN24-4-3-2	1 150 to 900			1 060 ± 60	
Special grades					
X2CrNiMoCuN25-6-3	1 150 to 1 000	air	+AT	1 080 ± 40	water, air
X2CrNiMoN25-7-4					
X2CrNiMoCuWN25-7-4					
<p>^a The temperatures of annealing should be agreed for simulated heat-treated test pieces.</p> <p>^b +AT = solution annealed.</p> <p>^c Solution annealing in the range specified, followed by sufficiently rapid cooling to avoid precipitation of deleterious phases, is essential after hot forming these steels.</p> <p>^d If heat treatment is carried out in a continuous furnace, the upper part of the range specified is usually preferred, or even exceeded.</p>					

Annex C (informative)

Post-weld heat treatment

C.1 In general, welded assemblies of stainless steels covered by this document are not subjected to any heat treatment with the following exceptions:

- martensitic grades are retempered;
- ferritic grades are reannealed if there is any risk of residual martensitic in the heat-affected zones; for appropriate temperatures see [Tables B.1](#) and [B.2](#).

C.2 During heating of high chromium and molybdenum austenitic-ferritic or austenitic steel weldments containing some ferrite, intermetallic phases may be formed which should be re-dissolved during post-weld heat treatment. As most filler metals are overalloyed in comparison with the equivalent basic grades, minimum solution temperatures higher than those in [Tables B.3](#) and [B.4](#) may be necessary.

In the case of fully austenitic weld structures, it should be verified that mechanical properties of heat-treated weldments conform to this document.

Oxidation of surfaces which necessitates pickling and possible distortion of the welded construction may raise further difficulties.

Consequently, post-weld heat treatment of duplex and austenitic steels should be avoided, and therefore welding should be planned carefully.

C.3 In special cases, e.g. for parts with a greater wall thickness, requirements concerning stress-relief and resistance to intergranular corrosion, in order to avoid failure by stress corrosion cracking or corrosion fatigue, may prove the necessity for post-weld heat treatment. This should be carried out according to [Table C.1](#) by holding at an intermediate stage below the usual solution temperature (see [Table B.3](#)) and is defined as stabilizing annealing for the niobium- or titanium-bearing grades and as stress-relieving for the unstabilized low-carbon grades.

In some cases, post-weld heat treatment may also be performed as solution annealing according to [Table B.3](#) or at a temperature below the precipitation range of carbides and intermetallic phases; however, the latter reduces only peak stresses.

C.4 Preheating of austenitic-ferritic steels is a very effective precaution against excessive stress increase caused by shrinkage of thicker welded cross-sections, because temperatures of 200 °C to 250 °C bring down room-temperature yield strength by about 50 %. Thus preheating is often more appropriate to avoid high stress levels in those weldments than any post-weld heat treatment. Preheating temperature between 120 °C and 200 °C according to the particular steel and thickness may be applied. Excessive preheating or excess weld heat input may promote the formation of undesirable intermetallic phases.

Table C.1 — Guidelines on post-weld heat treatment of austenitic steels

Steel grade	Temperature ^a in °C	Type of cooling
Stabilized steels		
X6CrNiTi18-10	900 to 940	air
X6CrNiNb18-10		
X6CrNiMoTi17-12-2	not recommended	
X6CrNiMoNb17-12-2		
Steels with ≤ 0,07 % C		
X5CrNi19-9	not recommended	
X5CrNi18-10		
X5CrNiMo17-12-2		
X3CrNiMo17-13-3		
X9CrMnNiCu17-8-5-2		
Steels with ≤ 0,03 % C		
X2CrNi18-7	900 to 940	air
X2CrNi18-9		
X2CrNi19-11		
X2CrNi18-10		
X2CrMnNi17-7-5		
X2CrNiMo17-12-2	960 to 1 040 ^b	air
X2CrNiMoN17-11-2		
X2CrNiMo17-12-3		
X2CrNiMoN17-13-3		
X2CrNiMo18-14-3		
X2CrNiMoN18-12-4		
X2CrNiMo18-15-4		
X2CrNiMoN17-13-5		
X2CrNiMoN21-9-1		
X1CrNiSi18-15-4		
Higher alloyed austenitic steels with ≤ 0,02 % C		
X1CrNi25-21	not recommended	
X1CrNiMoN25-22-2		
X1NiCrMoCu31-27-4		
X1NiCrMoCu25-20-5		
X1CrNiMoCuN25-25-5		
X1CrNiMoCuN20-18-7		
X1NiCrMoCuN25-20-7		
Creep-resisting steels		
X3CrNiMoBN17-13-3	900 to 950 ^c	air
X6CrNiTiB18-10		
X6CrNi18-10		
^a Minimum holding time: 30 min. ^b Not recommended if welded with stabilized filler metal. ^c The higher temperatures are recommended for components with greater wall thickness.		

Table C.1 (continued)

Steel grade	Temperature ^a in °C	Type of cooling
X6CrNi23-13	not recommended	
X6CrNi25-20		
X5NiCrAlTi31-20 (+RA)	900 to 950 ^c	air
X8NiCrAlTi32-21		
X8CrNiNb16-13		
^a Minimum holding time: 30 min.		
^b Not recommended if welded with stabilized filler metal.		
^c The higher temperatures are recommended for components with greater wall thickness.		

STANDARDSISO.COM : Click to view the full PDF of ISO 9328-7:2018

Annex D (informative)

Preliminary reference data for the tensile strength of austenitic-ferritic steels at elevated temperatures

Table D.1 — Minimum values for the tensile strength of austenitic-ferritic steels at elevated temperatures in the solution annealed condition (see [Table B.4](#))

Steel grade	Minimum tensile strength R_m (MPa) at a temperature (in °C) of				
	50	100	150	200	250
X2CrNiN23-4	577	540	520	500	490
X2CrNiN22-2	630	590	560	540	540
X2CrNiMoN22-5-3	621	590	570	550	540
X2CrNiMoCuN25-6-3	679	660	640	620	610
X2CrNiMoN25-7-4	711	680	660	640	630
X2CrNiMoCuWN25-7-4	711	680	660	640	630
X2CrMnNiN21-5-1	630	590	560	540	540
X2CrNiMnMoCuN24-4-3-2	621	590	570	550	540

Annex E (informative)

Reference data on strength values for 1 % (plastic) creep strain and creep rupture

The values given in [Tables E.1](#) and [E.2](#) and taken from EN 10028-7 are mean values of the scatter band considered to date. According to experience with long-time creep-testing it seems apparent that scattering of data is about $\pm 20\%$ in the long-range endurance of about 10^5 h up to $700\text{ }^\circ\text{C}$ to $800\text{ }^\circ\text{C}$. Above that temperature, scattering may be gradually more or less enlarged and be summarized with about 35% to 40% at a $1\ 000\text{ }^\circ\text{C}$ testing temperature. However, individual deviations must be presumed.

The strength values for 1 % (plastic) creep strain and creep rupture given up to the elevated temperatures listed in [Tables E.1](#) and [E.2](#) do not mean that the steels can be used in continuous duty up to these temperatures. The governing factor is the total stressing during operation. Where relevant, it is important that the oxidation conditions also be taken into account.

Table E.1 — Strength for 1 % (plastic) creep strain of austenitic creep-resisting steels in the solution annealed condition (see [Table B.3](#))

Steel grade	Temperature °C	Strength for 1 % (plastic) creep strain ^a (MPa) for	
		10 000 h	100 000 h
X6CrNi18-10	500	147	114
	510	142	111
	520	137	108
	530	132	104
	540	127	100
	550	121	96
	560	116	92
	570	111	88
	580	106	84
	590	100	79
	600	94	74
	610	88	69
	620	82	63
	630	75	56
	640	68	49
	650	61	43
	660	55	37
	670	49	32
	680	44	28
	690	39	25
700	35	22	
X6CrNi23-13	710	(31)	(15)
	720	(28)	(14)
	730	(26)	(13)
	740	(25)	(12)
	750	(24)	(11)
	550	107	60
	600	80	35
650	50	22	

^a Values in parentheses involved extended time and/or stress extrapolation.

Table E.1 (continued)

Steel grade	Temperature °C	Strength for 1 % (plastic) creep strain ^a (MPa) for	
		10 000 h	100 000 h
X6CrNi23-13	700	25	12
	750		
	800	10	
X5NiCrAlTi31-20	600	115	(85)
	610	109	(79)
	620	102	(74)
	630	96	(69)
	640	90	(64)
	650	84	(59)
	660	78	(55)
	670	73	(51)
	680	68	(47)
	690	63	(43)
700	58	(40)	
X5NiCrAlTi31-20+RA	550	164	(132)
	560	154	(122)
	570	144	(111)
	580	133	(101)
	590	123	(92)
	600	113	(82)
	610	103	(74)
	620	93	(65)
	630	84	(58)
	640	75	(51)
	650	67	(46)
	660	60	(41)
	670	55	(37)
	680	50	(33)
690	45	(30)	
700	41	(27)	
X8NiCrAlTi32-21	700	59,0	42,0
	710	55,5	38,0
	720	52,0	34,4
	730	48,5	31,3
	740	45,0	28,4
	750	41,7	26,0
	760	38,4	23,5
	770	35,6	21,3
	780	32,9	19,3
	790	30,5	17,6
	800	28,2	16,0
	810	26,2	14,7
	820	24,2	13,4
	830	22,4	12,1
	840	20,8	11,1
	850	19,1	10,0
	860	17,6	9,1
	870	16,1	8,2
	880	14,7	7,3
890	13,4	6,5	
900	12,1	5,7	

^a Values in parentheses involved extended time and/or stress extrapolation.

Table E.1 (continued)

Steel grade	Temperature °C	Strength for 1 % (plastic) creep strain ^a (MPa) for	
		10 000 h	100 000 h
X8NiCrAlTi32-21	910	10,9	5,0
	920	9,8	4,4
	930	8,8	3,9
	940	7,8	3,4
	950	6,9	2,9
	960	6,1	2,5
	970	5,3	2,1
	980	4,6	1,8
	990	4,0	1,6
	1 000	3,5	1,4
X8CrNiNb16-13	580	127	91
	590	120	84
	600	113	78
	610	106	73
	620	99	67
	630	92	61
	640	85	55
	650	78	49
	660	72	44
	670	66	39
	680	59	34
	690	54	30
	700	49	26
	710	45	24
	720	42	21
	730	39	19
	740	36	17
	750	34	16

^a Values in parentheses involved extended time and/or stress extrapolation.

Table E.2 — Creep rupture strength of austenitic creep-resisting steels in the solution annealed condition (see Table B.3)

Steel grade	Temperature °C	Creep rupture strength ^a (MPa) for						
		10 000 h	30 000 h	50 000 h	100 000 h	150 000 h	200 000 h	250 000 h
X3CrNi-MoBN17-13-3	550	290			220		200*	
	560	272			202		184*	
	570	254			186		166*	
	580	237			170		151*	
	590	220			155		137*	
	600	205			141		122*	
	610	190			127		113*	
	620	174			114		100*	
	630	162			102		91*	
	640	148			92		81*	
	650	135			83		73*	
	660	122			75		65*	
	670	112			68		58*	
	680	102			61		52*	
	690	93			56		46*	
	700	84			52		42*	

^a Values in parentheses involved time and/or stress extrapolation; values with an asterisk involved time extrapolation.

Table E.2 (continued)

Steel grade	Temperature °C	Creep rupture strength ^a (MPa) for						
		10 000 h	30 000 h	50 000 h	100 000 h	150 000 h	200 000 h	250 000 h
X3CrNi- MoBN17-13-3	710	78			48		39*	
	720	71			45		36*	
	730	65			41		34*	
	740	58			37		31*	
	750	52			34		28*	
	760	48			31		26*	
	770	44			28		24*	
	780	41			25		21*	
	790	37			22		19*	
	800	33			20		17*	
X6CrNi- TiB18-10	550	223			170		150	
	560	210			154		135	
	570	196			140		122	
	580	182			127		110	
	590	170			114		100	
	600	156			102		91	
	610	142			92		82	
	620	130			84		74	
	630	119			76		67	
	640	108			68		60	
	650	98			62		54	
	660	89			56		49	
	670	80			50		43	
	680	73			44		38	
	690	66			39		33	
	700	60			35		29	
X6CrNi18-10	510	239			182		166	
	520	227			172		156	
	530	215	165	155	162		146	
	540	203			151		136	
	550	191			140		125	
	560	177	154	145	128		114	
	570	165	144	136	117		104	
	580	154	135	126	107		95	
	590	143	126	118	98		86	
	600	132	117	110	89		78	
	610	122			81		70	
	620	113	109	102	73		62	
	630	104	101	94	65		55	
	640	95	94	87	58		49	
	650	87			52		43	
	660	80			47		38	
	670	73			42		34	
	680	67			37		30	
	690	61			32		26	
	700	55			28		22	
710	(45)			(22)				
720	(41)			(20)				
730	(38)			(18)				
740	(36)			(16)				
750	(34)			(15)				

^a Values in parentheses involved time and/or stress extrapolation; values with an asterisk involved time extrapolation.

Table E.2 (continued)

Steel grade	Temperature °C	Creep rupture strength ^a (MPa) for						
		10 000 h	30 000 h	50 000 h	100 000 h	150 000 h	200 000 h	250 000 h
X6CrNi23-13	550				90			
	600	160						
	650	120			65			
	700	70			35			
	750	36			16			
	800	18			7,5			
X6CrNi25-20	600	137	113	104*	92*	89*	82*	79*
	610	120	98	90*	79*	74*	71*	68*
	620	105	85	78*	69*	64*	61*	59*
	630	92	75	68*	60*	56*	54*	52*
	640	81	66	60*	53*	50*	47*	46*
	650	72	58	53*	47*	44*	42*	41*
X6CrNi25-20	660	64	52	47*	42*	39*	38*	36*
	670	57	46	42*	38*	35*	34*	33*
	680	51	42	38	34*	32*	31*	29*
	690	47	38	35	31*	29*	28*	27*
	700	42	34	32	28*	26*	25*	24*
	710	39	31	29	26*	24*	23*	22*
	720	35	29	26	23,5*	22*	21*	20*
	730	32	27	24,5*	22*	20*	19,5*	18,5*
	740	30	24,5	22,5*	20*	18,5*	18*	17*
	750	28	22,5	21*	18,5*	17*	16,5*	16*
	760	26	21	19*	17*	16*	15*	14,5*
	770	24	19,5	18*	15,5*	14,5*	14*	13,5*
	780	22	18	16,5*	14,5*	13,5*	13*	12,5*
	790	21	17	15,5*	13,5*	12,5*	12*	11,5*
	800	19,5	15,5	14*	12,5*	11,5*	11*	10,5*
	810	18	14,5	13*	11,5*			
	820	17	13,5	12*	10,5*	10,5*	10*	9,5*
	830	16	12,5	11,5*	10*	10*	9,5*	9*
	840	15	12	10,5*	9*	9*		
	850	14	11	10*				
	860	13						
870	12	10						
880	11,5	9,5	9*					
890	10,5	9*						
900	10,0							
910	9,5							
X5NiCrAl-Ti31-20	500	290			215		(196)	
	510	279			205		(186)	
	520	267			195		(176)	
	530	254			184		(166)	
	540	240			172		(155)	
	550	225			160		(143)	
	560	208			147		(130)	
	570	190			133		(117)	
	580	172			119		(105)	
	590	155			106		(93)	
	600	140			95		(83)	

^a Values in parentheses involved time and/or stress extrapolation; values with an asterisk involved time extrapolation.

Table E.2 (continued)

Steel grade	Temperature °C	Creep rupture strength ^a (MPa) for						
		10 000 h	30 000 h	50 000 h	100 000 h	150 000 h	200 000 h	250 000 h
X5NiCrAl- Ti31-20	610	128			85		(74)	
	620	118			78		(68)	
	630	109			72		(63)	
	640	103			67		(59)	
	650	97			63		(55)	
	660	91			59		(52)	
	670	85			55		(48)	
	680	80			52		(45)	
	690	74			48		(41)	
	700	69			44		(38)	
X5NiCrAl- Ti31-20+RA	500	315			258		(242)	
	510	297			241		(225)	
	520	280			224		(207)	
	530	262			206		(190)	
	540	243			189		(172)	
	550	224			171		(155)	
	560	204			153		(138)	
	570	184			136		(122)	
	580	165			119		(106)	
	590	147			104		(92)	
600	131			90		(80)		
X5NiCrAl- Ti31-20	610	117			79		(70)	
	620	106			70		(62)	
	630	96			62		(55)	
	640	87			56		(49)	
	650	80			51		(44)	
	660	73			46		(40)	
	670	67			42		(36)	
	680	61			38		(33)	
	690	55			34		(29)	
	700	50			30		(26)	
X8NiCrAl- Ti32-21	700	73,0	58,2		44,8		38,2*	
	710	67,8	54,0		41,4		35,2*	
	720	63,0	50,1		38,3		32,5*	
	730	58,5	46,5		35,4		30,0*	
	740	54,4	43,1		32,8		27,7*	
	750	50,6	40,0		30,3		25,6*	
	760	47,0	37,1		28,0		23,6*	
	770	43,7	34,4		25,9		21,8*	
	780	40,7	31,9		24,0		20,1*	
	790	37,8	29,6		22,1		18,5*	
800	35,2	27,4		20,4		17,0*		

^a Values in parentheses involved time and/or stress extrapolation; values with an asterisk involved time extrapolation.

Table E.2 (continued)

Steel grade	Temperature °C	Creep rupture strength ^a (MPa) for						
		10 000 h	30 000 h	50 000 h	100 000 h	150 000 h	200 000 h	250 000 h
X8NiCrAl- Ti32-21	810	32,7	25,4		18,9		15,6*	
	820	30,4	23,6		17,4		14,4*	
	830	28,3	21,8		16,0		13,2*	
	840	26,3	20,2		14,8		12,1*	
	850	24,4	18,7		13,6		11,1*	
	860	22,7	17,3		12,5		10,1*	
	870	21,0	16,0		11,5		9,23*	
	880	19,5	14,8		10,5		8,41*	
	890	18,1	13,6		9,60		7,63*	
	900	16,8	12,6		8,76		6,91*	
	910	15,6	11,6		7,98		6,23*	
	920	14,4	10,6		7,25		5,60*	
	930	13,3	9,77		6,57		5,01*	
	940	12,3	8,95		5,93		4,45*	
	950	11,4	8,19		5,33		3,93*	

^a Values in parentheses involved time and/or stress extrapolation; values with an asterisk involved time extrapolation.