

---

---

**Solar energy — Methods of testing  
preformed rubber seals and sealing  
compounds used in collectors**

*Énergie solaire — Méthodes d'essai des joints préformés en caoutchouc et des composés pour l'étanchéité utilisés dans les capteurs (DIS distribué en version anglaise seulement)*

STANDARDSISO.COM : Click to view the full PDF of ISO 9553:1997



**Contents**

1 Scope ..... 1

2 Normative references ..... 1

3 Classification ..... 2

4 Materials ..... 4

5 Dimensions and tolerances ..... 4

6 Physical requirements ..... 4

7 Test methods ..... 7

Annex A — Determination of adhesion of sealing compounds ..... 8

STANDARDSISO.COM : Click to view the full PDF of ISO 9553:1997

© ISO 1997

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization  
Case Postale 56 • CH-1211 Genève 20 • Switzerland  
Internet central@iso.ch  
X.400 c=ch; a=400net; p=iso; o=isocs; s=central

Printed in Switzerland

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 9953 was prepared by Technical Committee ISO/TC 180, *Solar energy*.

Annex A forms an integral part of this International Standard.

STANDARDSISO.COM : Click to view the full PDF of ISO 9553:1997

[STANDARDSISO.COM](https://standardsiso.com) : Click to view the full PDF of ISO 9553:1997

# Solar energy — Methods of testing preformed rubber seals and sealing compounds used in collectors

## 1 Scope

1.1 This International Standard gives requirements for the classification and testing of rubbers used to seal solar energy collectors in order to aid selection for specific applications.

NOTE Particular rubber applications, when specified, may necessitate other requirements that take precedence over these requirements.

1.2 The design requirements in this International Standard pertain only to permissible deflection of the rubber during thermal expansion or retraction of the seal in use and to the tolerances on dimensions of moulded and extruded seals.

1.3 This International Standard does not include requirements pertaining to geometrical design, fabrication or installation of the seals.

1.4 This International Standard is applicable in conjunction with long-term ageing and weathering tests. However, if long-term tests are performed, it is recommended that ISO 4892-2 be complied with for ageing tests and ISO 877 for accelerated weathering tests and material exposure tests, respectively.

NOTE The environmental conditions, test specimen configuration and any test deviations should be agreed upon between the parties involved. Also, if long-term tests are performed, the specific tests described in this International Standard should be performed before and after long-term testing is carried out.

## 2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this International Standard. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 37:1994, *Rubber, vulcanized or thermoplastic — Determination of tensile stress-strain properties.*

ISO 48:1994, *Rubber, vulcanized or thermoplastic — Determination of hardness (hardness between 10 IRHD and 100 IRHD).*

ISO 188: -<sup>1</sup>), *Rubber, vulcanized — Accelerated ageing and heat-resistance tests.*

ISO 471:1995, *Rubber — Temperatures, humidities, and times for conditioning and testing.*

ISO 812:1991, *Rubber, vulcanized — Determination of low-temperature brittleness.*

---

<sup>1</sup>) To be published. (Revision of ISO 188:1982)

ISO 815:1991, *Rubber, vulcanized or thermoplastic — Determination of compression set at ambient, elevated or low temperatures.*

ISO 877:1994, *Plastics—Methods of exposure to direct weathering, to weathering using glass-filtered daylight, and to intensified weathering by daylight using Fresnel 1 mirrors.*

ISO 1431-1:1989, *Rubber, vulcanized or thermoplastic — Resistance to ozone cracking — Part 1: Static strain test.*

ISO 3302-1:1996, *Rubber — Tolerances for products — Part 1: Dimensional tolerances.*

ISO 4632-1:1982, *Rubber, vulcanized — Classification system — Part 1: Description of the classification system.*

ISO 4661-1:1993, *Rubber, vulcanized or thermoplastic — Preparation of samples and test pieces — Part 1: Physical tests.*

ISO 4661-2:1987, *Rubber, vulcanized — Preparation of samples and test pieces — Part 2: Chemical tests.*

ISO 4892-2:1994, *Plastics — Method of exposure to laboratory light sources — Part 2: Xenon-arc sources.*

ISO 7619:1997, *Rubber — Determination of indentation hardness by means of pocket hardness meters.*

### 3 Classification

#### 3.1 Sealing

Sealing can be accomplished by one of the following methods:

- a) a preformed rubber seal (PS);
- b) a sealing compound (SC).

NOTE Sealing compounds should not be used in collectors in which the seal is under mechanical stress.

#### 3.2 Seal type

The following type classification is in accordance with ISO 4632-1. The type selected should be based on the maximum service temperature which normally occurs when the collector is under stagnation conditions and is receiving the maximum radiation flux to which it will be exposed.

Table 1 gives the maximum service temperatures and the test temperatures required in tables 3 and 4.

**Table 1 — Seal types, test temperatures and maximum service temperatures (ISO 4632-1)**

Type	Test temperature °C	Max. service temperature °C
B	100	70
C	125	100
D	150	125
E <sup>1)</sup>	175	150
F <sup>1)</sup>	200	175
G <sup>1)</sup>	225	200
H <sup>1)</sup>	250	225

<sup>1)</sup> Types E, F, G and H are not required for most solar collectors.

### 3.3 Seal grade

Table 2 shows differing degrees of rubber hardness in accordance with ISO 48 and ISO 7619. The grade to be used in a particular application depends on the design of the seal and shall be specified by the designer.

**Table 2 — Grade designation for different degrees of hardness**

Grade	Hardness
3	30 ± 5
4	40 ± 5
5	50 ± 5
6	60 ± 5
7	70 ± 5
8	80 ± 5

### 3.4 Seal class

**3.4.1** The classes shown in table 3 are established based on resistance to low temperatures. The class selected should be based on the lowest temperature of the collector expected in service.

**Table 3 — Seal classes, test temperatures and lowest service temperatures**

Class	Climate	Test temperature	Lowest service temperature
		°C	°C
W	Warm	0	– 10
M	Moderate	– 25	– 35
C	Cold	– 40	– 50
P	Polar	– 60	– 70

## 4 Materials

4.1 Seals shall be made from rubber compounds that are resistant to the effect of ultraviolet light and, when vulcanized as in 7.1, shall comply with the requirements in clause 5.

4.2 Seals shall be free from defects that adversely affect the serviceability of products. Surface texture of preformed seals should be appropriate to the method of manufacture decided by the parties concerned.

## 5 Dimensions and tolerances

5.1 Attention should be paid to the effects of seal thermal expansion. For this reason, dimensions will vary greatly in a solar collector due to the large range of temperatures reached.

NOTE If the thermal coefficient of linear expansion for the rubber is not known, a value of  $0,000\ 3\ \text{K}^{-1}$  may be assumed for design purposes.

5.2 The tolerance on dimensions shall conform to the following designations in ISO 3302-1:

### 5.2.1 Moulded seals

Good quality mouldings (Class M3)

High quality mouldings (Class M2)

### 5.2.2 Extruded seals

Good quality extrusion (Class E2)

NOTE The same consideration should be given to shrinkage.

## 6 Physical requirements

6.1 Preformed seals should conform to the requirements in table 4 when tested by the procedures given in clause 7.

NOTE The requirements for low-temperature flexibility and ozone resistance relate to the composition of the rubber vulcanized (type of rubber and formulation); these tests are required only when the composition is changed.

6.2 Sealing compounds shall conform to the requirements in table 5 when tested by the procedures in clause 7 (see note in 5.1).

## 7 Test methods

### 7.1 Preparation of test pieces

Prepare test pieces from preformed seals in accordance with ISO 4661-1 and test them in accordance with the test methods given in table 4.

For sealing compounds, prepare five sheets approximately 150 mm × 150 mm × 2 mm in accordance with instructions supplied by the manufacturer. Also, prepare five adhesion assemblies in accordance with annex A. Condition the sheets and adhesion assemblies for 14 days at standard laboratory conditions as given in ISO 471. Test the materials in accordance with test methods given in table 5.

Table 4 — Requirements for preformed seals

Property	Grade					Test method
	4	5	6	7	8	
Hardness, IRHD, +5 -4	40	50	60	70	80	7.2
Elongation at break, min. %	300	250	200	50	100	7.3
Compression set, max. %						
After 24 <sup>0</sup> <sub>-2</sub> h at high temperature <sup>1)</sup>	30	30	30	30	30	7.4
After 166 <sup>+2</sup> <sub>0</sub> h at low temperature	60	60	60	60	60	7.6
Resistance to heating <sup>1)</sup>						7.5
Hardness, change, max. IRHD	10	10	10	10	10	7.2
Elongation at break, change, max. %	30	30	30	30	30	7.3
Tensile strength change, max. %	20	20	20	20	20	7.3
Volatiles lost, max. %	1	1	1	1	1	7.5.2
Volatiles lost, max. %	0,1	0,1	0,1	0,1	0,1	7.5.3
Resistance to ozone	no cracking					7.6
Resistance to low temperature <sup>2)</sup>	no breaks or cracks					7.7
Classes M, C, and P only						
1) The temperature depends on the type.						
2) The temperature depends on the class.						

Table 5 — Requirements for sealing compounds

Property	Grade		Test method
	3	5	
<u>Hardness</u> , IRHD, +5 –4	30	40	7.2
<u>Elongation at break</u> , min. %	150	100	7.3
<u>Resistance to heating</u> <sup>(a)</sup>			7.5
Hardness, change, max. IRHD	10	10	7.2
Elongation at break, change, max. %	30	30	7.3
Tensile strength change, max. %	20	20	7.3
Volatiles lost, max. %	1	1	7.5.2
Volatiles condensable, max. %	0,1	0,1	7.5.3
<u>Resistance to ozone</u>	no cracking		7.6
<u>Resistance to low temperature</u> <sup>(b)</sup>	no breaks no cracks		7.7
Classes M, C, and P only			
<u>Adhesion loss</u> <sup>(c)</sup> , max. cm <sup>2</sup>	9	9	7.8
(a) The temperature depends on the type—see Table 1.			
(b) The temperature depends on the class—see Table 3.			
(c) The combined loss in bond and cohesion areas for the three specimens tested shall not exceed 9 cm <sup>2</sup> .			

## 7.2 Hardness

Test in accordance with ISO 48 or ISO 7619.

## 7.3 Tensile strength and elongation at break

Test in accordance with ISO 37 (Type 2: dumbbell test piece).

## 7.4 Compression set

Test in accordance with ISO 815 at high temperatures and ISO 1653 at low temperatures (small ISO 815 disc as test piece).

## 7.5 Resistance to heating

**7.5.1** Heat test pieces in a test tube in accordance with ISO 188, but for 14 days at the appropriate temperature for the type of seal given in table 1. The test tube shall be approximately 38 mm × 300 mm and be equipped with a two-hole heat-resistant stopper, a 9 mm × 420 mm inlet tube extending to within 25 mm of the bottom, a 9 mm × 380 mm outlet tube extending about 320 mm above the stopper, and a support to suspend three test pieces in the lower half of the test tube.

NOTE This high-temperature exposure is not an ageing process, and any correlation between this exposure and natural behaviour during service would be coincidental.

**7.5.2** After heating, condition the test pieces at standard laboratory temperatures for at least 16 h and perform the required tests within 96 h.

**7.5.3** Determine mass change (essentially due to volatiles lost) from the difference in masses of test pieces before and after ageing.

**7.5.4** Determine condensables which are volatile at 23 °C from the difference in masses of the outlet tube before and after heating the test pieces. Ensure that the exposed portion of the outlet tube is maintained at a temperature of  $(23 \pm 2)$  °C. If any volatiles condense on the inlet tube or other parts of the apparatus, they should be added to the mass of the material on the outlet tube.

## 7.6 Resistance to ozone

Determine in accordance with ISO 1431-1; Method A, 20 % elongation, ozone concentration in air  $200 \times 10^{-8}$ , for  $96_0^{+2}$  h at 40 °C.

## 7.7 Resistance to low temperature

Determine in accordance with ISO 812. Examine test pieces for brittleness (breaks or cracks) after test.

## 7.8 Adhesion loss

Determine in accordance with annex A.

## 8 Test report

The test report shall include at least the following information:

- a) complete identification of the seal tested;
- b) test methods and test conditions used (i.e. a reference to ISO 9553), including any deviations from specified procedures/conditions;
- c) test results;
- d) name of the person and organization responsible for the test.