

Transformed

**ISO**

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION

**ISO RECOMMENDATION  
R 1402**

**HYDROSTATIC TESTING OF RUBBER HOSE**

**1st EDITION**

July 1970

**COPYRIGHT RESERVED**

The copyright of ISO Recommendations and ISO Standards belongs to ISO Member Bodies. Reproduction of these documents, in any country, may be authorized therefore only by the national standards organization of that country, being a member of ISO.

For each individual country the only valid standard is the national standard of that country.

Printed in Switzerland

Also issued in French and Russian. Copies to be obtained through the national standards organizations.

STANDARDSISO.COM : Click to view the full PDF of ISO/R 1402:1970

## BRIEF HISTORY

The ISO Recommendation R 1402, *Hydrostatic testing of rubber hose*, was drawn up by Technical Committee ISO/TC 45, *Rubber*, the Secretariat of which is held by the British Standards Institution (BSI).

Work on this question led to the adoption of Draft ISO Recommendation No. 1402, which was circulated to all the ISO Member Bodies for enquiry in December 1967. It was approved, subject to a few modifications of an editorial nature, by the following Member Bodies :

Austria	Iran	Spain
Brazil	Ireland	Sweden
Czechoslovakia	Israel	Switzerland
France	Italy	U.A.R.
Germany	Japan	United Kingdom
Greece	Netherlands	U.S.A.
Hungary	New Zealand	U.S.S.R.
India	Poland	Yugoslavia

No Member Body opposed the approval of the Draft.

This Draft ISO Recommendation was then submitted by correspondence to the ISO Council, which decided to accept it as an ISO RECOMMENDATION.

STANDARDSISO.COM : Click to view the full PDF of ISO/R 1402:1970

## HYDROSTATIC TESTING OF RUBBER HOSE

### 1. SCOPE

This ISO Recommendation describes a method for the hydrostatic testing of rubber hose by subjecting the test piece or sample hose to the action of internal pressure up to a proof test pressure, checking the dimensional deviations which can occur in actual service, and then up to a minimum bursting pressure.

### 2. LENGTH OF TEST PIECE

#### 2.1 Hold test under proof pressure

This test will produce strains which in some cases can reduce hose life. Depending on the severity of service conditions it will be necessary in each case to decide whether the test is to be made on test pieces or on standard delivery lengths.

#### 2.2 Bursting test

For the bursting tests the free length of the test piece excluding end reinforcements or couplings should be preferably 1 m and in no case less than 0.5 m.

### 3. APPLICATION OF HYDROSTATIC PRESSURE

Unless otherwise specified to meet special requirements the test medium should be water. The use of air and other gaseous materials as testing media should be avoided because of the risk to operators. In special cases where such media are required for the tests, strict safety measures are imperative. Furthermore, it should be stressed that when a liquid is used as the test medium, all air should be expelled from the test piece because of the risk of injury to the operator due to the sudden expansion of trapped air released when the hose bursts.

#### 3.1 General

The hose should be connected to the water supply line and filled with water, all air in the hose being expelled through the valve or stop cock in the free end. The valve should then be closed, and hydrostatic pressure applied at a uniform rate of increase by means of a hand or power driven hydraulic pump or an accumulator system. The pressure should be measured with a calibrated dial gauge.

#### NOTES

1. In the interests of accuracy calibrated pressure gauges should be checked at frequent intervals, and the fitting of restrictors is recommended to minimize shock damage.
2. It is important to allow unrestricted movement to the free or plugged end of the test piece during the test.

### 3.2 Pressure increase rate

3.2.1 *Minimum rates* of pressure increase should be

- (a) 0.075 MN/m<sup>2</sup> per second for test pressures not above 7.0 MN/m<sup>2</sup>;
- (b) 0.15 MN/m<sup>2</sup> per second for test pressures above 7.0 MN/m<sup>2</sup>.

If these rates are not obtainable, the manufacturer and user should agree upon a suitable rate in advance. In cases where the minimum rate is somehow not reached, the report should state the rate actually attained.

3.2.2 *Maximum rates* of pressure increase should be

- (a) 0.175 MN/m<sup>2</sup> per second for test pressures not above 7.0 MN/m<sup>2</sup>;
- (b) 0.35 MN/m<sup>2</sup> per second for test pressures above 7.0 MN/m<sup>2</sup> and not above 42 MN/m<sup>2</sup>

A higher constant rate of pressure increase should be used when the test pressure is above 42 MN/m<sup>2</sup> in order that the final pressure is reached within 2 minutes. The rate of pressure increase should be reported in the test report.

## 4. TESTS AT PROOF PRESSURE

### 4.1 Proof pressure hold tests

The pressure should be increased at the rate specified in clause 3.2 until the test pressure has been reached. This pressure should be maintained for a period of 1 minute.

### 4.2 Measurement of deformation under proof pressure

When tests for change in length, change in outside diameter and twisting are required, the hose should be straightened, laid out horizontally for inspection and a hydrostatic pressure of 0.05 MN/m<sup>2</sup> applied. Three reference marks *a*, *b* and *c* should then be made on the outer surface of the hose, the middle mark *b* being made approximately midway along the length of the hose, and the two outer marks, *a* and *c*, 0.25 m from *b*. Each mark should consist of a segment of a circular arc and a straight line perpendicular to it, the three straight lines being colinear.

The initial pressure of 0.05 MN/m<sup>2</sup> should be maintained steady while the reference marks are measured. The specified hydrostatic proof test pressure should be applied at the rate recommended in clause 3.2, and should be maintained steady for 1 minute before carrying out the test measurements. The measurements should be made as quickly as possible to avoid extending the test for too long a period.

4.2.1 *Change in length.* The length between the two outermost marks, *a* and *c*, should be measured to a precision of  $\pm 1$  mm, using a measuring tape.

The change in length should be expressed as a percentage of the original length as follows :

$$V_L = \frac{L_1 - L_0}{L_0} \times 100$$

where

$L_0$  is the distance between the two outermost marks under a pressure of 0.05 MN/m<sup>2</sup>;

$L_1$  is the distance between the two outermost marks under the proof test pressure;

$V_L$  is the percentage change in length, which will be positive in the case of an increase in length and negative in the case of a decrease in length.

4.2.2 *Change in outside diameter.* Preferably, the outside diameters should be determined from circumferential measurements made with a precision of  $\pm 1$  mm using a measuring tape. The measurements may, however, be made direct using a caliper gauge having a minimum useful tip width of 5 mm.